

SPECIFICATIONS OF PRODUCTS

FERRO MANGANESE			
FeMn	High Carbon		
	75 - 80 Grade	70 - 75 Grade	65 - 70 Grade
Mn	75% - 80%	70% - 75%	65% - 70%
Si	1.5% Max	1.5% Max	1.5% Max
C	6% - 8% Max	6% - 8% Max	6% - 8% Max
P	0.35% Max	0.35% Max	0.35% Max
S	0.03% Max	0.03% Max	0.03% Max
FERRO MANGANESE			
FeMn	Medium Carbon		
	78 Grade	75 Grade	70 Grade
Mn	78% - 80%	75% Min	70% Min
C	1.5% Max	1.5% Max	1.5% Max
Si	1% Max	1% Max	1% Max
P	0.25% Max	0.25% Max	0.25% Max
S	0.03% Max	0.03% Max	0.03% Max
FERRO MANGANESE			
FeMn	Low Carbon		
	78 Grade	75 Grade	70 Grade
Mn	78% - 80%	75% Min	70% Min
C	0.5% Max	0.5% Max	0.5% Max
Si	1% Max	1% Max	1% Max
P	0.25% Max	0.25% Max	0.25% Max
S	0.03% Max	0.03% Max	0.03% Max
FeCr	FERRO CHROME		
	High Carbon		
Cr	58 to 65% min		
C	8.5 % max		
Si	4% max		
P	0.05% max		
S	0.05% max		

HIGH CARBON SILICO MANGANESE			
SiMn	HIGH CARBON		
	60/14 Grade	65/15 Grade	65/16 Grade
Mn	60% MIN	65% Min	65% Min
C	2.5% Max	2.25% Max	2% Max
Si	14% Min	15% Min	16% Min
P	0.35% Max	0.35% Max	0.35% Max
S	0.03% Max	0.03% Max	0.03% Max