XRM
Measuring Conditions of Sample 1

- magnification: LFOV
- number of projections: 901
- exposure for each projection: 50 s
- whole measuring time: ~ 16 h*
- pixel size: 128 nm

- magnification: HRES
- number of projections: 901
- exposure for each projection: 100 s
- whole measuring time: ~ 30 h*
- pixel size: 32 nm

* the measuring time includes a warmup procedure for each sample, the measurement itself and acquisition of reference images

© Fraunhofer-Institut für Mikrostruktur von Werkstoffen und Systemen IMWS

XRM
Measuring Conditions of Sample 2

- magnification: LFOV
- number of projections: 901
- exposure for each projection: 40 s
- whole measuring time: ~ 13.5 h*
- pixel size: 128 nm

- magnification: HRES
- number of projections: 901
- exposure for each projection: 115 s
- whole measuring time: ~ 34 h*
- pixel size: 32 nm

* the measuring time includes a warmup procedure for each sample, the measurement itself and acquisition of reference images

© Fraunhofer-Institut für Mikrostruktur von Werkstoffen und Systemen IMWS

XRM
Measuring Conditions of Sample 3

- magnification: LFOV
- number of projections: 901
- exposure for each projection: 40 s
- whole measuring time: ~ 13.5 h*
- pixel size: 128 nm

- magnification: HRES
- number of projections: 901
- exposure for each projection: 160 s
- whole measuring time: ~ 47 h*
- pixel size: 32 nm

* the measuring time includes a warmup procedure for each sample, the measurement itself and acquisition of reference images

© Fraunhofer-Institut für Mikrostruktur von Werkstoffen und Systemen IMWS