TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인천 도화 물류센터	4.	Slab ID:	지상5층 1공구 #
Project Location:	-		Date of Pouring:	#REF!
•	이처시		Date of Testing:	2024-03-12

D-Meter® Manufactured by Allen Face&Company, Serial Number: 448 2. Concrete Floor Installer: HEB Test Apparatus: Testing Technician:

최동현 (ALLEN FACE KOREA) 363 m² (for test area organization see attached drawing) 3. Testing Organization: ALLEN FACE KOREA Test Area: 5. Floor Tolerance Requirements:

TR34 FREE MOVEMENT FLOOR TOLERANCES							
Floor Classification	Property F (mm)	Property E (mm)					
Floor Classification	95% limit	95% limit					
FM1	1.8	4.5					
FM2	2.0	6.5					
FM3	2.2	8.0					
FM4	2.4	10.0					

TR34 4th Edition Convert into FF/FL number 값									
4th Edition	95	5%	F number						
등급	Property F mm(±)	Property E mm(±)	FF	FL					
FM1	1.8	4.5	42.9	46.6					
FM2	2.0	6.5	38.6	32.3					
FM3	2.2	8.0	35.1	26.2					
FM4	2.4	10.0	32.2	21.0					
And a sint on the Dancester Flagger and in autoide the 11 Flagger of details									

Analysis: Any point on the Property E survey grid is outside the ±15mm of datum															
Analysis:									Any point o	on the P	roperty E survey	gria is	outside the ±15mm o	i datum	
	TR34 FREE MOVEMENT RESULTS														
Run #:	un#: 21 22 23 24 25 26 All Runs:														
Run Length (m):		8.70	8.70	8.70	8.70	8.70	8.70				<u> </u>	<u> </u>	 		52.20
	Property F (95%)	NO	YES	YES	YES	YES	NO								YES
FM1	% Defective	7.41%	0.00%	0.00%	0.00%	0.00%	7.41%								2.47%
FIVII	Property E (95%)	YES	YES	YES	YES	YES	YES								YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (95%)	YES	YES	YES	YES	YES	YES								YES
FM2	% Defective	3.70%	0.00%	0.00%	0.00%	0.00%	3.70%								1.23%
FIVIZ	Property E (95%)	YES	YES	YES	YES	YES	YES								YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (95%)	YES	YES	YES	YES	YES	YES								YES
FM3	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%								0.00%
11015	Property E (95%)	YES	YES	YES	YES	YES	YES								YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (95%)	YES	YES	YES	YES	YES	YES	_							YES
FM4	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%			<u> </u>		<u> </u>	<u> </u>		0.00%
	Property E (95%)	YES	YES	YES	YES	YES	YES								YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%								0.00%

FM1 The analysed D-Meter® Runs satisfy the floor tolerance requirements. 7. Summary:

최동현 (ALLEN FACE KOREA)

TR34 (4th edition) Free Movement Floor Tolerance Report

Test Apparatus:

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1.	Project Name:	인천 도화 물류센터	4.	Slab ID:	지상5층 1공구 #4
	Project Location:	-		Date of Pouring:	#REF!
	-	인천시		Date of Testing:	2024-03-12

인천시 **2. Concrete Floor Installer:** HEB

The analysed D-Meter® Runs satisfy the

Testing Technician: 최동현 (ALLEN FACE KOREA)

3. Testing Organization: ALLEN FACE KOREA Test Area: 363 m² (for test area organization see attached drawing)

5. Floor Tolerance Requirements:

TR34 FREE MOVEMENT FLOOR TOLERANCES								
Floor Classification	Property F (mm)	Property E (mm)						
FIOOI Classification	100% limit	100% limit						
FM1	4.0	15.0						
FM2	4.5	15.0						
FM3	5.5	15.0						
FM4	7.5	15.0						

Any point on the Property E survey grid is outside the ±15mm of datum

D-Meter® Manufactured by Allen Face&Company, Serial Number: 448

6. Analysis:

7. Summary:

TR34 FREE MOVEMENT RESULTS																	
Run #:		21	22	23	24	25	26										All Runs:
Run Length (m):		8.70	8.70	8.70	8.70	8.70	8.70		1								52.20
	Property F (100%)	YES	YES	YES	YES	YES	YES										YES
FM1	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
FIVII	Property E (100%)	YES	YES	YES	YES	YES	YES		1		1						YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
FM2	Property F (100%)	YES	YES	YES	YES	YES	YES										YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
	Property E (100%)	YES	YES	YES	YES	YES	YES		T								YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
	Property F (100%)	YES	YES	YES	YES	YES	YES										YES
FM3	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
FIVI3	Property E (100%)	YES	YES	YES	YES	YES	YES		 		1	 					YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
	Property F (100%)	YES	YES	YES	YES	YES	YES										YES
FN44	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%
FM4	Property E (100%)	YES	YES	YES	YES	YES	YES		1	<u> </u>	1	 	<u> </u>				YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%										0.00%

floor tolerance requirements.

	_	최동현 (ALLEN FACE KOREA)

FM1







