## TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인천 도화 물류센터	4.	Slab ID:	지상4층 #13
Project Location:	-		Date of Pouring:	1900-01-00
-	인처시		Date of Testing:	2024-03-12

인선시 HEB D-Meter® Manufactured by Allen Face&Company, Serial Number: 448 2. Concrete Floor Installer: Test Apparatus: 최동현 (ALLEN FACE KOREA) Testing Technician:

3. Testing Organization: Test Area: m<sup>2</sup> (for test area organization see attached drawing) ALLEN FACE KOREA 5. Floor Tolerance Requirements:

TR34 FREE MOVEMENT FLOOR TOLERANCES							
Floor Classification	Property F (mm)	Property E (mm)					
FIOOF Classification	95% limit	95% limit					
FM1	1.8	4.5					
FM2	2.0	6.5					
FM3	2.2	8.0					
FM4	2.4	10.0					

TR34 4th Edition Convert into FF/FL number 값								
4th Edition	95	%	F number					
등급	Property F	Property E	FF	FL				
0 🗉	mm(±)	mm(±)	• •	' <del>-</del>				
FM1	1.8	4.5	42.9	46.6				
FM2	2.0	6.5	38.6	32.3				
FM3	2.2	8.0	35.1	26.2				
FM4	2.4	10.0	32.2	21.0				
Any point on the Property F survey grid is outside the +15mm of datum								

Analysis:	rsis:						Any point on the Property E survey grid is outside the ±15mm of datum									
							TR3	4 FREE MC	VEMENT	RESULTS						
Run #:		9	10	11	12											All Runs:
Run Length (m):		17.10	17.10	17.10	17.10											68.40
	Property F (95%)	YES	NO	YES	NO											YES
FM1	% Defective	1.82%	5.45%	3.64%	5.45%											4.09%
FIVIT	Property E (95%)	NO	NO	NO	NO	[										NO
	% Defective	27.66%	23.40%	40.43%	14.89%											26.60%
	Property F (95%)	YES	NO	YES	YES											YES
FM2	% Defective	0.00%	5.45%	1.82%	3.64%											2.73%
FIVIZ	Property E (95%)	YES	YES	NO	NO											NO
	% Defective	0.00%	2.13%	14.89%	8.51%											6.38%
	Property F (95%)	YES	NO	YES	YES											YES
FM3	% Defective	0.00%	5.45%	1.82%	0.00%											1.82%
FIVIS	Property E (95%)	YES	YES	NO	YES											YES
	% Defective	0.00%	0.00%	8.51%	2.13%											2.66%
	Property F (95%)	YES	YES	YES	YES											YES
FM4	% Defective	0.00%	3.64%	1.82%	0.00%											1.36%
rivi4	Property E (95%)	YES	YES	YES	YES											YES
	% Defective	0.00%	0.00%	2.13%	0.00%											0.53%

The analysed D-Meter® Runs satisfy the FM3 floor tolerance requirements. 7. Summary:

최동현 (ALLEN FACE KOREA)

## TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인천 도화 물류센터	4.	Slab ID:	지상4층 #13
Project Location:	-		Date of Pouring:	1900-01-00
•	인처시		Date of Testing	2024-03-12

인전시
2. Concrete Floor Installer: HEB

3. Testing Organization:
5. Floor Tolerance Requirements:

ALLEN FACE KOREA

TR34 ERFE N

TR34 FREE MOVEMENT FLOOR TOLERANCES							
Floor Classification	Property F (mm)	Property E (mm)					
Fiooi Classification	100% limit	100% limit					
FM1	4.0	15.0					
FM2	4.5	15.0					
FM3	5.5	15.0					
FM4	7.5	15.0					

Date of Testing: 2024-03-12
Test Apparatus: D-Meter® Manufactured by Allen Face&Company, Serial Number: 448

Testing Technician: 최동현 (ALLEN FACE KOREA)
Test Area: 427 m² (for test area organization see attached drawing)

Any point on the Property E survey grid is outside the ±15mm of datum

6. Analysis:

TR34 FREE MOVEMENT RESULTS													
Run #:		9	10	11	12								All Runs:
Run Length (m):		17.10	17.10	17.10	17.10				 		T		68.40
	Property F (100%)	YES	NO	YES	YES								NO
FM1	% Defective	0.00%	3.64%	0.00%	0.00%								0.91%
FIVII	Property E (100%)	YES	YES	YES	YES				 		T		YES
	% Defective	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (100%)	YES	NO	YES	YES								NO
FM2	% Defective	0.00%	3.64%	0.00%	0.00%								0.91%
FIVIZ	Property E (100%)	YES	YES	YES	YES						T		YES
	% Defective	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (100%)	YES	NO	YES	YES								NO
5142	% Defective	0.00%	1.82%	0.00%	0.00%								0.45%
FM3	Property E (100%)	YES	YES	YES	YES								YES
	% Defective	0.00%	0.00%	0.00%	0.00%								0.00%
	Property F (100%)	YES	YES	YES	YES								YES
F144	% Defective	0.00%	0.00%	0.00%	0.00%								0.00%
FM4	Property E (100%)	YES	YES	YES	YES	<b> </b>			 	 	<b>T</b>		YES
	% Defective	0.00%	0.00%	0.00%	0.00%								0.00%

7.	Summary:	The analysed D-Meter® Runs satisfy the	FM4	floor tolerance requirements.	
				_	최동현 (ALLEN FACE KOREA)

