TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인천 도화 물류센터	4.	Slab ID:	지상5층 #1
Project Location:	-		Date of Pouring:	#REF!
•	인천시		Date of Testing:	2024-03-12

2. Concrete Floor Installer:

Test Apparatus: Testing Technician: D-Meter® Manufactured by Allen Face&Company, Serial Number: 448 HEB 최동현 (ALLEN FACE KOREÁ)

m² (for test area organization see attached drawing) 3. Testing Organization: ALLEN FACE KOREA Test Area: 1,089

5. Floor Tolerance Requirements:	TD34 FDFF A	40\/EN4ENIT ELOOD :	FOLEDANICEC	TR34 4th Edition Convert into FF/FL number 값						
•	TR34 FREE MOVEMENT FLOOR TOLERANCES FIG. 1: Property F (mm) Property E (mm)			4th Edition	95	5%	F number			
	Floor Classification	Floor Classification Property F (mm) 95% limit		등급	Property F mm(±)	Property E mm(±)	FF	FL		
	FM1	1.8	4.5	FM1	1.8	4.5	42.9	46.6		
	FM2	2.0	6.5	FM2	2.0	6.5	38.6	32.3		
	FM3	2.2	8.0	FM3	2.2	8.0	35.1	26.2		
	FM4	2.4	10.0	FM4	2.4	10.0	32.2	21.0		

			FI	VI 4		4		0.0	1	FIVI 4		۷.4			10.0		32.2		.0
Analysis:									Any point on the Property E survey grid is outside the ±15mm of datum										
								TR34	FREE MO	VEMENT R	ESULTS								
Run #:		1	2	3	4	5	6												All Runs:
Run Length (m):		30.90	30.90	30.90	30.90	30.90	30.90												185.40
	Property F (95%)	YES	YES	YES	NO	YES	NO												YES
FM1	% Defective	2.97%	1.98%	2.97%	7.92%	1.98%	7.92%												4.29%
FIVII	Property E (95%)	NO	YES	NO	NO	YES	NO												NO
	% Defective	39.78%	0.00%	39.78%	23.66%	0.00%	23.66%												21.15%
	Property F (95%)	YES	YES	YES	NO	YES	NO												YES
FM2	% Defective	2.97%	1.98%	2.97%	6.93%	1.98%	6.93%												3.96%
FIVIZ	Property E (95%)	NO	YES	NO	NO	YES	NO												NO
	% Defective	22.58%	0.00%	22.58%	7.53%	0.00%	7.53%												10.04%
	Property F (95%)	YES	YES	YES	NO	YES	NO												YES
FM3	% Defective	0.99%	1.98%	0.99%	5.94%	1.98%	5.94%												2.97%
FIVIS	Property E (95%)	NO	YES	NO	YES	YES	YES												YES
	% Defective	9.68%	0.00%	9.68%	0.00%	0.00%	0.00%												3.23%
	Property F (95%)	YES	YES	YES	YES	YES	YES												YES
FM4	% Defective	0.99%	1.98%	0.99%	2.97%	1.98%	2.97%												1.98%
r1V14	Property E (95%)	YES	YES	YES	YES	YES	YES												YES
	% Defective	4.30%	0.00%	4.30%	0.00%	0.00%	0.00%												1.43%

The analysed D-Meter® Runs satisfy the FM3 floor tolerance requirements. 7. Summary:

최동현 (ALLEN FACE KOREA)

TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1.	Project Name:	인천 도화 물류센터	4.	Slab ID:	지상5층 #1
	Project Location:	-		Date of Pouring:	#REF!
	•	인천시		Date of Testing:	2024-03-12

TR34 FREE MOVEMENT FLOOR TOLERANCES Property F (mm)

100% limit

5.5

7.5

Floor Classification

FM3

FM4

The analysed D-Meter® Runs satisfy the

HEB **Concrete Floor Installer:** Test Apparatus: D-Meter® Manufactured by Allen Face&Company, Serial Number: 448 Testing Technician: 최동현 (ALLEN FACE KOREA)

Property E (mm)

100% limit

15.0

15.0

m² (for test area organization see attached drawing) **Testing Organization:** ALLEN FACE KOREA Test Area: 1,089 3. Floor Tolerance Requirements:

> Any point on the Property E survey grid is outside the ±15mm of datum 15.0 FM1 4.0 FM2 4.5 15.0

Analysis:

Summary:

TR34 FREE MOVEMENT RESULTS																
Run #:		1	2	3	4	5	6									All Runs:
Run Length (m):		30.90	30.90	30.90	30.90	30.90	30.90									185.40
	Property F (100%)	NO	YES	NO	YES	YES	YES									NO
FM1	% Defective	0.99%	0.00%	0.99%	0.00%	0.00%	0.00%									0.33%
FIVII	Property E (100%)	YES	YES	YES	YES	YES	YES				T			 		YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
	Property F (100%)	YES	YES	YES	YES	YES	YES									YES
FM2	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
FIVIZ	Property E (100%)	YES	YES	YES	YES	YES	YES				T					YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
	Property F (100%)	YES	YES	YES	YES	YES	YES									YES
EN42	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
FM3	Property E (100%)	YES	YES	YES	YES	YES	YES									YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
	Property F (100%)	YES	YES	YES	YES	YES	YES									YES
F144	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%
FM4	Property E (100%)	YES	YES	YES	YES	YES	YES				1	†			<u> </u>	YES
	% Defective	0.00%	0.00%	0.00%	0.00%	0.00%	0.00%									0.00%

floor tolerance requirements.

		최동현 (ALLEN FACE KOREA)

FM2



