## TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인천 도화 물류센터	4.	Slab ID:	지상4층 1공구 #11
Project Location:	-		Date of Pouring:	#REF!
•	인천시		Date of Testing:	2024-03-12

인천시 HEB Date of Testing: 2. Concrete Floor Installer: **Test Apparatus:** 

6.

최동현 (ALLEN FACE KOREA) Testing Technician: m<sup>2</sup> (for test area organization see attached drawing) 3. Testing Organization: ALLEN FACE KOREA Test Area: 5. Floor Tolerance Requirements:

TR34 FREE MOVEMENT FLOOR TOLERANCES							
Floor Classification	Property F (mm)	Property E (mm)					
Floor Classification	95% limit	95% limit					
FM1	1.8	4.5					
FM2	2.0	6.5					
FM3	2.2	8.0					
FM4	2.4	10.0					

111 (111 111 111 111 111 111 111 111 11								
TR34 4th Edition Convert into FF/FL number 값								
4th Edition	95	5%	F number					
등급	Property F mm(±)	Property E mm(±)	FF	FL				
FM1	1.8	4.5	42.9	46.6				
FM2	2.0	6.5	38.6	32.3				
FM3	2.2	8.0	35.1	26.2				
FM4	2.4	10.0	32.2	21.0				

D-Meter® Manufactured by Allen Face&Company, Serial Number: 448

Analysis:							Any point on the Property E survey grid is outside the ±15mm of datum									
TR34 FREE MOVEMENT RESULTS																
Run #:		1	2	3	4											All Runs:
Run Length (m):		9.60	9.60	9.60	9.60						<u> </u>					38.40
	Property F (95%)	YES	NO	NO	YES											NO
FM1	% Defective	0.00%	13.33%	13.33%	0.00%											6.67%
FIVII	Property E (95%)	YES	NO	NO	NO											NO
	% Defective	0.00%	50.00%	45.45%	36.36%											32.95%
	Property F (95%)	YES	NO	NO	YES											YES
FM2	% Defective	0.00%	10.00%	10.00%	0.00%											5.00%
FIVIZ	Property E (95%)	YES	NO	NO	NO											NO
	% Defective	0.00%	45.45%	18.18%	27.27%											22.73%
	Property F (95%)	YES	NO	NO	YES											YES
FM3	% Defective	0.00%	10.00%	6.67%	0.00%											4.17%
1 1013	Property E (95%)	YES	NO	NO	NO											NO
	% Defective	0.00%	40.91%	9.09%	9.09%											14.77%
	Property F (95%)	YES	NO	YES	YES											YES
FM4	% Defective	0.00%	6.67%	3.33%	0.00%											2.50%
. 101-4	Property E (95%)	YES	NO	YES	YES											YES
	% Defective	0.00%	18.18%	0.00%	0.00%											4.55%

The analysed D-Meter® Runs satisfy the floor tolerance requirements. 7. Summary:

FM4

최동현 (ALLEN FACE KOREA)

## TR34 (4th edition) Free Movement Floor Tolerance Report

Allen Face Europe TR34 Analysis, ©Allen Face Europe, www.allenface-europe.com

1. Project Name:	인전 도화 물류센터	4.	Slab ID:	지상4증 1공구 #11
Project Location:	-		Date of Pouring:	#REF!

인천시 2. Concrete Floor Installer: HEB

3. Testing Organization: ALLEN FACE KOREA

5.	Floor	Tolerance	Requirements:

TR34 FREE MOVEMENT FLOOR TOLERANCES							
Floor Classification	Property F (mm)	Property E (mm)					
Floor Classification	100% limit	100% limit					
FM1	4.0	15.0					
FM2	4.5	15.0					
FM3	5.5	15.0					
FM4	7.5	15.0					
	•	•					

Date of Testing: 2024-03-12

**Test Apparatus:** D-Meter® Manufactured by Allen Face&Company, Serial Number: 448

최동현 (ALLEN FACE KOREA) **Testing Technician:** 

m<sup>2</sup> (for test area organization see attached drawing) Test Area:

Any point on the Property E survey grid is outside the ±15mm of datum

6. Analysis:

TR34 FREE MOVEMENT RESULTS															
Run #:		1	2	3	4										All Runs:
Run Length (m):		9.60	9.60	9.60	9.60	<b>†</b>								 	38.40
	Property F (100%)	YES	NO	YES	YES										NO
FM1	% Defective	0.00%	3.33%	0.00%	0.00%										0.83%
FIVI	Property E (100%)	YES	YES	YES	YES	T			T		T		T		YES
	% Defective	0.00%	0.00%	0.00%	0.00%										0.00%
	Property F (100%)	YES	NO	YES	YES										NO
FN42	% Defective	0.00%	3.33%	0.00%	0.00%										0.83%
FM2	Property E (100%)	YES	YES	YES	YES				1		1		<u> </u>		YES
	% Defective	0.00%	0.00%	0.00%	0.00%										0.00%
	Property F (100%)	YES	YES	YES	YES										YES
	% Defective	0.00%	0.00%	0.00%	0.00%										0.00%
FM3	Property E (100%)	YES	YES	YES	YES										YES
	% Defective	0.00%	0.00%	0.00%	0.00%										0.00%
	Property F (100%)	YES	YES	YES	YES										YES
5344	% Defective	0.00%	0.00%	0.00%	0.00%						!				0.00%
FM4	Property E (100%)	YES	YES	YES	YES	1	j		1	· <del>†</del>	1				YES
	% Defective	0.00%	0.00%	0.00%	0.00%										0.00%

7. Summary:	The analysed D-Meter® Runs satisfy the	FM3	floor tolerance requirements.	
			_	+15-4 (**** 5 * 65 * 1/8 5 5 * )
				최동현 (ALLEN FACE KOREA)

