

Filament-Dokumentation (Vollständig)

PolyFlex TPU95 @Bambu Lab P1S 0.4 nozzle

Dieses Dokument enthält die vollständige alphabetische Auflistung aller 111 Parameter. Das Layout wurde so angepasst, dass lange Zeilen (wie z. B. Druckerlisten oder G-Code) garantiert umgebrochen werden und nicht mehr über den Seitenrand hinausragen.

JSON Parameter (Key)	Wert (Value)
activate_air_filtration	0
additional_cooling_fan_speed	70
additional_fan_full_speed_layer	0
chamber_temperatures	0
circle_compensation_speed	200
close_additional_fan_first_x_layers	1
close_fan_the_first_x_layers	1
compatible_printers	Bambu Lab P1S 0.4 nozzle, Bambu Lab X1 0.4 nozzle, Bambu Lab X1E 0.4 nozzle, Bambu Lab X1 Carbon 0.4 nozzle
complete_print_exhaust_fan_speed	70
cool_plate_temp	30
cool_plate_temp_initial_layer	30
cooling_perimeter_transition_distance	10
cooling_slowdown_logic	uniform_cooling
counter_coef_1	0
counter_coef_2	0.008
counter_coef_3	-0.041
counter_limit_max	0.033
counter_limit_min	-0.035
description	(leer)
diameter_limit	50
during_print_exhaust_fan_speed	70
eng_plate_temp	30
eng_plate_temp_initial_layer	30

JSON Parameter (Key)	Wert (Value)
fan_cooling_layer_time	100
fan_max_speed	100
fan_min_speed	100
filament_adaptive_volumetric_speed	0
filament_adhesiveness_category	600
filament_bridge_speed	25
filament_change_length	10
filament_contact_safe	1
filament_cooling_before_tower	0
filament_cost	20
filament_density	1.2
filament_dev_ams_drying_ams_limitations	1
filament_dev_ams_drying_heat_distortion_temperature	45
filament_dev_ams_drying_temperature	65, 75, 45, 45
filament_dev_ams_drying_time	12, 18, 12, 18
filament_dev_chamber_drying_bed_temperature	90.0
filament_dev_chamber_drying_time	16
filament_dev_drying_cooling_temperature	40
filament_dev_drying_softening_temperature	50
filament_diameter	1.75
filament_emission_safe	1
filament_enable_overhang_speed	1
filament_end_gcode	; filament end gcode
filament_extruder_compatibility	0
filament_extruder_variant	Direct Drive Standard
filament_flow_ratio	1.02
filament_flush_temp	0

JSON Parameter (Key)	Wert (Value)
filament_flush_volumetric_speed	0
filament_id	PMTP01
filament_ingredients_safe	1
filament_is_support	0
filament_long_retractions_when_cut	0
filament_max_volumetric_speed	8
filament_metal_stickiness	High
filament_minimal_purge_on_wipe_tower	15
filament_overhang_1_4_speed	0
filament_overhang_2_4_speed	50
filament_overhang_3_4_speed	30
filament_overhang_4_4_speed	10
filament_overhang_totally_speed	10
filament_pre_cooling_temperature	0
filament_pre_cooling_temperature_nc	0
filament_preheat_temperature_delta	0
filament_prime_volume	45
filament_prime_volume_nc	60
filament_printable	3
filament_ramming_travel_time	0
filament_ramming_travel_time_nc	0
filament_ramming_volumetric_speed	-1
filament_ramming_volumetric_speed_nc	-1
filament_retract_length_nc	14
filament_retraction_length	0.4
filament_scarf_gap	0%
filament_scarf_height	10%
filament_scarf_length	10

JSON Parameter (Key)	Wert (Value)
filament_scarf_seam_type	none
filament_settings_id	PolyFlex TPU95 @BBL P1S
filament_shrink	100%
filament_soluble	0
filament_start_gcode	<pre>; filament start gcode {if (bed_temperature[current_extruder] >35) (bed_temperature_initial_layer[current_extruder] >35)}M106 P3 S255 {elsif (bed_temperature[current_extruder] >30) (bed_temperature_initial_layer[current_extruder] >30)}M106 P3 S180 {endif} {if activate_air_filtration[current_extruder] && support_air_filtration} M106 P3 S{during_print_exhaust_fan_speed_num[current_extruder]} {endif}</pre>
filament_tower_interface_pre_extrusion_dist	10
filament_tower_interface_pre_extrusion_length	0
filament_tower_interface_print_temp	-1
filament_tower_interface_purge_volume	20
filament_tower_ironing_area	4
filament_type	TPU
filament_velocity_adaptation_factor	1
filament_vendor	Polymaker
from	User
full_fan_speed_layer	0
hole_coef_1	0
hole_coef_2	-0.008
hole_coef_3	0.23415
hole_limit_max	0.22
hole_limit_min	0.088
hot_plate_temp	35

JSON Parameter (Key)	Wert (Value)
hot_plate_temp_initial_layer	35
idle_temperature	0
impact_strength_z	10
inherits	Generic TPU
instantiation	true
long_retractions_when_ec	0
name	PolyFlex TPU95 @Bambu Lab P1S 0.4 nozzle
no_slow_down_for_cooling_on_outwalls	0
nozzle_temperature	250
nozzle_temperature_initial_layer	250
nozzle_temperature_range_high	230
nozzle_temperature_range_low	210
overhang_fan_speed	100
overhang_fan_threshold	95%
override_process_overhang_speed	0
reduce_fan_stop_start_freq	1
required_nozzle_HRC	3
retraction_distances_when_ec	0
setting_id	GFSR99
slow_down_for_layer_cooling	1
slow_down_layer_time	4
slow_down_min_speed	10
supertack_plate_temp	0
supertack_plate_temp_initial_layer	0
temperature_vitrification	0
textured_plate_temp	35
textured_plate_temp_initial_layer	35
type	filament

JSON Parameter (Key)	Wert (Value)
version	2.4.0.10
volumetric_speed_coefficients	0 0 0 0 0 0