# REPORT OF THE ASSOCIATION INTERNATIONALE POUR L'ÉTUDE DES ARGILES (AIPEA) NOMENCLATURE COMMITTEE FOR 2001:

# ORDER, DISORDER AND CRYSTALLINITY IN PHYLLOSILICATES AND THE USE OF THE "CRYSTALLINITY INDEX"

Stephen Guggenheim<sup>1,\*</sup>, Derek C. Bain<sup>2</sup>, Faíza Bergaya<sup>3</sup>, Maria F. Brigatti<sup>4</sup>, Victor A. Drits<sup>5</sup>, Dennis D. Eberl  $(Guest\ member)^6$ , Milton L. L. Formoso<sup>7</sup>, Emilio Galán<sup>8</sup>, Richard J. Merriman  $(Guest\ member)^9$ , Donald R. Peacor  $(Guest\ member)^{10}$ , Helge Stanjek<sup>11</sup> and Takashi Watanabe<sup>12</sup>

**Key Words**—Amorphous, Árkai Index, Crystallinity, Crystallinity Index, Disorder, Electron Amorphous, Hinckley Index, Kübler Index, Near Amorphous, Nomenclature, Order, X-ray Amorphous.

## INTRODUCTION

The purpose of this report is to describe the appropriate use of indices relating to crystallinity, such as the 'crystallinity index', the 'Hinckley index', the 'Kübler index', and the 'Arkai index'. A 'crystalline' solid is defined as a solid consisting of atoms, ions or molecules packed together in a periodic arrangement. A 'crystallinity index' is purported to be a measure of crystallinity, although there is uncertainty about what this means (see below). This report discusses briefly the nature of order, disorder and crystallinity in phyllosilicates and discusses why the use of a 'crystallinity index' should be avoided. If possible, it is suggested that indices be referred to using the name of the author who originally described the parameter, e.g. 'Hinckley index' or 'Kübler index', or in honor of a researcher who investigated the importance of the parameter extensively, e.g. 'Arkai index'.

In contrast to a crystalline solid, an 'amorphous' solid is one in which the constituent components are arranged randomly. However, many variations occur between the two extremes of crystalline vs. amorphous. For example, one type of amorphous material might consist simply of atoms showing no order and no periodicity. Alternatively,

\* E-mail address for correspondence: xtal@uic.edu

another amorphous material may consist of atoms arranged, for example, as groups of tetrahedra (*i.e.* limited order) with each group displaced or rotated (*e.g.* without periodicity) relative to another. Thus, this latter material is nearly entirely amorphous, but differs from the first. Likewise, disturbance of order and periodicity may occur in crystalline materials. The terms 'order' and 'disorder' refer to the collective nature or degree of such disturbances. Although seemingly simple notions, 'crystalline' and 'amorphous' are complex concepts.

Crystalline substances may show a periodic internal structure based on direction. For example, two-dimensional periodicity is common in phyllosilicates where two adjacent sheets or layers must mesh. For example, in serpentine, the 1:1 layer must match the periodicity of adjacent layers so that hydrogen bonding is optimized to link the layers. Adjacent layers may be offset by zero shifts,  $\pm a/3$  shifts, or  $\pm b/3$  shifts, but hydrogen bonding is still maintained and two-dimensional periodicity within each layer remains. Most materials (not necessarily clays, however), exhibit three-dimensional periodicity. Periodicity may be related also to domains, where short-range or long-range order may exist within domain boundaries.

Many forms of order and disorder occur in phyllosilicates, including order-disorder in stacking sequences, isomorphous substitutional order-disorder where various ions or vacancies occur in certain coordination sites, and

<sup>&</sup>lt;sup>1</sup> Chairman, AIPEA Nomenclature Committee, Department of Earth and Environmental Sciences, University of Illinois at Chicago, 845 W. Taylor St., Chicago, Illinois, 60607, USA

<sup>&</sup>lt;sup>2</sup> Macaulay Land Use Research Institute, Craigiebuckler, Aberdeen AB15 8QH, UK

<sup>&</sup>lt;sup>3</sup> Centre de Recherche de la Matière Divisée (CRMD), National Centre of Scientific Research, University of Orléans, 1b Rue de la Férollerie, 45 071 Orléans Cedex 2, France

<sup>&</sup>lt;sup>4</sup> Department of Earth Sciences, Modena and Reggio Emilia University, Largo S. Eufemia 19, I-41100, Modena, Italy <sup>5</sup> Geological Institute of the Russian Academy of Science, 7 Pyzerskii Per, Moscow J-17 Russia <sup>6</sup> US Geological Survey, 3215 Marine St., Boulder, Colorado, 80303, USA

<sup>&</sup>lt;sup>7</sup> 9500, Ave Bento Gonçalves, Campus do Vale, Institute of Geosciences, University Federal do Rio Grande do Sul, Porto Alegre
- RS - Brazil, CEP - 91540-000

<sup>&</sup>lt;sup>8</sup> Department of Crystallography and Minerals, Facultad de Quimica Universite, Sevilla, Spain
<sup>9</sup> British Geological Survey, Keyworth, Nottingham NG12 5GG, UK

Department of Geological Sciences, University of Michigan, Ann Arbor, Michigan, 48109, USA
 Lehrstuhl Für Bodenkunde, Technische Universtät Munchen, D-85350 Freising-Weihenstephan, Germany
 Joetsu University of Education, Joetsu Niigata 943, Japan

order-disorder in the arrangement of material in the interlayer. Phases involving interstratifications in phyllosilicates are common, with order-disorder in stacking of two or more kinds of layers. In addition, mosaic character, interstitial impurities, thermal or positional displacement, dislocations and other defects may also be related to order-disorder.

In practice, 'crystallinity' is defined as the degree of perfection of translational periodicity as determined by some experimental method. Diffraction techniques are the common methodologies to ascertain periodicity, but different diffraction techniques often do not convey the same information. For example, because of the different wavelengths and imaging capabilities of X-ray and electron-diffraction methods, X-ray diffraction (XRD) experiments may suggest that the periodicity of the material in the bulk sample may be non-existent, whereas electron diffraction may indicate, for example, that the atomic arrangements within finely-divided particles may be periodic. In addition to the choice of radiation, apparent crystallinity (or apparent periodicity) may be related also to sample preparation or experimental technique. For example, 'two-line' ferrihydrite is often considered amorphous or nearly amorphous because of the use of powder XRD patterns made with an improper choice of counting time and radiation. When scanned properly, however, this material may display more than six powder-diffraction peaks. As shown by accurate XRD and selected-area electrondiffraction data, both two-line and six-line ferrihydrites exist (e.g. Drits et al., 1993). Similarly, 'crystallinity' appears to decrease in powder XRD experiments of oriented clay-particle aggregates when the clay particles are partially or poorly oriented. Thus, the nature of the translational periodicity and the method of sample preparation and measurement are essential aspects that must be considered in any practical procedure to describe crystallinity.

Finally, note that this report is not comprehensive in that it considers only limited aspects of 'crystallinity' and does not consider environmental factors affecting disorder (e.g. mechanical actions), industrial implications, sample preparation methodologies, etc. The purpose of this report, as given above, is to consider some crystallographic aspects of crystallinity, such that appropriate nomenclature can be applied to this concept.

## THE TERM 'CRYSTALLINITY'

The term 'crystallinity' is qualitative and depends on the type of order (or disorder) as described above, the dimensional nature of the periodicity present, and the technique involved in its measurement. For phyllosilicates, which are low-symmetry materials characterized by strongly anisotropic structures, widely varying chemical compositions, and commonly having either irregular or regular interstratifications of various structures, the meaning of 'crystallinity' is ambiguous. Furthermore, the apparent 'crystallinity' is strongly dependent on crystallographic direction. Despite this, 'crystallinity' indices have been proposed for clay minerals for the last forty years, some of which have been widely accepted and applied worldwide.

#### HISTORICAL BACKGROUND AND COMMENTS

Hinckley (1963) attempted to define a 'crystallinity' index to quantify 'crystallinity' by describing how characteristics of powder XRD peaks may change among samples of kaolinite. Hinckley (1963) described a procedure to measure the maxima of the 111 and 021 powder-diffraction peaks. Brindley (1980, p. 152) noted that the measurement gives an indication of the "clarity of the two peaks, but it is not related to true peak intensities". Plançon and Zacharie (1990) noted that the procedure is incapable of quantifying the diversity of defect structures in kaolinite samples. The Clay Minerals Society Nomenclature Committee (R. Giese, pers. comm., 1998) suggested that the Hinckley index differentiates kaolinite samples containing "low" amounts of defects ('low-defect kaolinite') vs. "high" amounts of defects ('high-defect kaolinite'). Clearly, however, whatever the Hinckley index measures, the index is not a quantitative measure of 'crystallinity'.

Weaver (1960) was the first to realize that regular changes in shape of the first, 10 Å basal reflection of illite is a function of burial (increasing temperature and pressure). The "sharpness ratio" of Weaver (the 'Weaver index') is the ratio of intensities measured at the peak maximum (near 10 Å) and at 10.5 Å. The Weaver index increases with increasing depth in sedimentary basins. Kübler (1964) differentiated the "anchimetamorphic zone" (the "anchizone" of Dunoyer de Segonzac (1969) and others) to identify the transition between the dry-gas zone and the zone of unproductive ("overmature") rocks for hydrocarbon exploration. Kübler (1964, 1967) devised an illite "crystallinity" index (often abbreviated as IC) that relies on the full width at half maximum (FWHM) of the first, 10 Å XRD powder-diffraction peak of illite/muscovite, as measured on the <2 μm size-fraction of the air-dried clay using CuKα radiation. The Kübler index, expressed as small changes in the Bragg angle,  $\Delta^{\circ}2\theta$ , was introduced as a method of identifying the diagenesis-anchizone and anchizone-epizone metamorphic boundaries. Standardization of sample preparation, instrumental measuring conditions, and interlaboratory calibration are needed to do this (Kisch, 1990, 1991; Warr and Rice, 1994). Other crystallinity indices have been proposed for illite, including those of Weber (1972), Flehmig (1973) and Watanabe (1988), although these have been found to be less convenient or not as reproducible.

Although the Kübler index proved to be an easy-touse measure of grade of diagenesis and incipient metamorphism of clastic rocks, the use of the term 'illite crystallinity' is unfortunate, because it also involves illite-smectite and possibly white K-rich mica interstratifications and consequently, it is not a direct measure of the 'crystallinity'. Many authors use the term 'crystallinity' within quotation marks (e.g. Kisch, 1983; Frey, 1987), although Kübler (1984) preferred the term "largeur de Scherrer" (LS) or "Scherrer width" (SW) instead of 'illite crystallinity'.

The FWHM values of chlorite basal reflections have also been used as measures of 'chlorite crystallinity' (see reviews by Frey, 1987 and Árkai *et al.*, 1995). For the reaction series smectite-muscovite and smectite-chlorite, Árkai (1991) correlated the "chlorite crystallinity" indices measured on the 14 Å and 7 Å basal reflections with the Kübler index scale, metabasite mineral facies, coal rank and other metamorphic grade-indicating characteristics.

Investigations have shown that the Kübler index is influenced by the mean size of crystal domains that scatter X-rays coherently (Weber et al., 1976; Dunoyer de Segonzac and Bernoulli, 1976; Arkai and Tóth, 1983; Eberl and Velde, 1989; Drits et al., 1997, etc.). Crystallite size, especially at lower (diagenetic) grades, seems to be strongly affected by the amount of swelling of interstratified components (e.g. Eberl and Velde, 1989). Lattice strain may also influence the Kübler index, although it is a relatively minor contribution at these low- $\theta$  angles and the percentage strain in illite-muscovite crystallites tends to be small (Arkai and Tóth, 1983; Arkai et al., 1996). Jaboyedoff et al. (2001) suggested that the index is related to the mean number of layers and the variance of the distribution of the number of layers in the coherent scattering domain, the mean percentage of smectite layers present, the Reichweite (a parameter describing layer-stacking order), and instrumental parameters. Using TEM techniques, Merriman et al. (1990, 1995) showed that the Kübler index is largely controlled by the thickness of illite-muscovite crystallites.

Data from many sources (e.g. Eberl et al., 1987, 1990; Merriman et al., 1990, 1995; Środoń et al., 1992; Árkai et al., 1996, 2000; Jiang et al., 1997; Li et al., 1998; Warr and Nieto, 1998; Essene and Peacor, 1995) suggest that phyllosilicates in diagenetic and very lowgrade metamorphic conditions do not reflect thermodynamic equilibria. Consequently, the Kübler index and the FWHM values of chlorite, as well as the structural (e.g. mean crystallite size values) and chemical characterization of these metastable phases, cannot serve as geothermometers. These parameters are only qualitative indicators of the stages the investigated phyllosilicates have reached through a series of metastable mineral reactions (Peacor, 1992; Merriman and Peacor, 1999). Despite this, the Kübler index is a useful indicator of diagenesis and low-temperature metamorphism in different geotectonic regimes.

In summary, 'crystallinity', which may involve crystals that are three-dimensional in nature, cannot be described by one-dimensional diffraction data as in the case of the Kübler index. Thus, this index is not a true measure of 'crystallinity' because crystallinity is complex and cannot necessarily be represented by a single datum. In fact, deviations from perfect structure have specific diffraction effects that may not be measurable by documenting variations of width of a single peak; for example, effects involving diffuse scattering between peaks.

#### RECOMMENDATIONS

(1) It is the recommendation of this committee that the term 'crystallinity index' should not be used. However, it is appropriate to refer to a 'Hinckley index' or 'Kübler index', after those authors who initially described the parameters, or the 'Arkai index' for calibrated FWHM values of chlorite, after the researcher (Prof. Peter Arkai, Hungarian Academy of Sciences) who described the importance of this parameter extensively. In this way, the term 'crystallinity' is discriminated from parameters that may not describe all aspects of crystallinity. However, vast amounts of data exist based on 'crystallinity' or 'crystallinity indices' and reference to earlier work may be awkward without the use of these terms. Thus, limited use may be made of the term 'crystallinity', within quotation marks, only if its use is unavoidable.

(2) Because there is a continuum between phases that are amorphous and crystalline, clarifying the term 'amorphous' is important. The term 'amorphous' must be accompanied by a description of the diffraction effects or other properties that suggest the phase is, in fact, 'amorphous'. In addition, a description of the sample-preparation techniques and experimental conditions must be reported.

After the appropriate descriptions as discussed above are given, adjectival modifiers may be appropriate to describe amorphous, such as 'near amorphous', because this may be a better way to designate or describe the phase. It is appropriate also to use 'X-ray amorphous' to describe the amorphous state as determined by XRD techniques, or by analogy, 'electron amorphous' if determined by electron diffraction.

#### REFERENCES

Árkai, P. (1991) Chlorite crystallinity: an empirical approach and correlation with illite crystallinity, coal rank and mineral facies as exemplified by Palaeozoic and Mesozoic rocks of northeast Hungary. *Journal of Metamorphic Geology*, 9, 723–734.

Árkai, P. and Tóth, N.M. (1983) Illite crystallinity: combined effects of domain size and lattice distortion. Acta Geologica Hungarica, 26, 341–358.

Árkai, P., Sassi, F.P. and Sassi, R. (1995) Simultaneous measurements of chlorite and illite crystallinity: a more reliable geothermometric tool for monitoring low- to very low-grade metamorphisms in metapelites. A case study from the Southern Alps (NE Italy). European Journal of Mineralogy, 7, 1115–1128.

- Arkai, P., Merriman, R.J., Roberts, B., Peacor, D.R. and Tóth, M. (1996) Crystallinity, crystallite size and lattice strain of illite-muscovite and chlorite: comparison of XRD and TEM data for diagenetic and epizonal pelites. European Journal of Mineralogy, 8, 1119-1137.
- Árkai, P., Mata, M.P., Giorgetti, G., Peacor, D.R. and Tóth, M. (2000) Comparison of diagenetic and low-grade metamorphic evolution of chlorite in associated metapelites and metabasites: An integrated TEM and XRD study. *Journal of Metamorphic Geology*, 18, 531-550.
- Brindley, G.W. (1980) Order-disorder in clay mineral structures. Pp. 125–196 in: *Crystal Structures of Clay Minerals and their X-ray Identification* (G.W. Brindley and G. Brown editors). Monograph 5, Mineralogical Society, London.
- Drits, V.A., Sahkarov, B.A., Salyn, A.L. and Manceau, A. (1993) Structural model for ferrihydrite. *Clay Minerals*, **28**, 185–207.
- Drits, V.A., Środoń, J. and Eberl, D.D. (1997) XRD measurements of mean crystallite thickness of illite and illite/smectite: reappraisal of the Kübler index and the Scherrer equation. Clays and Clay Minerals, 45, 461–475.
- Dunoyer de Segonzac, G. (1969) Les minéraux argileux dans la diagenèse passage au métamorphisme. *Mémoires du Service de la Carte Géologique d'Alsace et de Lorraine*, **29**, 321 p.
- Dunoyer de Segonzac, G. and Bernoulli, D. (1976) Diagenese et métamorphisme des argiles dans le Rhétien Sud-alpin et Austro-alpin (Lombardie et Grisons). Bulletin Societé Géologique de la France, 18, 1283–1293.
- Eberl, D.D. and Velde, B. (1989) Beyond the Kübler index. *Clay Minerals*, **24**, 571–577.
- Eberl, D.D., Środoń, J., Lee, M., Nadeau, P.H. and Northrop, H.R. (1987) Sericite from the Silverton caldera, Colorado: Correlation among structure, composition, origin and particle thickness. *American Mineralogist*, 72, 914–934.
- Eberl, D.D., Środoń, J., Kralik, M., Taylor, B.E. and Peterman, Z.E. (1990) Ostwald ripening of clays and metamorphic minerals. Science, 248, 474-477.
- Essene, E.J. and Peacor, D.R. (1995) Clay mineral thermometry a critical perspective. *Clays and Clay Minerals*, **43**, 540–553.
- Flehmig, W. (1973) Kristallinität und Infrarotspektroskopie natürlicher dioktaedrischer Illite. Neues Jahrbuch für Mineralogie, Monatshefte, 351–361.
- Frey, M. (1987) Very low-grade metamorphism of clastic sedimentary rocks. Pp. 9–58 in: *Low Temperature Metamorphism* (M. Frey, editor). Blackie & Son Ltd., Glasgow, UK.
- Hinckley, D.N. (1963) Variability in "crystallinity' values among the kaolin deposits of the coastal plain of Georgia and South Carolina. Clays and Clay Minerals, II, 229-235.
- Jaboyedoff, M., Bussy, F., Kübler, B and Thelin, Ph. (2001) Illite "Crystallinity" Revisited. Clays and Clay Minerals, 49, 156-167.
- Jiang, W.-T., Peacor, D.R., Árkai, P., Tóth, M. and Kim, J.-W. (1997) TEM and XRD determination of crystallite size and lattice strain as a function of illite crystallinity in pelitic rocks. *Journal of Metamorphic Geology*, 15, 267–281.
- Kisch, H.J. (1983) Mineralogy and petrology of burial diagenesis (burial metamorphism) and incipient metamorphism in clastic rocks. Pp. 289-493 in: *Diagenesis of Sediments and Sedimentary Rocks*, 2 (G. Larsen and G.V. Chilingar, editors). Elsevier, Amsterdam.
- Kisch, H.J. (1990) Calibration of the anchizone: a critical comparison of illite 'crystallinity' scales used for definition. *Journal of Metamorphic Geology*, **8**, 31–46.
- Kisch, H.J. (1991) Illite crystallinity: recommendations on sample preparation, X-ray diffraction settings and interlaboratory standards. *Journal of Metamorphic Geology*, 9,

- 665 670.
- Kübler, B. (1964) Les argiles, indicateurs de métamorphisme. Revue de l'Institut Française du Petrole, 19, 1093-1112.
- Kübler, B. (1967) La cristallinité de l'illite et les zones tout à fait supécieures du métamorphisme. In Étages Tectoniques. *Collogue de Neuchâtel 1996*, pp. 105–121.
- Kübler, B. (1984) Les indicateurs des transformations physiques et chimiques dans la diagenèse, température et calorimétrie. Pp. 489-596 in: *Thermométrie et Barométrie Géologiques* (M. Lagache, editor). Societé Française Minéralogie et de Cristallographie, Paris.
- Li, G., Peacor, D.R., Buseck, P.R. and Árkai, P. (1998) Modification of illite-muscovite crystallite size distributions by sample preparation for powder XRD analysis. *The Canadian Mineralogist*, 36, 1435–1451.
- Merriman, R.J. and Peacor, D.R. (1999) Very low-grade metapelites: mineralogy, microfabrics and measuring reaction progress. Pp. 10-60 in: Low-grade Metamorphism (M. Frey & D. Robinson, editors). Blackwell Science, Oxford, IJK
- Merriman, R.J., Roberts, B. and Peacor, D.R. (1990) A transmission electron microscope study of white mica crystallite size distribution in a mudstone to slate transitional sequence, North Wales, U.K. Contributions to Mineralogy and Petrology, 106, 27-40.
- Merriman, R.J., Roberts, B., Peacor, D.R. and Hirons, S.R. (1995) Strain-related differences in the crystal growth of white mica and chlorite: a TEM and XRD study of the development of metapelite microfabrics in the Southern Uplands thrust terrane, Scotland. *Journal of Metamorphic Geology*, 13, 559–576.
- Peacor, D.R. (1992) Diagenesis and low-grade metamorphism of shales and slates. Pp. 335-380 in: *Minerals and Reactions at the Atomic Scale: Transmission Electron Microscopy* (P.R. Buseck, editor). Reviews in Mineralogy, 27, Mineralogical Society of America, Washington, D.C.
- Plançon, A. and Zacharie, C. (1990) An expert system for the structural characterization of kaolinites. *Clay Minerals*, 25, 249–260.
- Środoń, J., Elsass, F., McHardy, W.J. and Morgan, D.J. (1992) Chemistry of illite-smectite inferred from TEM measurements of fundamental particles. *Clay Minerals*, **27**, 137-158.
- Warr, L.N. and Nieto, F. (1998) Crystallite thickness and defect density of phyllosilicates in low-temperature metamorphic pelites: a TEM and XRD study of clay mineral crystallinity-index standards. *The Canadian Mineralogist*, **36**, 1453–1474.
- Warr, L.N. and Rice, A.H.N. (1994) Interlaboratory standardization and calibration of clay mineral crystallinity and crystallite size data. *Journal of Metamorphic Geology*, 12, 141–152.
- Watanabe, T. (1988) The structural model of illite/smectite interstratified minerals and the diagram for its identification. *Clay Science*, **7**, 97–114.
- Weaver, E.W. (1960) Possible uses of clay minerals in search for oil. *Bulletin of the American Association of Petroleum Geologists*, **44**, 1505–1518.
- Weber, F., Dunoyer de Segonzac, G. and Economou, C. (1976) Une nouvelle expression de la 'crystallinité' de l'illite et des micas. Notion d'epaisseur des cristallites. Compte Rendu Sommaire de Seances de la Societé Géologique de France, 5, 225-227.
- Weber, K. (1972) Notes on the determination of illite crystallinity. Neues Jahrbuch für Mineralogie, Monatshefte, 267-276.