

Renaissance Manufacturing Group
260 Central Castings Dr.
Anniston, AL 36206
Ph: 256-256-2566
Fx: 256-256-2566



Order Number Load

71246 3

Part Quantity	Part Number / Part Name / Description	Part Weight	Line Weight			
2500	3541719C3 / U Bolt Rear Spr Plate / Machined	13.5	33,750			
2000	3541720C3 / U Bolt Front Spr Plate / Machined	13.5	27,000			
Order Quantity	Load Quantity	Container	Container Quantity	Tare Weight	Gross Weight	
4500	336	Drop Pan	8	2,936	67,514	
		Bin	12	3,828		
Process:		Austemper	Material:	Ductile Iron	Process ID:	35417XXC3
Key Characteristic Inspection(s):						
Hardness	Scale	Min	Max	Quantity	{Inspection Location.bmp}	
	HBW	269	341	8		
Mag-Particle				100%		
PROCESS STEPS:						EQ# OP Date
1	Rec Insp	Receiving inspection completed upon issue of shop order.				
2	Rack	Load parts lying down X rows of X pieces XX layers a basket, XXX pieces a load Jig Tag:_____ Quantity:_____				
3	PreHeat	Pre-heat to 1100°f for 1 hour minimum.				
4	Austemper	Furnace Temp: XXXX°f Furnace Time: X hours and XX minutes Carbon: X.XX% ±.10 Quench Temp: X00°f Quench Time: X hours and XX minutes Water Flow: 35 mL 10s Time In: _____ Quench In: _____ Quench Out: _____				
5	Hot Wash	Wash parts off to remove salt				
6	Final Insp	Inspect parts as per customer requirements.				
7	Pack	Repackage parts back in the same containers as they were received in.				
RESULTS:			TEMPERED RESULTS:			
			FINAL INSPECTION:			
			PASS	☐	FAIL	☐
			Tested By:		Date:	
OK to Ship:		Date:				