


WAND REX 18.76.988



STANDAARDUITVOERINGEN

staal S 320 GD+Z	dikte mm	normen	
galva	0,63 / 0,75	verzinkt EN 10326	
polyester 25µ	0,63 / 0,75	gelakt EN 10169-1 / EN 10169-2	
plastisol 200µ	0,63	gelakt EN 10169-1 / EN 10169-2	
PVDF	0,63 / 0,75	gelakt EN 10169-1 / EN 10169-2	
HDS 35µ	0,63 / 0,75	gelakt EN 10169-1 / EN 10169-2	
graniet HDX 55µ	0,63 / 0,75	gelakt EN 10169-1 / EN 10169-2	

В	U	R	Ε	Α	U
V	Ε	R	ΙT	Ά	S
Ranno	ort				

> N° 1628665/1F

Doorbuigtesten volgens NF P 34-503 van november 1995

DIKTE	GEWICHT
mm	kg/m²
0,63	6,11
0,75	7,27

OVERSPANNINGTABEL

DRUK				ONDERDRUK				
		+		OVERSPANNING				
A	A	A	A	m	^	↑ ▲	A A	· •
0,63	0,75	0,63	0,75		0,63	0,75	0,63	0,75
251				1,10	253			
218	259			1,15	225	268		
190	226	333		1,20	202	240	240	
167	199	303	361	1,25	181	216	221	264
147	175	277	330	1,30	164	195	205	244
130	155	254	303	1,35	149	177	190	226
116	138	234	279	1,40	136	161	177	211
103	123	216	257	1,45	124	148	165	197
93	110	200	238	1,50	114	135	155	184
83	99	186	221	1,55	105	125	145	172
75	89	173	206	1,60	97	115	136	162
68	81	155	184	1,65	89	106	125	149
62	74	139	165	1,70	83	99	116	138
57	67	125	148	1,75	77	91	108	128
52	62	112	134	1,80	71	85	100	119
47	56	101	120	1,85	66	79	93	111
44	52	91	109	1,90	62	74	87	103
40	48	83	99	1,95	58	69	81	97
37	44	75	89	2,00	54	64	76	90
34	41	70	83	2,05	50	60	71	84
32	38	65	77	2,10	47	56	66	78
		60	72	2,15			61	73
		56	67	2,20			57	68

