MIL-P-8045B
AMENDMENT - 3
22 February 1974
SUPERSEDING
INTERIM Amendment-2(AS)
15 December 1969 and
Amendment-1
19 January 1969

MILITARY SPECIFICATION

PLASTIC, SELF-SEALING AND NON-SELF-SEALING TANK BACKING MATERIAL

This amendment forms a part of Military Specification MIL-P-8045B dated 10 April 1964, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 1

2.1 Under Federal Specifications delete "QQ-A-355"and"QQ-A-362" and add the following:

"QQ-A-250/4	Aluminum Alloy 2024, Plate and Sheet
QQ-A-250/5	Aluminum Alloy, Alclad 2024, Plate and Sheet
TT-S-735	Standard Test Fluids, Hydrocarbon"

Under Military Specifications delete "MIL-S-3136"and"MIL-P-7936."
Under Military Standards add "MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of."

Page 2

3.5 Delete and substitute:

"3.5 Flammability - The backing material for Class 1, Types II and III, shall be self extinguishing when tested in accordance with Method 2022 of Federal Test Method Standard 406. The burning rate of Class 1, Type I, and Class 2, Types I, II and III shall not be greater than two (2) inches per minute."

3.7 Delete "MIL-S-3136" and substitute "TT-S-735."

3.9 Delete last sentence.

3.10 Delete and substitute:

FSC 8030

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:51Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:51Z
Check the source to verify that this is the current version before use.

"3.10 Tensile strength - The minimum average ultimate tensile strength as received for Class 1, Types II and III material in both directions, shall be 22,000 psi. The minimum average ultimate tensile strength for Class 1, Types II and III, after 8 days ±5 hours exposure to 160 ±4°F shall be 18,000 psi in both directions. The average ultimate tensile strength for Class 1, Types II and III material after 7 days ±5 hours immersion in water shall be at least two-thirds of the average as-received value. The minimum average ultimate tensile strength as received for Class 1, Type I, and Class 2, Types I, II, and III in the lengthwise direction shall be 22,000 psi and in the crosswise direction shall be 18,000 psi. The minimum average ultimate tensile strength for Class 1, Type I, plastic backing material after 8 days ±5 hours exposure to 160 ±4°F shall be 15,000 psi; and for Class 2, Types I, II, and III plastic backing material after 8 days ±5 hours exposure to 275 ±4°F shall be 11,000 psi for either direction. The average ultimate tensile strength and secant modulus at 20 percent strain after 7 days ±5 hours immersion in water shall be at least two-thirds of the average as-received value for both lengthwise and crosswise directions."

Page 4

Table I: In "Item 7", under column 3 delete "18" and substitute "12".

Page 5

4.6.4 Delete "QQ-A-362"and"QQ-A-355" and substitute "QQ-A-250/5"and"QQ-A-250/4" respectively.

Page 6

4.6.5 Delete and substitute:

"4.6.5 Tensile impact tests - Tensile impact specimens shall be at least 9 inches by 1 inch in overall size and shall have a configuration similar to the flat tension specimen of Type I as specified in Method 1011 of Standard FED-STD-406. To insure failure of the specimen in the gage section, this section may be 0.40 inch wide instead of the specified 0.50 inch. Each grip end of the specimen shall have two bolt holes, each no larger than 1/4 inch in diameter, spaced at least 1 inch apart and 1/2 inch from the end along the longitudinal axis of the specimen. Tests shall be conducted on a pendulum-type impact machine. The specimen shall be held in rough surfaced grips with two bolts through each end (see Figure 1). The specimen shall be mounted so that one grip is stationary and the other is free to move in a direction along the longitudinal axis of the specimen. The free grip-end shall strike the anvil of the testing machine with sufficient force to break the specimen. Tests shall be conducted at standard conditions. At least twelve specimens shall be tested at standard conditions, half of them being tested in the lenghwise direction and half in the

Source: https://assist.dla.mil -- Downloaded: 20260-17T09:51Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:51Z
Check the source to verify that this is the current version before use.

crosswise direction. Test results shall be reported as the average in each direction in foot-pounds per inch of specimen width at the gage sections. Location of failure for all specimens shall be reported. If failure of a specimen does not occur in the gage section, an additional test shall be conducted. Any other tensile impact test grip can be used only after approval is granted by the procuring activity."

Page 7

5.2 Delete "Specification MIL-P-7936" and substitute "MIL-STD-794."

Custodians:
Army - MR
Navy - AS
Air Force - 11

Review Activities:
Army - AV
Navy - OS
Air Force - 84

User Activities:
Navy - MC

Preparing Activity:
Navy - AS
(Project No. 8030-0415)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:51Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:51Z
Check the source to verify that this is the current version before use.