A-A-2400
March 7, 1986

COMMERCIAL ITEM DESCRIPTION

PAD, FLOOR POLISHING MACHINE (THICK)

The General Services Administration has authorized the use of this commercial item description in preference to types I, IV, VI, and VII of Interim Federal Specification OO-P-0040.

This commercial item description covers floor maintenance pads used for polishing, buffing, scrubbing, and stripping floors and are suitable for mounting on power-driven, rotary-disc type floor maintenance machines which have a speed range between 150 and 350 rpm.

The floor pads are intended for heavy duty floor care maintenance. It is recommended that the using agency standardize on the more economical thick pad as covered by this CID. The use of thin pads (see CID A-A-2370) are only recommended for specific areas or requirements.

The floor pads shall be of the following types and classes (see notes).

Type I - Thick floor pads, nylon
(17 mm (11/16 inch) minimum thick)
- Class 1 - Buffing
- Class 2 - Scrubbing
- Class 3 - Stripping
- Class 4 - Polishing

Type II - Thick floor pad, polyester
(22 mm (7/8 inch) minimum thick)
- Class 1 - Buffing
- Class 2 - Scrubbing
- Class 3 - Stripping
- Class 4 - Polishing

Type III - Thick floor pad, nylon and polyester blend
(22 mm (7/8 inch) minimum thick)
- Class 1 - Buffing
- Class 2 - Scrubbing
- Class 3 - Stripping
- Class 4 - Polishing

Type IV - Thick floor pad, curled animal hair
(25.4 mm (1 inch) minimum thick)
- Class 1 - Buffing
- Class 2 - Scrubbing
- Class 3 - Stripping
- Class 4 - Polishing

FSC 7910

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

The floor pads shall be of the following diameters when ordered by size (see notes):

Size 12 - 304.8 mm (12 inches)	Size 18 - 457.2 mm (18 inches)
Size 13 - 330.2 mm (13 inches)	Size 19 - 482.6 mm (19 inches)
Size 14 - 355.6 mm (14 inches)	Size 20 - 508.0 mm (20 inches)
Size 15 - 381.0 mm (15 inches)	Size 21 - 533.4 mm (21 inches)
Size 16 - 406.4 mm (16 inches)	Size 22 - 558.8 mm (22 inches)
Size 17 - 431.8 mm (17 inches)	Size 23 - 584.2 mm (23 inches)

Salient characteristics.

Material. The materials used in the manufacture of floor maintenance pads shall be long strands of natural or synthetic fibers such as nylon, polyester, a blend of nylon and polyester, or animal hair and suitable for the intended use in accordance with good commercial practice. Abrasive particles shall be made of either natural or synthetic abrasives. Bonding adhesives shall be of such quality as to maintain the shape of the pad without disintegrating or balling when tested for durability. The materials used shall not support the growth of bacteria; and they shall be of such denier, density, strength, and quality to produce a cohesive pad, uniform in structure, and reversible with equal performance on both sides. The pads shall withstand repeated washings in strong detergents and ammonia used in stripping solutions for the removal of accumulated wax, dirt, etc., and the matrix shall retain its original condition and shape after rinsing with water, under pressure, and dried.

Design. The floor pads shall be suitably designed and fabricated for use with rotary disc electric floor machines and shall be suitable for use on various type floors. The floor pads shall be resilient so as to contact the floor over their entire area. The pads shall have a scored or removable center hole 14 mm plus or minus 3.2 mm (3-1/2 inches plus or minus 1/8 inch) in diameter. The center hole shall be concentric with the circumference. Maximum runout shall be less than 3.2 mm (1/8 inch). The sizes of the pads shall be as specified within a tolerance of plus or minus 3.2 mm (1/8 inch) on the diameter. The pad shall be thoroughly and uniformly impregnated with abrasive particles. The uniform distribution of particles in the cross-section shall be within plus or minus 15 percent. The flat surface of the pad shall also show no concentrations of particles visible to the eye when viewed toward a bright light source. There shall be no more than 15 percent difference between the two "percent of ash by weight" percentages (see Table II, line 6) for the same sample pad. There shall be no more than 10 percent difference between the highest and the lowest "total percent of ash by weight" percentages (see Table II,line 8) calculated for the four sample pads.

Type I nylon floor pads. Type I nylon floor pads shall be made of one piece, unified mat. The materials of the pads shall be formed or bonded into a solid disc. The pads shall maintain their thickness in accordance with Table II. Pads of spirally-wound ribbons of interlocking fibers are not acceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Class 1. The abrasive content for the type I, class 1 buffing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150-mesh screen. A minimum of 99 percent of the remaining abrasive particles shall pass through a 200-mesh screen. A minimum of 90 percent of the remaining abrasive particles shall pass through a 270-mesh screen.

Class 2. The abrasive content for the type I, class 2 scrubbing pads shall be no more than 60 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 85 percent of the remaining particles shall pass through a 150-mesh screen. A minimum of 55 percent of the remaining particles shall pass through a 200-mesh screen. One hundred percent of the remaining particles shall pass through a 270-mesh screen.

Class 3. The abrasive content for the type I, class 3 stripping pads shall be no more than 65 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 75 percent of the remaining particles shall pass through a 150-mesh screen. One hundred percent of the remaining particles shall pass through a 200-mesh screen.

Class 4. The abrasive content for the type I, class 4 polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 270-mesh screen.

Type II polyester floor pads. Type II polyester floor pads shall be made of one piece, unified mat. The materials of the pads shall be formed or bonded into a solid disc. The pads shall maintain their thickness in accordance with Table II. Pads of spirally-wound ribbons of interlocking fibers are not acceptable.

Class 1. The abrasive content for the type II, class 1 buffing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150-mesh screeen. A minimum of 99 percent of the remaining abrasive particles shall pass through a 200-mesh screen. A minimum of 90 percent of the remaining abrasive particles shall pass through a 270-mesh screen.

Class 2. The abrasive content for the type II, class 2 scrubbing pads shall be no more than 60 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 85 percent of the remaining particles shall pass through a 150-mesh screen. A minimum of 55 percent of the remaining particles shall pass through a 200-mesh screen. One hundred percent of the remaining particles shall pass through a 270-mesh screen.

Class 3. The abrasive content for the type II, class 3 stripping pads shall be no more than 65 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 75 percent of the remaining particles shall pass through a 150-mesh screen. One hundred percent of the remaining particles shall pass through a 200-mesh screen.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Class 4. The abrasive content for the type II, class 4 polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 270-mesh screen.

Type III nylon and polyester floor pads. Type III nylon and polyester floor pads shall be made of one piece unified mat. The materials of the pads shall be formed or bonded into a solid disc. The pads shall maintain their thickness in accordance with Table II. Pads of spirally-wound ribbons of interlocking fibers are not acceptable.

Class 1. The abrasive content for the type III, class 1 buffing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150-mesh screeen. A minimum of 99 percent of the remaining abrasive particles shall pass through a 200-mesh screen. A minimum of 90 percent of the remaining abrasive particles shall pass through a 270-mesh screen.

Class 2. The abrasive content for the type III, class 2 scrubbing pads shall be no more than 60 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 85 percent of the remaining particles shall pass through a 150-mesh screen. A minimum of 55 percent of the remaining particles shall pass through a 200-mesh screen. One hundred percent of the remaining particles shall pass through a 270-mesh screen.

Class 3. The abrasive content for the type III, class 3 stripping pads shall be no more than 65 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 75 percent of the remaining particles shall pass through a 150-mesh screen. One hundred percent of the remaining particles shall pass through a 200-mesh screen.

Class 4. The abrasive content for the type III, class 4 polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 270-mesh screen.

Type IV curled hair floor pads. Type IV curled hair floor pads shall be made of one piece, unified mat. The materials of the pads shall be formed or bonded into a solid disc. The pads shall maintain their thickness in accordance with Table II. Pads of spirally wound ribbons of interlocking fibers are not acceptable.

Class 1. The abrasive content for the type IV, class 1 buffing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150-mesh screeen. A minimum of 99 percent of the remaining abrasive particles shall pass through a 200-mesh screen. A minimum of 90 percent of the remaining abrasive particles shall pass through a 270-mesh screen.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Class 2. The abrasive content for the type IV, class 2 scrubbing pads shall be no more than 60 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 85 percent of the remaining particles shall pass through a 150-mesh screen. A minimum of 55 percent of the remaining particles shall pass through a 200-mesh screen. One hundred percent of the remaining particles shall pass through a 270-mesh screen.

Class 3. The abrasive content for the type IV, class 3 stripping pads shall be no more than 65 percent by weight. A minimum of 99 percent of the total abrasive particles shall pass through a 100-mesh screen. A minimum of 75 percent of the remaining particles shall pass through a 150-mesh screen. One hundred percent of the remaining particles shall pass through a 200-mesh screen.

Class 4. The abrasive content for the type IV, class 4 polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 270-mesh screen.

Workmanship. The floor pads shall be free from any defects, imperfections, or material that would adversely affect performance, serviceability, or appearance, or may cause any undesirable effects during use. The fibers shall not become matted nor lose their resilience.

Quality assurance provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations or tests shall be kept complete and available to the Government as specified in the contract or purchase order. The Government reserves the right to perform any of the inspections set forth in the CID where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Test equipment. The durability test shall be performed on a Schiefer Abrasion Testing Machine (see notes), or equal. The Schiefer machine is designed primarily for wear testing of fabrics under "dry" conditions. The machine is custom made and should be ordered with GSA modifications as follows:

(1) Water reservoir - A water reservoir, an ON-OFF stop cock, a metering stop cock, tubing to direct a constant rate of water to the abrading disc, and a catch basin with drain.

(2) Upper holding plate - Reduce the diameter of the upper specimum-holding rotating plate from 101.6 mm to 76.2 mm (4 inches to 3 inches) and add a gripping material to hold the test specimen. This material is similar to the material used on the floor maintenance machines for holding the floor pads in place, i.e., "Insta-lok", "EWU", or other gripping material that can be adhered to or attached to the metal plate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

(3) Lower holding plate - Increase the diameter of the lower rotating plate (for holding the abrading disc) from 101.6 mm to 127 mm (4 to 5 inches), and add two diametrically opposed pins to hold the abrading disc support plate. The abrading disc support plate is a rigid flat plate.

(4) Abrading disc support plate - The abrading disc support plate is a rigid flat plate approximately 3.2 mm (1/8 inch) by 127 mm (5 inches) in diameter with diametrically opposed holes or notches to fit securely over the pair of retaining pins inserted in corresponding locations near the outer rim of the lower drive plate. The plate may be made of any material that is non-corroding and will not deteriorate in water, such as aluminum or plastic.

(5) Abrading disc - A supply of 127 mm (5 inches) diameter, adhesive-backed, uncoated, silicon carbide (SiC) waterproof grinding discs with grit sizes of 120, 180, and 220. The disc may be 3M Scotch Brand or equivalent. One disc is required for each durability test.

(6) Metric weights - A series of metric weights of 250, 500, and 1000 grams to load the hub of the machine.

In addition to the above, some of the equipment required for the abrasive content and distribution tests and other tests are as follows:

(1) Abrasive distribution test equipment. The test equipment required to accomplish the tests are four vested sieves; one 100-mesh screen with a hole size of 149 microns; one 150-mesh screen with a hole size of 105 microns; one 200-mesh screen with a hole size of 74 microns; one 270-mesh screen with a hole size of 57 microns; and a bottom pan.

(2) Die cutter - A cutting die to remove a 76.2 mm (3 inches)-diameter disc test specimum from the sample pads. It can be made from a 79.4 mm (3-1/8 inches)-diameter steel hole saw with the teeth ground off and the resulting rim sharpened.

(3) Cylindrical weight - A 76.2 mm (3 inches)-diameter non-corroding metal cylindrical weight of 1.00 kg having parallel smooth faces. This weight simulates closely the pressure exerted by the average commercial floor maintenance machine.

(4) A flat 6.4 mm (1/4 inch) thick by 152.4 mm (6 inches) square plate made of a non-corroding material with a rigid vertical post to hold a thickness gauge from 0 to 50 mm calibrated in 0.1 mm increments. The gauge is to be adjusted for zero at the center of the top face of the disc resting on the base plate. The height of the test specimen can be read directly when it is placed under the disc.

(5) Other equipment should include a gram scale calibrated in centigrams; an 85 to 100 mm-diameter ashing dish; gas burner for igniting specimens (Meeker type or equivalent); and other items as specified in the test paragraphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Ashing procedure. Heat a suitably clean ashing vessel, such as a porcelain dish, approximately 85 to 100 mm in diameter, at 600 degrees Celsius (C) for 15 minutes. Cool in desiccator and weigh to nearest centigram. Add samples of the floor pad to be analyzed, favoring pieces approximately 1/2 g each, confining each within the perimeter of the vessel by means of a screen or similar means (This will help to prevent certain types of pad samples from floating out of the vessel). Weigh the vessel and contents. Compute and record the sample weight with the appropriate identification data. Initial ashing to drive off obnoxious organic volatiles should occur under a fume hood until a dry char is obtained. Finish ignition of the ash in the muffle furnace. A furnace with regulated air ventilation is preferable because air circulation aids the ashing which may be completed in approximately 15 minutes. Without air circulation, one-half to one hour may be required. When ashing is complete, remove vessel with ash to a refractory plate to cool, finishing the final cooling in a desiccator. Be careful to avoid expulsion of fluffy ash particles. When cooled to room temperature, weigh the vessel with the ash and transfer the ash to a small plastic or glass vial, properly identify and retain for the abrasive (particle size) distribution test.

Inspection. Sampling for inspection shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes, except where otherwise indicated herein. The lot size shall be consist of all pads of the same type and size offered for acceptance at one time. The sample unit is one floor pad.

Visual and dimensional examination. Remove and label four pads of the same type and size for examination and testing, each from a different carton. Each whole pad shall be examined for finish, construction, workmanship, and dimensional requirements. Defects shall be as classified in Table I. The inspection level shall be level II with an acceptable quality level (AQL) of 4.0 defects per hundred units for major defects and 6.5 defects per hundred units total.

TABLE I - Classification of defects

Examine	Defect	Classification Major	Minor
General	Not type specified	X	
	Not class specified	X	
	Not size specified	X	
	Not material specified	X	
	Design not as specified	X	
	Thickness not as specified	X	
	Workmanship not as specified		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Thickness test. Using the die cutter, cut eight 3-inch diameter discs, two from each pad. If concentrations of abrasives are visible within the pad indicating a definite variation in the distribution of abrasives material, cut one disc from the concentrated area and one disc from a non-concentrated area. If there are no visible concentrations, cut two discs from opposite ends of the pad at random diameters. Each sample disc should be labelled with pad number, pad type, concentrated or non-concentrated area, and other information as required for future identification. Select any four discs for thickness testing. Each disc is to be conditioned to ensure that any irregularity in thickness caused by storing and shipping is eliminated. Conditioning is achieved by placing the disc on a flat, level, hard surface and allowing it to remain for 48 hours at room temperature. After 48 hours, place the sample on the height gauge, and place the 100-gram leveling plate concentric and horizontal on the sample. Wait one minute and measure the height of the sample. Take four readings 90 degrees apart. Average the four readings and record the distance. Repeat the procedure using the other three discs. Average the four results. Pad thickness shall be no less than specified fot the type and class. The discs shall then be saved with the other four discs for the durability test.

Abrasive uniformity. Sampling shall be in accordance with MIL-STD-105, inspection level S-2 with an acceptable quality level (AQL) of 4.0 percent defective. Eight 1-inch square sections shall be cut from the pads, two from each pad similar to the abrasive samples below and close to the same areas where they are obtained. Each square shall be sliced into three approximate equal layers: top, middle, and bottom. Each layer shall be labeled with pad number, pad type, concentrated or non-concentrated area, top, middle, or bottom layer, and any other information that may be required for future identification. The eight top layers, or as many as will fit in the ashing dish, shall be ashed together in accordance with the ashing procedure. Calculate the percent of ash by weight (see Table II, line 6). Repeat the procedure for the middle layer samples and again for the bottom layer samples. The maximum difference of the percentages for the three layers shall be no more than 15 percent as specified in the design paragraph. If the percentage is greater than specified, the pad is considered defective. The ash shall be saved in accordance with the ashing procedure.

Abrasive content and distribution examination. Sampling shall be in accordance with MIL-STD-105, inspection level S-2, with an acceptable quality level (AQL) of 4.0 percent defective. Samples shall be cut from two different areas within each pad weighing 1/2 g or more. If concentrations of abrasives are visible within the pad indicating a definite variation in the distribution of abrasive material, cut one sample from the concentrated area and one sample from a non-concentrated area. If there are no visible areas, cut two samples from opposite ends of the pad at random diameters. Each sample should be labelled with pad number, pad type, concentrated or non-concentrated area, and any other information that may be required for future identification. Ash the samples in accordance with the ashing procedure. Use as many sample pieces from the pad as necessary to get enough ash for a good sampling. The ash shall be saved in accordance with the ashing procedu Calculate the average total abrasive content (see Table II, line 8) for conformance to the abrasive content requirement as applicable.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:22Z
Check the source to verify that this is the currentversion before use.

Abrasive distribution. Using the ash obtained above, assemble clean nested sieves with the pan in place, nesting the 100, 150, 200, and 270-mesh screens from top to bottom. Place the sample to be sieved into a small glass, agate, or polished porcelain mortar. Rub the mass while avoiding grinding to break up agglomeration of the individual finest particles. Avoid too vigorous action that may cause static electricity on the particles. Transfer the loosened mass to the top of the sieve set. Carefully assist the particles with crosswise rather than downward actions on the top screen. Use small semi-stiff hair or fine bristle type brushes trimmed to about 1/2-inch long and other convenient tools, such as a smooth-edged scraper or spatula to move the particles back and forth over the screen until all particles of appropriate size have passed through. (Avoid shaking the sieves, because the action could cause further agglomeration and would give false results favoring the larger sizes). Remove the top screen and repeat the procedure on the next finest screen. Proceed likewise from top to bottom until the finest fraction is through to the pan. Collect, weigh, and record weight of particles remaining on top of each screen, noting screen size. Total the recorded weights of all fractions recovered. (Note - This will invariably be a little less than the total ash weight.) Compute the percentage of each size fraction on the basis of the total recovered weight for conformance to the applicable requirements.

The samples cut from the pads may be labeled as follows: Pad 1 - sample A, Pad 1 - sample B, Pad 2 - sample A, Pad 2 - sample B, etc., with any additional information as required. For the table the samples are identified as A and B.

TABLE II - ABRASIVE CONTENT CALCULATIONS

1. (Wv) - weigh the vessel to the nearest gram (see ashing procedure).
2. (Wsv) - Add sample A to the vessel and reweigh.
3. (Ws = Wsv - Wv) - Subtract vessel weight = sample weight.

---- Ash the sample ----

4. (Wav) - weigh ash and contents.
5. (Wa = Wav - Wv) - Subtract vessel weight = ash weight.
6. (% ash weight) - 100 x Wa/Ws = percent of ash by weight.

---- Do steps 1 thru 6 for all samples ----

7. To calculate the total percent of ash by weight for each pad, add line 6 for sample A and sample B and divide by 2.
8. To calculate the percent of ash by weight of the pads for conformance to the requirements, average the sum of the percentages from line 7 for the four pads.

Durability test preparation. Balance the Schiefer machine before starting the durability test. Without any weight on top of the hub, move the lever arm to the midway floating position to free the cam and release the balance arm. The specimen holder is now in a free-floating mode. Be sure the cam is not touching the horizontal bar on either side. Turn on the drive motor. The upper rotary plate (specimen holder) should remain in it's

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

vertical position without any up and down bobbing or travel. If there is any, adjust the weight on the balance beam. When the machine is properly balanced, all test specimens should be tested without further machine adjustment. Check the balance at the start of each day of testing.

Before the start of each durability test, prepare the machine by selecting the appropriate abrasive disc and load weight for the class pad to be tested (see Table III). Press the abrasive disc evenly on the metal supporting plate and mount it on the lower plate of the machine. Fill the reservoir with water and open the on-off valve. Position the discharge tube to drop water on the lower plate close to the upper plate but not on it. Adjust the water control valve to deliver 20 plus or minus 2 drops per minute. Shut off the water at the on-off valve and add the required load to the top of the hub.

Durabilty test. The duability test shall be performed under the conditions as specified in Table III.

TABLE III - RECOMMENDED OPERATING PARAMETERS

Classes	SiC Abrasive Grit size	Test Load (Kg)	Wet or Dry
1. Strippers	Uncoated 120	1.25	Wet
2. Scrubbers	Uncoated 180	1.00	Wet
3. Buffers	Uncoated 180	0.75	Dry
4. Polishers	Uncoated 220	0.50	Dry

Durability test procedure. Press the test specimen onto the upper rotary sample holder. Move the lever to the extreme right position to lower the specimen onto the lower rotary plate. Manually press down to seat the specimen firmly before proceeding with the test. Zero the cycle counter. Set the timer to signal the approaching cycle (approximately 4 minutes for every 1000 cycles). Start the water flow if the specimen is a stripping or a scrubbing pad sample. Move the lever to the midway free-floating position. Turn on the motor and check that the specimen is making proper contact with the abraiding disc.

Stop the machine after 1000 cycles. Remove the test specimen. Record the cycle count and measure the pad thickness (T 1000). Remount the test specimen in the inverted mode and return the lever to the midway free-float position. Turn on the motor and resume the test. Reset the timer to signal the next approaching cycle (5000 cycles for stripping and scrubbing pads, 2000 cycles for polishing and buffing pads). Again stop the machine, remove the specimen, record the cycles, and measure remaining pad thickness with the Height Gauge. Invert specimen again and repeat operation as before until the pad's thickness is 35 plus or minus 5 percent of the original thickness at "X" cycles. Pads shall not wear down more than 30 percent below the original thickness, disintegrate or ball under 50,000 cycles.

Note the physical condition of the remnant of the specimen at the end of the test. Record whether it is completely intact, shows minor disintegration or complete disintegration. This characteristic is associated with the quality of the bonding material within the pad.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Calculations. (Record any condition that caused the test to be terminated,i.e., pad disintergration, balling, etc.)

$$\% Tr = Tc/Ti \times 1000$$

Where: Tr = Remaining pad thickness; Tw = Pad wear
Tc = Thickness at "x" cycles; Td = Pad thickness at disintegration
Ti = Initial thickness; Tf = Pad wear after 50,000 cycles

1. Calculate pad wear at 35 plus or minus 5 percent remaining thickness.

$$\% Tw = \frac{Ti-Tc}{Ti} \times 100$$

2. Calculate percentage of wear after 50,000 cycles.

$$\% Tw = \frac{Ti-Tf}{Ti} \times 100$$

3. Calculate percentage of pad wear when or if disintegration occurs before Tw approaches 35 plus or minus 5 percent or 50,000 cycles.

$$\% Tw = \frac{Ti-Td}{Ti} \times 100$$

Regulatory requirements. In accordance with the Section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or purchase order.

Notes. Purchaser must specify type, class, and size floor pad required. The Procuring Contracting Officer shall specify that the test for abrasive content and abrasive distribution are required during the initial inspection and testing and thereafter only when changes in the manufacturer, manufacturing process, material, or design are made during the period of the contract. If the same manufacturer is awarded the contract again for the following year, and the process, material, or design have not changed, the abrasive content and distribution examination is not required. If a mandatory source is awarded the contract, the raw material from the manufacturer must pass all the requirements of this CID. If the raw material is from a manufacturer who has passed all the requirements of this CID, and there have been no changes in the process, material or design, the abrasive distribution and content requirements may also be waived upon receipt of a certification of that fact from the manufacturer. A complete set of tests and examinations shall be performed at least every three years regardless of past performance.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:22Z
Check the source to verify that this is the currentversion before use.

The Schiefer Abrasion Testing Machine is manufactured by the Frazier Precision Instrument Company, Inc., 210 Oakmont Avenue, Gaithersburg, MD 20760. The machines are custom made and should be ordered with GSA modifications.

Product cleaning information - The thick pads should be cleaned immediately after use to prevent loading of the pad and to increase its life and serviceability. The pad should be cleaned with hot water, using a spray nozzle, to free dirt and other matter which has been picked up by the pad. In many instances, the pads are loaded with wax and other polishing particles which are very difficult to remove by water alone. In this case, the pads may be cleaned by soaking approximately one hour or more in a mild stripping solution. Pads should then be rinsed thoroughly with hot water and dried before use. Pads may soften while in the stripping solution but the original condition will return after drying. Under no circumstances should the pads be cleaned with any type of brush. This will tend to destroy or loosen the fibers of the pad, which will decrease the serviceability and life of the pad.

Copies of military standards may be obtained from the procuring activity or as directed by the contracting officer.

Interim Federal Specification OO-P-0040	CID A-A-2400
Type I	Type I
Type IV	Type IV
Type VI	Type II
Type VII	Type III

WHEN THIS COMMERCIAL ITEM DESCRIPTION IS USED FOR PROCUREMENT, THE COMMERCIAL ITEM CERTIFICATION CLAUSE DOES NOT NEED TO APPEAR IN THE SOLICITATION.

MILITARY INTEREST:

None

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.