U-P-401E
September 16, 1975
SUPERSEDING
Int. Fed. Spec. U-P-00401D
June 2, 1969 and
Fed. Spec. U-P-401C
June 23, 1959

FEDERAL SPECIFICATION

TAPE, ADHESIVE, SURGICAL

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers adhesive tape made of suitable cotton, synthetic, or combination thereof, fabric with an adhesive on one side for use in medical or surgical procedures.

1.2 Classification.

1.1.1 Types. Surgical tapes shall be of the following types, as specified (see 6.2):

Type I----------Standard base fabric, non-water-repellent.
Type II----------Waterproof-back fabric.
Type III----------Napped cotton-back cloth (Moleskin).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications

CCC-C-665	-	Crinoline; Surgical.
PPP-B-566	-	Boxes, Folding, Paperboard.
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-B-676	-	Boxes, Set-Up.
PPP-T-76	-	Tape, Pressure-sensitive Adhesive Paper, Water Resistant (For Carton Sealing).

FSC 6510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).
Fed. Test. Method Std. No. 191 - Textile Test Methods.
Fed. Std. No. 595 - Color.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications and standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Type I. Type I shall be adhesive tape, made of a white cotton, synthetic or combination thereof fabric backing evenly coated on one side with a suitable pressure sensitive adhesive mixture. The base of the mixture shall be new, natural rubber, new synthetic rubber, or new rubber substitutes. Reclaimed natural rubber, reclaimed synthetic rubber or reclaimed rubber substitutes

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

3.1.1 Type I (cont'd)

shall not be used wholly, or in part. As an alternate, the adhesive shall be spread in such a manner that numerous discrete open areas in the adhesive are present in a uniform pattern. Such a pattern may be lines (spaces) approximately 1/64 inches wide, 1/4 inch apart running at a 45° angle with the length of the tape.

3.1.2 Type II. Type II tape shall be made of a cotton synthetic or combination thereof fabric backing, the outer surface of which shall be coated with resins, esters of cellulose, or the like, which renders it water-repellent and easily washable. The inner surface shall be calendered spread with an adhesive mass similar in composition to that prescribed for type I plaster.

3.1.3 Type III. Type III tape shall be made of a thick, soft, napped, cotton backing white or tinted (moleskin) calendered spread with an adhesive mass on one side similar in composition to that prescribed for type I plaster. No reclaimed rubber or reclaimed rubber substitutes shall be used. The type III tape (moleskin) shall have a facing on the adhesive side. Facing shall be as described in paragraph 3.6. Facing shall be removable from the adhesive surface without excessive pull.

3.2 Continuous length. Each size except those indicated below shall be furnished in one continuous piece except 5 percent of each size may be furnished in two pieces, provided no piece is less than 12 inches in length. The following sizes and types shall be furnished in one continuous piece: One inch by one yard, waterproof, back, camouflaged. Two inches by 5 yards, waterproof back, white.

3.3 Type of rubber base material. When requested by the procuring activity, the contractor shall identify the type or types of the base material of synthetic rubber or rubber substitutes used (see 6.1).

3.4 Dimensions. Surgical adhesive tape shall be furnished in accordance with tables I, II, and III as specified (see 6.1), and shall be tested as specified in 4.3.2.

3.4.1 Tolerance. The actual length of the adhesive tape shall be not less than 98 percent of the label length of the tape. The width of the tape shall be ± 1/16 inch of the label width of the tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

3.4.2 Color. The color shall be as shown in tables I through III (see 6.1). For camouflaged (field brown), the cotton-fabric backing shall be dyed brown by the use of 2 ounces of Pontamine Brown B. T. Concentrate per 100 pounds of backing material or an equivalent approved by the procuring activity.

3.5 Backing.

3.5.1 Type I. The backing of type I surgical adhesive tape shall be a plain weave, white, bleached-cotton, synthetic or combination thereof having not less than 96 yarns per square inch, when tested as specified in 4.3.5, and weigh not less than 1.7 ounces per square yard. It shall have a breaking strength not less than 35 pounds (in the warp) per inch of width, when tested as specified in 4.3.4. The running length of the fabric shall be in the warp direction. As an alternate, the backing may be a plain weave white cotton, synthetic or combination thereof fabric which has been bleached and sized to improve handling and end use characteristics, without changing the above requirements or visual appearance.

3.5.2 Type II. The fabric, plus the water-repellent material forming the backing of type II, surgical adhesive tape, shall weigh not less than 2.9 ounces per square yard and shall have a breaking strength of not less than 35 pounds (in the warp) per inch of width when tested as specified in 4.3.4. Base fabric shall be white, bleached cotton, synthetic or combination thereof, of plain weave having a minimum thread count of 96 threads per square inch and minimum weight of 1.7 ounces per square yard.

TABLE I. Adhesive tape in rolls (uncut)

Backing and Color	*Width (Inches)	*Length (Yards)
**Moleskin, flesh and white	12	5

*Nominal dimensions
**Either color acceptable

TABLE. II Adhesive Tape in Rolls (cut)

Backing	Width Inches	Length Inches	Assorted cuts per 12 inch roll Number	Width of cut, inches
Plain back (white)	12	10	4	1/2
			3	1
			2	2
			1	3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

TABLE II. Adhesive Tape in Rolls (cut) (cont'd)

Backing	Width Inches	Length Inches	Cuts per 12 inch roll Number	Width of cut, inches
Plain Back (white)	12	10	24	1/2
	12	10	12	1
	12	10	8	1-1/2
	12	10	6	2
	12	10	4	3
	12	10	3	4
Waterproof back (white)	12	10	24	1/2
	12	10	12	1
	12	10	6	2
	12	10	4	3

TABLE III. Adhesive Tape on spools or cores (uncut)

Backing And Color	Width Inches	Length Yards
Plain back, white	2	10
Plain back, white	3	5
Waterproof back, white	1/2	5
Waterproof back, white	1/2	10
Waterproof back, white	1	5
Waterproof back, white	1	10
Waterproof back, white	2	5
Waterproof back, camouflaged (field brown)*	1	1
Plain back, camouflaged (field brown)	1	5

*This size shall be evenly wound on a flat waxed cardboard core. The tape shall strip completely and cleanly from the core. To facilitate stripping the tape, the core may first be wound with one turn of crinolone.

3.5.3 Type III. The fabric forming the backing of type III, surgical adhesive tape, shall weigh not less than 9 nor more than 10.5 ounces per square yard and shall have a breaking strength of not less than 40 pounds (in the warp) per inch of width when tested as specified in 4.3.4. The running length of the fabric shall be in the warp direction.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.

3.6 Facing. Facing shall be polyethylene, crinoline, silicone treated release paper, or continuous organic film embossed or unembossed. If crinoline is used, it shall conform to the requirements of Federal Specification CCC-C-665, except that the basic fabric shall be type I, plain gauze.

3.7 Weight of adhesive mass. The minimum weight of the adhesive mass, when tested as specified in 4.3.1, shall be as follows:

Type I - 3.5 ounces per square yard
Type II - 3 ounces per square yard
Type III- 3 ounces per square yard

3.8 Adhesive quality. The adhesive quality of surgical adhesive tape shall be not less than 40 pounds when tested as specified in 4.3.3.

3.9 Workmanship. The adhesive tape shall be free from imperfections which might affect the appearance or serviceability of the tape. The plaster mass and water-repellent substances shall be homogeneous and uniformly spread. Each size shall be evenly cut, free from ravels, extraneous matter, and excessive bumps due to imperfections in the fabric. No residual film of adhesive shall cover the threads at the open areas, and the threads of the cloth shall not be damaged. The tape shall be wound on the spools, rolls or flat cores with uniform pressure in such a manner as to prevent excessive sticking of the layers of tape as the core is unwound. Tape edges shall be straight or pinked, and the tape shall be evenly wound on the core.

3.10 Delivery. Not more than six months shall have elapsed from the date of manufacture of the adhesive tape to the date of delivery to the Government.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of cloth or flannel backing, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the item identification, the name of the component/material, the lot number, individual test results, and the specification requirements.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in tables VI and VII.

4.2.1 Sampling for examination. Sampling shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in tables IV and V below. The unit of product for examination purposes shall be the individual roll, spool, or flattened core packet of tape.

TABLE IV. Visual Examination

	Inspection level	AQL
Major A	S-2	1.0 percent defective
Minor A	S-2	4.0 percent defective

TABLE V. Destructive Visual Examination

	Inspection level	AQL	Minimum sample size
Major B*	S-1	Note 1	3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

*If any defects are found, the inspection level shall go to S-3 with an AQL of 1.5 percent defective, and full sample shall be tested.

Note 1. Unless otherwise modified, acceptance number shall be zero for all sample sizes.

4.2.2 Examination. The tape shall be examined for defects including, but not limited to, those listed in table VI.

TABLE VI. Categories and defects

Major A	
101	Tape rolls or spools not uniformly and smoothly wound.
102	Sides of tape rolls or spools not free of cuts or deformed areas.
Major B	
151	Adhesive separates from backing upon unwinding.
152	Tape, roll or spool, not two or less pieces.
153	Tape in roll or spool not free from holes, tears, breaks, cuts, or splits.
154	Adhesive coating on roll or spool not uniform and free of breaks.
Minor A	
201	Tape roll or spool crushed to the extent of presenting an oval rather than a round profile.
202	Color not as specified.

4.2.3 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table VII.

TABLE VII. Sampling for Tests

Characteristic	Test procedure	Sample unit	Insp. level	AQL	Minimum sample size
Weight, backing	4.3.1	roll, spool or core	S-1	*	3
Weight, adhesive mass	4.3.1	roll, spool or core	S-1	*	3
Adhesive quality	4.3.3	roll, spool or core	S-1	*	3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

TABLE VII. Sampling for Tests (Con.)

Characteristic	Test procedure	Sample unit	Inspection level	AQL	Minimum sample size
Breaking strength	4.3.4	roll, spool or core	S-1	*	3
Width	4.3.2.1	roll, spool or core	S-1	*	3
Length	4.3.2.2	roll, spool or core	S-1	*	3

The sample unit of rool, spool or core shall be used for referee testing. All testing shall be performed on in-process specimens where appropriate and applicable.

*Unless otherwise modified acceptance number shall be zero for all sample sizes.

Where possible, the same sample shall be used for the determination of two or more characteristics for which test procedures are specified.

4.3 Examination of preparation for delivery. An examination shall be made to determine compliance with the packaging, packing and marking requirements of section 5. Defects shall be scored as specified in table VIII. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with AQL of 4.0 expressed in terms of percent defective.

TABLE VIII. Examination of preparation for delivery

Examine	Defect
Contents	Not as specified.
Container	Not as specified.
Marking	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Material	Component missing or damaged.
Workmanship	Bulging or discoloration of containers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.3.1 Examination of closure, waterproofing and banding of container. When the shipping container is required to comply with PPP-B-636, the examination for defects in closure, waterproofing or banding shall be in accordance with the appendix of the box specification.

4.4 Tests.

4.4.1 Weight, backing, and adhesive mass. The weight of a sample measuring 20 square inches shall be determined. The sample shall be placed mass side down on a glass plate and the backing wetted with Petroleum Ether, U.S.P. After 30 seconds, the backing shall be stripped from the glass plate leaving the bulk of the mass behind. The remaining mass shall be removed from the sample by repeated immersion in Petroleum Ether. The fabric backing shall then be air dried and the weight determined. The weight of the adhesive mass is the original weight of the adhesive tape, minus the determined weight of the backing. This factor multiplied by a factor of 2.28 will convert the actual mass weight into ounces per square yard.

4.4.2 Dimensions.

4.3.2.1 Width. Measure the width of the plaster at five points evenly spaced throughout the length of the roll or spool; the average of the five measurements shall be the width of the tape.

4.4.2.2 Length. Length of surgical adhesive tape shall be measured under only sufficient tension to straighten the tape and prevent wrinkles.

4.4.3 Adhesive quality. The adhesive quality of all types of tape shall be determined by cutting strips 1 inch wide and approximately 6 inches long from each sample unit selected for test. Two square inches (1 by 2 inches) of these strips shall be applied to a bakelite surface by means of a rubber roller under pressure of 30 ounces. The rubber roller shall have a durometer hardness of 70-80. The roller shall pass over the tape twice at the rate of 12 inches per minute. The temperature of the bakelite surface and the tape shall be adjusted approximately 37° centigrade, and immediately tested. The tape shall be pulled (sheared) from the board by means of the machine specified in method 5100 of Federal Standard 191, the jaws separating at the rate of 12 ± 0.5 inches per minute. The adhesive quality shall be the average of the results obtained from not less than five specimens from each sample roll.

Source: https://assist.dla.mil -- Downloaded: 20261O-26T11:20Z
Check the source to verify that this is the current version before use.

4.4.4 Breaking strength of cloth backing. Each sample unit shall be tested to determine the breaking strength of the cloth backing as specified in method 5102 of Federal Standard 191. Test shall be conducted without the removal of the adhesive mass or other soluble material(s). The breaking strength of the cloth backing shall be the average of the results obtained from not less than five specimens from each sample roll.

4.4.5 Thread count of cloth backing. The total number of yarns per square inch (warp and filling) shall be counted on five specimens from each sample roll. The average of the results obtained on the five specimens shall be the thread count for the sample roll.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Packaging quantities. The number of units of issue indicated in table IX shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

TABLE IX. Packaging quantities

Type	Size	Unit of issue	Unit package	Intermediate package	Exterior container
I	3" by 5 yds.	Spool	1	6	144
I	12" by 10 yds.	Roll	1	12	24
III	12" by 5 yds.	Roll	1	Not Required	12
*II	2" by 5 yds.	Package	1	Not Required	4
I	1" by 5 yds.	Spool	1	12	288
I	2" by 10 yds.	Spool	1	6	144
**II	1" by 1 yd.	Box	1	Not Required	24

* Each unit package contains 36 spools of tape.

** Each box shall contain one hundred one inch by one yard pieces of adhesive tape wound on flat waxed carboard cores.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.1.1.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.2 Level A.

5.1.2.1 Unit package.

5.1.2.1.1 Type I.

5.1.2.1.1.1 Spools. Adhesive tape wound on spools shall be packaged in a metal sleeve so designed that the spool may be easily removed and returned to the container. Spools containing comouflaged tape shall have the exterior surfaces of the spool and sleeve coated with a lusterless, olive drab, color comparable to color number 34087 shown in Federal Standard 595.

5.1.2.1.1.2 Roll. The twelve inch slit roll shall be assembled on a suitable spiral wound paperboard core or other suitable material approximately 1/2 inch longer than the entire roll. The core shall be of such a diameter to permit ready dispensing of the tape. A suitable disk separator shall be placed between adjacent cut rolls and on the outer ends of the roll to prevent adhesion of the rolls. Each slit shall be packaged in cylindrical paperboard container fitted with metal ends, or folding carton, fabricated of not less than 30-point solid kraft fiberboard with a minimum bursting strength of not less than 175 pounds. The unit container shall be of such design or include suitable interior fittings as to center the roll within the container and prevent the roll from contacting the inner side walls of the container.

5.1.2.1.2 Type II.

5.1.2.1.2.1 Package. Thirty-six spools of tape enclosed in metal sleeves as specified in 5.1.2.1.1.1 shall be packaged in a snug fitting box constructed in accordance with PPP-B-636, class domestic. Closure of the box shall be adequate to prevent accidental opening.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.1.2.1.2.2 Box. Each one inch by one yard strip of adhesive wound on a flat waxed cardboard core shall be packaged in an extruded, stainless, lay flat 100 percent, virgin polyethylene tubing having a minimum thickness of 0.00225 inches, a maximum of 1-3/8 inches + 1/8 inch in width and 2-5/8 inches in length. Closure shall be effected by heat sealing. The maximum dimension of the package tape with end of the bag folded back on the flattened tape and core unit shall be 2 inches in length, 1/4 inch in thickness and one inch + 1/16 inch in width. One hundred individually packaged wound strips of adhesive shall be further packaged in a snug fitting box constructed in accordance with PPP-B-566 or PPP-B-676. Closure of the box shall be adequate to prevent accidental opening.

5.1.2.1.3 Type III. Each roll shall be packaged in a substantial cylindrical fiber container with ends of metal or other suitable material, so constructed that in use the roll may be easily removed and returned to its container.

5.1.2.2 Intermediate package. The intermediate package may be a snug fitting box constructed in accordance with PPP-B-566, PPP-B-636, class domestic or PPP-B-676. Closure shall be adequate to prevent accidental opening.

5.1.3 Level B.

5.1.3.1 Unit package. Adhesive tape of one type and size not longer than 10 yards shall be furnished in a spool container as specified in 5.1.2.1.1.1.

5.1.3.2 Intermediate package. Twelve (12) unit packages of tape 1 inch or less in width or six (6) unit packages of tape over 1 inch in width shall be packaged in a box as specified in 5.1.2.2.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose within the continental limits of the United States of America.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification. For NSN 6510-00-203-5500, the intermediate packages shall be placed within the exterior container in such a manner that the rolls will remain in a vertical position.

5.2.1.2 Case liner. Each Level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproofed as specified in the appendix of PPP-B-636.

NOTE: Strapping will not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification. Fiberboard box shall be closed in accordance with method II as specified in the appendix of PPP-B-636. Intermediate packages containing Type I rolls shall be placed within the exterior container in such a manner that the rolls will remain in a vertical position. When specified (see 6.2) twelve (12) intermediate packages shall be packed in a box conforming to PPP-B-636, class domestic. The box shall be closed in accordance with the appendix of the box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 For civil agencies. Unit packages, intermediate packages, and shipping containers shall be marked in accordance with Federal Standard No. 123.

5.3.2 For military agencies.

5.3.2.1 Individual container.

5.3.2.1.1 Type II Tape 2 inches by 5 yds. Each spool or sleeve shall be marked with the item identification, name and address of manufacturer, contract or purchase order number, Lot (control) number, date of manufacture, and the statement: "ADHESIVE GUARENTEED FOR 2 YEARS FROM DATE OF MANUFACTURE." In addition markings required by Federal Food, Drug and Cosmetic Act shall also be shown.

5.3.2.2 Unit package. Each unit package shall be marked in accordance with the requirements of the Federal Food, Drug and Cosmetic Act, and in addition shall include the National Stock Number, Item Identifications, quantity and unit of issue, name and address of manufacturer, Lot (control) number and the date of manufacture. The date of manufacture may be shown either on the unit package or on the tape. If the date of manufacture is placed on the tape it shall be so located as to be readily visible upon removal of the spool or roll from the unit package.

5.3.2.3 Intermediate package. Each intermediate package shall be marked in accordance with Military Standard MIL-STD-129. Date of manufacture (month, year) shall be shown in lieu of date packed. Lot (control) number shall be shown.

5.3.2.4 Exterior container. Exterior container shall be marked in accordance with Military Standard MIL-STD-129. Date of manufacture (month, year) shall be shown in lieu of date packed. Lot (control) number shall be shown.

5.3.2.4 Special markings.

5.3.2.4.1 Type I Rolls. In addition to the markings specified, the unit, intermediate, and exterior container shall be marked with the legend: "PROTECT FROM EXCESSIVE HEAT." The unit package shall also be marked with the legend: "STORE ON END." The exterior container shall also include arrows and the word "UP" as specified in MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.3.2.4.2 Type I spools camouflaged. Each unit package shall be marked with the following statements: "FOR USE ONLY AS A COMPONENT OF MEDICAL FIELD ASSEMBLIES," AND "ADHESIVENESS GUARANTEED FOR 2 YEARS FROM DATE OF MANUFACTURE".

5.3.2.4.3 Type II tape camouflaged. Each unit package shall be marked with the following statements: "FOR USE ONLY AS A REPLACEMENT ITEM FOR SURVIVAL KITS, INDIVIDUAL, OPERATIONAL AND RESERVE PACKET," and "ADHESIVENESS GUARANTEED for 2 YEARS FROM DATE OF MANUFACTURE.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type required (see 1.2.1).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 The following types and sizes of adhesive tape now appear in the Federal Supply Catalog.

NSN	Item Identification	Unit of issue	Type
6510-00-203-5000	ADHESIVE TAPE, SURGICAL, 3 inches by 5 yards	Spool	I
6510-00-203-5500	ADHESIVE TAPE, SURGICAL, 12 inches by 10 yards	Roll	I
6510-00-203-6010	ADHESIVE TAPE, SURGICAL, 12 inches by 5 yards: Moleskin	Roll	III
* 6510-00-512-4570	ADHESIVE TAPE, SURGICAL, 2 inches by 5 yards, 36s	Package	II
6510-00-526-0162	ADHESIVE TAPE, SURGICAL, CAMOUFLAGED, 1 inch by 5 yards	Spool	I
6510-00-550-8501	ADHESIVE TAPE, SURGICAL, 2 inches by 10 yards	Spool	I
* 6510-00-782-6426	ADHESIVE TAPE, SURGICAL CAMOUFLAGED, 1 inch by 1 yard, 100s	Box	II

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.

* Each unit package contains 36 spools of tape.

**Each box shall contain one hundred one inch by one yard pieces of adhesive tape wound on flat waxed cardboard cores.

Military Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DSA-DM

Project No. 6510-0600

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 45 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers' vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)

TELEPHONE NO.

DATE

DD FORM 1426

PREVIOUS EDITIONS OF THIS FORM MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

Each box shall contain one hundred one inch by one yard pieces

FOLD

POSTAGE AND FEES PAID

OFFICIAL BUSINESS
ENALTY FOR PRIVATE USE $300

Commander
Defense Personnel Support Center
ATTN: DPSC-ATTS
2800 South 20th Street
Philadelphia, Pennsylvania 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.