INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

LACES, NYLON

This interim amendment was developed by the U.S. Army Natick Research and Development Center (GL), Natick, MA 01760-5014 based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to V-L-61H, dated June 15, 1984.

PAGE 1

1.2.1, line 1: Delete "two types" and substitute "three types".

Add the following:

Type III - Multifilament nylon laces

Class 1 - 4/32 inch each side, square

PAGE 3

3.3.1: Add the following sentence to end of paragraph:

"The type III, class 1 laces shall be made from 210 denier by 5 by 3 cabled yarns manufactured from high tenacity, continuous multifilament nylon yarns."

PAGE 4

3.5: Delete and substitute:

"3.5 Braid. The braid for the laces shall be tubular braided without a core except for type II, class 3 which has a stuffer core. All laces shall use a two over and two under braiding except type II, class 2 which shall braid one pair over and one pair under and type III, class 1 which shall be square. The braid machine used for type III, class 1 shall be set such as to

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T14:31Z
Check the source to verify that this is the current version before use.

PAGE 4 (cont'd)

produce a resultant square braid exhibiting four separate sides with an equal number of picks per inch and an equal width per side of 4/32 ± 1/32 inch. The braid shall be pressed flat for type I, classes 1, 2 and 3, and for type II, class 2 laces in accordance with commercial practice. The braid for type II, classes 1, 3 and 4 laces shall be round and shall not be pressed. The braid for type III, class 1 laces shall be square and shall not be pressed. The braid for the laces shall conform to the physical requirements in table I when tested as specified in 4.4.4."

Table I: Add the following under the listed headings:

"Type	Class	Width Tol. ± 1/32 inch	Carriers minimum	Ends per carrier minimum	Warp ends minimum	Stuffer minimum	Picks per inch minimum	Breaking strength lbs. minimum
III	1	4/32 (each side)	8	1	-	-	14	250 "

PAGE 5

4.3, line 3: Delete "table III" and substitute "table II".

PAGE 7

Table II, opposite "Width or diameter" in "Results reported as" column: Delete "1/2" and substitute "1/32".

Custodian:

Army - GL

Preparing activity:

Army - GL

Project No. 8335-A154

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:21Z
Check the source to verify that this is the current version before use.