MIL-I-48145 (MU)
9 February 1973

MILITARY SPECIFICATION

IGNITER TUBE

1. SCOPE

1.1 This specification covers one type of igniter tube for use with 152MM cartridges.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified.

SPECIFICATIONS

MILITARY

MIL-P-116 - Preservation, Methods of
MIL-A-2550 - Ammunition and Special Weapons; General Specification for
MIL-I-45607- Inspection Equipment; Supply and Maintenance, For Ordnance
MIL-C-50269- Cellulose, Woodpulp (Sulfate) for nonmetallic Cartridge Cases, Kraft
MIL-F-50533- Fiber, Acrylic, Fibrillated

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes (ABC-STD-105).
MIL-STD-109 - Quality Assurance Terms and Definitions
MIL-STD-286 - Propellants, Solid: Sampling, Examination and Testing
MIL-STD-650 - Explosive: Sampling, Inspection & Testing
MIL-STD-1235- Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-1168- Lot Numbering of Ammunition

FSC: 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

FEDERAL

FED-STD-406 - Plastics; Method of Testing

PPP-B-26 - Bag, Plastic, Polyethylene

DRAWINGS

ARMY

9279018 - Tube
9247366 - Composition

PUBLICATIONS

ARMY

ET-9279018 - Equipment Tabulation

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications.-The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

CODE OF FEDERAL REGULATIONS, Title 49: Transportation; Parts 49 CFR 0-190

(The Code of Federal Regulations is available from the Superintendent of Documents, Government Printing Office, Washington,D.C., 20402. Orders should cite "49 CFR 0-190 (latest revision)")

3. REQUIREMENTS

3.1 Materials.-The constituent materials shall comply with the requirements of all applicable drawings and specifications (see 6.4).

3.2 Parts.-The igniter tube shall comply with all the requirements specified in Drawing (dwg.) 9279018 and 9247366 and with all the requirements specified in the applicable specifications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

3.3 Stability.-The nitrocellulose in the igniter tube shall not completely change the color of the methyl violet paper to salmon pink color in less than thirty-five (35) minutes when tested according to 4.3.3.1.

3.4 Weight.-The weight of the igniter tube shall be as specified below when tested in accordance with 4.3.3.2.

3.4.1 Drawing 9279018-1.-The weight shall be 14.8 ± 2 grams.

3.4.2 Drawing 9279018-2 .-The weight shall be 13.4 ± 2 grams.

3.5 Workmanship.-All parts shall be fabricated in a thorough, workmanlike manner, and shall be free of molding flaws, cracks, warpage outside the material envelope, crevassing, soft spots, frayed edges, foreign material greater than 1/4 inch in any dimension and delaminations.

3.6 First article inspection.-This specification makes provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.-Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the suppler may use his own or any other facilities suitable for the performance of the inspection requirements specified here, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this Specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements. Reference shall be made to Standard MIL-STD-109 in order to define terms used herein. The provisions of Specification MIL-A-2550 shall apply.

4.1.1 Submission of product.-When an inspection lot of igniter tubes is submitted to the Government for acceptance, the contractor shall supply the following information, accompanied by a certificate which attests that the information provided is correct and applicable to the product being submitted:

a. A statement that the inspection lot of igniter tubes

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

complies with all of the quality assurance provisions specified within this specification.

b. Number of components in the inspection lot.

c. Number of components in the inspection lot that were inspected.

d. Results obtained, by defect code, for all inspections performed.

e. Drawing, specification number, and date, together with identification and date of changes.

f. Certificates of conformance.

g. Date submitted.

The certificate shall be signed by a responsible agent of the certifying organization. The initial certificates submitted shall be substantiated by evidence of the agent's authority to bind his principal. Substantiation of the agent's authority will not be required with subsequent certificates unless, during the course of the contract, this authority is vested in another agent of the certifying organization.

4.2 First article inspection

4.2.1 Examination

4.2.1.1 Submission.-The contractor shall submit a first article sample, as designated by the contracting officer, for evaluation in accordance with the provisions of 4.2.1.2. The first article sample shall consist of 10 parts (minimum) which have been produced by the contractor or furnished by a supplier, and which have been manufactured using the same production processes, procedures, molds, dies (see 6.6) and equipment which will be used in fulfilling the contract. All parts and materials, including packaging and packing, shall be obtained from the same sources of supply as will be used in regular production. Prior to submission, the contractor shall inspect the sample to the degree necessary to assure that it conforms to the requirements of the contract, and submit a record of this inspection with the sample, including statements of findings for materials, processes and tests. A sample containing known defects will not be submitted unless specifically authorized by the contracting officer. (A first article sample, or portion thereof, as directed by the contracting officer, shall also be submitted whenever there is a lapse in production for a period in excess of 90 days, or whenever a change occurs in manufacturing process, material used, drawing, specification or source of supply as to significantly affect product uniformity as determined by the Government).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

4.2.1.2 Inspections to be performed.-Parts will be subjected by the Government to any or all of the examinations or tests specified in 4.3.2 and 4.3.3 of this specification, and any or all requirements of the applicable drawings. All tests shall be performed as specified in 4.4.

4.2.2 Rejection.-If any part fails to comply with the requirements for the inspections performed in accordance with 4.2.1.2, the first article sample shall be rejected. The Government reserves the right to terminate its inspection upon any failure of a part in the sample to comply with any or all of the stated requirements. In the event of rejection the Government reserves the right to require the contractor to take corrective action and submit a new first article sample, or portion thereof. Until the first article sample is accepted, the contractor is in no way authorized by the Government to initiate regular production, unless otherwise directed by the contracting officer.

4.2.3 New equipment approval.-Prior to the use of a new mold of die in regular production of the igniter tube, the contractor shall submit to the Government five (5) parts produced from the new mold or die for inspection. If any part fails to comply with the applicable drawings or specification requirements, when tested as specified in 4.2.1.2, the mold or die shall not be approved for use in regular production.

4.3 Inspection provisions

4.3.1 Lot formation.-The term "lot", as used throughout this specification, refers to an inspection lot, which is defined as an essentially homogeneous (see 6.7) collection of igniter tubes from which a representative sample is drawn and inspected to determine conformance of the lot with applicable requirements. The sample selected shall represent only that quantity of units from which the sample was drawn, and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the lot has been produced by one manufacturer, in one unchanged process, using the same materials and methods, in accordance with the same specification revisions. Changes to the process, specification, or drawing not affecting safety, performance interchangeability, or storage, as determined by the Government, shall not be deemed to alter the homogeneity of the lot. A maximum of ten percent of the total number of items

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

deliverable under the contract may be submitted as hybrid lots (see 6.8). Inspection lots shall comply with Standard MIL-STD-105. Inspection lots shall be homogeneous and of a size mutually convenient to both the contractor and the Government inspector. Lot numbering, as required, shall be in accordance with Standard MIL-STD-1168. Each lot of igniter tubes shall contain parts produced from:

a. Nitrocellulose from one manufacturer and from not more than one production lot.

b. Diphenylamine from one manufacturer and from not more than one production lot.

c. Acrylic fibers from one manufacturer and from not more than one production lot.

d. Resin from one manufacturer.

e. Kraft from one manufacturer and from not more than one production lot.

4.3.2 Examination.-The examinations listed in the following subparagraphs shall be performed on inspection lots (see 4.3.1) of the components or assemblies designated in the applicable paragraph headings. Inspection for critical defects (and major defects, when so specified) shall be in accordance with MIL-STD-105 except that continous sample plans in accordance with MIL-STD-1235 may be used if approved by the Government. Instead of applying the AQL's designated herein to the groups of major and minor defects listed, the contractor may elect to apply AQL's to individual defects using an AQL of 0.40 percent for each major defect and an AQL of 0.65 percent for each minor defect. When this method is elected, it shall be applied to all of the major and minor defects listed in the applicable subparagraph of this section, except where 100 percent inspection is specified, and be documented as part of the contractor's inspection system. Equipment necessary for the perforamnce of the inspections listed shall be in accordance with 4.4.3. Conditioning shall be at 23 ± 2°C and 50 ± 5% R.H. for a minimum of 24 hours.

4.3.2.1 Tube, Igniter (see dwg. 9279018).

Category	Defect	Method of Inspection	Code No. (see 6.2)
Critical:	None defined.		
Major:	AQL 1.00 percent		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

101.	Length (max.).....Gage	01001
102.	Inside diameter.....Gage	01002
103.	Outside diameter.....Gage	01003

Minor: AQL 1.00 percent

201.	Workmanship (see 3.5).....Visual	01004

4.3.3 Testing

4.3.3.1 Stability (see 3.3), Major defect (Code No. 02001).-A stability heat test at 134. 5°C shall be performed in accordance with MIL-STD-286, Method 404.1.2. A random sample of 10 tubes shall be selected from the first article sample and the first three production lots to provide the required test specimens. Failure of any specimen is cause for lot rejection. When three consecutive lots have been accepted, sampling may be reduced to 5 tubes from each lot. However, if a failure occurs, sampling shall revert to 10 per lot until 3 consecutive lots have been accepted.

4.3.3.2 Weight (see 3.4), Major defect (Dwg. 9279018-1 Code No. 02002; Dwg. 9279018-2, Code No. 02003).- Samples shall be selected in accordance with Standard MIL-STD-105 (or Standard MIL-STD-1235). AQL for this defect shall be 0.40%. All samples shall be weighed individually, using any Government approved and suitably calibrated scale capable of reading to the nearest 0.1g. Test samples shall be preconditioned for a minimum of 4 hours at 23 $\pm$ 2 degrees C and 50 $\pm$ 5% R.H. prior to weighing.

4.3.3.3 Composition (see dwg. 9247366), Major defect (Code No. 02004) (see 3.1).-Ten tubes shall be randomly selected from the first article sample and from each of the first three production lots to provide the required test specimens. Failure of any specimen is cause for lot rejection. When three consecutive lots have been accepted, sampling may be reduced to five from each lot. If a failure occurs, sampling shall revert to ten per lot until three consecutive lots have been accepted. Duplicate specimens shall be obtained from each sample for analysis in accordance with 4.4.1.

4.3.4 Inspection equipment.-Equipment Tabulation number ET-9279018 identifies the inspection equipment required to perform the examinations and tests precribed in this section. The contractor shall design inspection equipment in accordance with the instructions in paragraph 6.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

4.3.4.1 Government use of contractor's inspection and test equipment.-The contractor shall make available to the Government all inspection and test equipment necessary for determining conformance with contract requirements. Personnel for operating the equipment, and verification of its accuracy, shall be supplied by the contractor for performance of the examination or test by the Government.

4.3.4.2 Government rights to documentation.-Inspection equipment drawings and lists provided and revised in accordance with the requirements of the ET may be used for DOD activities for design, procurement, manufacture, testing, evaluation, identification of stock, ordering and storage of replacement parts, inspection of items at overhaul, general maintenance of equipment, construction, survey, and whenever inspection equipment drawings are needed.

4.4 Test methods and procedures

4.4.1 Composition

4.4.1.1 Preparation of specimen (see 4.3.3.3).-Each specimen shall be divided into 1/8 inch (approximate) cubes or equivalent. The specimens shall then be thoroughly mixed to form a composite. From the composite, approximately 1.0 g shall be selected as the analysis sample and weighed to the nearest 0.2 milligram (mg), (Weight A) in an extraction thimble. The same thimble should be carried through the extractions in 4.4.1.3.1 and 4.4.1.3.3.

4.4.1.2 Total volatiles.-The samples from 4.4.1.1 shall be dried for 3 hours at 100 $\pm$ 2°C, cooled in a desicator (1/2 hr. min.), and weighed to the nearest 0.2 mg (Weight W). Calculate the percent total volatiles as follows:

$$\% \text{ Total Volatiles} = \frac{A - W \times 100}{A}$$

4.4.1.3 Analytical procedure

4.4.1.3.1 Extraction.-Using a tared, extra-coarse, sintered glass thimble, extract each sample from 4.4.1.2, with methylene chloride, for a minimum of 16 hours in a Roweg extractor (MIL-STD-286, Method 104.1). Evaporate the extract to dryness, using a current of clean, dry air. This extract is to be used for diphenylamine determination in 4.4.1.3.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

Dry the residues (non-extractable material) in the extraction thimbles by aspirating the thimble and contents until the odor of methylene chloride is not discernable. Dry the thimble plus residue for 1/2 hour minimum at 100 ± 2°C. Cool in a desiccator (1/2 hr. min). Determine the dry weight of this residue (Weight C) to the nearest 0.2 mg as the difference between this weight and the weight of the empty thimble. This residue is to be used for the nitrocellulose determination in 4.4.1.3.3.

4.4.1.3.2 Diphenylamine (DPA).-To the dried extract from 4.4.1.3.1, add 50 milliliters (ml) of glacial acetic acid. If necessary, warm slightly to dissolve the extract, then cool to room temperature. Complete the determination of diphenylamine in the solution according to Method 201.1 (starting with paragraph 5.5) of Standard MIL-STD-286, except that 25 ml of methylene chloride is to be added after addition of the potassium iodide solution. When the end point appears to have been reached, (absence of blue color) the flask is stoppered and shaken. If no color appears, the end point has been reached; otherwise, continue titration until the blue color is discharged and shaking produces no further color. Calculate the percent DPA as shown in Standard MIL-STD-286, Method 201.4, paragraph 5.11.

4.4.1.3.3 Nitrocellulose.-To provide good heat conduction to the solvent, place a sufficient quantity of glycerin on the flask bottom and the surface of the heat source to produce a continuous film. Add 10 ml of ethyl alcohol to the thimble and residue from 4.4.1.3.1 and extract with acetone using the method in 4.4.1.3.1. After extracton dry the residue remaining at 100 ± 2°C for one hour. Cool in a desiccator (1/2 hr. min.) weigh to the nearest 0.2 mg (Weight D) and save for the acrylic determination in 4.4.1.3.4. Evaporate the acetone extract to dryness and add 25 ml of n-butyl acetate and 45 ml of glacial acetic acid. Replace the air with a stream of inert gas (CO_2 or N_2). Maintain the inert atmosphere throughout this test. Reflux the solution for five (5) minutes. Add to the flask, via the condenser, 25 ml of 0.7N ferrous ammonium sulfate (prepared per MIL-STD-286, Method 604.1) and 10 ml concentrated hydrochloric acid. Reflux for thirty (30) minutes more to obtain a yellow liquid in which the specimen is completely disintegrated. With the inert gas still running, cool in a water bath to room temperature. Add 5 ml

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

of 20% ammonium thiocyanate solution (MIL-STD-286, Method 601.1). Titrate with a 0.2N titanous chloride solution (MIL-STD-286, Method 601.1). Perform a blank titration on the reagents. Calculate the percent NC as follows:

$$\% \text{ NC} = \frac{46.69N\ (V-B)\ \ X\ 100}{E\ W}$$

Where:

V = Volume titanous chloride used for sample, ml
B = Volume titanous chloride used for blank, ml
W = Weight of dried sample, gm
N = Normality of titanous chloride
E = Percent nitrogen in the nitrocellulose

4.4.1.3.4 Acrylic

Reagents

SULFURIC ACID - 93 - 98% H_2SO_4, N_2 - Free

MERCURIC OXIDE (HgO) - Reagent Grade, N_2 Free

POTASSIUM SULFATE OR ANHYDROUS SODIUM SULFATE - Reagent Grade, N_2 Free

THIOSULFATE SOLUTION - 160 g $NA_2S_2O_3.5H_2O$ dissolved in one liter of H_2O

SODIUM HYDROXIDE - 400 g solid NaOH dissolved in H_2O and diluted to one (1) liter

METHYL RED INDICATOR - 1 g methyl red dissolved in 200 ml ethyl alcohol

METHYLENE BLUE INDICATOR - 1 g methylene blue dissolved in 200 ml ethyl alcohol

HYDROCHLORIC OR SULFURIC ACID STANDARD SOLUTION - 0.1N

BORIC ACID SOLUTION - 4 g H_3BO_4 dissolved in 100 ml H_2O

HENGAR GRANULES

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

Apparatus

DIGESTION - Use Kjeldahl flasks of hard, moderately thick well annealed glass with total capacity of 500 to 800 ml. Conduct digestion over a safety approved heating device adjusted to bring 250 ml H_2O at 25°C to a rolling boil in 5 minutes.

DISTILLATION - Use a Kjeldahl flask of 500 to 800 ml capacity fitted with a rubber stopper. The low end of an efficient scrubber bulb or trap is passed through the rubber stopper to prevent mechanical carryover of NaOH during distillation. Use rubber tubing to connect the upper end of the bulb to the condenser tube. Trap the condenser outlet to insure complete absorption of distilled NH_3 into boric acid in the receiver.

Analysis

Quantitatively transfer the residue from 4.4.1.3.3 to a Kjeldahl flask. Add 3-4 Hengar granules, 0.7g of HgO, 15.0g of K_2SO_4 or NA_2SO_4 and 25 ml H_2SO_4 to the flask. Place the flask in an inclined position, and heat gently until the solution clears. Continue boiling for 1/2 hour minimum. Allow the solution to cool to room temperature. Add 200 ml H_2O. Cool the solution to below 25°C.

Add 25 ml thiosulfate solution and mix to precipitate the mercury. Tilt the flask and add a layer of 100 ml NaOH solution without agitation. Immediately connect the flask to the distilling bulb on the condenser. With the tip of the condenser immersed in the boric acid in the receiver, rotate the flask to mix the contents throughly. Heat the flask until all of the NH3 has distilled (approximately 250 ml). Titrate the boric acid solution with the standard acid using a mixed indicator containing 4 drops of methyl red, and 2 drops of methylene blue solution. Correct for the reagent blank. Calculate the percent acrylic as follows:

$$\% \text{ Acrylic} = \frac{6.05\ (V-B)\ N}{W} \times 100$$

Where:

V = Volume of standard acid for sample, ml
B = Volume of standard acid for blank, ml

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

N = Normality of standard acid
W = Dried sample weight, g

4.4.1.3.5 Kraft, resin and additives.-Calculate the percent Kraft, resin and additives as follows:

%Kraft + %resin + %additives = 100 - (%MC + %Acrylic + %DPA)

4.4.1.3.6 Report the total methylene chloride extractables $\frac{(W - C) \times 100}{W}$ and the total acetone extractables $\frac{(C-D) \times 100}{W}$

5. PREPARATION FOR DELIVERY

5.1 Packing

5.1.1 Level C.-All parts shall be packed in such a manner as to afford protection against damage during shipment from the supply source to the first receiving activity and in accordance with MIL-STD-1169.

5.2 Marking.-In addition to any special marking which may be required by the contract or order, marking shall be in accordance with MIL-STD-1169.

6. NOTES

6.1 Ordering data.-Procurement documents shall specify the following:

a. Title, number and date of this specification.
b. Data cards.-Data cards shall be prepared for each inspection lot in accordance wtih the information specified in Standard MIL-STD-1167.
c. Provisions for submission of first article samples.

6.2 Inspection code numbers.-The five digit code numbers assigned to the inspections herein are to facilitate future data collection and analysis by the Government. These code numbers are used to correlate the characteristics cited on Equipment Lists with the inspections listed in this specification. They should also be cited as references on drawings of equipment designs submitted by the contractor (see 6.3.5).

6.3 Inspection Equipment.-The contractor shall design inspection equipment as required by the referenced Equipment Lists (EL) in accordance with the instructions of paragraphs 6.3.1 through 6.3.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

6.3.1 Equipment Lists (EL).-Inspection equipment lists indicate the availability of inspection equipment designs by showing in the number column of the list of inspection equipment (Form SMUPA 1010) the numbers of drawings of Federal Stock Numbers of existing equipment designs or codes, as indicated in paragraph 6.3.2. Design action required of the contractor is described in paragraphs 6.3.3 and 6.3.4. The contractor will be required to prepare detailed drawings in accordance with 6.3.4 for all the equipment coded as "Contractor Design" in the number column. These contractor designs must be approved by the Government prior to fabrication or procuring of the equipment. Designs shall be submitted for approval as specified in 6.3.5.

6.3.2 Equipment list codes.-The inspection equipment, as defined in 6.3.3 and 6.3.4, will be designated in the EL by the following codes:

CD - Contractor design or controlled contractor format and/or commerical equipment.
MU - Army design, mandatory for use.

6.3.3 Army designs.-Army designs are reflected on detailed drawings which completely depict all the information necessary for the fabrication of the item of inspection equipment. The contractor need provide no design when an Army design is listed for an item of inspection equipment. Army designs fall into two basic classifications: mandatory (designated "MU") and non-mandatory (indicated by drawing or Federal Stock Number). When an inspection equipment list references mandatory Army designs, the contractor shall comply with, and use these designs accordingly. The contractor may, however, in connection with non-mandatory designs, and with the approval of the Government, design alternate inspection equipment or use comparable commerical equipment to facilitate his operations. Such contractor-prepared designs or commerical equipment selections must be approved by the Government prior to fabrication or procuring of the equipment. Designs shall be submitted for approval as specified in 6.3.5.

6.3.4 Contractor designs.-Contractor designs are designs of inspection equipment for which the Government has assigned design responsibility to the contractor.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

Contractor designs shall be supported by detailed drawings which depict all information necessary to completely fabricate, calibrate and operate an item of inspection equipment. This requires that the necessary views, dimensions, materials, finish, notes, operating and calibration instructions be properly depicted in accordance with approved practices to the extent that further calculation or clarification will not be required. Unless otherwise specified, Contractor design may be developed on the format the contractor normally employs in his equipment design procedure provided such format reflects the detail and information specified above, subject to the following controls: All submitted contractor designs shall conform to MIL-D-1000, Category E, Form 2. Legibility and reproducibility shall permit conventional making of clearly understandable, high contrast reproductions. Contractors shall submit two copies of final designs as a rolled set. Designs shall be submitted for approval as specified in 6.3.5.

6.3.5 Submission of contractor designs.-All submitted designs shall contain a reference to the applicable five digit Code Number contained in Section 4 of this specification and the appropriate component or assembly drawing number and revision letter to which the specific design applies. Unless otherwise specified on the EL, all designs of equipment for inspection of defects classified as critical and major shall be submitted for approval to the Commanding Officer, Picatinny Arsenal, ATTN: SMUPA-QA-A-A. All other designs of inspection equipment shall be approved by the inspection element of the agency administering the contract; submission shall be as directed by the contracting officer. Partial submission of inspection equipment designs is permissible and encouraged. However, the Arsenal completion date for design review will be based on the date of the final submission of designs. Picatinny Arsenal design review will be accomplished normally within one month after receipt.

6.4 Additives shall have prior approval by the contracting officer. Mold release agents and processing aids are considered additives.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

6.5 Submission of first article sample.-Instructions as to the location for the evaluation of first article samples shall be obtained from the contracting officer, upon request. All inquiries should be forwarded to: Commander, Picatinny Arsenal, ATTN: SMUPA-QA-KA, Dover, New Jersey 07801

6.6 First article sample.-The first article sample shall contain a representative quantity (a minimum of five (5) parts) fabricated from each mold and die intended for use in regular production. Each sample shall be appropriately labelled as to mold and die used during its fabrication.

6.7 Homogeneous lots.-A lot shall be considered homogeneous if the lot contains source materials in compliance with 4.3.1; i.e., contains no more than one (1) lot of nitrocellulose, one (1) lot of woodpulp, one (1) lot of acrylic, and one (1) lot of DPA.

6.8 Hybrid lots.-A lot shall be considered hybrid if the lot contains source materials which are not in compliance with 4.3.1; i.e., the lot contains more than one (1) lot of NC, Acrylic, woodpulp, or DPA.

6.9 Submission of data.-One copy of all data generated shall be forwarded to SMUPA-QA-A-P and SMUPA-ADEP-3.

Custodian:
Army-MU

Preparing Activity:
Army-MU

Project Number: 1320-A-148

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4 REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.