GG-P-455B
AMENDMENT-2

July 10, 1972
SUPERSEDING
Amendment-1
June 24, 1969

AMENDMENT

TO

FEDERAL SPECIFICATION

PLATES AND FOILS, PHOTOGRAPHIC

(PHOTOSENSITIVE ANODIZED ALUMINUM)

This amendment, which forms a part of Federal Specification GG-P-455B, dated May 1, 1967, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 2

Paragraph 3.1.1 - Delete the first sentence and substitute the following: "The anodic layer thickness of photosensitive anodized aluminum plates furnished under this specification shall be 0.00045 + 0.0001 inches."

PAGE 11

Add the following new paragraph.

"6.5.3 Photographic subtractive color process. A photo chemical procedure in which a latent image is formed in a layer of polymeric resin by photographic methods, leaving the exposed area covered by a layer of chemical resin. The unexposed resins are washed away and the now unprotected areas are chemically leached to remove unwanted color from the anodized layer. Subsequent processing removes the remaining resins and leaves an image sealed in the totally anodized surface."

FSC 6750

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.