MILITARY SPECIFICATION

# BRAID, TEXTILE AND LACE, VELLUM, WOVEN, TEXTILE (FOR BLUE DRESS UNIFORM)

This specification is approved for use by the U.S. Army Natick Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This document covers textile braids and woven laces for blue dress uniforms worn by military personnel of the Department of the Army.

1.2 Classification. The braids and laces shall be of the following types, classes, and styles as specified (see 6.2):

Type I - Braid

Class 1 - Soutache
Class 2 - Cord-edge

Class 3 - Combination
Class 4 - Plain with vellum stripe

Type II - Lace, Woven

Class 1 - Plain with vellum stripe

Style A - 1/2 inch
Style B - 1 1/2 inch

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8315

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

Class 2 - Colored center stripe

Style A - 3/4 inch
Style B - 1 3/4 inch

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

| | |
|---|---|
| V-T-276 | - Thread, Cotton |
| PPP-B-636 | - Boxes, Shipping, Fiberboard |
| PPP-B-676 | - Boxes, Setup |
| PPP-T-45 | - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing |

MILITARY

| | |
|---|---|
| MIL-L-35078 | - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For |

STANDARDS

FEDERAL

| | |
|---|---|
| FED-STD-191 | - Textile Test Methods |
| FED-STD-751 | - Stitches, Seams, and Stitchings |

MILITARY

| | |
|---|---|
| MIL-STD-105 | - Sampling Procedures and Tables for Inspection by Attributes |
| MIL-STD-129 | - Marking for Shipment and Storage |
| MIL-STD-147 | - Palletized Unit Loads |
| MIL-STD-731 | - Quality of Wood Members for Containers and Pallets |



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

THE COLOR ASSOCIATION OF THE UNITED STATES, INC.

Department of Defense Standard Color Card for Heraldic Yarns, Embroidery and Ribbons

Standard Color Card of America

(Application for copies should be addressed to the Color Association of the United States, 343 Lexington Avenue, New York, NY 10016.)

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Guide samples. Samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variations from this document may appear in the sample, in which case the document shall govern.

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Materials.

3.3.1 Cotton yarn. The yarns shall be cotton yarns in the sizes specified in 3.5.

3.3.2 Rayon or nylon yarn. The yarns shall be multifilament bright or semi-dull rayon (2 ply) (cuprammonium or viscose) or nylon (singles) of a suitable denier to meet the requirements of this document.

3.3.3 Mohair yarn. The mohair used shall be not lower in grade than 28's and shall be carded, combed, and spun on the worsted system and twisted into 2/30 (± 1 count) yarn.

3.3.4 Thread. The cotton thread shall be dyed Blue, AB, CA 66044, as listed in the Department of Defense Standard Shades for Sewing Threads, and shall conform to type IA3, ticket No. 50, 3 ply of V-T-276. The cotton thread shall show fastness to perspiration, wet-dry cleaning, and light equal to or better than the standard sample (see 6.3), or shall show "good" fastness to perspiration, wet-dry cleaning, and light.

* 3.4 Color. The color or colors of the dyed braids and laces shall be as listed in table I. The yarns for the braids and woven laces shall be yarn dyed. The rayon and nylon yarns may be spinning solution dyed.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE I. Color requirements

| Component | Type | Class | Color 1/ |
|---|---|---|---|
| Braid, soutache | I | 1 | Goldenlite, cable No. 67107 |
| Braid, cord-edge: | | | |
| Cord portion | I | 2 | Goldenlite, cable No. 67107 |
| Flat braid portion | I | 2 | Blue, shade No. 173 |
| Braid, combination: | | | |
| 1/2 inch | I | 3 | Goldenlite, cable No. 67107 |
| 1 1/4 inch | I | 3 | Blue, shade No. 173 |
| Braid, plain | I | 4 | Goldenlite, cable No. 67107 |
| Lace, plain | II | 1 | Goldenlite, cable No. 67107 |
| Lace, center stripe | II | 2 | 2/ |

1/ Cable numbers are from the Department of Defense Standard Color Card for Heraldic Yarns, Embroidery, and Ribbons.

2/ The edge stripes shall be Goldenlite, cable No. 67107 and the center stripe(s) colors(s) shall be as specified in 3.4.4.

3.4.1 Labile sulfur. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and finished braids and laces shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.4.3. When a standard sample is not available, the dyed and finished braids and laces shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.4.3.

* 3.4.2 Matching. The colors of the finished braids and woven laces shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

of 7500 ± 200 K, with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200 K.

* 3.4.3 Colorfastness. The colorfastness of the dyed and finished braids and woven laces shall be as specified in the applicable end item document or as set forth in the contract or purchase order (see 6.2). When the colorfastness requirements are not specified, the dyed and finished braids and laces shall show fastness to perspiration, wet-dry cleaning, light, and crocking equal to or better than the standard samples, or shall show good fastness to perspiration, wet-dry cleaning, and light and shall have an AATCC Chromatic Transference Scale rating not lower than 2.5 when tested as specified in 4.4.3.

* 3.4.4 Colors for type II, class 2 lace. The colors shall be as listed in table II and 3.5.4.1.

TABLE II. Colors for type II, class 2 lace

| Arms and services | Color | Cable No. 1/ |
|---|---|---|
| Adjutant General's Corp | Dark Blue | 65012 |
| | Scarlet | 65006 |
| Armor | Yellow | 65002 |
| Artillery | Scarlet | 65006 |
| Aviation | Ultramarine | 65010 |
| | Golden Orange | 65003 |
| Chaplains | Black | 65018 |
| Chemical Corps | Cobalt Blue | 65011 |
| | Golden Yellow | 65001 |
| Corps of Engineers | Scarlet | 65006 |
| | White | 65005 |
| Finance Corps | Silver Gray | 65008 |
| | Golden Yellow | 65001 |
| Infantry | Light Blue | 65014 |
| Inspector General | Dark Blue | 65012 |
| | Light Blue | 65014 |
| Judge Advocate General's Corp | Dark Blue | 65012 |
| | White | 65005 |
| Army Medical Service Corps | Maroon | 65017 |
| | White | 65005 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE II. Colors for type II, class 2 lace - Continued

| Arms and services | Color | Cable No. 1/ |
|---|---|---|
| Intelligence and Security | Oriental Blue | 70209 |
| | Silver Gray | 65008 |
| Military Police Corps | Green | 65007 |
| | Yellow | 65002 |
| National Guard Bureau | Dark Blue | 65012 |
| Ordnance Corps | Crimson | 65013 |
| | Yellow | 65002 |
| Permanent Professors of the U.S. Military Academy | Scarlet | 65006 |
| | Silver Gray | 65008 |
| Quartermaster | Buff | 65015 |
| Signal Corps | Orange | 65004 |
| | White | 65005 |
| Staff Specialists Reserve | Green | 65007 |
| Transportation Corps | Brick Red | 65020 |
| | Golden Yellow | 65001 |
| Unassigned to Branch | Teal Blue | 70147 |
| | White | 65005 |
| Warrant Officers | Brown | 65016 |

1/ Cable numbers in the 65,000 series are from the Department of Defense Standard Color Card for Heraldic Yarns, Embroidery, and Ribbons and cable numbers 70209 and 70147 are from the Standard Color Card of America (see 2.2).

3.5 Construction.

3.5.1 Type I, class 1. The soutache cover shall be made of rayon or nylon yarns braided around two cotton warp ends. Each cotton warp end shall be a 20/3/4-ply cord or equal. The soutache shall conform to the physical requirements in table III.

3.5.2 Type I, class 2. The flat braid section and the cord shall be braided together in one operation on a cord-edge braider.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

3.5.2.1 Cord cover. The cord cover shall be composed of rayon or nylon yarns (see 3.3.2) braided around a braided core (see 3.5.2.1.1) and shall conform to the physical requirements in table III.

3.5.2.1.1 Core. The core cover shall be braided with not coarser than 38/2 cotton yarn around a cotton stuffer. The cotton yarn for the stuffer shall be not coarser than 10/1. The core yarns shall be bleached or unbleached. The core shall conform to the physical requirements in table III.

3.5.2.2 Flat braid. The flat braid section shall be braided with not coarser than 28/2 nor finer than 32/2 cotton yarn, dyed Blue 173, and shall conform to the physical requirements in table III.

3.5.3 Type I, class 3. The 1/2-inch braid and the 1 1/4-inch braid shall be stitched together using stitch type 304 and seam type FSa-1 conforming to FED-STD-751 using thread type IA3 (see 3.3.4). The seam shall be stitched with 10 to 12 stitches per inch.

3.5.3.1 Braid, 1/2-inch. The braid shall be a nylon or rayon braid containing a braided cotton stuffer for each vellum and one cotton stuffer end at each edge of the braid. The cotton yarn for the stuffers shall be approximately 40/2. The 1/2-inch braid shall conform to the physical requirements in table III.

3.5.3.2 Braid, 1 1/4-inch. The braid shall be composed of mohair yarn (see 3.3.3) and cotton yarn of approximately 40/2. The yarns shall be dyed Blue 173. The braid shall conform to the physical requirements in table III.

3.5.3.3 Type I, class 4. The braid shall be a rayon or nylon braid containing a braided cotton stuffer for each vellum and one cotton stuffer end at each edge of the braid. The 9/32-inch braid shall conform to the physical requirements in table III.

3.5.4 Type II, class 1 and 2. All warp and stuffer yarns shall be not coarser than 38/2 nor finer than 40/2 mercerized cotton except that the center stripe yarn for class 2, styles A and B, shall be rayon or nylon (see 3.3.2). The filling yarn for all laces shall be rayon or nylon (see 3.3.2). The laces shall conform to the physical requirements in table IV.

3.5.4.1 Colored center stripe. The colored center stripe shall be in accordance with the cable number for the branch of service as designated (see 3.4.4). The center stripe shall match the first color designated for branch of service except that when two colors are designated for class 2, style B the 3/4-inch center stripe shall have a 1/8-inch piping of the second named color on each side of a 1/2-inch stripe of the first named color.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

3.6 Braid and lace requirements. The braid and lace physical requirements shall be as shown in tables III and IV, respectively.

3.6.1 Weave for type II, class 1, style A lace. The weave shall be a filling effect weaving as follows:

Every pick over and under - 4 ends
Every pick over and under - 4 ends
Every pick over and under - 24 ends
Every pick over and under - 2 ends
Every pick over and under - 24 ends

The center warp section of 4 ends 3 times shall weave as follows:

First 4 ends over and under every pick
Second 4 ends over 1 pick - under 1 pick
over 1 pick - under 2 picks
over 1 pick - under 1 pick, over 1 pick

Third 4 ends over and under every pick

Every pick over and under - 24 ends
Every pick over and under - 2 ends
Every pick over and under - 24 ends
Every pick over and under - 4 ends
Every pick over and under - 4 ends



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE III. Physical requirements for type I braid

| Class | Width (inches) | Weight per gross yard (ounces) | Number of carriers | | Ends per carrier | | Number of vellum | Stuffer yarns | | Warp ends | | Lines | | Picks per inch | Breaking strength (pounds) | Type braid |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Min | | Min | Max | Min | Max | | Min | Max | Min | Max | Min | Max | Min | Min | |
| 1 | 1/8 | 8.5 | 13 | - | 1 | - | - | - | - | 2 | - | - | - | 32 | - | Soutache |
| 2 | 3/32 | 24.0 | 19 | - | 3 | - | - | - | - | - | - | - | - | 23 | - | Plain braid over 2/under 2 |
| | Core | - | 8 | 12 | 2 | 3 | - | 28 | 32 | - | - | - | - | 24 | - | Plain braid over 2/under 2 |
| | Flat braid 3/16 1/2 1/ | - | 21 | 25 | 1 | 1 | - | - | - | 10 | 12 | 5 | 6 | 26 | - | Plain braid over 2/under 2 |
| 3 | | 20 | 49 | - | 2 | - | 2 (braided core) | - | - | 2 | - | - | - | 30 | - | 2/32-inch plain braid over 1 cotton end 3/32-inch vellum 6/32-inch plain braid 3/32-inch vellum 2/32-inch plain braid over one cotton end |





Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE III. Physical requirements for type I braid - Continued

| Class | Width (inches) | Weight per gross yards (ounces) | Number of carriers | | Ends per carriers | | Number of vellum | Stuffer yarns | | Warp ends | | Lines | | Picks per inch | Breaking strength (pounds) | Type braid |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Min | | Min | Max | Min | Max | | Min | Max | Min | Max | Min | Max | Min | Min | |
| 3 | 1 1/4 | 72 | 58 braiding in pairs | - | 3 | - | - | - | 28 spools of 2 ends | - | - | 16 | - | 8 | 125 | Basket or diamond braid over 6/under 6 cotton end 2/32-inch |
| 4 | 9/32 | 15 | 32 | - | 1 | - | 2 (braided core) | - | - | 2 | - | - | - | 34 | - | 1/32-inch plain braid over cotton end 2/32-inch vellum 3/32-inch plain 2/32-inch vellum 1/32-inch plain braid over 1 cotton end |

1/ Braided on a bi-circle or radial braider.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE IV. Physical requirements for type II woven laces

| Class | Style | Width (inch) | Total No. of ends | Weight per linear yard (ounces) | Picks per inch | Number of vellum | Weave pattern | Ribs per inch (center stripe) | Warp breaking strength (pounds) |
|---|---|---|---|---|---|---|---|---|---|
| | | Min | Min | Min | Min | | | | Min |
| 1 | A | 1/2 | 128 cotton | 0.20 | 250 1/ | 2 | Filling effect weave (see 3.6.1) | - | 110 |
| 1 | B | 1 1/2 | 268 cotton | 0.50 | 250 1/ | 2 | Filling effect weave | - | 160 |
| 2 | A | 3/4 | 172: 51 cotton, 70 center stripe, and 51 cotton | 0.24 | 250 1/ | - | Filling effect weave 1/4-inch gold color, 1/4-inch, branch of service color, 1/4-inch gold color | 22 | 120 |
| 2 | B | 1 3/4 | 456: 128 cotton, 200 center stripe, and 128 cotton | 0.60 | 250 | - | Filling effect weave 1/2-inch gold color, 3/4-inch, branch of service color (See 3.5.4.1), 1/2-inch gold color | 22 | 200 |

1/ A nominal denier size of 210 shall be used with a nylon filling; 100 denier, 2 ply, with a rayon filling.





Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

* 3.7 Put-up and length. Unless otherwise specified (see 6.2), the braid or lace of one class, style, and color only, shall be put up on commercial size double-headed spools and flat chipboards as follows:

a. Type I, classes 1, 2, and 4 shall be wound on a chipboard spool consisting of a tube with mechanically attached circular ends. The total amount wound on each spool shall be 144 yards (± 10 yards).

b. Type I, class 3, and type II, classes 1 and 2 shall be wound on a flat chipboard board having a minimum thickness of 0.050 inch and measuring approximately 10 inches in length by 6 1/4 inches in width. The total amount wound on each board shall be 20 yards (± 2 yards).

There shall be not more than three lengths per spool for 144 yard spools, and not more than two lengths per board. No one length shall be less than 5 yards.

3.8 Marking. Each spool or board shall have firmly attached a white paper label printed in black with the following information:

Stock number
Item description
Document number
Contractor's name
Contract number and date
Name of contracting agency
Gross yards

3.9 Workmanship. The finished braid or lace shall conform to the quality of product established by this document, and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.1.3 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects listed in 4.4.2.1 and 4.4.2.2 and tested as specified in 4.4.3. The presence of any defect or failure of any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document. Components and materials listed in table V shall be accepted on the basis of contractor's certification of compliance with requirements specified (see 6.2).



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE V. Components and materials

| Type | Class | Component material | Characteristics | Requirement reference |
|---|---|---|---|---|
| I<br>II | 1, 2, 3, 4<br>1, 2 | Nylon or rayon yarn | Material, luster filament, and ply | 3.3.2 |
| I | 1 | Cotton yarn | Material, count, ply | 3.5.1 |
| I | 2 | Cotton core and stuffer yarn | Material, count, ply | 3.5.2.1.1 |
| | | Cotton flat braid yarn | Material, count, ply | 3.5.2.2 |
| I | 3 (1/2 inch) | Cotton stuffer yarn | Material, count, ply | 3.5.3.1 |
| I | 3 (1 1/4 inch) | Mohair yarn | Material, grade, processes, size | 3.3.3 |
| | | Cotton yarn | Material, count, ply | 3.5.3.2 |
| II | 1, 2 | Warp and stuffer yarn | Material, mercerized, count, ply | 3.5.4 |

4.4.2 End item examination.

* 4.4.2.1 Yard-by-yard examination. The braid or lace shall be examined for the defects listed in table VII. All defects found shall be counted regardless of their proximity to each other. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The lot size shall be expressed in yards. The sample unit shall be 1 linear yard. The number of spools or boards from which the sample is to be selected shall be in accordance with table VI. The sample yardage shall be apportioned equally among the selected rolls. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 1.0 for major defects and 4.0 for total combined major and minor defects.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE VI. Sample size

| Lot size (yards) | Sample size (spools or boards) | Acceptance number 2/ |
|---|---|---|
| Up to and including 3,200 1/ | 5 spools or 35 boards | 0 |
| 3,201 up to and including 8,000 | 7 spools or 49 boards | 0 |
| 8,001 up to an including 22,000 | 10 spools or 70 boards | 0 |
| 22,001 up to and including 110,000 | 15 spools or 105 boards | 1 |
| 110,001 or over | 25 spools or 175 boards | 1 |

1/ If a lot contains fewer than 5 spools or fewer than 35 boards, each spool or board shall be examined.

2/ Applicable only to overall examination in 4.4.2.2 and length examination in 4.4.2.3.

TABLE VII. Yard-by-yard examination defects

| Examine | Defect | Classification | |
|---|---|---|---|
| | | Major | Minor |
| Braid | Abrasion mark | X | |
| | Any cut, hole, or tear | X | |
| | Broken or missing yarn | X | |
| | Core not completely covered | X | |
| | Uneven tension, resulting in thick and thin places | X | |
| | Tight or loose yarns, causing distortions or loopiness | X | |
| | Spot, stain, or streak 1/ | X | |
| | Width less than specified | | X |
| | Wrong stitch or seam type (type I, class 3) | | X |
| | Twisted or puckered seam (type I, class 3) | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE VII. Yard-by-yard examination defects - Continued

| Examine | Defect | Classification | |
|---|---|---|---|
| | | Major | Minor |
| Braid - continued | Seaming or stitching broken or skipped (type I, class 3) | X | |
| | Stitches per inch more or less than specified (type I, class 3) | | X |
| Lace | Abrasion mark | X | |
| | Broken or missing end or pick | X | |
| | Any hole, cut, or tear | X | |
| | Spot, stain, or streak 1/ | X | |
| | Edges, frayed, slack, or tight | X | |
| | Width less than specified | | X |

1/ Clearly visible at the normal inspection distance (approximately 3 feet).

* 4.4.2.2 Overall examination. The braid or lace shall be examined for the defects listed below. Each defect shall be counted not more than once in each spool or board examined. The sample shall consist of the applicable number of spools or boards indicated in table VI. The lot shall be rejected if the total number of defects in the sample exceeds the applicable acceptance number specified in table VI.

Overall defects

Does not match referenced color
Shaded end to end
Mottled or uneven color
Not clean throughout
Objectionable odor
Type and class other than specified
Identification marking missing, illegible, or incorrect
Improperly or insecurely wound on spools or boards, tangled and will not unwind properly
Not singed



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

* 4.4.2.3 Length examination. Each spool or board of braid or lace used in the overall examination shall be examined for the defects listed below. If the total number of length defects found in the sample exceeds the acceptance number specified in table VI or if the total of the gross lengths of the sample spools or boards is less than the total of the gross lengths marked on the spool or board tickets, the lot shall be rejected.

Length defects

Any gross length on a spool or board is more than the maximum specified or less than the minimum specified.

Any gross length on a spool or board is more than 2 yards less than the gross length marked on the spool or board ticket.

Any spool or board containing more than the maximum allowable number of pieces.

Any individual piece less than 5 yards in length.

* 4.4.3 End item testing. The braid or lace shall be tested for the characteristics indicated in table VIII. The method of testing specified in FED-STD-191, wherever applicable, and as listed in table VIII shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method, except for the weight characteristic, for which the lot average of all sample units shall apply. The sample unit for test purposes shall be 7 yards of the finished braid or 4 yards of lace. Except for the weight, the lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. For the weight characteristic, acceptance shall be based on conformance with the lot average requirement. All test reports shall contain the individual values used in expressing the final result. The sample size for each characteristic shall be as follows:

| Lot size in yards | Sample size (sample unit) |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE VIII. End item testing

| Characteristic | Requirement reference | Test methods |
|---|---|---|
| Braid only | | |
| Construction: | | |
| No. of carriers | Table III | Visual 1/ |
| Ends per carrier | Table III | Visual 1/ |
| No. of vellum | Table III | Visual 1/ |
| No. of stuffer yarns | Table III | Visual 1/ |
| No. of warp ends | Table III | Visual 1/ |
| No. of lines | Table III | Visual 1/ |
| Picks per inch | Table III | 5050 |
| Type of braid | Table III | Visual 1/ |
| Weight, oz/gr yd | Table III | 4.5.1 |
| Breaking strength, warp | Table III | 6016 2/ |
| Lace only | | |
| Construction: | | |
| Total ends | Table IV | Visual 1/ |
| Picks per inch | Table IV | 5050 |
| No. of vellum | Table IV | Visual 1/ |
| Weave | Table IV | Visual 1/ |
| Ribs per inch | Table IV | 5050 |
| Weight/lin. yd | Table IV | 4.5.1 |
| Breaking strength, warp | Table IV | 5100 3/ |
| Braid and lace | | |
| Labile sulfur | 3.4.1 | 2020 |
| Colorfastness: | | |
| Fastness to perspiration | 3.4.3 | 5680 |
| Fastness to wet dry cleaning | 3.4.3 | 5622 |
| Fastness to light | 3.4.3 | 5660 |
| Fastness to crocking | 3.4.3 | 5651 |

1/ One determination per sample unit and results reported as "actual count."



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

TABLE VIII. End item testing - Continued

| |
|---|
| 2/ Except the machine shall have smooth grips of the drum type not less than 2 inches in diameter. The distance between the center of the drums at the beginning of the tests shall be 6 inches. |
| 3/ Except that the breaking strength of the lace shall be determined by breaking the full width of the lace. |

4.4.4 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

| Examine | Defect |
|---|---|
| Marking (exterior and interior) | Omitted; incorrect; illegible; of improper size, location, sequence, or method of application |
| Materials | Any component missing, damaged, or not as specified |
| Workmanship | Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling<br>Bulged or distorted container |
| Weight | Net weight of shipping container exceeds maximum requirements |

* 4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1, and the AQL, expressed in terms of defects per hundred units, shall be 6.5.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

| Examine | Defect |
|---|---|
| Finished dimensions | Length, width, or height exceeds specified maximum requirement |
| Palletization | Pallet pattern not as specified<br>Interlocking of loads not as specified<br>Load not bonded with required straps as specified |
| Weight | Exceeds maximum load limits |
| Marking | Omitted; incorrect; illegible; of improper size, location, sequence, or method of application |

4.5 Methods of inspection.

4.5.1 Weight. Select two specimens of the finished item in excess of 1 yard each from each sample unit. Measure the specimens of braid or lace in the relaxed state and cut to exactly 1 yard each. While in a standard condition as defined in FED-STD-191, each specimen shall be weighed on a balance or scale accurate to 0.01 ounce (a scale or balance graduated in grams may be used and the results converted to ounces). Average the weight of all braid specimens and multiply this value by 144 to determine ounces per gross yards to the nearest 0.5 ounce; the weight of all lace specimens shall be averaged to determine ounces per linear yard to the nearest 0.01 ounce.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A.

* 5.1.1.1 Type I, classes 1, 2, and 4. As specified in 3.7, the braid on each spool shall be completely wrapped with a band of transparent plastic film or bleached sulphite paper. The wrap shall be secured with gummed or pressure-sensitive tape.

* 5.1.1.2 Type I, class 3 and type II, classes 1 and 2. As specified in 3.7, each board of braid or lace shall be completely wrapped in transparent plastic film or bleached sulphite paper. The wrap shall be secured with gummed or pressure-sensitive tape. Five boards of braid or lace, of one class, style, and color only, shall be unit packed in a setup paperboard box conforming to type II, variety 1, class A, style 4 of PPP-B-676. The depth of the lid shall



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

be not less than 1 1/4 inches. Box closure shall be secured with 2-inch minimum width gummed paper tape conforming to type III, grade B of PPP-T-45 applied completely around the center girth of the box.

* 5.1.2 Commercial. Braid or lace shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

* 5.2.1 Level A packing. Braid or lace of one class, style and color only, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Shipping containers packed with braid or lace unit packed as specified in 5.1.1.2 shall not require box liners. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of PPP-B-636. The weight of the contents of each shipping container shall not exceed 65 pounds. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Braid or lace of one class, style and color only, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, variety DW, class domestic, grade 275 of PPP-B-636. Shipping containers packed with braid or lace unit packed as specified in 5.1.1.2 shall not require box liners. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636. The weight of the contents of each shipping container shall not exceed 65 pounds.

5.2.2.1 Weather-resistant shipping containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

* 5.2.3 Commercial packing. Braid or lace, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

* 5.3 Palletization. When specified (see 6.2), braid or lace, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be in accordance with appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The braids and laces are used for decorative accessories to the blue dress uniforms for officers and enlisted personnel of the U.S. Army. The types, classes, and styles are used as follows:

Type I - Enlisted personnel

Class 1 - Coat sleeves
Class 2 - Coat shoulder loops
Class 3 - Blue dress cap
Class 4 - Belt and trouser stripes (Army Band Uniform)

Type II - Officers and enlisted personnel

Class 1, style A - General officer's trouser stripes, and enlisted men's service stripes
Class 1, style B - Officers' and enlisted men's trouser stripes and general officers' coat sleeve ornamentation
Class 2, style A - Officers' coat sleeve ornamentation
Class 2, style B - Officers' cap band

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Type, class, and style required (see 1.2).
c. When a first article is required (see 3.2, 4.3, and 6.4).
d. Colorfastness required (see 3.4.3).
e. When method of put-up is other than specified (see 3.7).
f. When certificate of compliance is acceptable (see 4.4.1).
g. Applicable levels of preservation and packing (see 5.1 and 5.2).



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

h. Type and class of unit load specified (see 5.2.1).
i. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
j. When palletization is required (see 5.3).

6.3 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Subject term (key word) listing.

Braid, uniform
Lace, uniform
Uniform, decorations

6.6 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - GL

Review activities:

Army - MD
DLA - CT

Preparing activity:

Army - GL

Project No. 8315-A323



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| MIL-B-13466D(GL) | Braid, Textile and Lace, Vellum, Woven, Textile (For Blue Dress Uniform) |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR<br>☐ USER<br>☐ MANUFACTURER<br>☐ OTHER *(Specify)*: _____ |
| b. ADDRESS *(Street, City, State, ZIP Code)* | |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:35Z
Check the source to verify that this is the current version before use.