NOT MEASUREMENT SENSITIVE

A-A-59291B
17 August 2023
SUPERSEDING
A-A-59291A
30 January 2011

COMMERCIAL ITEM DESCRIPTION

INK, MARKING
(FOR PARACHUTES AND OTHER TEXTILE ITEMS)

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers a permanent and colorfast marking ink for fabrics and webbing. The ink is generally used to identify parachute components and other items of cloth construction. It is available for use in various methods of application that are identified by type.

2. CLASSIFICATION. The ink is available in the following various methods of application that have been designated by types:

2.1 Types (methods of application).

Type I - Stamp pad
Type II - Felt tip
Type III - Ball point
Type IV - Stencil

3. SALIENT CHARACTERISTICS.

Beneficial comments, recommendations, additions, deletions, clarifications, and any other data that may improve this document should be sent to Commanding Officer, Naval Air Warfare Center Aircraft Division Lakehurst, System Standardization and PHS&T Branch, Code BL32600, B120-3, Highway 547, Lakehurst, NJ 08733-5100 or emailed to lke-navairdoccom.fct@navy.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:08Z
Check the source to verify that this is the current version before use.

3.1 Thinner. When required, a thinner, and instructions for its use, shall be available for use with the ink.

3.2 Legibility and drying. The ink, regardless of method of application, shall produce a sharp, legible impression of uniform intensity on nylon cloth and nylon webbing that will dry within 10 seconds.

3.3 Colors. The color of the ink shall be as specified (see 7.4). Unless color standards are specified or are included with the order, the ink need only comply with the generic requirements for color, e.g., light blue, orange-yellow, or black.

3.4 Fastness. The ink impressions on nylon cloth and nylon webbing shall show good fastness to laundering, when tested in accordance with AATCC 61, and weathering (light fastness), and shall not run or spread in water and salt water.

3.5 Performance. Performance characteristics of nylon cloth and nylon webbing that has been marked with the ink shall be in accordance with table I.

TABLE I. Breaking strength of nylon cloth and nylon webbing.

Property	Requirement	Test Method or Paragraph
Initial (unmarked) Initial (marked), minimum	As reported 95% of unmarked value	ASTM D5035
After weathering (marked), minimum 1/	90% of initial unmarked value	ASTM D5035
After distillation (marked), minimum	90% of initial unmarked value	3.5.1
After oven aging (marked), minimum	90% of initial unmarked value	3.5.2

1/ 80 hours of exposure

3.5.1 Distillation. A 50-milliliter sample of marking ink shall be steam distilled in an apparatus so that the temperature of the ink does not exceed that of the boiling water. Raveled specimens of nylon cloth and the center section of specimens of nylon webbing shall be immersed in the top layer of distillate for 1 hour. The specimens shall then be removed, air dried, conditioned at a temperature of 21 °C ±1 °C (70 °F ±2 °F) and a relative humidity of 65 ±2 percent, and tested for breaking strength in accordance with ASTM D5035.

3.5.2 Oven aging. Specimens of nylon cloth and nylon webbing shall be exposed in an air-circulating oven at a temperature of 71.1 °C (160 °F) for 100 hours. The specimens shall then be removed, conditioned at a temperature of 21 °C ±1 °C (70 °F ±2 °F) and a relative humidity of 65 ±2 percent, and tested for breaking strength in accordance with ASTM D5035.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:08Z
Check the source to verify that this is the current version before use.

3.6 Stability.

3.6.1 Storage. The ink shall show no signs of livering, curdling, or excessive bodying and shall produce sharp, legible impressions on nylon cloth when stored in its original, unopened container at a temperature of 43 °C (110 °F) for 100 hours.

3.6.2 Exposure. Ink, when applied to a stamp pad, shall not harden or form a crust and shall produce sharp, legible impressions of uniform intensity on nylon cloth when exposed to the atmosphere at a temperature of 21 °C ±1 °C (70 °F ±2 °F) and a relative humidity of 65 ±2 percent for 6 hours.

4. REGULATORY REQUIREMENTS.

4.1 Regulatory requirements. The offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with 23.403, 23.404(b) of the Federal Acquisition Regulation FAR, or the sustainable acquisition of EO 13693; as applicable.

4.2 Toxicity. The use of benzene or carbon tetrachloride, and any known carcinogens as ingredients, is prohibited. The use of lead is prohibited. Trace amounts of benzene derivatives present in commercial grades of acceptable aromatics are permissible. Inks shall contain no chlorinated compounds or other toxic hydrolyzable chlorine derivatives. The use of any toxic substance must be in accordance with applicable federal statutes.

4.3 Safety data sheets. Safety data sheets shall be furnished in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in appendix B of FED-STD-313.

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5.2 Market acceptability. The following market acceptability criteria is necessary to document the quality of the product to be provided under this CID.

5.2.1 The company producing the marking ink must have been producing a product meeting the requirements of this CID for at least 6 months.


Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:08Z
Check the source to verify that this is the current version before use.

6. PACKAGING.

6.1 Preservation, packing, and marking. Preservation, packing, and marking shall be as specified in the contract or order.

7. NOTES.

7.1 Part or Identification Number (PIN). The following part or identification numbering procedure is for government purposes and does not constitute a requirement for the contractor. PINs to be used for ink procured to this commercial item description are created as follows:



7.2 National Stock Numbers (NSNs). The following is a list of NSNs assigned that correspond to this CID. The list may not be indicative of all possible NSNs associated with the CID.

7510-00-144-9672
7510-00-286-5362
7510-00-634-6583
7510-01-235-2607

7.3 Source of documents.

7.3.1 AATCC 61 is available online at https://www.aatcc.org.

7.3.2 ASTM D5035 is available online at https://astm.org.

7.3.3 EO 13693 is available online at https://federalregister.gov.

7.3.4 FED-STD-313 is available online at https://assist.dla.mil.

7.3.5 The Federal Acquisition Regulation (FAR) is available online at https://ecfr.gov.

7.4 Ordering data. The purchaser should select the required options permitted herein and include the following information in procurement documents:

a. Title, number, and date of this commercial item description.
b. Application type.
c. Color.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:08Z
Check the source to verify that this is the current version before use.

d. Preservation, packaging, and packing.

7.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

CONCLUDING MATERIAL

MILITARY INTERESTS:

Custodians:
Army – GL
Navy – AS
Air Force - 99

Review activities:
Army – CR4, MI
Navy – CG

CIVIL AGENCY COORDINATING ACTIVITY:

GSA/FAS – 2FYI

Preparing activity:
Navy - AS
(Project 7510-2023-001)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:08Z
Check the source to verify that this is the current version before use.