OO-P-65A
July 1, 1975
SUPERSEDING
Int. Fed. Spec. OO-P-0065 (GSA-FSS)
December 10, 1959

FEDERAL SPECIFICATION

PAD, FLOOR POLISHING MACHINE (STEEL WOOL)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers steel wool pads for use with electric floor polishers.

1.2 Classification. Steel wool pads shall be of the following types, grades, and sizes, as applicable (see 6.2):

Type I - Disc-shaped, plain.

Grade 3 - Very coarse.

Size - 17-inch diameter.
Size - 22-inch diameter.

Type II - Disc-shaped, reinforced.

Grade 2 - Coarse.

Size - 15-inch diameter.
Size - 18-inch diameter.

Grade 3 - Very coarse.

Size - 15-inch diameter.

Type III - Ring-shaped, reinforced.

Grade 0 - Fine.

Size - 15-inch diameter.

Grade 3 - Very coarse.

Size - 18-inch diameter.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

FF-W-1825 - Wool, Metallic.
OO-P-570 - Polisher, Floor, Electric (Commercial Type).
PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.

Federal Standard:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Material. The steel wool used in the pad shall conform to type I of FF-W-1825 and shall be in accordance with 3.1.1 for the specified grade (see 1.2).

3.1.1 Grade. The pad shall be graded by the thickness of the individual steel wool fibers in accordance with table I (see 4.4.1).

TABLE I. Wool thickness, individual fibers

Grade	Not more than 5 percent under		Not more than 5 percent over		No fiber to exceed	
	Inch	mm	Inch	mm	Inch	mm
0	0.0003	0.0076	0.0070	0.1780	0.0120	0.3050
2	.0010	.0254	.0140	.3560	.0250	.6350
3	.0020	.0508	.0180	.4570	.0400	1.0200

3.2 Design. The steel wool pads shall be either disc-shaped or ring-shaped and shall be suitably designed for use with rotary electric floor polishers covered by OO-P-570.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.

3.3 Construction.

3.3.1 Type I. Type I plain pads shall be disc-shaped with or without center hole. When provided, center hole shall be not larger than one inch in diameter. Pads shall consist of steel wool either compacted into disc-shape or steel wool ribbons spirally wound into disc-shape. The individual strands of steel wool shall be intermingled, wound, or otherwise fabricated so that the entire pad is a cohesive unit. The type I pad shall be a minimum of two inches in thickness (see 4.3.2).

3.3.2 Type II. Type II reinforced pads shall be disc-shaped with or without center hole. When provided, center hole shall be not larger than one inch in diameter. Pads shall be reinforced as specified in 3.3.2.1 through 3.3.2.4, inclusive.

3.3.2.1 Welded pads. Welded pads shall consist of a series of individual bar welds penetrating the full thickness of the pad. Welds shall be spaced radially around the disc at intervals not to exceed 45 degrees and shall extend from center to circumference. Additionally, shorter welds of equal length may be interposed uniformly to extend from the center of the pad.

3.3.2.2 Stitched pads. Stitched pads shall consist of ribbons of steel wool spirally wound with the steel wool strands running in circular form. The pad shall be stitched in at least three places completely across the disc to form a minimum of six segments of 60 degrees or less.

3.3.2.3 Wired pads. Wired pads shall consist of ribbons of steel wool spirally wound with the steel wood strands running in circular form. The pad shall be wired completely through the disc with a continuous or connected wire from center to circumference in six equally spaced segments. Minimally, the alternate segments shall be wire reinforced on the outer periphery.

3.3.2.4 Roped pads. Roped pads shall consist of ribbons of steel wool spirally wound with the steel wool strands running in circular form. The pad shall be bound together with steel wool ropes of the same grade of steel wool as used in the disc. The pad shall be roped completely through the disc in at least two places to hold the pad in shape.

3.3.3 Type III. Type III reinforced pads shall be ring-shaped with center hole conforming to table II for the specified size. Methods of reinforcement shall conform to type II pads or those specified in 3.3.3.1 and 3.3.3.2.

3.3.3.1 Braided pads. Braided pads shall consist of steel wool strands bunched into ropes and braided together to form a ring shape.

3.3.3.2 Corded pads. Corded pads shall consist of individual strands of steel wool arranged radially in a helical pattern to form a doughnut-shaped ring. A continuous cord shall be inserted through the steel wool mass adjacent to the inner diameter of the ring.

3.4 Sizes and weights. The size of the pad shall be the nominal dimension of the outside diameter of the pad. Diameters and weights shall be in accordance with table II for the type pad specified (see 4.3.2 and 4.4.2).

TABLE II. Pad diameters and weights

Types	Outside diameter (nominal) 1/	Hole diameter (maximum) 2/	Weight (minimum)
	Inches	Inches	Ounces
I	17	1.0	9.0
	22	1.0	15.0
II	15	1.0	7.5
	18	1.0	12.0
III	15	6.5	6.0
	18	8.5	9.5

1/ Tolerance of 0.25 inch allowed.
2/ When center hole is provided for types I and II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.

3.5 Marking for identification. Each pad shall be marked with the size, grade of the steel wool pad, and the manufacturer's name, trade name, or trademark by use of a label, tag, wrapper, or bag.

3.6 Workmanship. Steel wool pads shall be of uniform quality, clean, and free from foreign material, chips, and defects which render them unsuitable for use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling.

4.2.1 Lot. Unless otherwise specified (see 6.2), a lot shall consist of all steel wool pads of the same type, grade, and size submitted for inspection at the same time. The sample unit shall be one completely fabricated end item.

4.2.2 Sampling for examination and tests. Sampling for visual and dimensional examination shall be in accordance with level S-4 of MIL-STD-105. Sampling for tests shall be in accordance with level S-1 of MIL-STD-105.

4.3 Examination.

4.3.1 Visual examination. Examine steel wool pads in accordance with table III. The acceptable quality level (AQL) shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects.

TABLE III. Classification of defects

Defects	Major	Minor
Type not as specified	X	
Reinforcement not as specified (types II and III only)	X	
Foreign matter in wool		X
Carbon steel wool stained with rust		X
Distorted; does not lay substantially flat on a plane surface		X
Identification marking missing, illegible, or incorrect		X

4.3.2 Dimensions. Type I steel wool pads shall be measured for compliance with the thickness requirement in 3.3.1. Steel wool pads shall be measured dimensionally for compliance with 3.4. Failure to meet the dimensional requirement shall be cause for rejection of the lot.

4.3.3 Inspection of preparation for delivery. An inspection shall be made to determine that the packaging, packing, and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table IV. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, selected at random just prior to the closing operations. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

TABLE IV. Classification of preparation for delivery defects

Examine	Defect
Marking	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Material	Any component missing, damaged or not conforming to the applicable specification or requirements stated herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of preparation for delivery defects (con.)

Examine	Defect
Workmanship	Inadequate application of components such as loose strapping, incomplete closure of container flaps, inadequate stapling or distortion of container.
Contents	Quantity per container is more or less than required. Gross weight exceeds the requirements of the box specification.

4.4 Tests.

4.4.1 Fiber thickness. Measure 25 fibers for maximum lateral dimension under a 50X or greater magnification using a microscope with recticle suitable for measuring the fiber width in thousands of an inch (two hundreds of a millimeter). Nonconformance to the specified grade shall be cause for rejection of the lot (see 3.1.1 and table I).

4.4.2 Weight. Pads shall be weighed on a scale graduated in ounces and fractions thereof to determine compliance with 3.4 and table II. Noncompliance shall be cause for rejection of the lot.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A. Pads of one description shall be packaged in a box conforming to PPP-B-636, V3c. The box shall be waterproof sealed with tape in accordance with the appendix to the box specification.

5.1.2 Level C. The pads shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Pads of one description shall be packed in a box conforming to PPP-B-585, class 3; PPP-B-591, class II; PPP-B-601, overseas type; PPP-B-621, class 2; PPP-B-636, class weather resistant; or PPP-B-640, class 2. The box shall be closed and strapped in accordance with the applicable specification or appendix thereto. The gross weight of the triple wall box and the wood boxes shall not exceed 200 pounds. The gross weight of the box conforming to PPP-B-636 shall not exceed the weight limitation of the box specification.

5.2.2 Level B. Twelve (12) pads of one description shall be packed in a box conforming to PPP-B-636, class domestic. Closure shall be in accordance with method I of the appendix to the box specification.

5.2.3 Level C. Pads of one description shall be packed to insure carrier acceptance and safe delivery at destination in containers complying with the National Motor Freight Classification Rules or Uniform Freight Classification Rules, as applicable.

5.3 Marking. In addition to the markings required by the contract or order, the packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

6. NOTES

6.1 Intended use. Steel wool pads are used as an abrasive in floor preparation and maintenance. Typical uses are polishing, wet or dry scrubbing, and cleaning. Normal application for the grades covered by this specification are:

Grade 0 - Cleaning and polishing.
Grade 2 - Preparing floors for wax or the scrubbing of rough floors.
Grade 3 - Removing paint and varnish; smoothing and buffing wood floors.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type, grade, and size required (see 1.2).
(c) Size of lot, if different from 4.2.1.
(d) Level of packaging and packing (see 5.1. and 5.2).

6.3 Deletions. Classes, size numbered designations, grades 00 and 1, and diameters 10-1/2 to 11-1/4-inch and 12-1/2 to 13-1/4-inch of OO-P-0065 (GSA-FSS) have been deleted.

Preparing activity:

GSA - FSS

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 30 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:58Z
Check the source to verify that this is the current version before use.