MIL-P-25716C(USAF)
23 August 1962
Superseding
MIL-P-25716B(USAF)
2 May 1962

MILITARY SPECIFICATION

PARACHUTE SYSTEM, HEAVY DUTY, GENERAL SPECIFICATION FOR

1. SCOPE

1.1 This specification covers the general requirements for heavy-duty parachute systems.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Military

MIL-C-5040	Cord, Nylon
MIL-P-5610	Parachutes and Parachute Component Parts, Packaging and Packing for Domestic and Overseas Shipment of
MIL-I-6903	Ink, Marking (for Parachutes and Other Textile Items)
MIL-T-7807	Thread, Nylon

STANDARDS

Federal

FED-STD-595	Colors
FED-STD-751	Stitches, Seams, and Stitchings

Military

MIL-STD-129	Marking for Shipment and Storage
MIL-STD-130	Identification Marking of U. S. Military Property
MIL-STD-143	Specifications and Standards Order of Precedence for the Selection of
MS33586	Metals, Definition of Dissimilar

FSC 1670

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

PUBLICATIONS

Air Force Specification Bulletin

529	Parachute Defects, Classification of, Heavy Duty Parachutes Only
530	Verification Testing of Parachute Textile Materials

(Copies of documents required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 QUALIFICATION.- The parachute system furnished under this specification shall be a product which has been tested, and has passed the qualification tests specified herein, and has been listed on or approved for listing on the applicable qualified products list.

3.2 COMPONENT PARTS.- The parachute system shall consist of the component parts specified in the applicable assembly drawing.

3.3 SELECTION OF SPECIFICATIONS AND STANDARDS.- Specifications and standards for necessary commodities and services not specified herein shall be selected in accordance with MIL-STD-143 except as provided in 3.3.1 and 3.3.2.

3.3.1 COMMERCIAL PARTS.- Commercial parts having suitable properties may be used where, on the date of invitation for bids, there are no standard parts. In any case, commercial utility parts, such as screws, bolts, nuts, and cotter pins, having suitable properties may be used provided:

a. They can be replaced by the standard parts (MS or AN) without alteration.

b. The corresponding standard part numbers are referenced in the parts list and, if practical, on the contractor's drawings.

3.3.2 STANDARD PARTS.- With the exception in 3.3.1, MS and AN standard parts shall be used where they suit the purpose. They shall be identified on the drawings by their part numbers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

3.4 MATERIALS

3.4.1 FUNGUS-PROOF MATERIALS.- Materials that are nutrients for fungi shall not be used where it is practical to avoid them. Where used and not hermetically sealed, they shall be treated with a fungicidal agent acceptable to the procuring activity. However, if they will be used in a hermetically sealed inclosure, fungicidal treatment will not be necessary.

3.4.2 TEXTILE.- Textile materials which have been manufactured (as evidenced by date of manufacture) more than 2 years prior to the date of award of contract shall not be used in the fabrication of parachute component parts. When the color of textile materials used in the fabrication of parachute components is called out as natural, all colored marker threads shall be omitted where now required by applicable specifications and replaced with natural colored marker threads. All natural color textile materials shall be free of blemishes and foreign matter. Only natural color textile materials shall be used in the fabrication of canopies and pilot chutes.

3.4.3 METALS.- Metals shall be of the corrosion-resistant type or suitably treated to resist corrosion due to fuels, salt spray, or atmospheric conditions likely to be met in storage or normal service.

3.4.3.1 DISSIMILAR METALS.- Unless protected against a electrolytic corrosion, dissimilar metals shall not be used in intimate contact with each other. Dissimilar metals are defined in MS33586.

3.5 DESIGN AND CONSTRUCTION.- The design and construction of the parachute component parts shall conform to applicable drawings or detail specifications.

3.5.1 OPERATION.- The sequence of operation shall be such that the pilot chute will be activated by a static line connected directly to either the aircraft or to any automatic means of deployment. The pilot chute shall remove the deployment bag from the vehicle cavity and in turn deploy the canopy.

3.6 CANOPY.- The canopy shall be of the ribbon, the ring slot, the solid flat, or the guide surface type. Canopy layout and construction details shall conform to applicable drawing or detail specification.

3.6.1 DRAG SURFACE.- All material required to manufacture the drag surface for the canopy shall be taken from a minimum practical number of lots of each individual type of material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

3.6.2 SUSPENSION LINES.- Suspension lines shall be continuous and without splices for each length specified by the applicable drawing.

3.6.2.1 The suspension line length from the canopy skirt to the attachment loop shall be marked after the drag surface portion of the line is sewn into the radial seam of the canopy.

3.6.2.2 All suspension lines for one canopy shall be marked within an 8-hour period or one work shift.

3.6.2.3 All suspension lines for one canopy shall be taken from the same lot and loom.

3.7 DEPLOYMENT BAG.- The deployment bag shall conform to the applicable drawing.

3.8 PILOT CHUTE.- The pilot chute shall be of the guide surface or Fist ribbon type. Canopy layout and construction details shall conform to the applicable drawings or detail specifications.

3.9 BRIDLE LINE.- When required (see 6.2), the bridle line shall conform to the applicable drawing.

3.10 STATIC LINE.- When required (see 6.2), the static line shall conform to the applicable drawing.

3.11 COVER ASSEMBLY.- When required (see 6.2), the cover assembly shall conform to the applicable drawing.

3.12 HARDWARE.- The hardware shall conform to the applicable drawing.

3.13 THREAD.- The thread used for stitching shall conform to type I or II, class 1 of MIL-T-7807. The size of the thread shall be as specified in the drawing or detail specification.

3.14 STITCHING.- The stitches shall conform to FED-STD-751. Unless otherwise specified, stitch type 301 shall be used. The size of the thread and the number of stitches per inch applicable to stitch type shall be as specified in table I.

3.14.1 TENSION.- The tension of the bobbin and needle threads shall be equal so that the thread lock will lie as close as possible in the center of the layers below the surface. Multiple-needle machines shall be adjusted to provide the same tension from each needle.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

TABLE I - THREAD SIZE AND STITCHES PER INCH

Thread or Cord Size	Stitches Per Inch		
	Straight Stitch 1/	Zigzag Stitch	
	Type 301	Single Throw	Double Throw
E	7 to 12 2/	12 to 16	8 to 12
F	7 to 11 2/	12 to 14	7 to 10
FF	7 to 11 2/	12 to 14	7 to 10
3 cord	6 to 9		4 to 6
5 cord	5 to 8		3 to 5
6 cord	5 to 8		3 to 5
8 cord	4 to 6		

1/Where abrupt changes occur in the thickness of material in excess of 1/32 inch, the number of stitches specified in this table may vary plus or minus 2 stitches per inch for a distance not exceeding 3/4 inch.
2/A maximum of 16 stitches per inch for a length not exceeding 2 inches in any one place with a minimum distance of 12 inches between locations will be acceptable. No section or gore shall contain more than 16 stitches per inch.

3.14.2 STRAIGHT STITCHING.- All single-needle straight stitching shall be backstitched for a distance of not less than 1/2 inch. Multiple rows of straight stitching shall be distributed equally across the seam when a single-needle machine is used. When using commercial, multiple-needle machines, the standard gages will be acceptable. For both single-needle and multiple-needle machine stitching, the distance from the edge of the seam or material to the outside row of stitching shall be 1/8 inch, plus or minus 1/16 inch.

3.14.2.1 CROSS AND BOX STITCHING.- The cross and box stitching shall be straight, neat, and even. To insure good workmanship outlines may be used as stitching guides. To preclude the possibility of damage to the canopy, outlines or any marking shall be of approved materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

3.14.3 ZIGZAG STITCHING (SEE 6.5.1)

3.14.3.1 PARALLEL STITCHING.- When parallel to straight stitching, zigzag stitching shall normally not overlap the straight stitching.

3.14.3.2 CENTERING.- When only one row of zigzag stitching is specified, the stitching shall be centered.

3.14.3.3 MATERIAL THICKNESS.- Where the material thickness is more than doubled, the width of the stitching may vary plus or minus 50 percent or the number of stitches may vary plus or minus 2 stitches per inch, beyond that specified in table I, for a distance not exceeding 3/4 inch.

3.14.3.4 LENGTH TOLERANCE.- The tolerance on the length of zigzag-stitch rows shall be plus 1/2 or minus 0 inch.

3.14.3.5 SINGLE NYLON CORD.- When one row of double-throw zigzag stitching on a single cord is specified, one-quarter of the length of any stitched row may be pierced by only two needles provided that the cord conforms to MIL-C-5040.

3.14.4 BASTING STITCH.- It is not necessary to remove the basting thread, provided that nylon thread, size E or lighter, is used.

3.15 SEAMS.- The seams shall conform to FED-STD-751. The seams shall be flat and smooth to preclude pleating, ragged edges, cloth edges not properly caught, and puffiness of fabric between the rows of stitching. In the interest of good workmanship, every effort shall be made to produce a fully folded flat seam which shall contain no excessive puffiness. Finished fell and hem seams showing raw edges shall be repaired.

3.16 SPLICING.- Unless otherwise specified, splices of webbings, tapes, and ribbons used in assembling the parachute component parts shall be held to a minimum and shall not exceed the number specified in table II. When two or more layers of the same material are used in a seam, one layer shall be continuous across the splice of the other layer. Unless otherwise specified, the splice shall be made by overlapping the ends for a distance of not less than 4 inches. Unless otherwise specified, vent reinforcement splices shall be across at least two adjacent radial reinforcements. Vent, skirt, and reinforcing band splices shall not appear in the same gore.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

TABLE II - FREQUENCY OF SPLICES AND REPAIRS

Length of Seam (Inches)	Number of Splices	Number of Repairs
0 to 2	0	0
2 to 12	0	1
12 to 72	0	2
72 to 240	1	3
240 to 360	2	4
360 to 480	3	5
480 to 600	4	6
Over 600	1 per 120 inches	1 per 100 inches

3.16.1 CONTINUOUS RIBBON.- All continuous horizontal ribbon construction shall have the splices centered at the radial reinforcement and staggered in a spiral manner around the canopy. The number of splices per continuous ribbon shall be in accordance with the applicable specification or drawing.

3.17 REPAIRS (SEE 6.5.2)

3.17.1 REPAIR OF STITCHING.- All stitching defects shall be repaired by either overstitching or adjacent stitching which shall extend a length of 3 inches, plus or minus 1 inch, beyond the ends of the defective stitching. Repair of stitching shall be made with stitch type 301.

3.17.1.1 FREQUENCY OF STITCHING REPAIRS.- The frequency of stitching repairs shall be not more than specified in table II.

3.17.2 DARNING.- Holes (see 6.5.3) not exceeding 1/4 inch in diameter may be darned. The darned area shall extend 3/8 inch beyond the hole on all sides and shall result in round or rectangular patterns. Linear tears or cuts up to 1/2 inch may be darned. The darned area shall form a rectangular pattern extending 1/4 inch beyond each side and each end of the tear. All darns shall be neat and flat and shall not pucker the cloth. Size A thread or yarns from the cloth shall be used for darning. The color of the darning thread or yarn shall match the material being darned. This paragraph is not applicable to ribbon canopies on which no darning is permitted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

3.18 STITCHING DEFECTS

3.18.1 Repair shall be made as specified in 3.17.1 and 3.17.2. It is not necessary to remove the original stitching if the following defects occur during the sewing operation:

a. Thread breakage

b. Two consecutive skipped stitches

c. Two inches or less of intermittent skipped stitches

d. Kinks or so-called "knotty thread" 2 inches or less from each other.

3.18.2 The stitching shall be removed and the item resewn if the following defects occur:

a. The number of stitches per inch is less than specified in table I.

b. The stitching runs-off, that is, extends beyond the edge of the seam or material.

c. More than two consecutive skipped stitches

d. More than 2 inches of intermittent, skipped stitches.

3.19 MEASUREMENTS

3.19.1 CLOTH.- All cloth shall be measured and cut while under substantially no tension. Tightly rolled materials shall be relaxed by unrolling for a period of at least 24 hours to permit material to return to its natural state. Patterns shall be carefully placed on the cloth to distribute the small inequities because of various cloth widths (within tolerances specified) on each side of the pattern. When multiple layers of cloth are being cut at the same time, extreme care shall be taken to prevent the cloth from slipping during any part of the cutting operation.

3.19.2 SUSPENSION AND VENT LINES.- Suspension and vent lines shall be measured under the tensions specified in table III. Care shall be exercised in preparing proper line-measuring equipment. If pulleys, guides, reels, et cetera are used, they shall not induce false loads on the material, nor shall they be cause of uneven load distribution on multiple-line measuring systems. Care shall be exercised to maintain uniformity in time control of load applications

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

and control of large changes in temperature and humidity. Suspension lines of any one canopy measured under tension in accordance with table III and the applicable drawing shall not vary by more than 1 percent.

TABLE III - TENSIONS FOR MEASUREMENT OF SUSPENSION AND VENT LINES

Tensile Strength (Pounds)	Tension (Pounds)
100 to 500	10 plus or minus 1/2
500 to 1,000	20 plus or minus 1
1,000 and up	40 plus or minus 2

3.19.3 WEBBINGS.- All webbings, tapes, and ribbons used in assembling the drag surface shall be measured under no tension. The webbings shall not be measured while in the stretched state which is caused by winding the webbing onto the spool while the webbing is under tension. A uniform period of time, at least 24 hours, between unwinding from a spool or relaxing from a stretched state and marking shall be maintained.

3.19.4 DRAG SURFACE.- When finished dimensions are specified, the contractor shall provide proper allowances for stitching take-up to obtain the finished dimensions within the specified tolerances under any condition of humidity. Unless otherwise specified in the applicable drawing, all measurements of finished dimensions shall be made on the finished drag surface under nominal tension within 15 seconds after application of the nominal tension (see 6.5.4).

3.19.5 STITCHES.- The number and spacing of stitching shall be measured under a tension of not less than 1/2 pound nor more than 1 pound.

3.20 DIMENSIONS.- Unless otherwise specified, the general tolerances on dimensions shall be in accordance with table IV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

TABLE IV - TOLERANCES ON DIMENSIONS

Dimensions (Inches)	Tolerances (Inch)
Under 2 1/	plus or minus 1/16
2 to 10	plus or minus 1/8
10 to 30	plus or minus 1/4
30 to 60	plus or minus 3/8
60 and up	plus or minus 1 percent

1/Where a dimension of 1/16 inch is given, the tolerance shall be plus or minus 1/32 inch.

3.21 ADDITIONAL REQUIREMENTS.- The requirements specified in the applicable drawings shall be applicable as requirements of this specification.

3.22 FINISH

3.22.1 ENDS.- The ends of all material not covered by other cloth, tapes, webbings, or ribbons in the final assembly shall be treated to prevent fraying. The exposed ends of nylon cords, webbings, tapes, and ribbons shall be cut and turned under or seared smoothly and evenly or dipped in a hot mixture of 50 percent beeswax and 50 percent paraffin. Other solutions to prevent fraying may be used if samples are submitted and written approval obtained from procuring activity (see 6.3). The ends of suspension lines shall be neatly trimmed back to the stitching, leaving an end that is no longer than 1/4 inch.

3.22.2 SEARING.- Searing shall not be permitted after stitching. Any searing permitted shall not leave sharp edges or points that may cause snagging of cloth material. Searing shall not be used where the end of the material is sandwiched between two other pieces of material or where the stitching runs continuously over the exposed ends. All finishing shall be done neatly and shall have no sharp edges or excess melted materials that might cause localized stresses. Whenever searing is used, the

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

finished component part shall be carefully examined for holes and snags caused by poorly seared materials. One broken warp thread will be allowed in a tape or webbing, provided that the strength of the material is not below specification strength.

3.22.3 CLEANLINESS.- All finished components without regard to complexity of design or manufacture shall be free of blemishes and foreign matters such as dirt, paint, oil, grease, graphite, stains, and any other discoloration.

3.23 MARKING

3.23.1 IDENTIFICATION OF PRODUCT.- Equipment, assemblies, and parts shall be marked for identification in accordance with MIL-STD-130. Unless otherwise specified on the applicable drawing, the marking shall be as follows:

CANOPY, PARACHUTE_____*
_____Ft Diameter
USAF Part No. (Drawing No.)_____
Manufacturer's Serial No._____
Contract No._____
Manufacturer's Name or Trademark
U. S. Property
Date of Manufacture

*Guide Surface, Ring Slot, Ribbon, etc.

3.23.2 CANOPY MARKING.- The marking of the canopy shall be stamped or stenciled on the lower section of the last gore in the numbering order, which is adjacent to the number 1 gore. The size of the letters shall be not less than 1/2 inch high.

3.23.2.1 GORE NUMBERS.- All gores shall be numbered by stamping or stencilling the number in the right-hand corner on the outside of the lower sections on or adjacent to the skirt reinforcement. Numbering sequence shall be clockwise when viewing the canopy from the top. The size of the numbers shall be not less than 1/2 inch high.

3.23.3 ASSEMBLY AND STITCHING PATTERNS.- Marking of canopy, deployment bag, and other component parts using fluids, chalk, pencil, etc as an aid to assembly and to indicate stitching patterns shall be accomplished in a manner that will not adversely affect the utility, strength, or appearance of the parachute. The color shall be in accordance with 3.23.5. Drilling and notching shall be kept to a minimum and the use thereof shall be restricted to the same limitations as marking. A hot needle shall not be used for marking or assembly if discoloring of the natural color textile materials takes place.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

3.23.4 MARKING FLUID.- Marking fluid for all textile parts shall conform to MIL-I-6903.

3.23.5 COLOR.- Unless otherwise specified on the applicable drawing, the color of all markings on textile parts and all natural color textile materials shall be color No. 13538 of FED-STD-595.

3.24 WORKMANSHIP.- The parachute system, including all parts and assemblies, shall be fabricated and finished in a workmanlike manner. Particular attention shall be given to cleanliness, accuracy of dimensions and markings, neatness and thoroughness of stitching, and proper assembly of component parts. The hardware components of the parachute shall be free from burrs and sharp edges.

3.24.1 CANOPY.- The quality of the ribbon and guide surface cahopies shall be exceptional in all respects. Dimensions specified for the over-all diameter shall be closely controlled and maintained because of the nature of the requirements. Proper fullness is mandatory for balanced load distribution of the vent, the skirt, and the horizontal and the vertical ribbons.

4. QUALITY ASSURANCE PROVISIONS

4.1 SUPPLIER'S RESPONSIBILITY.- The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 CLASSIFICATION OF TESTS.- The inspection and testing of parachute systems shall be classified as follows:

a. Acceptance tests

b. Qualification testing.

4.3 ACCEPTANCE TESTS.- Acceptance tests shall consist of the following:

a. Individual tests

b. Sampling plan and tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

4.3.1 INDIVIDUAL TESTS.- Each parachute component part shall be subjected to the Examination of Product as described under 4.4 Test Methods of this specification.

4.3.2 SAMPLING PLAN AND TESTS

4.3.2.1 SAMPLING PLAN A.- Samples of parachute systems from each production contract shall be selected in accordance with table V. One of these samples shall be from the first 10 production items. At the discretion of the procuring activity these samples will be subjected to any or all of the following tests as described under 4.4 Test Methods of this specification:

a. Conformance with drawings

b. Drop tests

c. Compliance with this specification.

TABLE V - NUMBER OF SAMPLES TO BE TESTED

No. of Items on Contract	No. of Samples to Be Submitted for Testing 1/
Less than 500	2
500 to 1,000	3
1,001 to 2,000	4
2,001 to 5,000	5

1/In systems where identical components are used, as in a cluster configuration, only one of each component will be required.

4.3.2.1.1 REJECTION AND RETEST.- When one or more items from a lot fail to meet the specification, acceptance of all items in the lot shall be withheld until the extent and cause of the failure have been determined. The contractor shall explain fully to the Government representative the cause of failure and the action taken to preclude recurrence.

4.3.2.1.2 INDIVIDUAL TESTS MAY CONTINUE.- For production reasons, individual tests or other sampling plans may be continued pending the investigation of a sampling test failure. But final

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

acceptance of the entire lot or lots produced later shall not be made until it is determined that all items meet all the requirements of the specification.

4.3.3 DEFECTS IN ITEMS ALREADY ACCEPTED.- The investigation of a test failure could indicate that defects may exist in items already accepted. If so, the contractor shall fully advise the procuring activity of all defects likely to be found and methods of correcting them.

4.4 TEST METHODS

4.4.1 EXAMINATION OF PRODUCT.- The parachute component parts shall be inspected to determine compliance with the requirements specified herein with respect to material, dimensions, workmanship, cleanliness, and marking. Materials shall be verified in accordance with Bulletin 530. The classification of defects found during inspection shall be in accordance with Bulletin 529.

4.4.1.1 SEAM EXAMINATION.- All canopy seams shall be examined for conformance to the applicable drawing by projection of a strong light through the seams. This inspection shall be accomplished prior to hemming and installation of suspension.

4.4.1.2 FINAL INSPECTION.- Final inspection of the completed canopy shall be by the projection of a strong light through or from above the canopy, whichever is the more suitable, to determine if broken, run-off, or missing stitching is apparent; to locate holes in the canopy caused by line threading needle, snags, cuts, strains, and material defects; and to determine cleanliness.

4.4.2 DROP TESTS.- All drop tests shall be conducted on complete parachute assemblies and component parts when specified by the procuring activity and in accordance with the instructions of the procuring activity. The conditions for drop testing shall be in accordance with the operational requirements or the military characteristics of the specific system.

4.5 QUALIFICATION TESTING

4.5.1 TEST SAMPLES.- The qualification test sample shall consist of one complete parachute system or of any component thereof upon which qualification is desired and shall comply with all provisions of this specification and applicable drawings. In systems where identical components are used, as in a cluster configuration, only one of each component shall be required with the other parts of the system. Samples shall be identified with the manufacturer's part number and any additional information required by the letter of authorization.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

4.5.1.1 The following samples of material shall be submitted: 10 yards of all types of webbing, ribbons, and tapes; one spool of each type of thread used; and one sample of each of the hardware fittings used in the manufacture of the parachutes.

4.5.1.2 Qualification test samples of parachute systems shall be accompanied by a certificate to the effect that such samples were manufactured by the submitter during the preceding 90 days.

4.5.2 QUALIFICATION REQUIRED.- Prior to actual procurement, the product which this specification covers shall pass the qualification tests specified herein. If the product is later modified in any way, the modified form shall be subjected to and shall pass the same qualification tests.

4.5.3 QUALIFICATION TESTS.- The qualification tests shall consist of all tests described under 4.4 Test Methods of this specification.

4.6 INSPECTION OF PRESERVATION, PACKAGING, AND PACKING.- The inspection of preservation, packaging, and packing shall be in accordance with the requirements of section 5 or the documents referenced therein.

5. PREPARATION FOR DELIVERY

5.1 PACKAGING, PRESERVATION, AND PACKING.- Unless otherwise specified by the procuring activity (see 6.2), the preservation, packaging, and packing of parachutes shall be in accordance with MIL-P-5610.

5.2 MARKING.- Interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 INTENDED USE.- The heavy-duty parachute system covered by this specification is intended for use with heavy-weight special loads at release conditions of high speed and low or high altitudes.

6.2 ORDERING DATA.- Procurement documents should specify the following:

a. Title, number, and date of this specification

b. Preservation and packaging and packing required

c. Whether a bridle line, a static line, and a cover assembly are required (see 3.9, 3.10, and 3.11)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

d. Requirements for packing for drop test (see 4.4.2)

e. Samples specified in 4.3.2.1, 4.5.1 and 4.5.1.1 shall be forwarded to the Transportation Officer, Building 258, AFB 2300, Mark For Department 251, Attention: ASNPSP-4, Wright-Patterson Air Force Base, Ohio. The following information shall accompany the samples:

Samples for acceptance testing
Nomenclature
Part No. (Applicable AF Drawing No.)
Name of manufacturer
Submitted by (name - date) for testing
in accordance with the requirements of MIL-P-25716C(USAF)
Under (order - contract number)

6.3 QUALIFICATION.- With respect to products requiring qualification, awards will be made only for such products as have, prior to the time set for opening of bids, been tested and approved for inclusion in the applicable Qualified Products List whether or not such products have actually been so listed by that date. The attention of suppliers is called to this requirement, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification, in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the qualified products list is the Aeronautical Systems Division, Attention: ASNPSP-4, Wright-Patterson Air Force Base, Ohio, and information pertaining to qualification of products may be obtained from that activity.

6.4 DISCREPANCIES.- It will always be the contractor's responsibility to report in writing, immediately upon delivery, any discrepancies between this specification, and detailed specifications or applicable drawings.

6.5 DEFINITIONS

6.5.1 ZIGZAG STITCHES.- A single-throw zigzag stitch is defined as having two needle drops, and a double-throw zigzag stitch is defined as having three needle drops.

6.5.2 REPAIR.- A repair is a replacement of missing, broken, or removed thread or yarn.

6.5.3 HOLE.- A hole in the material is two or more broken yarns in the direction of either the warp or the fill, or both, of the material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

6.5.4 NOMINAL TENSION.- Nominal tension is a pull of 1 percent of the specification strength of the material not to exceed 40 pounds.

NOTICE.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

JMA/rrw
ASNP&P-1

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

San Antonio ALC (SWRCS)
Kelly AFB TX 78241

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:08Z
Check the source to verify that this is the current version before use.