MILITARY SPECIFICATION

PRIMER, ELECTRIC, M83
LOADING, ASSEMBLING AND PACKING

This amendment forms a part of Military Specification MIL-P-63311 (AR), dated 29 June 1979, and is approved for use by the U. S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Title: Delete: "(ALTERNATE)".

1.1: Delete: "(Alternate)".

2.1: Specifications:

MIL-E-46215: Change "Igniter, Electronic Primer, M63 and Electric Primers, M80A1 and M83" to "Electric Primers, M80A1, M83 and M120".

PAGE 2

2.1: Standards:

Add: "MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes".

Change: "MIL-STD-286 Propellants: Sampling, Inspection and Testing" to "MIL-STD-286 Propellants, Solid: Sampling, Examination and Testing".

Drawings, 8847476: Delete: "(Sheet 2)".

3.1.1: Delete: "(Sheet 2)".

AMSC N/A FSC: 1390

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:37Z
Check the source to verify that this is the current version before use.

PAGE 3

3.6: After "3", change "or" to "of".

3.7c: Change "chall" to "shall".

PAGE 4

4.3.1, Drawing 8847476: Delete: "(Sheet 2)".

PAGE 6

Table 1, Examination or Test block: Change: "(Dwg. 8847476 - sheet 2" to "(Dwg. 8847476)".

PAGE 7

4.4.2a: Change: "Tast" to "Test".

PAGE 10

4.4.2.3, Next Higher Assembly block: Delete: "(sheet 2)".

PAGE 11

4.4.2.4, Next Higher Assembly block: Delete: "(sheet 2)".

PAGE 12

4.4.2.5, Drawing Number block: Delete: "(sheet 2)".

* 4.4.2.5, Critical Defect: Add:

"2 Plug missing 100% 3.1.1 Visual"

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:37Z
Check the source to verify that this is the current version before use.

PAGE 19

4.4.3.2.1: Change: "Beginning with the first lot produced and continuing until three" to "Beginning with the first lot produced, or a lot following a rejected lot in 4.4.3.22, and continuing until three".

4.4.3.2.2: Add to end of paragraph: "If a lot is rejected under these criteria, continue testing lots in accordance with 4.4.3.2.1".

4.5.1, Line 3: Change: "surrent" to "current".

PAGE 20

4.5.2.3: Change: "Method 102.1" to "Method 102.1.3".

4.5.3, Line 2: Delete: "(Sheet 2)".

4.5.6, 4.5.6.1, 4.5.6.2, 4.5.6.3 and 4.5.6.4: Delete in their entirety and substitute:

"4.5.6 Determination of ignition charge composition. The chemical composition of the ignition charge shall be considered satisfactory if it is in accordance with the following:

Component	Percentage
Potassium Chlorate & Gum Solids	46.1 ± 2.1%
Lead Thiocyanate	35.5 ± 2%
Charcoal	20.0 ± 1.5%

4.5.6.1 Charcoal. Transfer approximately 2 grams of the igniter charge composition into a tared medium porosity crucible. Place in oven 70°C overnight to drive off water. Place crucible in desiccator to cool and then weigh to establish sample weight. Wash with ten 25 ml portions of 5 percent potassium nitrate solution followed by 50 ml of distilled water. Use a small glass rod to break up any lumps in the sample during the extraction process. Preserve the filtrate for the determination for lead thiocyanate. Place in oven maintained at 100 ± 5°C for 2 hours, cool in a desiccator and weigh. Calculate the percentage of charcoal as follows:

$$\text{Percent charcoal} = \frac{(A-B)\ (100)}{A}$$

A = Beginning sample weight
B = Empty crucible weight

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:37Z
Check the source to verify that this is the current version before use.

4.5.6.2 Lead thiocyanate. Exactly 35 ml of standardized Ø.1 normal (N) silver nitrate shall be added to the filtrate reserved from the charcoal determination. The flask and contents shall be swirled and 1ØØ ml of 3N nitric acid (nitric acid used should be water white and free of oxides of nitrogen) shall be added. The swirling of the mixture shall be continued for five minutes, 5 ml of a saturated solution of ferric ammonium sulfate be added and the solution titrated with standardized Ø.1N potassium thiocyanate solution to the first permanent pale rose coloration. The percentage of lead thiocyanate in the sample shall be calculated on a dry basis as follows:

$$\text{Percent lead thiocyanate} = \frac{16.17\ (AB-CD)}{E}$$

A = Volume of silver nitrate solution used
B = Normality of silver nitrate solution
C = Volume of potassium thiocyanate solution
D = Normality of potassium thiocyanate
E = Weight of sample

4.5.6.3 Potassium chlorate and gum solids. The percentage of potassium chlorate and gum solids is obtained by subtracting the total percentage of charcoal and lead thiocyanate from one hundred percent."

PAGE 22

5.1 Delete in its entirety and substitute:

"5.1 Packaging and marking. Primers shall be packaged and marked in accordance with dwg. 8847545".

5.1.1: Delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:37Z
Check the source to verify that this is the current version before use.

PAGE 23

5.1.2: Delete in its entirety.

6.1: Change: "M456A1 (HEAT) and M490 (TP)" to "M456A1 (HEAT-T), M456A2 (HEAT-T-MP) and M490 (TP-T)".

6.3: Change: "QAR-I" to "QAT-I".

6.5: Delete: "(Alternate)", 2 places.

Line 4: Change: "whic" to "which".

6.5.1, Last line: Change: "Method 102.1" to "Method 102.1.3".

6.5.3, Last line: Change: "e" to "be".

6.7: Change: "Rock Island, IL 61201" to "Rock Island, IL 61299".

Change: "QAR-E" to "QAT-A".

PAGE 25

Figure 1, Title: Change: "PAINT" to "LACQUER".

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

Project No. 1390-A611

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:37Z
Check the source to verify that this is the current version before use.