INCH-POUND

MIL-P-63462 (AR)
AMENDMENT 1
30 June 1990

MILITARY SPECIFICATION

PLASTIC MOLDING AND EXTRUSION MATERIAL, ETHYL CELLULOSE, FOR ROCKET GRAIN INHIBITING MATERIALS

This Amendment forms a part of Military Specification MIL-P-63462 (AR) dated 10 September 1979 and is approved for use within the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.1.2: Delete section 3.1.2 in its entirety and substitute the following:

"3.1.2 Plasticizer, substituted phenyl ether - with bis (p-1, 1'3, 3' tetramethyl butyl phenyl) ether as the principal constituent. Dow P-1099 plasticizer is the only Government-approved commercial form of this material currently authorized for use.

Specification:

(1)	Color	Light Amber
(2)	Absorption Coefficient	0.23 Max.
(3)	Viscosity at 25 degrees C	
	m^2/s	$4 - 8 \times 10^{-3}$
	(Centistokes)	(4000 - 8000)
(4)	% Volatiles (148.5 degrees C & 500 Pa (4mm Hg) pressure for one hour) maximum	9
(5)	Acid Number, maximum	0.5
(6)	Specific Gravity, 25/4 degrees C	0.92 - 0.95"

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:55Z
Check the source to verify that this is the current version before use.

PAGE 8

4.2.3.2, Table V: Delete Table V in its entirety and substitute the following:

"TABLE V Lot Acceptance Tests

Applicable to: Type	Class	Specific gravity	Tensile strength	Deflection temperature	Flow temperature
I	1 to 3	R1/	R	R	R
II	1	R1/	R	R	R

1/ Indicates test is required"

PAGE 9

4.3 Water absorption: Delete "4.3 Water absorption." and substitute "4.3.5 Water absorption."

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 9330 - A027)

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:55Z
Check the source to verify that this is the current version before use.