H-B-1490A/GEN
AMENDMENT-1
April 23, 1976

FEDERAL SPECIFICATION

BRUSHES, SCRUB

GENERAL SPECIFICATION FOR

This amendment, which forms part of Federal Specification H-B-1490A dated October 17, 1973 is approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

2.1 Under listing of Federal Specifications. Delete "PPP-B-1729" in its entirety and substitute "PPP-B-1880 - Brushes, Preparation of Delivery of."

PAGE 4

Table I Delete in its entirety and substitute:

" TABLE I. Requirements for polypropylene plastic

Property 23°C (73°F)	Units	Property values
Density		
Solid	gm/ml	Min 0.901 Max 0.907
Foam	gm/ml	Min 0.50 Max 0.60
Tensile yield strength	psi	Min 4900
Izod impact strength	ft lb/in.	Min 0.5
Rockwell hardness	R scale	Min 96 "

3.3.2.4, line 2. Delete "class 2".

FSC 7920

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

PAGE 5

3.3.4.1, 3.3.4.2 and 3.3.4.3 Delete and substitute:

"3.3.4.1 Corrosion resisting steel CRES. CRES staple wire shall be commercial quality 14 gage wire except type 302. When type 302 CRES is specified, the wire shall be either round or flat and conform to FED-STD-66. The round wire shall be 25 gage and the flat wire shall be not less than 0.000314 square inch in cross-sectional area.

3.3.4.2 Carbon steel. Carbon steel staple wire shall be commercial quality 18 or 19 gage wire, as specified in the specification sheet, and finished to resist corrosion."

PAGE 9

4.4 Delete "PPP-B-1729" and substitute "PPP-B-1880".

PAGE 10

5.1 Delete "PPP-B-1729" and substitute "PPP-B-1880".

Custodians:

Army - GL
Air Force - 84

Review activities:

Army - MD

User activities:

Army - ME
Navy - SA, MC, MS

Preparing activity:

Army - GL

Civil Agency Coordinating Activity:

GSA - FSS
HEW - NIH
JUS - FPI

Project No. 7920-0236

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.