


MILITARY SPECIFICATION SHEET
BATTERY, STORAGE BB-436/U

The complete requirements for procuring storage batteries described herein shall consist of this document and the issue in effect of Specification MIL-B-55118(EL).





DETAIL A



INCHES	MM
0.005	0.13
0.015	0.38
0.025	0.64
0.363	9.22
0.420	10.67
0.840	21.34
1.375	34.93
2.100	53.34
3.360	85.34
3.540	89.92
3.875	98.43

NOTE: See notes on next sheet.

FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T22:26Z
Check the source to verify that this is the current version before use.

NOTES (Applicable to foregoing drawing):

1. All dimensions shown on figure are in inches. Unless otherwise specified, tolerance is ± 0.015 in.

2. Metric equivalent shown on specification sheet are for general information only and are based upon 1 inch = 25.4 millimeters.

3. The standard bayonet type filler cap shall be Military Part No. MS75046-2.

4. An electrolyte level line should not be furnished on cell's container. The level of electrolyte shall be measurable by a glass tube. Level shall be adjusted with distilled water to 1/4 to 3/8 in. above the top of the plates after full charge.

5. The slotted hex head screw shall be Military Part No. MS75043-2.

6. The flat washer on each terminal shall be Military Part No. MS75045-2.

7. The Belleville spring on each terminal shall be Military Part No. MS75044-2.

8. The 3.540 height dimension measures from cell bottom to the surface of the cell post top that contacts the bottom of the intercell link, as shown in Detail A.

9. The intercell link shown in Detail A is not furnished as part of the cell when cells are procured.

10. The head-space for the cell is defined as the space between plate tops and bottom of the cell's cover for electrolyte and gas. This space shall be at least twenty (20)% of the overall cell container volume.

11. For design feature purposes, this specification sheet takes precedence over procurement documents referenced herein.

12. Referenced documents shall be of the issue in effect on date of invitation for bid unless a specific exception is taken to same.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T22:26Z
Check the source to verify that this is the current version before use.

BATTERY, STORAGE
BB-430/U
(CELL)

REQUIREMENTS:

Class: Vented nickel cadmium cell.

Dimensions and configuration: See figure and notes.

Weight (max): 0.6 pound.

Terminals: Two slotted hex hd screws, each complete with Belleville spring and flat washer per figure and notes.

Container: Polyamide, ABS or equal

Head space: 20% minimum per Note 10.

Filler cap: Std. per Note 3.

Vent release pressure: 6.0 ± 4.0 psig.

Nominal voltage: 1.2 volts.

Final voltage: 1.0 volt.

Rated capacity, (5 hr. rate): 5.5 amp. hrs.

Normal charge: 0.33 C_5 to 1.50 volts. then 0.17 C_5 for 2.0 hrs.

Normal discharge rate: 0.20 C_5.

0.17 C_5 rate: 0.90 amps.

0.20 C_5 rate: 1.10 amps.

0.23 C_5 rate: 1.27 amps.

0.33 C_5 rate: 1.83 amps.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T22:26Z
Check the source to verify that this is the current version before use.

BATTERY, STORAGE
BB-436/U
(CELL)

First Article Inspections	MIL-B-55118 Inspection Paragraph	Requirement
Visual and mechanical examination	4.7.1	Table IX
Initial full capacity Discharged (upright)	4.7.14.1	5.5 AH @ 0.20 C_5
Discharged (on side)	4.7.3.1	5.5 AH @ 0.20 C_5
Cycle life	4.7.15	1008 cycles to 3.8 AH
Potassium carbonate	4.7.7	Less than 60 grams per liter
Retention of charge I (14 days)	4.7.13.1	4.9 AH @ 0.20 C_5
Retention of charge II (4 days)	4.7.13.2	2.2 AH @ 0.20 C_5
Low temperature	4.7.14.5	3.3 AH @ 0.20 C_5
Temperature cycling	4.7.10	No physical defects per Table IX
Full capacity (upright)	4.7.14.3	5.5 AH @ 0.20 C_5
Mechanical shock	4.7.11	No physical defects per Table IX
Full capacity (upright)	4.7.14.3	5.5 AH @ 0.20 C_5
Vibration	4.7.12	No physical defects per Table IX
Full capacity (upright)	4.7.14.3	5.5 AH @ 0.20 C_5
Internal pressure	4.7.2	No leakage
Electrical leakage	4.7.9	More than 50 megohms

Quality conformance inspection:

It encompasses same inspections as first article except cycle life shall be 504 cycles to 4.7 AH.

Sampling: See latest issue of MIL-B-55118(EL).

Custodian:
Army-EL

Preparing Activity
Army-EL

Project No. 6140-A301

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T22:26Z
Check the source to verify that this is the current version before use.