MIL-C-10083C(MU)
17 November 1967
SUPERSEDING
MIL-C-10083C(MU)
31 January .1964

MILITARY SPECIFICATION

CLAMPS, WIRE, GAS MASK

1. SCOPE

1.1 This specification covers wire clamps.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

QQ-W-461 - Wire, Steel, Carbon, (Round, Bare and Coated).

STANDARDS

FEDERAL

FED-STD-151 - Metals, Test Methods.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

FSC 4240

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

DRAWINGS

US ARMY MUNITIONS COMMAND

Individual drawings required for the manufacture of the clamps will be specified at the time of procurement (see 6.2).

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification

(Application for copies of these ratings, rules and regulations should be addressed to the Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Materials. The wire used to manufacture the clamps shall conform to steel composition number 1010, finish 4, class 1 of QQ-W-461 , All other materials shall conform to the requirements on the applicable drawing.

3.2 Manufacture. The clamps shall be manufactured in accordance with the applicable drawing (see 6.2) and the requirements of this specification.

3.3 Tensile strength. The tensile strength of the brazed or welded joint shall be no less than 90 pounds when tested as specified in 4.2.4. When the joint is at the alternate location, the tensile strength of the clamp or joint shall be no less than 180 pounds,

3.4 Protrusion of braze or weld. The protrusion of the braze or weld due to mis-alignment of the ends of the wire or excess braze or weld metal, shall be no more than one-sixty-fourth of an inch beyond the normal surface of the wire.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

3.5 Workmanship. The clamp shall be free from any abraded, bent or burred metal sections or foreign matter (dirt, oily or viscous materiel).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.

4.1.1 Supplier's responsibi lity. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as othewise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirement.

4.1.2 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirement of 3.1 and Section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.2 Regular production

4.2.1 Lotting. A lot shall consist of the clamps produced by one manufacturer, at one plant, from the same materials, under essential 1 y the same manufacturing conditions.

4.2.2 Sampling.

4.2.2.1 For examination. Sampling shal I be conducted in accordance with MI L-STD-105.

4.2.2.2 For destructive tests. Sampling shall be conducted in accordance with MI L-STD-105, Level S-4.

4.2.3 Inspection.

4.2.3.1 For examination. Sample clamps shall be examined in accordance with the classification of defects and MIL-STD-105.

4.2.3.2 For destructive tests. Sample clamps shal I be tested in accordance with 4.2.4 and MIL-STD-105 using an AQL of 1.0 percent defective for acceptance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

4.2.3.3 Classification of defects.

(a) Clamp, wire, gas mask Drawing as specified in 6.2).

Categories	Defects
Critical:	None defined
Major	AQL 1.0 percent defective
101	Length of clamp (before bonding end) incorrect
102	Excessive flash at weld (see 3.4)
103	Workmanship (see 3.5)
Minor:	AQL 2.5 percent defective
201	Width of eyes incorrect
202	End incorrectly bent

4.2.4 Tensile strength test. The tensile strength of the brazed or welded ioint shall be determined in accordance with method 211.1 of FE D-STD-151 . If the braze or weld is made at the alternate location (see applicable drawing), the strength of the braze or weld shut I be tested by inserting a mandrel in the end loop of the clamp which includes the braze or weld then attaching the mandrel to one jaw of the testing machine. The other end of the clamp shall be held in the other jaw. The radius of the mandrel used shall be the same as the inside radius of the loop at the end of the clamp.

5. PREPARATION FOR DELIVERY

5.1 Packaging, level C. The wire clamps shall be packaged to provide adequate protection against corrosion, deterioration, and damage from the supply source to the first receiving activity for immediate use.

5.2 Packing, level C. The wire clamps, packaged as specified in 5.1, shall be pocked to insure carrier acceptance and safe delivery to the first domestic destination. Containers shall be in compl ionce with Uniform Freight Classification rules or the regulations of other common carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, unit and intermediate packages and shipping containers shal I be marked in accordance with MI L-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

5.4 Repair part When this item is procured for storage and issue as a repair part, preservation, packaging, packing and marking shall be as specified on the repair part packaging data sheet which is identified by the Federal stock number for the repair part.

6. NOTES

6.1 Intended use. The wire clamps are intended to be used with protective masks and hospital protector head pieces.

6.2 Ordering data. Procurement documents should specify:

(a) The title, number, and date of this specification.
(b) The title, number, and date of the applicable drawings.
(c) Whether the clamp shall be furnished straight or formed.

Custodian:

Army - MU

Preparing activity:

Army - MU (EA)

Project No. 4240-A347

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)* | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT
$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE C-0279

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Commanding Officer
Edgewood Arsenal
Attn: SMUEA-TSE-DD
Edgewood Arsenal, Maryland 21010

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:31Z
Check the source to verify that this is the current version before use.