MIL-C-63227A(AR)
AMENDMENT 1
17 JUNE 1982

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, PA101 FOR
PROJECTILE, 155MM, HE, GUIDED, CANNON
LAUNCHED, M712 AND TRAINING M823

This Amendment forms a part of Military Specification MIL-C-63227A, dated 9 September 1981, and is approved for use by the U.S. Army Armament and Research Development Command, and is available for use by all Departments and Agencies of the Department of Defense.

Page 1

Delete FSC: 1320 and substitute FSC: 8140.

Page 2

Change paragraph 3.4 to read as follows:

3.4 Environmental conditions. The container, when loaded with a tactical projectile or an inert or simulated projectile having the same external configuration, weight, and center of gravity as the tactical projectile, shall withstand exposure to the following environments. After completion of the leak test, the container cover should be opened without the use of a bar or any other device. There shall be no damage to the gasket. The projectile or an inert or simulated projectile is unloaded from the container for inspection and detection of any damage. There shall be no weld cracks allowable on the container except those resulting from fragility shock test which have been specified in Table 1. Then the projectile or the inert or simulated projectile is reinserted inside the container. There shall be no physical damage to the container contents (projectile itself or/and any one of the elements of container assembly) which would render them unserviceable as determined by the procuring agency. (NOTE: Minor dents, scratches, and

FSC 8140

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:26Z
Check the source to verify that this is the current version before use.

other forms of permanent deformations to the container that do not obstruct handling, assembly or ability of container to protect its contents through its continued use shall not constitute cause for rejection.

Page 4

Table I

Change paragraph g to read as follows:

(g) Leakage test 1/

Add Note 1/ as follows:

1/ Crack criteria for welding. After completion of environment and leakage test the following criteria shall apply:

	On each side of Bulkhead	On each TIG weld	Around Each cover stop
Maximum number of cracks	2	1	1
Shortest distance in inches between two nearest cracks allowable	4	--	--
Length of individual crack	0.5	0.25	0.25

Page 12

Category Minor 202 under paragraph 4.4.2.8 - change hole to holes.

Page 28

Change Major 103 under paragraph 4.4.2.24 to read as follows:

103 Location of cover stops (at 6 places)

Delete Major 102 under paragraph 4.4.2.24.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:26Z
Check the source to verify that this is the current version before use.

Page 30-A

Add Classification of Defects and Tests as shown in the attached sheet.

Page 31

Change paragraph no. from 5.4.1.4 to paragraph no. 4.5.1.4.

Change paragraph no from 5.4.1.5 to paragraph no. 4.5.1.5

Page 33

Delete Project Number: 1320 and substitute 8140.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 8140-A546)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63227A(AR) Amend 1

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.27	Container Assembly				9300440
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
	a) Transportation vibration test			3.4.2	4.5.1.2
	b) Loose cargo vibration test			3.4.3	4.5.1.3
	c) Transit drop test			3.4.4	4.5.1.4
	d) Leakage test	Note a	Note b	3.2	4.5.2
	e) Post test examinations			3.4	3.4
Minor	None Defined				

NOTES: a. For lot size 2 to 50 -2 samples;
for lot size 51 to 500 -3 samples; for lot size 501 to 3200 -5 samples.
b. There shall not be any failure in any of the samples.

DRDAR-QA Form 160 Jul 77

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:26Z
Check the source to verify that this is the current version before use.