MIL-P-60358 (AR)
AMENDMENT 1
25 August 1981

MILITARY SPECIFICATION

PROPELLANT M5

FOR USE IN CHARGE, PROPELLING XM178
FOR 90MM RECOILLESS RIFLE

This amendment forms a part of Military Specification MIL-P-60358 (MU), dated 24 February 1966.

PAGE 1

Add the following preamble underneath the title:

"This specification is approved by the U.S. Army Armament Research and Development Command, and is available for use by all Departments and Agencies of the Department of Defense."

PAGE 3

Add new paragraph 3.4 to read as follows:

"3.4 Total graphite. The total graphite content shall not exceed 0.55 percent when determined as specified in 4.3.4.1."

PAGE 5

4.3.1: Add the following sentence:

"Proof projectiles of the correct weight and rotating band configuration shall be used when testing is conducted utilizing the 90MM Rifle."

4.3.2:

Line 3: Delete "15 days" and substitute "24 hours".

Line 6: Delete "which have been accepted."

FSC: 1375

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:30Z
Check the source to verify that this is the current version before use.

PAGE 6

Add new paragraph 4.3.4 as follows:

"4.3.4 Graphite content determination.

4.3.4.1 Total graphite content. The total graphite content shall be determined in accordance with Method 308.1 of MIL-STD-286.

4.3.4.2 Graphite determination in propellant composition. The percent graphite in the propellant composition shall be calculated as follows:

Total graphite percent, minus percent graphite added (glazed), equals percent graphite in propellant composition."

Custodian:
Army-AR

Preparing Activity:
Army-AR

Project No.: 1375-A208

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:30Z
Check the source to verify that this is the current version before use.