INCH-POUND

MIL-C-43468G
17 July 1990
SUPERSEDING
MIL-C-43468F
26 July 1988

MILITARY SPECIFICATION

CLOTH, CAMOUFLAGE PATTERN; WIND RESISTANT POPLIN, COTTON

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers wind resistant cotton poplin cloth, dyed and over printed with organic colors to the prescribed camouflage pattern.

1.2 Classification. The cloth shall be of the following types as specified (see 6.2).

Type III - Woodland Camouflage Pattern
Type IV - Woodland Camouflage Pattern, Quarpel treated

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions and deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

A-A-50199 - Thread, Polyester Core: Cotton-, Rayon-, or Polyester-Covered
PPP-P-1134 - Packaging of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-1-1516 - Woodland Pattern - 48 inches
2-1-1516B - Woodland Pattern - 60 inches

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-EMSS, Natick, MA 01760-5014.)

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies are available from the Federal Trade Commission, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580-0001.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1424 - Tear Resistance of Woven Fabrics by Falling-Pendulum (Elmendorf) Apparatus

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

3.2 Standard sample. The dyed and printed finished cloth shall match the standard sample for shade and appearance, and shall unless otherwise indicated (see 3.4.3), be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.3.1 Cotton. The cotton shall be carded, combed, drawn, spun, and twisted into 2-ply yarn for the warp and 2-ply or single yarn for the filling. Testing shall be as specified in 4.4.3.

3.4 Color. The cloth shall be dyed to a ground shade either matching or approximating Light Green 354, and subsequently overprinted with the applicable camouflage pattern. When the ground shade is dyed to match Light Green 354, the three remaining colors shall be obtained by roller or screen printing using three rollers or screens as appropriate for the Dark Green 355, Brown 356, and Black 357 areas of the pattern. If the ground shade is dyed to

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:29Z
Check the source to verify that this is the currentversion before use.

approximate Light Green 354, four rollers or screens shall be used to match the required colors (see 6.8). Resin bonded pigments are not permitted (see 4.4.1.1).

3.4.1 Labile sulfur. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and printed finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.4.3. When no standard sample is available, the finished cloth shall show no more than a slight trace of labile sulfur when tested as specified in 4.4.3.

3.4.2 Visual matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200 K, with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200 K.

3.4.2.1 Instrumental matching. As an alternate to visual color matching the following instrumental color matching requirement may be used. The four colors in the Woodland pattern for the printed finished cloth listed below shall match the corresponding colors in the standard sample when measured on a spectrophotometer (see 6.5) in the visible wavelength range of the electromagnetic spectrum, 400 to 700 nanometers (nm). The following are the maximum numerical tolerances for acceptability (ΔA) for each of the four colors in the Woodland pattern, when tested as specified in 4.4.3:

Color		ΔA
Light Green	354	1.60
Dark Green	355	1.60
Brown	356	1.30
Black	357	1.00

3.4.3 Colorfastness. The printed finished cloth shall show fastness to laundering (after 3 cycles) and perspiration equal to or better than the standard sample or equal to or better than a rating of "good" for each of the pattern areas except Black 357 which shall have a rating equal to or better than "fair" for fastness to laundering (after 3 cycles) and "good" for perspiration when tested as specified in 4.4.3. The cloth shall show fastness to crocking equal to or better than than the standard sample or shall have an AATCC Chromatic Transference Scale rating not lower than 3.5 for all the pattern areas, except Black 357 which shall have an AATCC Chromatic Transference Scale rating not lower than 1.0, when tested as specified in 4.4.3.

3.4.3.1 Colorfastness to light. The printed finished cloth shall show a minimum fastness (after 40 standard fading hours) for each of the pattern areas equal to or better than the standard sample or equal to or better than a

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

minimum rating as follows: Light Green 354 "fair", Dark Green 355 "good", Brown 356 "good", and Black 357 "good". Testing shall be as specified in 4.4.3.

3.5 Pattern execution. The pattern on the finished cloth shall match the standard sample with respect to design, colors, and registration of the respective areas. Each pattern area shall show solid coverage; skitteriness exceeding that shown by the standard sample in any of the printed areas shall not be acceptable. The pattern repeat of the types III and IV printed finished cloth shall be 27.25 +1.25 -2.5 inches. When the standard sample is not referenced for pattern execution of types III and IV, a pattern drawing shall be provided and the pattern on the finished cloth shall match that of the drawing (see 6.2).

3.5.1 Printing screens or rollers, types III and IV. Screens or rollers shall conform to the required pattern Drawing 2-1-1516 for 48-inch width, and Drawing 2-1-1516B for 60-inch width fabric.

3.6 Spectral reflectance, types III and IV. The spectral reflectance of each color for the Woodland camouflage printed finished cloth, shall conform to the requirements specified in table I when tested as specified in 4.4.3.

TABLE I. Spectral reflectance requirements, types III and IV

	Values (percent)				
Wavelength nanometers	Light Green 354 Min	Light Green 354 Max	Dark Green 355 and Brown 356 Min	Dark Green 355 and Brown 356 Max	Black 357 Max
600	8	21	3	10	10
620	8	21	3	10	10
640	8	21	3	10	10
660	8	22	3	12	10
680	10	27	3	16	10
700	13	40	4	18	10
720	16	53	5	20	10
740	21	64	7	28	10
760	27	73	11	36	10
780	34	80	17	44	10
800	41	85	24	52	10
820	48	88	32	60	10
840	50	90	39	68	10
860	52	91	46	74	10

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:29Z
Check the source to verify that this is the currentversion before use.

3.7 Physical requirements. The camouflage printed finished cloth shall conform to the requirements in table II when tested as specified in 4.4.3.

TABLE II. Physical requirements

Type	Wt. per sq. yd. Min. Ounces	Wt. per sq. yd. Max. Ounces	Yarns per inch minimum Warp	Yarns per inch minimum Filling	Breaking strength minimum Warp Pounds	Breaking strength minimum Filling Pounds	Tearing strength minimum Warp Pounds	Tearing strength minimum Filling Pounds	Air permeability (cu. ft/min/sq. ft.) max.	Air permeability (cu. ft/min/sq. ft.) ave.
III	5.7	7.0	104	52	110	68	4.0	4.0		18.0
IV	5.7	7.2	104	52	100	60	4.0	4.0		15.0

3.7.1 Width. The width of the cloth shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of the selvage when fly shuttle looms or shuttleless with tuck-in selvage looms are used. For all other shuttleless looms the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe(s).

3.7.2 Weave. The weave shall have reinforcement ribs in both the warp and the filling directions forming a uniform pattern. The warp repeat shall be 2 ends weaving as one in a plain weave manner with 23 ends weaving plain weave. The filling repeat shall be 2 picks weaving as one in a plain manner with 12 picks weaving plain weave. Testing shall be as specified in 4.4.3.

3.8 Finish. The cloth shall be thoroughly prepared, including singeing and mercerizing. When type IV is specified, the cloth shall be given an approved quarpel-type (see 6.7) water repellent treatment and shall conform to the requirements in table III when tested as specified in 4.4.3. The use of materials other than approved water repellents is prohibited. The cured fabric shall be afterwashed to remove all unreacted reagents.

TABLE III. Water repellency (type IV)

	Dynamic absorption, percent, maximum (lot average)	Spray rating 1/
Initial	30	90, 90, 80
After 15 launderings	30	

1/ The results of the three individual determinations on the sample unit for spray rating shall be equal to or better than the ratings when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

3.8.1 Nonfibrous material. The cloth prepared for printing shall contain no more than 2.0 percent starch and protein content (including chloroform-soluble and water-soluble material) when tested as specified in 4.4.3.

3.8.2 pH. The pH of the water extract of the finished cloth shall be no lower than 5.0 nor higher than 8.5 when tested as specified in 4.4.3.

3.8.3 Resistance to organic liquid. The type IV finished cloth shall show no wetting by n-tetradecane either initially or after 15 launderings when tested as specified in 4.4.3.

3.8.4 Preshrinking. The cloth shall be preshrunk. The preshrinking process used shall not be identified by name or trademark on the cloth, ticket, or package.

3.9 Dimensional stability. The shrinkage or elongation both in the warp and in the filling of the finished cloth shall not be greater than 3 percent for the individual sample unit and not greater than 2.5 percent for the lot average when tested as specified in 4.4.3.

3.10 Seam efficiency. The finished cloth shall have a seam efficiency of not less than 80 percent when tested as specified in 4.4.3.

3.11 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put up on full width rolls as specified in 5.1.

3.12 Fiber identification. Each roll of the finished cloth shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.13 Workmanship. The dyed and printed finished cloth shall conform to the quality of product established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the applicable established maximum point values.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the currentversion before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth is this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Certificates of compliance. Where certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for appearance, color, and finish defects and shall be tested for the characteristics specified in table IV.

4.4 Quality conformance inspection.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents, unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.4.1.1 Component and material certification. A certificate of compliance shall be submitted as evidence that resin bonded pigments have not been used (see 3.4) for printing the camouflage pattern.

4.4.2 End item examination.

4.4.2.1 Yard-by-Yard examination. Each roll in the sample shall be examined on the printed side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects as defined in Section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.4.2.1.1 except that only those slubs and knots which exceed the limits shown on Sears Fabric Defect Scale (see 6.9), "D" or "3-1/2" as applicable for slubs and "C" for knots, shall be scored and coarse yarn shall only be scored as a defect when the coarse yarn is twice the

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

diameter of the yarn normally used in the fabric. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than four points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 30.0 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 45.0 points. If one roll exceeds 45.0 points per 100 square yards, a second sample of 20 rolls shall be examined for individual roll quality only. The lot shall be unacceptable if one or more rolls in the second sample exceeds 45.0 points per 100 square yards. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{Total yards inspected}} = \text{Points per 100 square yards}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

The following defects, when present, shall be scored four points for each yard in which they occur:

Objectionable odor
Baggy, ridgy, or wavy cloth
Width less than specified
Edge ravels when pulled outward
Slack or tight selvages 1/
Overall uncleanness
Pattern design not equal to standard sample
Incorrect color in any part of the pattern
Pattern repeat not equal to the standard sample
Pattern repeat less than 24.75 inches or more than 28.50 inches (types III and IV)
Skitteriness (mottled, uneven color) of pattern exceeds that shown by standard sample
Excessive feathering or spew (fuzziness at color boundries) of pattern as compared to the standard sample
Excessive grinning (off register, gap where ground shade shows through) of pattern as compared to the standard sample
Excessive haloing or trapping (overlapping of colors) of pattern as compared to the standard sample

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

1/ To determine the presence of unacceptable selvage conditions, the following procedure shall be observed: During the visual examination, the perch shall be stopped a minimum of three times for each roll in the sample, the tension removed, and the finished cloth examined for the selvage conditions. A waviness in the selvage causing significant waviness or ripples within the body of the cloth is an indication of slack or tight selvages.

4.4.2.2 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective with respect to length or if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4.2.3 Shade and appearance examination. During the yard-by-yard examination, each roll in the sample shall be examined for shade and appearance on the face side. Any roll that fails to meet the requirement for shade and appearance match with respect to all areas of the pattern shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Roll identification examination. During the yard-to-yard examination, each roll in the sample shall be examined for the defects listed below. The lot shall be unacceptable if two or more rolls in the sample contain one or more of the following defects:

The preshrinking process is identified by name or trademark on the cloth, ticket, or package.
Not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

4.4.3 End item testing. The cloth shall be tested for the characteristics listed in table IV. The methods of testing specified in FED-STD-191 whenever applicable and as listed in table IV shall be followed. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be 1/4 yard full width of cloth prepared for printing for determination of nonfibrous material, and 4 continuous yards full width of type III, and 5 continuous yards full width of type IV finished cloth for all other physical and chemical tests except dimensional stability (see 4.4.3.1). The lot shall be unacceptable if one or more sample units or the lot average for dimensional stability fail to meet any requirement specified. The maximum lot size shall be 150,000 linear yards. The sample size, except for dimensional stability, shall be in accordance with the following:

Lot size (yards)	Sample size (number of sample units)
800 or less	2
801 up to and including 22,000	3
22,001 up to and including 150,000	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

TABLE IV. End item tests

Characteristic	Requirement paragraph	Test method
Cotton identification	3.3.1	1200 1/
Combed cotton yarn	3.3.1	1/
Yarn ply	3.3.1	2/
Presence of labile sulfur	3.4.1	2020 1/
Instrumental match	3.4.2.1	4.5.1
Colorfastness to:		
Laundering (after 3 cycles)	3.4.3	5610 and 4.5.2
Perspiration	3.4.3	5680 and 4.5.2
Crocking	3.4.3	5651 and 4.5.3
Light	3.4.3.1	5660
Spectral reflectance, types III and IV	3.6	4.5.4
Weight	3.7	5041
Yarns per inch	3.7	5050
Breaking strength	3.7	5100
Tearing strength	3.7	ASTM D 1424
Air permeability	3.7	5450
Weave	3.7.2	Visual
Singeing	3.8	1/
Mercerization	3.8	Microscopic examination 1/
Water repellent treatment (type IV)	3.8	3/
Dynamic absorption (type IV):		
Initial	3.8	5500
After 15 launderings (cotton method)	3.8	5556 and 5500 4/
Spray rating (type IV) (initial)	3.8	5526
Nonfibrous material	3.8.1	2611
pH	3.8.2	2811
Resistance to organic liquid (type IV):		
Initial	3.8.3	4.5.5
After 15 launderings (cotton method)	3.8.3	4.5.5 and 5556 4/
Dimensional stability	3.9	4.4.3.1
Seam efficiency	3.10	5110 5/

1/ A certificate of compliance shall be submitted and will be acceptable for the stated requirement.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the currentversion before use.

2/ One determination shall be made from each sample unit and the result reported as "pass or fail".

3/ The contractor shall report the approved water repellent treatment used, and certify that no other material (except the specified buffer and acetic acid) has been added.

4/ Specimens shall be subjected to 15 complete cycles (wash and dry) prior to determination of dynamic absorption and resistance to organic liquid after laundering.

5/ The needle shall measure 0.040 ± 0.001 inch across the blade at the eye. The thread for all types shall be polyester-, cotton-, rayon-, or polyester-covered in accordance with A-A-50199, ticket no. 50, 2 or 3 ply for the needle and ticket no. 70, 2 or 3 ply for the looper.

4.4.3.1 Dimensional stability testing. In addition to the testing specified in 4.4.3, the cloth shall be tested for dimensional stability in accordance with Method 5550 of FED-STD-191. The sample unit shall be 2 continuous yards full width of the finished cloth. The lot size shall not exceed 150,000 yards. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (number of sample units)
10,000 or less	5
10,001 up to and including 35,000	8
35,001 up to and including 150,000	13

The lot average shall be determined by averaging the results of the sample units tested.

4.4.4 Packaging inspection. The inspection shall be in accordance with the quality assurance provisions of PPP-P-1134.

4.5 Methods of inspection.

4.5.1 Colorimetric measurements for the acceptability equation. Each of the four colors from the Woodland pattern cited in 3.4.2.1 for both the standard sample and the test specimen shall be measured as specified in 4.5.4, except the spectral reflectance factor data shall be obtained in the visible wavelength range 400 to 700 nm only, and at 20 nm (or less) intervals. When the spectrophotometer is operated in the polychromatic mode, a source simulating CIE illuminant source D_{65} should be used. Colorimetric data (see 6.10), computed from the resulting spectral reflectance data, are applied to the equation for acceptability (see 6.11).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

4.5.2 Colorfastness evaluation test. When testing for colorfastness to laundering and perspiration, identical portions of the pattern in the submitted specimen and standard sample shall be selected for the test. Each individual shade in the pattern shall be evaluated and reported separately in accordance with the provisions of the applicable test method.

4.5.3 Colorfastness to crocking evaluation test. When testing for colorfastness to crocking, the individual shades of the pattern shall be so selected that only the specific shade being evaluated is included in the test area of the submitted specimen as well as of the standard. Individual shades in the pattern shall be evaluated and reported separately.

4.5.4 Spectral reflectance measurements in the visible/near infrared. Spectral reflectance data shall be obtained from 600 to 860 nanometer (nm), at 20 nm intervals on a spectrophotometer (see 6.5) relative to a barium sulfate standard, the preferred white reference standard. Other white reference materials may be used, provided they are calibrated to absolute white; e.g. Halon, magnesium oxide, or vitrolite tiles (see 6.6). The spectral band width shall be less than 26 nm at 860 nm. Reflectance measurements may be made by either the monochromatic or polychromatic mode of operation. When the polychromatic mode is used, the spectrophotometer shall operate with the specimen diffusely illumiated with the full emission of a source that simulates either CIE Source A or CIE Source D65. The specimen shall be viewed at an angle no greater than 10° from normal, with the specular component included. Photometric accuracy of the spectrophotometer shall be within one percent and wavelength accuracy within 2 nm. The standard aperture size used in the color measurement device shall be 1.0 to 1.25 inches in diameter. Areas to be measured for each color shall be lightly marked with a circle, at least 1.50 inches in diameter, on the reverse side of the fabric, and at least 6 inches from either selvage. The specimen shall be measured as a single layer backed with layers of the same fabric and shade. Three backing layers shall be used for Light Green 354, Dark Green 355 and Brown 356 colors. Two backing layers shall be used for Black 357. When presented to the sample port, the specimen shall be oriented so that the reinforcement ribs in the fill direction are parallel with the horizontal plane. Measurements shall be taken on a minimum of three different areas for each color and the data averaged. When the measured spectral reflectance values for any color at four or more wavelengths do not meet the limits specified in 3.6, it shall be a test failure.

4.5.5 Resistance to organic liquid test. Place a small specimen of the cloth on a smooth horizontal surface, face up. Using a pipette or eye dropper, gently deposit one drop of n-tetradecane on the surface of the specimen. After 1 minute, examine the specimen under light at an angle. Absence of light reflectance at the fabric-drop interface shall be taken as evidence of wetting. Three specimens (or areas) taken at various locations across the sample shall be tested. Evidence of wetting on one or more specimens shall be considered a test failure.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and Commercial. The cloth, shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

5.2.1 Levels A, B and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required in the contract or purchase order, the shipments shall be marked in accordance with the requirements of PPP-P-1134.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cloth is intended for use in woodland camouflage clothing.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type of cloth required (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Pattern drawing if required (see 3.5).
f. Width required (see 3.7.1).
g. Minimum length if other than specified (see 3.11).
h. Levels of preservation and packing (see 5.1 and 5.2).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 20260-21T21:29Z
Check the source to verify that this is the current version before use.

6.4 Sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Spectrophotometers. Suitable spectrophotometers for measuring spectral reflectance in the visible/near infrared are the Diano Hardy, Diano Match Scan, Hunter D54P-IR, Hunter VIS/NIR spectrocolorimeter, and Macbeth 1500 with IR option.

6.6 White standard. Barium sulfate of suitable quality for use as a white reference standard is available from the Eastman Kodak Company. The same source has available magnesium reagent (ribbon) and Halon. Suitable tiles can be obtained from the National Bureau of Standards or the instrument manufacturers.

6.7 Quarpel water repellent. The "Quarpel-type" water repellent treatment consists of the co-application of an emulsified fluorocarbon and a fluorocarbon extender. Approval of such components and combinations is the responsibility of the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, and is based on extensive tests, including those for toxicity, which are not set forth in this document. Because of the time necessary to conduct a full evaluation (approximately 6 months), only those chemical treatments already approved and so listed in the invitation for bids or request for proposal shall be considered acceptable for the related procurement.

6.8 Pattern areas. The areas of the pattern have been found to be satisfactory when dyed or printed by the selection from among the following colorants:

Light Green 354

Vat Orange 2
Vat Green 1
Vat Yellow 2

Dark Green 355

Vat Brown 3
Vat Green 1
Vat Yellow 2

Brown 356

Vat Brown 57
Vat Brown 3
Vat Yellow 2
Vat Green 1

Black 357

Sulphur Black 6
Vat Blue 20
Vat Brown 3
Vat Black 11

Ground Shade

Vat Orange 2
Vat Green 1
Vat Yellow 2

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

6.8.1 Printing. Satisfactory printing on the shades Light Green 354, Dark Green 355, and Brown 356 has been accomplished by the use of vat dyes only. Shade Black 357 has been satisfactorily printed with a combination of vat and sulfur dyes and with a combination of vat dyes.

6.9 Fabric defect scales. Fabric Defect Replica Kits are available from Sears Roebuck and company, Department 817 (ATTN: BSC 23-29), Sears Tower, Chicago, IL 60684.

6.10 CIE Tristimulus, and CIE $L^*a^*b^*$ values. The spectral reflectance values obtained from 400 to 700 nm for a color are used to compute the tristimulus values X, Y and Z, using CIE illuminant D_{65} and the 1964 CIE 10° Supplementary Standard Colorimetric Observer. The tristimulus values are converted to CIE $L^*a^*b^*$ for use in the acceptability equation (see 6.11). Most spectrophotometers are interfaced to computers that automatically compute CIE tristimulus values, and CIE $L^*a^*b^*$ values. Derivation of tristimulus values can be found in, "Color in Business, Science and Industry", Third Edition, D.B. Judd and G. Wyszecki, John Wiley & Sons, New York, NY. Conversion of tristimulus values to CIE $L^*a^*b^*$ values is described in CIE publication, "Recommendations of Uniform Color Spaces, Color Difference Equations, and Psychometric Color Terms", Supplement No. 2 to CIE Publication No. 15, "Colorimetry", E-1.3.1 (1971), Bureau Central de la CIE, Paris (1978).

6.11 Acceptability Equation. Color acceptability is determined by the following equation:

$$\Delta A = \left[g_{11}(\Delta a^*)^2 + 2g_{12}\Delta a^*\Delta b^* + g_{22}(\Delta b^*)^2 + g_{33}(\Delta L^*)^2 \right]^{1/2}$$

where ΔA is an acceptability figure, scaled according to color (see 3.4.2.1); and the quantities Δa^*, Δb^*, ΔL^* are sample minus standard in CIELAB coordinates. The coefficients g_{11}, $2g_{12}$, g_{22} and g_{33} are given by the following equations, where a^*_O and b^*_O represent the CIELAB a^* and b^* values of the standard, c is the chroma tolerance, h is the hue tolerance, and v (for value) is the lightness tolerance:

$$\theta = \tan^{-1}(b^*_O/a^*_O)$$

$$g_{11} = (\cos^2\theta/c^2) + (\sin^2\theta/h^2)$$

$$2g_{11} = 2 \sin\theta \cos\theta \left[(1/c^2) - (1/h^2)\right]$$

$$g_{22} = (\sin^2\theta/c^2) + (\cos^2\theta/h^2)$$

$$g_{33} = 1/v^2$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.

Hue, Chroma and Lightness Tolerances for the Woodland Pattern, Cotton, Poplin

	Lightness (v)	Chroma (c)	Hue (h)
Light Green 354	2.26	1.32	1.16
Dark Green 355	2.20	1.30	1.11
Brown 356	1.88	1.28	0.74
Black 357	2.70	1.50	1.25

Specimens recording ΔA values less than those listed for each color in 3.4.2.1 represent acceptable matches for color to the standard; those specimens with higher ΔA values are unacceptable.

Natick TR-80/036, Investigations to Define Acceptability Tolerance Ranges in Various Regions of Color Space, E. Allen and B. Yuhas, U.S. Army Natick RD&E Center, Natick, MA 01760-5019, Sept. 1981, is available from Natick for those interested in writing a software program for the acceptability equation.

6.12 Subject term (key word) listing.

Clothing
Printed cloth
Water repellent treated

6.13 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

(Project 8305-0351)

Review activities:

Army - MD
Navy - MC
Air Force - 82
DLA - CT

User activity:

Air Force - 45

☆U.S. GOVERNMENT PRINTING OFFICE: 1990 - 704-034/30041

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-C-43468G	1990 July 17

3. DOCUMENT TITLE

CLOTH, CAMOUFLAGE PATTERN; WIND RESISTANT POPLIN, COTTON

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
U.S. Army Natick RD&E Center	(1) Commercial 508-651-5221	(2) AUTOVON 256-5221
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-ES Natick, MA 01760-5014	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 NATICK OP, APR 90 *Previous editions are obsolete.* 198/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.