INCH-POUND

MIL-C-43473F
INTERIM AMENDMENT 1 (GL)
3 December 1990

MILITARY SPECIFICATION

CLOTH, COATED, NYLON, POLYURETHANE COATED

This interim amendment is approved for use within the Department of the Army, with MIL-C-43473F, dated 29 March 1988.

PAGE 1

1.1, line 1: Delete "two" and substitute "three".

1.2: Add new type:

"Type IV - Desert camouflage (3 color) pattern and clear polyurethane coated".

PAGE 2

2.1.2: Add new drawing:

"2-1-2240 - Desert Camouflage (3 color) pattern - 48 inches and 60 inches".

PAGE 4

Add new paragraph:

"3.3.1.3 Type IV. The base cloth shall be 1.6 ounces per square yard ripstop nylon cloth conforming to type III of MIL-C-7020. The base cloth shall be dyed to ground shade approximating light Tan 492 and overprinted on one side only by using acid dyestuff combinations. The cloth shall be overprinted using the 3 color desert camouflage pattern obtained by roller or screen printing for the Light Tan 492, Light Brown 493 and Light Khaki 494 areas of the pattern.".

3.3.2, line 3: Delete "type III" and substitute "type III and type IV".

3.4, line 1: Delete "(both types)" and substitute "(all types)".

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T21:29Z
Check the source to verify that this is the current version before use.

Add new paragraph:

"3.4.1.2.1 Type IV. The finished coated cloth shall match shades Light Tan 492, Light Brown 493, and Light Khaki 494. Each area shall match the specific colors of the pattern in accordance with applicable reference standard."

3.4.1.3, line 3: Delete "type III" and substitute "types III and IV"

Lines 5 thru 9: Delete "in respect to ..... not less than 3.5." and substitute ". When a standard sample has not been established or designated, all colors except Black 357 shall show an AATCC Chromatic Transfer Scale rating for crocking not less than 3.5.".

3.4.1.5: Delete and substitute:

"3.4.1.5 Pattern execution (type III and type IV). The pattern shall reproduce the standard sample in respect to design, colors, and registration of the respective areas. The pattern repeat of the dyed, printed and finished cloth for type III shall be 27.25 inches (+ 1.25 inches, - 2.50 inches) in the warp direction. The pattern repeat of the dyed, printed, and finished cloth for type IV shall be 16.75 inches (+ 1.25 inches, - 1.75 inches) in the warp direction. The various areas of the pattern shall be properly registered in relation to each other and present definite sharp demarcations with minimum of feathering or spew. Each pattern area shall show solid coverage. Skitteriness exceeding that shown by the standard sample in any of the printed areas will not be acceptable. When a standard sample is not referenced for pattern execution or design, a pattern drawing shall be provided. The pattern on the type III finished cloth shall match that of Drawing 2-1-1516 or 2-1-1516B as applicable (see 6.2). The pattern on the type IV finished cloth shall match that of Drawing 2-1-2240."

Table III, in "Examine" column, after "Camouflage pattern": Delete "(type III only)" and substitute "(type III and type IV only)".

In "Defect" column: Delete "Warpwise pattern ..... 28.50 inches" and substitute "Warpwise pattern repeat less than 24.75 inches or more than 28.50 inches for type III and warpwise pattern repeat less than 15.00 inches or more than 18.00 inches for type IV".

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:29Z
Check the source to verify that this is the current version before use.

PAGE 14

Table V, in "Test method" column: Delete the second "4.5.6.1" and substitute "4.5.6.2".

PAGE 18

6.3, line 2: after "woodland camouflage pattern drawing": Add "and the desert camouflage (3 color) pattern drawing".

PAGE 19

6.8, line 1, after "Pattern areas": Add ", type III".

Preparing activity:

Army - GL

(Project 8305-A420)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:29Z
Check the source to verify that this is the current version before use.