INCH-POUND

MIL-D-70436 (AR)
AMENDMENT 3
29 September 1994
SUPERSEDING
AMENDMENT 2
2 December 1985

MILITARY SPECIFICATION

DETONATOR ASSEMBLY
FOR
FUZE, POINT DETONATING, M759

This amendment forms a part of MIL-D-70436 (AR), dated 15 July 1983, and is approved for use by the US Army Armament, Munitions, and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 5

Table 1, Sample size: Delete “200” and substitute "315”.

PAGE 7

4.4.2: Delete last sentence and add:

“Equipment necessary for performance of the inspections listed shall be in accordance with Paragraph 4.4.4 of MIL-A-48078."

PAGE 11

4.4.2.3. Note 2: Delete “0.7 grams” and substitute “2 grams".

PAGE 13

4.4.2.4, Minor 201: Delete "Charge weight" and substitute "Charge Height”.

Minor 202: Deleted.

Minor 203 becomes 202 and reads: “Insert cup lower charge height, below minimum (primer mix)".

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.

PAGE 14

4.4.2.5, Major 104: Delete "3.2" and substitute "3.4.1"

Add "Minor 201 Workmanship, .65, 3.6".

PAGE 16

4.5.3: Delete the second sentence.

PAGE 18

4.5.5.2.1: Delete $\frac{\text{"F-(A-B)"}}{W(1-.01M)D}$ and substitute $\frac{\text{"F(A-B)"}}{W(1-.01M)D}$

PAGE 19

4.5.5.2.1: Delete first and second sentences and substitute:

"Transfer a portion of this solution to an acorex glass spectrophotometric cell having a width of 1 centimeter (cm) and determine its absorbance at wave length of 410 millimicrons. Use as reference a similar cell containing saturated ammonium acetate solution of the same concentration as the sample in the final dilution. "

Delete "basic" and substitute "normal" in the formula.

Delete $\frac{\text{"F-(A-B)"}}{WD}$ and substitute $\frac{\text{"F(A-B)"}}{WD}$

PAGE 20

4.5.5.3: Delete "Antimony Formula and Definition" and substitute "Percentage of Tetracene $= \frac{(C-D)100}{W(1-.01M)}$

Where C + weight of crucible and residue after extraction with saturated ammonium acetate solution.

D = weight of crucible and residue after treating with hot water.

W = weight of sample.

M = moisture content of sample obtained from 4.5.3 in percent."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.

Add new paragraph 4.5.5.4 as follows:

"4.5.5.4 Antimony sulfide. The weight of the residue shall be calculated from the determination of tetracene to percentage antimony sulfide in the sample on a dry basis as follows:

$$\text{Percentage of Antimony sulfide} = \frac{*(D-E)}{W(1-.01M)}$$

Where D = weight of crucible and sample after treating with hot water.
E = weight of crucible.
W = weight of sample.
M = moisture content of sample obtained in 4.5.3 in percent."

4.5.6.1: Delete in its entirety and substitute the following:

* "4.5.6.1 Sensitivity and output. The sample detonators shall be randomly selected from each lot. The detonator shall be assembled with lead 11834335 in accordance with drawing 11834340 or 11834346 modified. If 11834346 is used the explosive pellet and explosive holder shall be omitted and the spitback standoff test holder (11834349) placed directly against the witness plate (11834351). A weight of 0.25 ounce plus or minus 0.01 ounce shall be dropped on the firing pin, to function the detonator, from a height of five (5) inches plus or minus 0.1 inch. The height of the drop shall be measured as the height from the top of the firing pin to the bottom of the weight. A detonator that fails to fire shall be classed defective. A detonator that fires but fails to initiate the lead sufficiently to produce a dent in the steel witness block of the required depth shall be classed defective if the detonation confinement sleeve expansion is less than 0.330 inch diameter. If the confinement sleeve extension is 0.330 inch diameter or greater the detonator shall not be classed defective, but the test lead classed defective and the result a no-test. The indentation depth shall be measured using a probe with a 0.017 inch plus or minus 0.002 inch spherical radius tip."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1305-AE90)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.