INCH-POUND

MIL-PRF-19500/707
6 February 2002

PERFORMANCE SPECIFICATION

SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED
(TOTAL DOSE AND SINGLE EVENT EFFECTS)
TRANSISTOR, N-CHANNEL, SILICON TYPES 2N7500U5, 2N7501U5, AND 2N7502U5
JANTXVR AND JANSR

This specification is approved for use by all Departments
and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for a N-Channel, enhancement-mode, MOSFET, radiation hardened (total dose and Single Event Effects (SEE)), power transistor. Two levels of product assurance are provided for each device type as specified in MIL-PRF-19500, with avalanche energy maximum rating (E_{AS}) and maximum avalanche current (I_{AS}).

1.2 Physical dimensions. See figure 1, (surface mount, LCC-18).

1.3 Maximum ratings. T_A = +25°C, unless otherwise specified.

Type	P_T (1) T_C = +25°C	P_T T_A = +25°C	V_{DS}	V_{DG}	V_{GS}	I_{D1} (2) T_C =+25°C	I_{D2} T_C = +100°C	I_S	I_{DM} (3)	T_J and T_{STG}	V_{ISO} 70,000 ft. altitude
	W	W	V dc	V dc	V dc	A dc	A dc	A dc	A (pk)	°C	V dc
2N7500U5	25	1.25	130	130	±20	9.0	6.0	9.0	36.0	-55	N/A
2N7501U5	25	1.25	200	200	±20	6.3	4.0	6.3	25.2	to	N/A
2N7502U5	25	1.25	250	250	±20	5.4	3.4	5.4	21.6	+150	N/A

(1) Derate linearly 0.2 W/°C for T_C > +25°C; $P_T = (T_{JMAX} - T_C)/R_{\theta JC}$.
(2) $I_D = ((T_{JMAX} - T_C)/((R_{\theta JC})X (r_{DS(ON)} \text{ at } T_{JMAX})))^{1/2}$.
(3) I_{DM} = 4 X I_{D1}; I_{D1} as calculated by note (2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Supply Center Columbus, ATTN: DSCC-VAC, P. O. Box 3990, Columbus, OH 43216-5000, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 I_D = 1.0mA Dc	$V_{GS(TH)1}$ $V_{DS} \geq V_{GS}$ I_D = 1.0 mA dc		Max I_{DSS1} V_{GS} = 0 V_{DS} = 80 percent of rated V_{DS}	Max $r_{DS(on)}$ (1) V_{GS} = 12V, I_D = I_{D2}		$R_{\theta JC}$ Max	E_{AS}
					T_J = +25°C	T_J = +150°C		
	V dc	V dc		µA dc	Ω	Ω	°C/W	mJ
		Min	Max					
2N7500U5	130	2.5	4.5	10	0.130	0.260	5.0	56
2N7501U5	200	2.5	4.5	10	0.270	0.621	5.0	40
2N7502U5	250	2.5	4.5	10	0.450	0.990	5.0	30

(1) Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD

DEPARTMENT OF DEFENSE

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Document Automation and Production Services (DAPS), Building 4D (DPM-DODSSP), 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 1. Physical dimensions for LCC-18.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.345	.360	8.77	9.14
BW	.280	.295	7.12	7.49
CH	.095	.115	2.42	2.92
LL_1	.040	.055	1.02	1.39
LL_2	.055	.065	1.40	1.65
LS	.059 BSC		1.27 BSC	
LS_1	.025 BSC		.635 BSC	
LS_2	.008 BSC		.203 BSC	
LW	.020	.030	0.51	0.76
Q_1	.105 REF		2.67 REF	
Q_2	.120 REF		3.05 REF	
Q_3	.045	.055	1.15	1.39
TL	.070	.080	1.78	2.03
TW	.120	.130	3.05	3.30

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. Dimensions and tolerancing shall be in accordance with ANSI Y14.5M-1982.

FIGURE 1. Physical dimensions for LCC-18 - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The requirements for acquiring the product described herein shall consist of this document and MIL-PRF-19500.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1 (LCC-18) herein.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.5 Electrostatic discharge protection. The devices covered by this specification require electrostatic discharge protection (see 6.2).

3.5.1 Handling. Metal oxide semiconductor (MOS) devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended (see 3.5).

a. Devices should be handled on benches with conductive handling devices.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source, $R \leq$ or 100 kΩ, whenever bias voltage is applied drain to source.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3 and 1.4 herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups as specified in group A, table I herein.

3.8 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking of the country of origin may be omitted from the body of the transistor but shall be retained on the initial container.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I and II).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein. Alternate flow is allowed for qualification inspection in accordance with figure 4 of MIL-PRF-19500.

4.2.1 Group E inspection. Group E inspection shall be conducted in accordance with MIL-PRF-19500, and table III herein.

4.2.1.1 SEE. Design capability shall be tested on the initial qualification and thereafter whenever a major die design or process change is introduced. See the design safe operation area figures herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS, JANTX, and JANTXV). Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS	JANTX and JANTXV
(1)	Method 3470 of MIL-STD-750, E_{AS} test (see 4.5.4)	Method 3470 of MIL-STD-750, E_{AS} test (see 4.5.4)
(1)	Method 3161 of MIL-STD-750, thermal impedance (see 4.5.3)	Method 3161 of MIL-STD-750, thermal impedance (see 4.5.3)
(1)	Gate stress test (see 4.5.5)	Gate stress test (see 4.5.5)
(2) 9	Subgroup 2 of table I herein I_{DSS1} , I_{GSS} as a minimum	Not applicable
10	Method 1042 of MIL-STD-750, test condition B	Method 1042 of MIL-STD-750, test condition B
11	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(ON)}$, $V_{GS(TH)}$ Subgroup 2 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±10 µA dc or ±100 percent of initial value, whichever is greater.	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(ON)}$, $V_{GS(TH)}$ Subgroup 2 of table I herein.
12	Method 1042 of MIL-STD-750, test condition A	Method 1042 of MIL-STD-750, test condition A
13	Subgroups 2 and 3 of table I herein ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±10 µA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.	Subgroups 2 and 3 of table I herein ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±10 µA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.

(1) Shall be performed anytime before screen 10.
(2) Shall be performed after E_{AS} test, thermal impedance test, and gate stress test.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500. Alternate flow is allowed for conformance inspection in accordance with figure 4 of MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table V of MIL-PRF-19500 and table I herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) and table VIb (JANTX and JANTXV) of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with table I, group A, subgroup 2 herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1051	Test condition G, 100 cycles.
B3	2077	Scanning electron microscope (SEM).
B4	1042	Intermittent operation life, condition D, 2,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. t_{on} = 30 seconds minimum.
B5	1042	Accelerated steady-state gate bias, condition B, V_{GS} = rated; T_A = +175°C, t = 24 hours minimum; or T_A = +150°C, t = 48 hours minimum.
B5	1042	Accelerated steady-state reverse bias, condition A, V_{DS} = rated; T_A = +175°C, t = 120 hours minimum; or T_A = +150°C, t = 240 hours minimum.
B5	2037	Bond strength (Al-Au die interconnects only), test condition A.
B6	3161	Thermal resistance, see 4.5.2.

4.4.2.2 Group B inspection, table VIb (JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	1051	Test condition G, 25 cycles.
B3	1042	Intermittent operation life, condition D, 2,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. t_{on} = 30 seconds minimum.
B5 and B6		Not applicable.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, group A, subgroup 2 herein.

Subgroup	Method	Condition
C2	2036	Terminal strength is not applicable.
C6	1042	Intermittent operation life, condition D, 2,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. t_{on} = 30 seconds minimum.

4.4.4 Group D inspection. Group D inspection shall be conducted in accordance with table VIII of MIL-PRF-19500 and table II herein.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with MIL-PRF-19500, and table III herein.

4.4.5.1 SEE. Design capability shall be tested on the initial qualification and thereafter whenever a major die design or process change is introduced. See the design safe operating area figures herein. End-point measurements shall be in accordance with table III.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Thermal resistance. Thermal resistance measurements shall be performed in accordance with method 3161 of MIL-STD-750. The maximum limit of $R_{\theta JC}$ = 5.00 °C/W. The following parameters shall apply:

a. Drain heating current (I_H)..... 1.39 A.

b. Heating time (t_H)..... Steady-state (see method 3161 of MIL-STD-750).

c. Drain-source heating voltage (V_H)..... 12 V.

d. Measuring current(I_M)..... 10 mA.

e. Measurement time delay (t_{MD})..... 30 to 60 µs.

f. Sample window time (t_{SW})..... 10 µs maximum.

4.5.3 Thermal impedance ($Z_{\theta JC}$ measurement). The $Z_{\theta JC}$ measurement (or equivalent ΔV_{SD} measurement) shall be performed in accordance with method 3161 of MIL-STD-750. The maximum limit (not to exceed figure 2, thermal impedance curves and the group A, subgroup 2 limits) for $Z_{\theta JC}$ in screening (table IV of MIL-PRF-19500) shall be derived by each vendor by means of statistical process control. When the process has exhibited control and capability, the capability data shall be used to establish the fixed limit. In addition to screening, once a fixed limit has been established, monitor all future sealing lots using a random five piece sample from each lot, to be plotted on the applicable X and R chart. If a lot exhibits an out of control condition, the entire lot shall be removed from the line and held for engineering evaluation and disposition. This procedure may be used in lieu of an in line process monitor.

a. Drain heating current (I_H)..... 1.39 A.

b. Heating time (t_H)..... 10 ms.

c. Drain-source heating voltage (V_H)..... 12 V.

d. Measuring current (I_M)..... 10 mA.

e. Measurement time delay (t_{MD})..... 30 - 60 µs.

f. Sample window time (tSW)..... 10 µs maximum.

4.5.4 Single pulse avalanche energy (E_{AS}).

a. Peak current, $I_{AS} = I_{D1}$

b. Inductance, $L = (2*E_{AS}/(I_{D1})^2)*((V_{BR}-V_{DD})/V_{BR})$ mH minimum.

c. Gate to source resistor, R_{GS}: 25 Ω ≤ R_{GS} ≤ 200 Ω.

d. Supply voltage, V_{DD} = 25 V dc, except V_{DD} = 50 V dc for 2N7502U5.

e. Initial case temperature, T_C = +25° C, -5° C, +10° C.

f. Gate voltage, V_{GS} = 12 V dc.

g. Number of pulses to be applied: 1 pulse minimum.

4.5.5 Gate stress test.

a. V_{GS} = 24 V, minimum.

b. t = 250 µS, minimum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Condition		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance 2/	3161	See 4.5.3	$Z_{\theta JC}$	2.0		°C/W
Breakdown voltage drain to source	3407	V_{GS} = 0V, I_D = 1 mA dc, bias condition C	$V_{(BR)DSS}$			
2N7500U5				130		V dc
2N7501U5				200		V dc
2N7502U5				250		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)1}$	2.5	4.5	V dc
Gate current	3411	V_{GS} = ±20V dc, bias condition C, V_{DS} = 0V	I_{GSS1}		±100	nA dc
Drain current	3413	V_{GS} = 0V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS},	I_{DSS1}		10	µA dc
Static drain to source "ON" state resistance	3421	V_{GS} = 12V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(ON)1}$			
2N7500U5					0.130	Ω
2N7501U5					0.270	Ω
2N7502U5					0.450	Ω
Forward voltage	4011	V_{GS} = 0V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D1}$	V_{SD}		1.5	V dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Condition		Min	Max	
Subgroup 3						
High temperature operation		$T_C = T_J = +125°C$				
Gate current	3411	$V_{GS} = \pm 20V$ dc, bias condition C, $V_{DS} = 0V$	I_{GSS2}		±200	nA dc
Drain current	3413	$V_{GS} = 0V$ dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS2}		25	µA dc
Static drain to source "ON" state resistance	3421	V_{GS} = 12V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(ON)3}$			
2N7500U5					0.247	Ω
2N7501U5					0.540	Ω
2N7502U5					0.945	Ω
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)2}$	1.5		V dc
Low temperature operation		$T_C = T_J = -55°C$				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS(TH)3}$, I_D = 1 mA dc	$V_{GS(TH)3}$		5.5	V dc
Subgroup 4						
Forward transconductance	3475	$I_D = I_{D2}$, V_{DD} = 15 V dc (see 4.5.1)	g_{FS}			
2N7500U5				5.0		S
2N7501U5				4.2		S
2N7502U5				4.0		S
Switching time test	3472	$I_D = I_{D2}$, V_{GS} = 12 V dc, R_G = 7.5 Ω, V_{DD} = 50 percent of rated V_{DS}				
Turn-on delay time			$t_{D(on)}$		25	ns
Rise time			t_r		100	ns
Turn-off delay time			$t_{D(off)}$		35	ns
Fall time			t_f		40	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Condition		Min	Max	
Subgroup 5						
Safe operating area test (high voltage)	3474	See figure 3 t_p = 10 ms min. V_{DS} = 80 percent of max. rated V_{DS}				
Electrical measurements		See table I, group A, subgroup 2				
Subgroup 6						
Not applicable						
Subgroup 7						
Gate charge	3471	Condition B, $I_D = I_{D1}$, V_{GS} = 12 V dc V_{DD} = 50 percent of rated V_{DS}				
On-state gate charge			$Q_{G(ON)}$			
2N7500U5					48	nC
2N7501U5					47	nC
2N7502U5					28	nC
Gate to source charge			Q_{GS}			
2N7500U5					16	nC
2N7501U5					12	nC
2N7502U5					7.4	nC
Gate to drain charge			Q_{GD}			
2N7500U5					18	nC
2N7501U5					16	nC
2N7502U5					12	nC
Reverse recovery time	3473	di/dt = -100 A/µs, $V_{DD} \leq$ 50 V $I_D = I_{D1}$	t_{rr}			
2N7500U5					250	ns
2N7501U5					274	ns
2N7502U5					287	ns

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurements only:
Group B, subgroups 2 and 3 (JANTX/JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroup 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Pre-irradiation limits		Post-irradiation limits		Unit
				R		R		
	Method	Conditions		Min	Max	Min	Max	
Subgroup 1								
Not applicable								
Subgroup 2		T_C = + 25°C						
Steady-state total dose irradiation (V_{GS} bias) 4/	1019	V_{GS} = 12 V; V_{DS} = 0 V						
Steady-state total dose irradiation (V_{DS} bias) 4/	1019	V_{GS} = 0 V; V_{DS} = 80 percent of rated V_{DS}(preirradiation)						
End-point electricals								
Breakdown voltage, drain to source	3407	V_{GS} = 0 V; I_D = 1 mA; bias condition C	$V_{(BR)DSS}$					
2N7500U5				130		130		V dc
2N7501U5				200		200		V dc
2N7502U5				250		250		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$ I_D = 1 mA	$V_{GS(th)1}$	2.5	4.5	2.0	4.5	V dc
Gate current	3411	V_{GS} = +20 V; V_{DS} = 0 V bias condition C	I_{GSSF1}		100		100	nA dc
Gate current	3411	V_{GS} = -20 V; V_{DS} = 0 V bias condition C	I_{GSSR1}		-100		-100	nA dc
Drain current	3413	V_{GS} = 0 V V_{DS} = 80 percent of rated V_{DS} (preirradiation) bias condition C	I_{DSS}		10		10	µA dc
Static drain to source on-state voltage	3405	V_{GS} = 12 V; I_D = I_{D2} condition A, pulsed (see 4.5.1)	$V_{DS(on)}$					
2N7500U5					0.780		0.780	V dc
2N7501U5					1.080		1.080	V dc
2N7502U5					1.530		1.530	V dc
Forward voltage source drain diode	4011	V_{GS} = 0 V; I_D = I_{D1} bias condition C	V_{SD}		1.5		1.5	V dc

1/ For sampling plan see MIL-PRF-19500
2/ Group D qualification may be performed prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other performance specification utilizing the same die design.
3/ At the manufacturer's option, group D samples need not be subjected to the screening tests, and may be assembled in it's qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.
4/ Separate samples shall be pulled for each bias.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) - for qualification only.

Inspection	MIL-STD-750		Qualification and large lot quality conformance inspection
	Method	Conditions	
Subgroup 1			12 devices c = 0
Temperature cycling	1051	Test condition G, 500 cycles	
Hermetic seal	1071		
Fine leak Gross leak			
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 2 1/			12 devices c = 0
Steady-state gate bias	1042	Test condition B; 1,000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Steady-state reverse bias	1042	Test condition A; 1,000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 3			
Not applicable			
Subgroup 4			12 devices c = 0
Thermal resistance	3161	$R_{\theta JC}$ = 5.0°C/W maximum. See 4.5.2	
Subgroup 5			
Not applicable			
Subgroup 6			3 devices c = 0
ESD	1020		
Electrical measurements		See table I, group A, subgroup 2	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) - for qualification only - Continued.

Inspection	MIL-STD-750		Qualification and large lot quality conformance inspection
	Method	Conditions	
Subgroup 7			3 devices
SEE 2/ 3/ 4/	1080	See figure 4	
Electrical measurements 5/		I_{GSS1} and I_{DSS1} in accordance with table I, group A, subgroup 2	
SEE Irradiation		Fluence = 3E5 ± 20 percent ions/cm^2 Flux = 2E3 to 2E4 ions/cm^2/sec, temperature = 25 ± 5 °C	
		LET = 37 MeV-cm^2/mg, Range = 39 microns, Energy = 305 MeV	
2N7500U5		Insitu bias conditions: V_{DS} = 130V and V_{GS} = -20V	
2N7501U5		Insitu bias conditions: V_{DS} = 200V and V_{GS} = -20V	
2N7502U5		Insitu bias conditions: V_{DS} = 250V and V_{GS} = -20V	
		LET = 60 MeV-cm^2/mg, Range = 32 microns, Energy = 340 MeV	
2N7500U5		Insitu bias conditions: V_{DS} = 130V and V_{GS} = -10V V_{DS} = 100V and V_{GS} = -15V V_{DS} = 50V and V_{GS} = -20V	
2N7501U5		Insitu bias conditions: V_{DS} = 200V and V_{GS} = -10V V_{DS} = 185V and V_{GS} = -15V V_{DS} = 120V and V_{GS} = -20V	
2N7502U5		Insitu bias conditions: V_{DS} = 250V and V_{GS} = -15V V_{DS} = 240V and V_{GS} = -20V	
		LET = 82 MeV-cm^2/mg, Range = 28 microns, Energy = 350 MeV	
2N7500U5		Insitu bias conditions: V_{DS} = 130V and V_{GS} = 0V V_{DS} = 120V and V_{GS} = -5V V_{DS} = 30V and V_{GS} = - 10V	
2N7501U5		Insitu bias conditions: V_{DS} = 200V and V_{GS} = -5V V_{DS} = 150V and V_{GS} = -10V V_{DS} = 50V and V_{GS} = -15V V_{DS} = 25V and V_{GS} = -20V	
2N7502U5		Insitu bias conditions: V_{DS} = 250V and V_{GS} = -5V V_{DS} = 225V and V_{GS} = -10V V_{DS} = 175V and V_{GS} = -15V V_{DS} = 50V and V_{GS} = -20V	
Electrical measurements 5/		I_{GSS1} and I_{DSS1} in accordance with table I, group A, subgroup 2	

1/ A separate sample for each test shall be pulled.
2/ Group E qualification of SEE testing may be performed prior to lot formation. Qualification may be extended to other performance specifications utilizing the same structurally identical die design.
3/ Device qualification to a higher level LET is sufficient to qualify all lower level LET's.
4/ The sampling plan applies to each bias condition.
5/ Examine I_{GSS1} and I_{DSS1} before and following SEE irradiation to determine acceptability for each bias condition. Other test conditions in accordance with table I, group A, subgroup 2, may be performed at the manufacturer's option.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 2. Thermal impedance curve.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 3. Safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 3. Safe operating area graph - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 3. Safe operating area graph - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.




FIGURE 4. SEE safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.

b. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.2.1).

c. Packaging requirements (see 5.1).

d. Lead finish (see 3.4.1).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers' List (QML) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center, Columbus, ATTN: DSCC/VQE, P.O. Box 3990, Columbus, OH 43216-5000.

6.4 Cross-reference list. The following table shows the generic P/N and its associated military P/N (without JAN and RHA prefix).

Generic P/N	Military P/N
IRHE57133SE	2N7500U5
IRHE57230SE	2N7501U5
IRHE57234SE	2N7502U5

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA - CC

Review Activities:
Army – AV, MI
Air Force - 71, 99

Preparing activity:
DLA - CC

(Project 5961-2551)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-PRF-19500/707	2. DOCUMENT DATE 6 February 2002

3. **DOCUMENT TITLE**
SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED (TOTAL DOSE AND SINGLE EVENT EFFECTS) TRANSISTOR, N-CHANNEL, SILICON TYPES 2N7500U5, 2N7501U5, AND 2N7502U5 JANTXVR AND JANSR.

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) COMMERCIAL DSN FAX EMAIL	7. DATE SUBMITTED

8. PREPARING ACTIVITY

a. Point of Contact Alan Barone	b. TELEPHONE Commercial 614-692-0510 DSN 850-0510 FAX 614-692-6939 EMAIL alan.barone@dscc.dla.mil
c. ADDRESS Defense Supply Center Columbus ATTN: DSCC-VAC P.O. Box 3990 Columbus, OH 43216-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman, Suite 2533 Fort Belvoir, VA 22060-6221 Telephone (703) 767-6888 DSN 427-6888

DD Form 1426, Feb 1999 (EG) Previous editions are obsolete WHS/DIOR, Feb 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:03Z
Check the source to verify that this is the current version before use.