[METRIC]

A-A-1019C
October 8, 1993
SUPERSEDING
A-A-1019B
September 16, 1991

COMMERCIAL ITEM DESCRIPTION

STAPLES, PAPER FASTENING, STANDARD AND LIGHT DUTY

The General Services Administration has authorized the use of this Commercial Item Description.

1. SCOPE: This description covers preformed standard and light duty staples which are used for clinching paper, and wire spool staplers. The staples shall be of the following Classes, as specified:

Class A - Standard duty preformed staples
Class B - Wire spool for forming staples
Class C - Light duty preformed staples

2. SALIENT CHARACTERISTICS:

A. Dimensions.

Class A. Standard duty staples shall have 12.67-12.83 mm (0.499-0.505)" crowns and 6.25-6.65 mm (0.246-0.262)" legs. The top face of the staple shall be 0.47-0.52 mm (0.0185-0.0205)" inches wide. The wire thickness shall be 0.43-0.48 mm (0.0170-0.0190)" thick. Each staple strip shall have a maximum length of 11 cm (4.310").

Class B. Wire spool shall contain a sufficient amount of wire for making 5,000 ± 100 staples with a crown width of 7.87-7.98 mm (0.310-0.314)". The diameter of the wire shall be 0.394-0.445 mm (0.015-0.017)". The diameter of sides of spool shall be 44±0.4 mm (1.75±0.16)". The width of spool shall be 19±0.8 mm (0.75±0.031)". Diameter of hole in spool shall be 19±0.8 mm (0.75±0.031)".

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document, should be sent to: General Services Administration, Federal Supply Service, 26 Federal Plaza, New York N.Y. 10278 ATTN: Engineering Branch (2FYEE).

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:11Z
Check the source to verify that this is the current version before use.

Class C. Light duty staples shall have a 11.1-11.2 mm (0.436-0.440)"crowns, and 6.4-6.8 mm (0.250-0.266)" legs. The top face shall be 0.53-0.58 mm (0.021-0.023)". The wire thickness shall be 0.394-0.445 mm (0.015-0.017)".

B. Construction.

Class A & C. The temper (carbon content) of the wire shall be such as to permit penetration and firm seated clinching without buckling or fracturing the crown or legs. Staples shall not blemish paper and shall be made of either a corrosion resistant metal or have a finish that resists corrosion. Each staple leg shall be perpendicular to the staple crown in accordance with normal commercial practice. Staples shall be cemented together to form a strip. Cement shall be applied smoothly and shall adhere to each staple sufficiently to insure its exit from the vertical chute without accumulation therein. Unless otherwise specified, strips shall contain no less than 200 staples, and shall be supplied at no less than 5,000 to a box. The staple legs shall have blunt or chisel-point ends and shall be able to form a standard or pin clinch as specified below:

Standard Clinch. The standard clinch is represented by a staple driven home through two sheets of paper. Each leg shall be folded under so the tips of each leg face inward towards each other. Further, each tip shall be in a downward slope back toward reentering the paper.

Pin Clinch. The pin clinch is represented by a staple driven home through two sheets of paper. Each leg shall be folded under so the tips of each leg face outward away from each other. Further, each tip shall be in a downward slope back toward reentering the paper.

Class B. Wire shall be wound on spool so as to unwind easily without tangling or becoming taut on spool as wire is pulled forward by the stapler. The wire shall be such as to permit penetration and forming of a standard clinch, as specified above. Staple wire shall be made of brass in accordance with normal commercial practice.

Note: If requested by the Government, contractor shall provide certificate of compliance for corrosion resistance.

C. Testing.

(1). Class A. No evidence of staple fracture, malformation, or malfunction shall be observed, when tested as specified in (3.C.1). Tensile strength of the staple wire shall be not less than 930 MPa (135,000 psi), when tested as specified in (3.C.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

(2). Class B. No evidence of staple fracture, malformation, or malfunction shall be observed, when tested as specified in (3.C.2).

(3). Class C. No evidence of staple fracture, malformation, or malfunction shall be observed, when tested as specified in (3.C.3).

D. Workmanship. Except for the staple points (leg ends), the staple strips shall be free of sharp edges. The staple strips shall also be free of any defects which impair serviceability, including, but not limited to, superfluous cement coating or burrs, or anything which might constitute a personal hazard to the user. The staples shall not exhibit evidence of deformity or cracking.

3. QUALITY ASSURANCE:

A. Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this Commercial Item Description, where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

B. Sampling. Samples shall be selected for inspection in accordance with MIL-STD-105, using the plans described in Table I. A lot shall consist of a number of sample units manufactured by the same process from the same components at the same time. Random samples shall be drawn from each lot for the end item inspection. Unless otherwise specified, every lot shall be tested.

TABLE I

Inspection Type	AQL (%) Defective	Inspection Level	Sample Unit	Requirement Paragraph/s
Dimensions, Construction, Workmanship	4.0	S-3	One staple strip or wire spool	2A,B,D
Testing	4.0	S-1	One staple strip or wire spool	2C
Packaging Packing & Marking	4.0	S-2	One shipping container	5

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:11Z
Check the source to verify that this is the current version before use.

C. Testing.

(1). Performance test (Class A). Using bond paper with a basis weight of 75g/m^2 (20-lb_m, 17" x 22" - 500), this test shall demonstrate the capability of the staples to consistently clinch 20 sheets. The stapling operation shall be done 100 times to form a standard clinch and 10 times to form a pin clinch. In order to be considered an acceptable specimen, at least 95% of operations shall comply with the requirements set forth in paragraph 2.C.(1) herein.

(2). Performance test (Class B). Spool of staple forming wire, shall be inserted in the stapler and shall form a standard clinch through 2, 6, and 16 sheets of 60g/m^2 (16-lb_m, 17" x 22" - 500) bond paper . For each of the three tests, 20 staples shall be used. In order to be considered an acceptable specimen, at least 95% of operations shall comply with paragraph 2.C.(2) herein.

(3). Performance test (Class C). Using bond paper with a basis weight of 60g/m^2 (16-lb_m, 17" x 22" - 500), this test shall demonstrate the capability of the staples to consistently clinch 20 sheets. The stapling operation shall be done 100 times to form a standard clinch. In order to be considered an acceptable specimen, at least 95% of operations shall comply with paragraph 2.C.(3). herein.

(4). Tensile strength test (Class A). Tensile strength shall be tested in accordance with ASTM E 8. Certificate of compliance is acceptable.

4. REGULATORY REQUIREMENTS: The offeror/contractor is encouraged to use recovered materials in accordance Paragraph 23.403 of the Federal Acquisition Regulation.

5. PACKAGING, PACKING, AND MARKING: Packaging, packing, and marking shall be as specified in the contract or order.

6. REFERENCED DOCUMENTS: The issue of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

A. Federal Regulations:

Federal Acquisition Regulation. Paragraph 23.403

Copies of the U.S. Code may be obtained through the Congressional Sales Office, U.S. Government Printing Office, Washington D.C. 20402.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

B. Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

Available from: Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, or as directed by the contracting officer.

C. ASTM References

ASTM E 8 - Standard Test Method of Tension Testing of Metallic Materials.

Available from: ASTM., 1916 Race Street, Philadelphia, PA 19103.

7. NOTES: Purchasers shall specify the following in the contract or purchase order:

A. Ordering Data.

(a) Title, number, and date of this Commercial Item Description
(b) Class of staples required.
(c) Unit of issue and quantity
(d) Arrangements for inspections and inspection facilities. (If different than provisions under Quality Assurance)
(e) Packaging, packing, marking and palletization requirements.

B. Item Identification.

A-A-1019 - A This example covers standard duty preformed staples

Class A - Standard duty preformed staples
Class B - Wire spool for forming staples
Class C - Light duty preformed staples

MILITARY INTERESTS:

DoD has no registered interest in revisions and amendments to this Commercial Item Description until further notice.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.