[INCH - Pound]

A-A-117D
December 31,1990
SUPERSEDING
A-A-117C
June 18, 1986

COMMERCIAL ITEM DESCRIPTION
PROTECTOR, DOCUMENT (BINDER FILLER)

This Commercial Item Description is approved by the Commissioner, Federal Supply Services, General Services Administration, for the use of all Federal agencies.

This description covers document protectors which are intended for keeping documents neat and clean.

Classification - Each document protector shall be defined by type and size as indicated below. The protector selected, shall be indicated by an item identifier number, as indicated on page 4.

Type A - Biaxially oriented polypropylene, polished both sides, not less than 0.0020 inches thick.

Type B - Colorless plastic, matte both sides, not less than 0.0035 inches thick.

Type C - Polypropylene, polished both sides, not less than 0.0040 inches thick.

Size 1 - 11 inch length x 8-1/2 inch width.
Size 2 - 11 inch length x 9 inch width.

1. Salient characteristics.

A. The document protector shall consist of a flexible plastic sheet which is folded to form a double thickness of the size specified. A single sheet of black album paper, the same size as the protector, shall be inserted into the fold between the plastic.

B. The black album paper shall not be less than 25 percent chemical wood pulp and shall have a basis weight of 56 $\pm$ 4 pounds (24 x 36 - 500 sheets). This weight basis shall be measured in accordance with TAPPI Standard T410.

C. The binding edge shall be along the length dimension and consist of the black album paper plus the triple thickness of the plastic sheet, all of which shall be punched with three holes.

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

D. Size 1 protectors shall have round or oblong holes and fit easily into a standard three ring binder having 4-1/4 inch center to center distance between rings. The long axis of the oblong holes shall be parallel to the width dimension. The round holes shall be 1/4 + 1/32 inch in diameter. Oblong holes shall be 3/8 + 1/16 inches long by 1/4 + 1/32 inches wide. The 3/8 inch dimension shall be perpendicular to the binding edge. The center line of the holes shall be 3/8 inch + 1/32 inch from the binding edge.

E. Size 2 protectors shall be provided with oblong holes only. These oblong holes shall be similar to those described in Size 1.

F. The plastic shall be clear and sufficiently transparent so that typed documents shall be easily legible under typical office lighting conditions through one thickness of the plastic.

G. Workmanship, Protectors shall be free of dirt, rips, scratches, blisters, discoloration, and any other defects Which may affect the durability, appearance or serviceability. All protectors shall be squarely and uniformly cut.

2. Tests

A. Burning Resistance
The burning rate of the plastic sheet shall not be greater than 1-1/2 inches per second when tested as specified in ASTM D 568.

B. Hole Strength
Remove the black album paper. Place a commercial binder ring with a five (5) pound weight attached through one of the punched holes of the plastic sheet (triple thickness). The punched hole shall be capable of sustaining the five (5) pound weight for a sixty second period of time without tearing or ripping. All three punched holes of the plastic sheet shall be tested in this manner.

3. Quality Assurance

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the government. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description, where such inspections are deemed necessary to assure that supplies and services conform to the prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

Each lot of protectors shall be inspected for conformance to the requirements herein. Sampling for inspection shall be in accordance with MIL-STD-105 using the plans specified below.

A. Visual and dimensional characteristics - Inspection Level S-3 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one protector.

B. Sampling for Test. A sample shall be taken from each lot in accordance with MIL-STD-105, inspection Level S-1. With an Acceptable Quality Level (AQL) of 2.5 percent defective. The sample unit shall be one protector.

C. Packaging, Packing, and Marking - Inspection Level S-2 with an AQL of 4.0 percent defective. The sample unit shall be one fully prepared shipping container.

4. Preparation for delivery

Packaging, packing and marking shall be as specified in the contract or purchase order.

5. Recovered materials

The offeror/ contractor is encouraged to use recovered materials in accordance with Public Law 94-580,to the maximum extent practicable.

6. Application for copies of technical documents referenced herein:

The issue date in effect on date of invitation for bids or request for proposal shall apply.

ASTM standard test methods can be obtained from the American Society for Testing and Materials; 1916 Race Street; Philadelphia, PA 19103.

MIL-STD-105 is available from Naval Publications and Forms Center; 5801 Tabor Avenue; Philadelphia, PA 19120.

Public Law 94-580, Resource Conservation and Recovery Act, is part of U.S. Code, Title 42. Available from congressional sales office, U.S. Government Printing Office, Washington,D.C. 20402.

Tappi Standards are available from:The Technical Association Of The Pulp And Paper Industry, P.O. Box 105113, Atlanta, Ga 30348

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

7. NOTES:

A. Ordering Data:

Purchasers should select the preferred options permitted herein, and include the following information in the procurement documents:

B. ITEM IDENTIFIERS/REFERENCE PART NUMBER SYSTEM (FOR CATALOGING USE ONLY)

PART REFERENCE NUMBERS:

AA117-1 A : This example describes a DOCUMENT PROTECTOR
: (Type A) - Biaxially oriented polypropylene, polished both sides, not less than 0.0020 inches thick, (Size 1) 11 inch length x 8-1/2 inch width.

---A - Size 1 - 11 inch length x 8-1/2 inch width.
B - Size 2 - 11 inch length x 9 inch width.

-----1 - Type A - Biaxially oriented polypropylene, polished both sides, not less than 0.0020 inches thick.

2 - Type B - Colorless plastic, matte both sides, not less than 0.0035 inches thick.

3 - Type C - Polypropylene, polished both sides, not less than 0.0040 inches thick.

MILITARY INTERESTS:

None. DoD has determined that no military activity has an official interest in this Commercial Item description

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.