[METRIC]
A-A-2985
March 15, 1996

COMMERCIAL ITEM DESCRIPTION

ADHESIVE, AIR-CURE, SILICONE RUBBER

The General Services Administration has authorized the use of this commercial item description, for all federal agencies.

1. Scope: This Commercial Item Description covers a synthetic adhesive suitable for use in bonding silicone rubber to itself and to aluminum without the use of heat and pressure. The product may be either a one-part or a two-part adhesive.

2. Salient Characteristics: The adhesive shall be a silicone rubber material which will produce a product that meets all the requirements specified herein.

2.1 Curing time: The adhesive shall be tack-free after curing for 24 hours and it shall fully cure within 72 hours at 23 +/- 2°C(73 +/- 4°F.) Successful completion of the peel strength test as specified in 2.4 shall verify the curing time.

2.2 Pot life: Pot life of the material shall be a minimum of three hours. Spread 10 grams of single component or mixed adhesive (if two-part) onto a non-porous surface that has been conditioned at 23 +/- 2°C(73 +/- 4°F.) Maintain room temperature for three hours. If the material remains spreadable after three hours, the pot life requirement has been met.

2.3 Viscosity: Viscosity shall be 1000 to 5000 centipoises as determined in accordance with ASTM D 1084, Method B.

2.4 Peel Strength: Peel strength, performed after a 24-hour cure, shall be not less than 14N/cm (8 pounds/inch.) After a 72-hour cure , peel strength shall be not less than 17N/cm(10 pounds/inch.) Four specimens of each bond being tested shall be used for each peel test performed. Test specimens shall be prepared in accordance with ASTM D 413, Section 6 (for Strip Specimens - Type A.) Rubber specimens shall be R.H. Carlson, Inc. P/N RHC NORSIL-9235[1]. Alclad aluminum specimens shall conform to SAE J454(2024). Residual mold release material may be removed from the surface of the rubber material prior to bonding; however, the surface of the rubber must be dull and smooth, without visible scratches. Peel tests shall be conducted in accordance with ASTM D 413, Section 10 (Strip Specimens: Type A, 180° peel.)

Beneficial comments, recommendations, additions, deletions, clarification, etc., and any data which may improve this document, should be sent to: GSA, Paints and Chemicals Commodity Center, 400 15th Street, S.W., Auburn, WA 98001.

[1] P/N RHC NORSIL-9235 and may be obtained from R.H. Carlson, Inc., 41 Chestnut Street, P.O. Box 1687, Greenwich, Connecticut 06836-1687.

DISTRIBUTION STATEMENT A: Approved for public release. Distribution is unlimited.

FSC 8030

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.

2.4.1 Water resistance: Rubber bonded to aluminum specimens shall be immersed in water at 23 +/- 2°C(73 +/- 4°F) for 24 hours. The specimens shall then be tested as specified in 2.4 within five minutes after removal from the water. The peel strength shall not have decreased more than 15 percent of the 72 hour cure peel strength value (without immersion) determined in 2.4.

2.4.2 Oil resistance: Rubber bonded to aluminum specimens shall be immersed in oil conforming to ASTM D 471, Reference oil #2, at 23 +/- 2°C(73 +/- 4°F.), for 24 hours. The peel strength shall not have decreased more than 20 percent of the 72 hour cure peel strength value (without immersion) determined in 2.4..

3. Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

4. Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

5. Contractor Certification: The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

6. Copies of ASTM specifications or standards may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

7. Copies of SAE specifications or standards may be obtained from the Society of Automotive Engineers, 400 Commonwealth Dr., Warrendale, PA 15096-0001.

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.