[METRIC-SI]
AA O-00250F/GEN (GSA-FSS)
July 1, 1993
SUPERSEDING
Int. Fed. Spec AA-O-00250E
July 21, 1989

INTERIM FEDERAL SPECIFICATION

OFFICE FURNITURE, WOOD, UNITIZED

(GENERAL SPECIFICATION)

This Interim Federal Specification was developed by the National Furniture Center, Federal Supply Service, General Services Administration, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1 SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the general requirements for unitized wood office furniture. Specific requirements, figures and drawings, and other information pertaining to any individual piece of furniture in this group will be found in the applicable detailed specification.

1 2 Classification.

1 2.1 Types, classes, styles, designs, and sizes. The type, classes, styles, designs, and sizes of furniture items covered by this specification shall be as specified in the applicable detailed specifications, which are as follows:

AA-O-00250/1 - Office Furniture: Bookcase, Wood, Unitized.
AA-O-00250/2 - Office Furniture: Credenza, Wood, Unitized.
AA-O-00250/6 - Office Furniture: Tables, Wood, Unitized.

2 APPLICABLE DOCUMENTS

2 1 The following documents of the issues in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Military Standards

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

Federal Standards:

FED-STD-595B - Colors Vol. 1.

(Copies may be obtained from the Standardization Documents Order Desk, Building. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American National Standards Institute Publications:

ANSI/HMPA HP-1983 Hardwood and Decorative Plywood
ANSI A161.1-1990 Standards for Kitchen and Vanity Cabinets
ANSI A208.1 - 1991 - Wood Particleboard
ANSI X5.5 - 1989 Desk Product Test

(ANSI standards are available from American National Standards Institute, Inc. 1430 Broadway, New York, NY 10018.)

American Society for Testing and Materials Standards:

ASTM D 905 Standard Method of Test for Strength Properties of Adhesives in Shear by Compression Loading.
ASTM D 1211 - Temperature-Change Resistance of Clear Nitrocellulose Lacquer Films Applied to Wood

(ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 10103.)

Hardwood Plywood Manufacturers Association Publication:

HPMA FE-86 - Voluntary Standard for Formaldehyde Emission from Hardwood Plywood Wall Paneling, Wood Composition Board Wall Paneling and Industrial Panels having Face Veneers.

HPMA HP-1 1992 - Interim Voluntary Standard for Hardwood and Decorative Plywood

(Copies may be obtained from the Hardwood Plywood Manufacturers Association, 1825 Michael Faraday Drive, Reston, VA 22090-2789)

National Electrical Manufacturer's Association Publication

Source: https://assist.dla.mil -- Downloaded: 2020-10-20 11:39Z
Check the source to verify that this is the current version before use.

NEMA LD 3 - 1991 - High Pressure Decorative Laminates

(NEMA standards are available from the National Electrical Manufacturer's Association, 2101 L Street, NW., Suite 300, Washington, DC 20037.)

3. REQUIREMENTS

3.1 Regulatory requirement. The offferer/contractor is encouraged to use recovered materials in accordance with Public Law 94-580, as amended, to the maximum extent practicable.

3.1.1 Formaldehyde emission requirements. All plywood, particleboard, medium density fiberboard, wood veneered and plastic laminated panels shall meet Voluntary Standard HPMA FE-86 on formaldehyde emissions with the changes listed below.

Under Section III, FORMALDEHYDE EMISSION STANDARDS, Product Category.
Change "Wall Paneling - Plywood" to "Furniture panels, 6.5 mm thick or less, such as plywood drawer bottoms."
Change "Industrial Panels" to "Furniture Panels greater than 6.5 mm, such as drawer sides/backs, end panels, top panels, etc."
Loading Ratios and Maximum Emission Levels for these two categories remain the same.

Formaldehyde emission requirements do not apply to hardboard panels.

3.2 Materials. The materials used in construction of the furniture shall be as follows:

3.2.1 Adhesives. The adhesives to be used and their permitted application shall be as shown in Table I.

TABLE I. Adhesives

Application	Requirements
All glue blocks, assembly joints, glued laminated stock, edge joining of lumbercore panels, and bonding of plastic laminate to core.	Any adhesive that will develop an average block shear strength of not less than 19 000 kPa when tested as specified in 4.6.2.
All plywood gluing, edge-joining of veneer plies, and edge banding.	Any adhesive that will meet the test requirement of the Type II bond or better as described in HP-1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

3.2.2 Glass. Sheet glass, A-quality, double strength, 3 mm thick.

3.2.3 RESERVED

3.2.4 Wood.

3.2.4.1 Wood species. Woods permitted are those listed in Table II.

TABLE II. Wood Species.

Exposed Veneer 1/	Exposed Solid Parts 1/ 2/	Unexposed Wood and Veneer
Walnut	Andiroba (Carapa guianensis) Cherry Mahogany (Swietenia or Khaya) Pecan Walnut	Andiroba (Carapa guianensis) Ash Beech Birch Cherry Magnolia Mahogany (Swietenia or Khaya) Maple Oak Poplar Sweetgum Sycamore Tupelo Walnut

1/ Includes exposed interior surfaces such as door backs, shelves and interior panels.

2/ Only one species may be used for exposed solid parts.

3.2.4.2 Solid wood requirements. Wood used for exposed parts, including drawer parts, shall be bright, well sanded, and free from brashness, discolorations, worm holes, splits, shake or other defects which affect the appearance or which may affect the serviceability of the finished product. Wood used in unexposed parts may contain small defects such as pin-knots, sapwood or mineral streaks provided they do not affect the strength of the part

3.2.4.3 Wood seasoning. All wood, including veneers, shall be uniformly kiln-dried to a 5 to 8 percent moisture content. After drying it shall be held in temperature and humidity controlled storage for a sufficient time to ensure uniform moisture

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

distribution among the individual parts. After gluing and before planing and sanding for crossbands, lumber cores shall be permitted to cure-out to ensure uniform distribution of glue joint moisture and to minimize sunken joints, spring back and stresses

3.2.4.4 Hardwood plywood. All plywood shall be constructed in accordance with HPMA HP-1 and as specified herein. Glue bond shall be Type II or better. All B grade (B) face veneers shall be edge glued. Wood used in plywood construction shall conform to 3.2.4.1. When edge banding is specified, it shall be minimum 8 mm thick wood of the same species used for other exposed parts of the unit. Banding shall be Lap or mitered at the corners. The core and edge banding assembly shall be dressed to a uniform thickness before the application of the crossbands, face and back veneers. Veneers and cores shall be as specified in Table III.

TABLE III.

Face Veneers	Back Veneers	Cross bands and/or Veneer Core	Lumber core	Particleboard Core
Panels exposed to view in normal use positions including exposed interior surfaces.				
0.7 mm min (before sanding) B grade (B) 1/ (see 3.2.4.5)	0.7 mm min (before sanding) Sound grade (2)	1 mm min. Sound grade (2)	Sound grade	See 3.2.4.6
Drawer bottoms and partitions, unexposed case backs.				
1 mm min. (before sanding) Sound grade (2)	1 mm min. (before sanding) Sound grade (2)	Sound grade (2)	N.A	N.A.
Dust panels				
1 mm min. Utility grade(3)	1 mm min. Utility grade(3)	Utility grade (3)	N.A.	N.A.

1/ Exposed interior surfaces shall have Sound grade (2) veneer minimum.

3.2.4.5 B Grade (B) Veneer Requirements. As specified in HPMA HP-1 and the following. Plain sliced, no wild figure, limited number of pin knots permitted provided they are not in clusters and do not detract from the overall appearance of the panel. (More pin knots permitted in kneespace and bookcase interior areas, except back of doors.) Exposed areas: 20% sapwood maximum. Kneespace and bookcase interiors unlimited sap permitted

3.2 4.6 Particleboard. ANSI A208.1-1991 grade 1-M-2 with following exception for 22 mm thick panels or less: minimum

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

average screw-holding capacity of 1268 N face, 1046 N edge. Moisture content 9 percent maximum at time of laminating.

3.2.4.7 High pressure laminate (HPL). Shall meet NEMA LD 3-1991, grade GP 50 for exposed surfaces and grade BK 20 as specified for unexposed surfaces. Gatorply (0.762 mm thick) may alternatively be used for unexposed surfaces. All panels shall meet warp/sag requirements in 3.3.4.

3.2.5 RESERVED

3.2.6 Steel. The steel shall be commercial quality cold rolled. The steel shall be smooth, free from rust, scale, pits, scratches, laps and buckles affecting strength or appearance.

3.2.7 Hardware.

3.2 7.1 Pulls. The door pulls shall be brass plated zinc with clear top coat or brass colored anodized aluminum, 25 mm (± 3 mm) diameter. The design of the pulls shall conform to the figures in applicable detailed specification. Final finish shall be as specified in 3.4.1. The screws that fasten the pulls to the furniture shall be of the same color as the pulls.

3.2.7.2 Adjustable Glides. The upper surface of the glide shall be satin chrome, brass plated, or nickel plated and the lower surface (in contact with the floor) shall be either stainless steel or high impact plastic. Glide shall be between 38 mm and 51 mm in diameter and shall be in proportion to the thickness of the leg. Glide shall have a minimum 38 mm leveling bolt.

3.2.7.3 Shelf standards and supports. The shelf standards and supports shall be of cold rolled steel or anodized aluminum alloy and shall have a brushed brass satin finish. The standards shall be of the surface mounting type and shall be 16 mm wide. They shall have adjustments every 13 mm on the length dimension and shall be numbered every other one. Standards shall be secured with brass plated screws, or brass plated screw nails.

3.2.7.4 Screws. All screws shall be Number 10 minimum unless otherwise specified in applicable construction paragraphs.

3 2.7.5 Hinges.

3 2 7 5 1 Hinges, knife type Semi-invisible knife hinges, brass plated steel, 2.1 mm thick minimum, with clear top coat. When door is closed, hinge knuckle shall protrude 6 mm maximum. Secure hinge with min 6 brass plated, flat head screws.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

3.2.7.5.2 Hinges, butt type. Hinges shall be butt type. 64 mm long, brass plated steel, with a clear topcoat. Each hinge shall be secured to the unit with 6 brass plated flat head screws.

3.3 Construction.

3.3.1 Design and construction. The design and construction shall be as specified herein and in the applicable detailed specification. In any case where there is a conflict between the text of the specification the figures, illustrations or drawings, the text shall prevail.

3.3.2 Tolerances. Where tolerances are not specified, the following tolerances will be permitted:

Overall dimensions,	width:	+50 mm, -2 mm
	depth:	+20 mm, -2 mm
	height:	+ 4 mm, -2 mm
Solid wood part dimensions:		+ 4 mm, -2 mm
Plywood part dimensions for 3.8 mm thick plywood or thicker:		+ 2 mm, -1 mm

3.3.3 Joinery. All joints shall be as specified in applicable construction paragraphs. All joints shall be securely glued (3.2.1). Starved or insufficiently glued joints will not be acceptable.

3.3.4 Plywood panels (general requirements). Balanced construction with lumber, veneer, particleboard core. Designed to prevent "telegraphing" of core. Maximum sag or warp in any panel shall be 0.001 mm/mm of panel length/width. (Example: 0.001 mm x 2000 mm length = 2 mm sag or warp.)

3.3.5 Plastic laminate panel construction. Assembly shall consist of particleboard (3.2.4.6, 3.3.4) or 5 ply plywood (3.2.4.4, 3.3.4) surfaced with decorative plastic laminate on the face, and backing sheet on the back (3.2.4.7). The laminate shall be securely applied, providing a tight, uniform bond. When edge banding is specified, it shall be minimum 8 mm thick wood of the same species used for other exposed solid parts of the unit. Banding shall be full length strips, lap joined at the corners and shall be applied before the application of the plastic laminate.

3.3.6 Tops. The tops shall be a plastic laminate assembly (3.3.5). All edges of the top shall be banded as specified in 3.3.5. Unless otherwise specified in the detailed specification, all corners shall be rounded to a 4.8 mm radius, minimum. All top edges of the top shall be chamfered a minimum of 1.6 mm at a 45 degree angle. The bottom edges of the top shall be eased. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

thickness of the tops shall be as specified in the detailed specification. All tops shall be attached to supporting members as indicated in construction detail paragraphs herein.

3.3.7 Legs. Legs shall be of 1.52 mm (+0.09,-0.08 mm) square tubular steel (3.2.6). The finish shall be as specified in 3.4.2. All legs shall be equipped with leveling glides specified in 3.2.7.4. Threaded nut assembly for receiving leveling glide, shall be securely fastened to the bottom of the leg. Threaded portion of nut assembly shall be 6 mm minimum. The end of the leg tubing just above the glide shall be ground smooth to remove sharp edges. The size of the legs shall be as specified in the detailed specification.

3.3.8 Mounting plates. Mounting plates shall be 4.8 mm thick steel, 89 mm square. Holes shall be drilled for 8 mm machine bolts. When legs are offset on mounting plates, mounting holes shall be positioned so that leg cannot be mounted backward. Holes shall align with "T" nuts in the pedestal base. The plates shall be welded to the legs (3.3.7) and the entire assembly finished as specified in 3.4.2. The legs shall be positioned on the plates as specified in the detailed specification.

3.3.9 Direction of grain. Unless otherwise specified in the detailed specification, the grain direction shall run as specified herein. It shall be vertical for end panels, doors (except for framed glass doors), panel posts, back panels, including kneespace panels. For framed glass doors, the grain direction shall run vertically for upright members and horizontally for the top and bottom members. The grain direction of all other components shall run horizontally.

3.3.10 Panel posts. Panel posts shall be one piece of solid wood (3.2.4.1), 19 x 28 mm. End panels shall be tenoned into the panel posts. Where the outside end panel is joined with back panel, the back panel shall be rabbeted into the panel post. There shall be a veinline a maximum of 1.6 mm in width and depth, at the point of joinery of the panel post and panel. The veinline shall run the entire length of the joint.

3.3.11 Chamfered corners. Unless otherwise specified in the detailed specification, the outside panel post corners of all units, including all pedestals, shall be chamfered 6 mm.

3.3.12 Case back attachment. Case backs shall be secured to the credenzas and the Type II bookcase, with pneumatically driven staples. Staples shall be spaced a maximum of 75 mm apart. Staples shall penetrate the case 13 mm minimum.

3.4 Metal, laminate and wood finishes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

3.4.1 Face hardware finish. All face hardware on a piece of furniture shall match each other as closely as possible within the limits of the base metal. Hardware shall be coated with a clear topcoat. Final finish shall be satin.

3.4.2 Enamel finish on steel. Exterior metal surfaces shall be cleaned and prepared to receive enamel finish. A coat of baked enamel shall be applied. The finish shall be baked according to the time-temperature cycle recommended by the manufacturer of the finish and shall have a minimum dry film thickness of 1.0 mils. The finish shall level out to produce smooth, uniform surfaces without runs, wrinkles, grit, areas of thin film, no film, or separation of color. The cured film shall pass the tests for hardness and adhesion in 4.6.3. Enamel finish shall match color No. 37038 (black) of Fed. Std. 595B.

3.4.3 Plastic laminate. Plastic laminate shall match GSA Standard sample (walnut) FSS-L-01002 (6.3) for color and appearance.

3.4.4 Finish, exposed wood parts and surfaces. (Includes exposed interior surfaces such as door backs, and interior compartments.) All surfaces exposed to view in normal use shall be finished, sanded smooth with all corners and edges eased. Exposed wood finish shall match walnut standard sample FSS-L-01002 (6.3) for color and appearance. The natural grain of the wood shall not be clouded by the finishing materials. Bleaching agents or materials shall not be used. The application of materials drying time, sanding, cleaning and rubbing shall be controlled to produce items of uniform finish without sags, runs, orange peel or other defects detrimental to a smooth quality appearance. Final finish shall be satin. Finish shall meet test requirements in 4.6.3.4.4.1 Recommended procedure for finishing exposed wood surfaces.

1. Sap stain to equalize color.
2. Apply selected stain to produce color specified.
3. Wash coat with adhesive sealer.
4. Scuff sand, using sandpaper grit of fineness needed to produce proper surface.
5. Fill to degree necessary to match standard sample.
6. Seal with adhesive type sealer.
7. Sand, using sandpaper grit of fineness needed to produce proper surface
8. Shade to tie-in color variation, if necessary.
9. Top coat with 2 coats of lacquer.
10. Rub with material necessary for final finish to conform to standard sample.

NOTE: Operation number 8 may be performed where shown or after operation number 5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

3.4.5 Finish, unexposed parts and surfaces. All unexposed wood interior parts and surfaces shall be machined smooth and cleaned. The unexposed areas shall receive one coat of lacquer sealer and one coat of lacquer. No finishing material shall be applied to drawer suspension parts which discolors or interferes with the easy operation of the suspension.

3 5 Identification marking. Each unit shall be permanently and clearly marked with contrasting ink in an inconspicuous place, with the National Stock Number, contract number, this specification number, the month and year of manufacture, and the manufacturer's name or trademark.

3 6 Workmanship. Method of machining, construction, veneering, joinery, gluing, assembly, and drawer fit and action shall be suitable for use in executive offices. Joints shall be tight, well fitted and securely glued. Veneers shall be securely and smoothly applied without gaps or filler.

Gap around drawer fronts shall be uniform. 3 mm gap required above top drawer fronts. Drawer faces shall be even and parallel with each other. Drawers shall operate smoothly and quietly and shall not interfere with each other or have excessive side play. Locks shall operate smoothly and quietly.

All surfaces (including drawer parts, stationary racks, and drawer partitions) shall be smoothly machined and sanded. Dovetails and other joints shall be tight and well fitted. Units shall be free of splinters, sharp edges, and sharp corners to prevent injury to personnel or damage to their clothing. Unexposed surfaces shall be smooth and clean.

The natural grain of the wood shall not be clouded by the finishing materials. The application of materials, drying time, sanding, cleaning, and rubbing shall be controlled to produce items of uniform finish without sags, runs, orange peel, overspray or other defects detrimental to a smooth quality appearance. Unexposed parts shall be finished as required. Drips and runs on unexposed parts is not acceptable.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that the supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

4.2 First article inspection and testing. The required samples shall be inspected and tested by the contractor for all the requirements of the contract. A record of this inspection and test, including certificates of conformance for materials, shall be submitted to the government for approval. The Government reserves the right to witness the contractor's inspection and tests.

The sample required for first article inspection and testing shall be examined and tested for all the requirements of this purchase description. The first article samples shall be manufactured in the same manner, using the same materials, equipment, processes, and procedures as used in regular production.

All parts and materials, including packaging and packing, shall be obtained from the same source of supply as used in regular production. Use first article samples as manufacturing standards. Manufacturer shall maintain first article samples until the last order is shipped, received, and accepted. New first article samples are required for each new contract. Old first article samples shall not be reused.

4.3 Lot acceptance tests. Lot acceptance tests shall be conducted under the supervision of the Government Inspector at the manufacturer's plant. In the event the manufacturer does not have the facilities to perform the required tests, he shall engage the services of a commercial testing laboratory acceptable to the Government. Copies of the laboratory report shall be submitted to the Government Inspector upon receipt from the laboratory. All examination and testing shall be in accordance with Section 4 of this specification. 4.4 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

4.5 Inspection levels and acceptable quality levels (AQL's). Inspection levels and acceptable quality levels expressed in defects per hundred units shall be as shown in Table IV.

TABLE IV.
Acceptable quality levels in accordance with MIL-STD-105

For examination in	Inspection level	Major	Total
4.5.1	II	4.0	6.5
4.5.2	S-2		4.0
4.5.3	S-2		4.0
4.5.4	S-2		4.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

4 5.1 Visual examination. Examination of the end item(s) shall be in accordance with the classification of defects specified in Table V and acceptable quality levels (AQL's) specified in 4.5 herein. The lot size shall be all units of the same type offered for inspection at one time. The sample unit for this examination shall be one complete item.

TABLE V. Classification of End Item Defects

Examine	Defect	Classification Major	Minor
Finish and appearance of exposed wood parts visible in normal use position	Does not match standard reference panel with respect to color	X	
	Discoloration (Bleeding) over 25 mm^2		X
	Spotted, affecting appearance.		X
	Area of no lacquer film over 25 mm^2 in area	X	
	Glue stain or glue line clearly showing, affecting appearance.		X
	Excess glue not removed.	X	
	Finish peeling, flaking, blistered, cracked, checked or wrinkled.		X
	Light or dark colored areas, affecting appearance.	X	
	Finish cut or rubbed through to wood		X
	Open Grain. Finish material not filling pores.		X
	Orange peel, affecting appearance.		X
	Damage or scratch, less than 25 mm long, or 25 mm square.		X
	Damage or scratch over 25 mm square or 25 mm long.	X	
	Finish tack, i e., not completely dry	X	
	Rough or gritty surface or foreign matter imbedded in finish.		X
	Light colored edge not touched up	X	
	Burn-in or repairs not neatly accomplished		X
	Unstained (white) wood visible when item is in normal use position		X
	Not polished or rubbed where required	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of End Item Defects (continued)

Examine	Defect	Classification Major	Minor
Finish of exterior wood parts not visible in normal use	Finish not applied where required		X
	Stain or sealer coat omitted where required.	X	
Finish of hardware.	Not as specified.	X	
	Component tarnished or stained, affecting appearance		X
	Rusted or corroded.	X	
	Not coated with protective finish.	X	
Quality of plywood and laminated wood on exposed surfaces	Not harmonious grain match between panels on any one item		X
	Species of wood not as specified		X
	Number of plies not as specified	X	
	Open joint in face veneer	X	
	Face veneer not a continuous strip.		X
	Uneven core surface telegraphing.		X
	Any cross break in veneer.	X	
	Sanded through face ply.	X	
	Waves of uneven sanding, affecting appearance		X
	Machine mark, affecting appearance.		X
	Veneer blister	X	
	Veneer chipped or splintered.		X
	Any loose or unsound knot.		X
	Conspicuous patch.	X	
	Decay, affecting appearance.		X
	Veneer joint less than 25 mm from edge of panel, except drawer fronts	X	
	Void at exposed edge	X	
	Lumber-core not "clear edge" where required		X
Quality of solid wood on exposed and unexposed surfaces	Species of wood not as specified	X	
	Component not fabricated of one piece solid wood where required.		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of End Item Defects (continued)

Examine	Defect	Classification Major	Minor
Quality of solid wood on exposed and exposed surfaces (cont)	More than 1 species of wood used for exposed wood components of any item except panel posts		X
	Direction of grain not as specified		X
	Check or split over 25 mm in length.	X	
	Wood warped, affecting appearance or serviceability.	X	
	Loosened grain or shake on exposed surface	X	
	Loosened grain or shake on unexposed. surface		X
	Honeycomb.		X
	Loose or unsound knot		X
	Hole on exterior surface, affecting appearance	X	
	Glue line in built-up stock open over 25 mm in length.		X
	Glued up pieces uneven in built-up stock.		X
	Wave of uneven sanding.	X	
	Machine mark on exposed surface, affecting appearance.	X	
	Any mineral streak on exposed surface over 1 x 100 mm or 2 x 50 mm		X
	Wood chipped or splintered on exposed surface of drawer interior.		X
	Any manufacturing defect or defect native to the wood filled in with plastic wood or other filler material.	X	
Quality of plywood on unexposed surfaces	Any manufacturing defect or defect native to the wood filled in with plastic wood or other filler material.		X
	Species of wood not as specified.		X
	Number of plies not as specified.		X
	Veneer delaminated	X	
	Any knot holes		X
Quality of particleboard on unexposed surfaces	Not material specified	X	
Quality of laminated plastic	Not material specified	X	
	Color or grain character of face sheet not as specified	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of End Item Defects (continued)

Examine	Defect	Classification Major	Minor
Quality of etc (cont)	Face or backing sheet missing.	X	
	Top surface not proper finish	X	
	Sheet containing area of non adhesion		X
	Face sheet damaged, dented, cracked, marred, or discolored.	X	
	Scratch or nick in face sheet, affecting appearance.		X
	Evidence of telegraphing.		X
Quality of glass in glass doors	Glass cracked or broken.	X	
	Not quality specified.	X	
	Surface scratched or chipped.		X
	Bubble larger than 1.5 mm diameter in glass door		X
Quality of metal components (except attaching implements)	Not fabricated of material specified	X	
	Broken, cracked, dented or fractured		X
	Nicked, pitted, malformed or bent, affecting appearance.		X
	Machine or die marked, affecting appearance		X
	Contains hole where not required, does not have one where required.		X
	Fin, burr, or sharp edge which may cause personal injury or damage to clothes.		X
Construction, assembly and attachment of unexposed and exposed parts	Component missing.	X	
	Component in wrong location.		X
	Component loose or insecurely fastened where rigidity is required.		X
	Component out of alignment or out of square affecting serviceability		X
	Poor fit of component part or of mating part		X
	Defective hinge or other mechanism that does not function properly		X
	Wood component not glued as specified		X
	Solid wood used in place of veneer or vice versa		X
	Wood component damaged or not properly machined		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of End Item Defects (continued)

Examine	Defect	Classification Major	Minor
Construction, assembly, and attachment of exposed and unexposed parts (cont)	Routing not uniform or uneven.		X
	Component not chamfered where required.		X
	Edges not "eased off" where required		X
	Any loose or unsound glued joint		X
	Wood joint not as specified.		X
	Glue joint open 1.5 mm or more on exposed part		X
	Glue joint open over 3 mm or more on unexposed part.		X
	Top panels warped 6 mm or more W or L	X	
	Overhang of top panel uneven or not as specified		X
	Door clearance not as specified	X	
	Door does not close completely.	X	
	Door binds when opening or closing.		X
	Door catch does not operate smoothly		X
	Drawer does not operate smoothly full extent of travel.		X
	Glides not securely attached		X
	Legs uneven		X
	Not as specified or not as shown on drawings or figures		X
	Component not size or shape specified.		X
	Component not type or design specified.		X
Workmanship and attachment of screws, bolts, nuts, washers and rivets	Any attachment device not type or size as specified		X
	Material not as specified.		X
	Spacing of screws not as specified		X
	Screw point visibly bulging wood		X
	Screw not countersunk when specified		X
	Screws, bolts, or rivets broken off		X
	Screw or bolt in wrong location		X
	Screws, bolts, nuts, or rivets specified missing.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of End Item Defects (continued)

Examine	Defect	Classification Major	Minor
	More than 1 bolt, screw or nut not drawn up tightly.		X
	Threads on nuts or bolts stripped.		X
	Text incomplete		X
	Missing, incorrect or illegible.		X
	Marking in wrong location		X

4.5.2 Assembly examination. Examination of assembly shall be in accordance with paragraph 4.2 in the detailed specifications.

4.5 3 Examination of dimensions. Any dimension that is not as specified in figures or text shall be classified as a defect.

4.5.4 Examination of preparation for delivery. Examination of preparation for delivery shall be in accordance with MIL-STD-105.

4.6 Tests. Perform all finish tests at first article inspection and again one year after the start of the schedule contract period Perform finish tests 4.6.1(d) once a month during the contract period. On contract with an option year(s), rerun all tests after the first, second etc. year(s).

4.6.1 Finish test requirements. (See 3.4.1) The following tests (except UV test) shall be performed on a sample panel finished in the same manner as units are finished in production.

All test panels shall be produced from finish materials currently being used in production. All samples tested shall meet the following test requirements. Actual test results are required. Certifications are not acceptable.

(a) Cold check. Age panel one week. Follow ASTM D 1211 test procedure After exposure of 10 cycles, there shall be no checking or cracking. True film checking is one or more wavy or straight lines which cross the grain and do not appear related to grain structure. When a panel displays veneer checks, check running parallel to the grain, or glue line fracture, the panel shall be disregarded and another panel tested.

(b) Cold print. Age panel 48 hours. A 50 x 50 mm (approx.) piece of duck material (canvas) 280 g/m^2, minimum count of 23 6 x 22.8 yarns per cm, shall be placed on the panel Place a 455 g weight on the material for 24 hours at 24 degrees C. Bottom (contact surface) of the weight shall be flat and have a 28 mm diameter. After the weight is removed, light polishing with a soft cloth and liquid polish must remove any imprint.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

(c) Ultra violet light resistance. Spray one-half of a 150 mm x 230 mm white porcelain panel with two coats of the lacquer to be tested. Allow panel to air dry for at least 18 hours. Place panel 305 mm from an ultraviolet light (Uviarc 420-U1 light with UA-3 lamp) with a 3.18 mm thick pane of window glass placed between the lamp and the panel, and expose for 24 hours. After exposure, spray the other half of the panel in the same manner and allow to dry for at least 4 hours. Compare the two finishes There shall be no more than a slight darkening of the UV light exposed film when checked under cool white fluorescent light.

Uviarc 420-U 1 light and UA-3 lamp are available from George W. Gates Co., Inc., P.O. Box 216, Franklin Square, Long Island, NY.

(d) Toughness and adhesion. Perform test for toughness and adhesion on a sample panel finished in the same manner as the furniture using Organic Coating Adhesion Tester, Model No, 1001 in accordance with manufacturer's instructions. Mar the panel both parallel and perpendicular to the grain. Film must conform to resulting indentation. Whitening (film separation) or cracking is not acceptable.

Organic Coating Adhesion Tester Model No. 1001 is available from U.S. Testing Company, Inc. Instrument Marking Division, 1415 Park Avenue, Hoboken, NJ 07030.

4.6.2 Test for adhesives. Test for adhesives shall be as shown in Table VII.

Table VII. Test for Adhesives

Component	Characteristic	Requirement Reference	Test Method
Adhesive	Block shear test	3.2.1	ASTM D 905

Disregard a test specimen if:

a. It fails at less than 19 300 kPa; and
b. It has 50 percent or more wood failure.

Rerun test if:

a Average shear strength is less than 19 300 kPa and
b. There is a 10 percent or greater difference between high and low test specimen values, and
c One of more samples fails at 19 300 kPa or more.

4.6 3 Tests for enamel finish on steel The tests shall be made as indicated herein on completely finished legs, H-frames, and mounting plates prepared in accordance in 3 4.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

4 6.3.1 Hardness. The dried film shall withstand the firm stroke of a 2H pencil held at a 45 degree angle and pushed across the film surface without evidence of marring when viewed at an oblique angle in a strong light.

4.6.3 2 Adhesion. The dried film shall not be removed from the panel when the latter has been scored with a razor blade through the film to the base metal in such a manner as to produce a grid of 3 mm squares and a 25 mm wide piece of cellophane tape (Scotch Brand No. 600 or equal) is applied firmly to the grid surface and then quickly pulled from the surface.

5. PREPARATION FOR DELIVERY

5.1 Preparation for delivery requirements shall be as specified in section 5 of the applicable detailed specifications.

6. NOTES

6.1 Intended use. The wood unitized furniture items covered by this general specification in conjunction with the applicable detailed specifications are designed for use in executive offices, courtrooms, and conference rooms of Federal agencies.

6.2 Ordering data shall be specified in section 6 of the applicable detailed specifications.

6.3 Standard samples.

Plastic laminate. A sample plastic laminate panel (walnut: FSS-L-01002) and a list of manufacturers with their product numbers who make an approved match, may be obtained from:

National Furniture Center
Engineering Division
GSA-FSS-3FNEW-CO
Washington, DC 20406

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.

6.4 SI - English unit equivalents.

1 m^2 (square meter)	= 1.19617 $yard^2$
1 kg/m^3 (kilogram/cubic meter)	= 0.06242 lb.(mass)/ft^3
1 mm (millimeter)	= 0.03937 inch (thickness of one dime)
1 m(meter) = 1 000 mm	= 1.0936 yard (39.7 in)
1 N(Newton)	= 0.225 lb. (force)
1 kg(kilogram)	= 2.2 lb.(mass)
1 g(gram)	= 0.0022 lb. (mass)
1 g(gram)	= 0.03527 oz.(mass avoirdupois)
1 kPa(kilo Pascal)	= 0.14514 lb(force)/in^2(PSI)
(C^o x 9/5) + 32 (Celsius)	= F^o (Fahrenheit)
1 g/m^2(gram per square meter)	= 0.02949 oz/yd^2 or0.04426 oz/linear yard 54" W basis)

To convert SI units to English units, multiply SI measurement by the appropriate English conversion factor listed above. See example on next below:

900 mm X 0.03937 in./mm = 35.43 inches

To convert Celsius temperature to Fahrenheit temperature use the above conversion equation. See example below:

(20°C X 1.8) + 32 = 68°F

Preparing Activity
GSA/FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:39Z
Check the source to verify that this is the current version before use.