MILITARY SPECIFICATION

CLOTH, COATED, NYLON, POLYURETHANE DOUBLE COATED

This amendment forms a part of Military Specification MIL-C-43906B, dated 27 June 1984, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 4

Table I, in column headed "Minimum", opposite "Initial": Delete "250" and substitute "200"; opposite "After accelerated weathering": Delete "200" and substitute "150"; opposite "After abrasion": Delete "200" and substitute "150"; opposite "After strength of coating": Delete "200" and substitute "150"; opposite "After high humidity": Delete "200" and substitute "150".

In column headed "Characteristic": Delete "Stiffness, warp only mm": and substitute "Stiffness, warp only cm":

In column headed "Maximum", opposite "At 70°F": Delete "90" and substitute "10"; opposite "At 0°F": Delete "120" and substitute "13".

In column headed "Minimum", opposite "Adhesion of coating, lbs./2-inch width": Delete "15.0" and substitute "12.0".

PAGE 5

3.4.3: Delete and substitute:

"3.4.3 Matching. The color and and shade shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7000± 500K, with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 100K."

3.4.4.1, line 2: Delete "21 ± 2 percent" and substitute "21 ± 5 percent".

PAGE 13

4.3.3, line 2: Delete "type I" and substitute "type II, concentration A".

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:53Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Navy - MC
Air Force - 82
DLA - CT

Preparing activity:

Army - GL

Project No. 8305-0072

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:53Z
Check the source to verify that this is the current version before use.