INCH-POUND
MIL-DTL-32092A
19 August 2021
SUPERSEDING
MIL-DTL-32092
8 November 2001

DETAIL SPECIFICATION

LEATHER, CATTLEHIDE, DEERSKIN AND HORSEHIDE, CHROME TANNED

This specification is approved for use by all Departments and Agencies of the Department of Defense (DoD).

1. SCOPE

1.1 Scope. This specification covers the requirements for chrome tanned, full grain cattlehide, deerskin and horsehide and the cattlehide flesh splits.

1.2 Classification. The leather is available in the following types and classes as specified (see 6.2)

1.2.1 Types.

Type I - Cattlehide, full grain, for garments and equipage
Type II - Deerskin, full grain, for garments and equipage
Type III - Horsehide, full grain, for garments and equipage
Type IV - Cattlehide, flesh splits for garments and equipage
Type V - Cattlehide, full grain for gloves
Type VI - Deerskin, full grain for gloves
Type VII - Horsehide, full grain for gloves
Type VIII - Cattlehide, flesh splits for gloves

1.2.2 Classes. The following classes only apply to Types I thru IV.

Class 1 - Mold resistant treated
Class 2 - Not mold resistant treated

Comments, suggestions, or questions on this document should be addressed to: Attn: DLA Troop Support Standardization Team, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, you may want to verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil/.

AMSC N/A FSC 8330

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation or contract.

ENVIRONMENTAL PROTECTION AGENCY (EPA)

Federal Insecticide, Fungicide and Rodenticide (FIFRA)
(40 CFR part 162 State Registration of Pesticides Products)

Federal Insecticide, Fungicide and Rodenticide (FIFRA)
as amended by the Food Quality Protection Act of 1996 and the Pesticide Registration Improvement Act of 2003

(Copies of these documents are available online at https://www.epa.gov/pesticides.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

AATCC EP8 - Evaluation Procedure for AATCC 9-Step Chromatic Transference Scale
AATCC EP9 - Evaluation Procedure for Visual Assessment of Color Difference of Textiles

(Copies of this document are available on line at https:/aatcc.org.)

AMERICAN SOCIETY FOR QUALITY (ASQ)

ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available online at https://asq.org.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

ASTM INTERNATIONAL

ASTM D1813	- Standard Test Method for Measuring Thickness of Leather Test Specimens
ASTM D2211	- Standard Test Method for Elongation of Leather
ASTM D2617	- Standard Test Method for Total Ash in Leather
ASTM D2807	- Standard Test Method for Chromic Oxide in Leather (Perchloric Acid Oxidation)
ASTM D2810	- Standard Test Method for pH of Leather
ASTM D2813	- Standard Practice for Sampling Leather for Physical and Chemical Tests
ASTM D2821	- Standard Test Method for Measuring the Relative Stiffness of Leather by Means of a Torsional Wire Apparatus
ASTM D3495	- Standard Test Method for Hexane Extraction of Leather
ASTM D3884	- Standard Guide for Abrasion Resistance of Textile Fabric (Rotary Platform, Double-head Method
ASTM D4705	- Standard Test Method for Stitch Tear Strength, Double Hole
ASTM D5053	- Standard Test Method for Colorfastness of Crocking of Leather
ASTM D6012	- Standard Test Method for Determination of Resistance of Leather to (Bleeding) Color Stain Transfer
ASTM D6075	- Standard Test Method for Cracking Resistance of Leather
ASTM D6076	- Standard Test Method for Shrinkage Temperature of Leather
ASTM D6116	- Standard Test Method for Blocking
ASTM D6182	- Standard Test Method for Flexibility and Adhesion of Finish on Leather

(Copies of these documents are available online at https://www.astm.org.)

INFORMA HEALTHCARE

Repeat Insult Patch Test - Modified Draize Procedure –
Principles and Methods of Toxicology, A Wallace Hayes (editor).

(Copies of this document are available online at https://www.crcpress.com.)

INTERNATIONAL ORGANIZATION for STANDARDIZATION (ISO)

ISO 13365-1 - Leather – Chemical Determination of the Preservative (TCMTB, PCMC, OPP, OIT) Content in Leather by Liquid Chromatography Part 1 – Acetonitrile Extraction Method

(Copies of this document are available online at https://www.iso.org.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations, unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.2 Recycled, recovered, or environmentally preferable or biobased materials. Recycled, recovered, or environmentally preferable, or biobased materials should be used to the maximum extent possible, provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

3.3 Materials.

3.3.1 Types I, II and III. The leather shall be full grain cattlehide, deerskin or horsehide as required for the type specified (see 1.2 and 6.2) and shall be suitable for the use in garments and equipage. The flesh side of the leathers shall be smooth and free of loose flesh. When deerskin is specified, only skins from North America whitetailed or blacktailed (mule) deer shall be used.

3.3.2 Type IV. The leather shall be flesh splits obtained from cattlehide bends. The leather shall be suitable for use in garments and equipage. Both sides of the leather shall be smooth and free of loose flesh. Middle splits, head splits, belly splits and shall splits shall not be used.

3.3.3 Types V, VI and VII. The leather shall be full grain cattlehide, deerskin or horsehide as required for the type specified (see 1.2 and 6.2) and shall be suitable for the use in gloves. The flesh side of the leathers shall be smooth and free of loose flesh. When deerskin is specified, only skins from North America whitetailed or blacktailed (mule) deer shall be used.

3.3.4 Type VIII. The leather shall be flesh splits obtained from cattlehide bends. The leather shall be suitable for use in gloves. Both sides of the leather shall be smooth and free of loose flesh. Middle splits, head splits, belly splits and shoulder splits shall not be used.

3.4 Tannage. The leather shall be chrome tanned.

3.5 Color. The color of the leather shall be as specified in (see 6.2). Both sides of the leather shall be the same color. Slight color variations on the flesh side resulting from buffing or shaving the leather shall be permitted.

3.5.1 Dyeing. The leather shall be drum dyed. The dye shall penetrate from the flesh side to the underside of the skin. The color of the leather shall be a good match to the shade of the leather called out in the contract before application of the finish (see 3.7).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

3.6 Finish. The grain side of Types I, II and III leather shall have a light application of finish and dye containing only sufficient pigment to assist in making the color uniform, and shall be a good match to the specified shade. No finish shall be applied to Types IV, V, VI, VII and VIII leather.

3.6.1 Finish stability (Types I, II and III). The finish shall not crack, flake, part from the leather, be free from surface adhesion (blocking) when tested as specified in 4.5.

3.7 Physical requirements. The finished leather shall conform to the physical and chemical requirements listed below in Table I, when tested as specified in 4.5. The thickness of the leather shall be as specified (see 6.2). A thickness tolerance of (± 1/2) ounce (1 ounce = 1/64 inch) is permitted when tested as specified in 4.5.

THIS SPACE IS INTENTIONALLY LEFT BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

TABLE I. Physical and chemical requirements.

Characteristic	Requirement							
	Type I	Type II	Type III	Type IV	Type V	Type VI	Type VII	Type VIII
Resistance to staining (bleeding) (min.)	4.0	4.0	4.0	-	-	-	-	-
Colorfastness to crocking (min.):								
Dry	4.0	4.0	4.0	-	4.0	4.0	4.0	-
Wet	3.5	3.5	3.5	-	3.5	3.5	3.5	-
Cracking, low temperature	No cracking or parting of the grain surface or finish from the leather	No cracking or parting of the grain surface or finish from the leather	No cracking or parting of the grain surface or finish from the leather	-	-	-	-	-
Shrinkage temperature (Celsius) (min.)	≥ 97	≥ 92	≥ 97	≥ 97	≥ 97	≥ 92	≥ 97	≥ 97
Hexane soluble material, percent (max.) 1/	25	25	25	25	25	25	25	25
Total ash, percent (max.) 1/	9.0	9.0	9.0	12.0	9.0	9.0	9.0	12.0
Chromic oxide, percent (min.) 1/	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
pH (min.)	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3

1/ Calculated on a moisture-free basis.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

3.7.1 Elongation. At least 80 percent of the specimens tested shall meet the elongation values at a load of 25 pounds as specified in Table II when tested as specified in 4.5.

TABLE II. Elongation.

Types	Elongation percent	
	Minimum	Maximum
I, II, III, IV	25.0	60.0
V, VI,VII,VIII	25.0	-------

3.7.2 Stitch tearing strength. At least 80 percent of the specimens tested shall meet the stitch tearing strength values specified in Table III when tested as specified in 4.5.

TABLE III. Stitch tearing strength.

Types	Thickness of Leather (ounces)	Stitch Tearing Strength pounds, (minimum)
I, IV, V, VIII	2 ½ and less	17.0
	Over 2 1/2	30.0
II, VI	2 and less	15.0
	Over 2	20.0
III, VII	2 ½ and less	20.0
	Over 2 1/2	30.0

3.7.3 Stiffness. At least 80 percent of the specimens tested shall have stiffness values as specified in Table IV when tested as specified in 4.5.

TABLE IV. Stiffness.

Types	Thickness of Leather (ounces)	Stiffness value before soaking (degrees, maximum)	Stiffness value after soaking (degrees maximum)
V, VII	2 1/2 or less	116	132
	Over 2 1/2	260	320
VI	2 or less	60	1/
	Over 2	90	1/
VIII	Over 2	260	320

1/ Type VI leather shall not be tested for stiffness after soaking.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

3.7.4 Trim (form and area). Types I and V cattlehide leather shall be furnished in the form of whole hides or sides. Types II and VI deerskin leather shall be furnished in the form of whole skins. Types III and VII horsehide shall be furnished in the form of horsehide fronts. Types IV and VIII cattlehide flesh splits shall be furnished in the form of bends. The area of the leather in terms of square feet shall be legibly marked on the butt end of the flesh side.

3.8 Fungicide (mold resistance), Class 1 only. Unless otherwise specified (see 6.2), the leather shall be treated with one of the following fungicides to provide mold resistance. The fungicides to treat the leather shall be an EPA registered product that complies with the Federal Insecticide, Fungicide and Rodenticide Act (FIFRA) (see 2.2.2).

3.8.1 2-(Thiocyanomethylthio) bensothiazole (TCMTB). The leather shall contain not less than 100 ppm and not more than 400 ppm of active ingredient TCMTB when tested as specified in 4.5.

3.8.2 *Ortho*-phenyl phenol (OPP). The leather shall not contain no less than 540 ppm and not more than 2580 ppm of active ingredient OPP when tested as specified in 4.5

3.8.3 Diiodomethyl-*para*-tolylsulfone (DIMPTS). The leather shall contain no less than 300 ppm or more than 2000 ppm of active ingredient DIMPTS when tested as specified in 4.5.

3.9 Toxicity. The finished leather skin shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 4.5. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used.

3.10 Workmanship. The finished leather shall be uniform in quality and shall conform to the quality of product established on this specification. The occurrence of defects as specified in 4.3 and 4.4 shall not exceed the quality acceptance levels as specified in the contract or purchase order.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2).
b. Conformance inspection (see 4.3).

4.2 First article inspection. A first article, submitted in accordance with 3.1, shall be inspected, examined for appearance and finished defects listed in 4.4 and tested for the characteristics as specified in 4.5 and 4.6.

4.3 Conformance inspection. Conformance inspection shall include the visual examination of 4.4 and the tests of 4.5 through 4.6 as applicable. Sampling for inspection shall be performed in accordance with ASQ/ANSI Z1.4 and with acceptance quality limits

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

(AQLs) as specified in the contract and/or order, except where otherwise indicated (see 6.2).

4.3.1 Inspection conditions. Unless otherwise specified in this specification or applicable procurement documents (see 6.2), all inspections shall be performed in accordance with this specification and all the requirements of referenced documents.

4.4 Visual examination of the end item. The leather for each type shall be examined and defects shall be classified as stated in Table V. The sample unit for these examinations shall be one (1) hide, side, skin, front or bend as required for each type specified. The contract or purchase order shall identify the number of samples required for thickness for acceptance and rejection of the leather skins. Separate examinations shall be performed for visual and the thickness, but the same sample may be used for each examination.

TABLE V. Visual examination defects.

Examination	Defect 1/
Leather Type I, II, III, V, VI, VII	Not full grain
Type IV, VIII	Not flesh splits
Trim Type I, V	Not in a form of a whole hide or side
Type II, VI	Not in the form of a whole skin
Type III, VII	Not in the form of a front
Type IV, VIII	Not in a form of a bend
Color (all types)	Not the same color on both sides Not uniform
Dyeing (all types)	Not drum dyed
Finish Type I, II, III	Finish missing on grain side
All Types	Streaky, flaky, cracked or tacky Extremely pigmented, shiny appearance
Type IV, V, VI, VII, VIII	Any application of finish

THIS SPACE IS INTENTIONALLY LEFT BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

TABLE V. Visual examination defects. - Continued

Examination	Defect 1/
Quality of leather	Not clean; stain or other foreign matter Coarse loose fiber on flesh side Not soft and pliable, hard bony, boardy or loose, or loose spongy leather Any cut, hole brand, hip, mark, scratch
	Heavy vein, deep wrinkle, or surface imperfections which individually or collectively impair the cutting value of more than 12 percent of the total area of the side, whole side, skin, front or bend
Area (expressed in terms of square feet)	Not as marked on leather
Marking	Omitted, not readable

1/ Light, well healed scratches and grub holes, light fat wrinkles, and slight stains shall not be classified as defects.

4.5 End item testing. The finished leather shall be tested for the characteristics as specified in Table VI. The methods of testing as specified wherever applicable and as listed in Table VI shall be followed. The sampling location from which the sample unit is to be obtained shall be in accordance with ASTM D2813. The area of leather from which the pieces are obtained for preparing the test specimens shall be expanded to 12 inches by 12 inches. Fifteen units of product shall be selected at random from each lot for the purpose of testing. For lots consisting of less than 15 units of product, each unit shall be sampled for testing. The sample(s) required for testing the lot for physical and chemical characteristics shall be selected from the samples for visual or dimensional thickness examination. The pieces shall be marked to indicate the side that is parallel to the backbone and to indicate the root of the tail. All test reports shall contain the individual values utilized in expressing the final result. The lot shall be rejected if any of the following conditions exists:

a. More than three (3) failures occur for elongation,
b. More than three (3) specimens fail to meet stitch tearing strength requirements
c. More than three (3) specimens fail to meet stiffness requirements
d. One (1) or more specimens fail to meet any of the remaining requirements applicable to the sample unit.
e. Any composite fails to meet the specified requirement.

THIS SPACE IS INTENTIONALLY LEFT BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

TABLE VI. End item tests.

Characteristic	Requirement Reference	Test Method	Requirement	
			Sample unit	Composite sample
Material	See 3.3	Visual (see 6.4)		-
Tannage	See 3.4	Visual (see 6.4)		-
Color	See 3.5	4.6.1, 4.6.1.1		-
Dyeing	See 3.5.1	ASTM D3884 See 4.6.1.1		-
Finish stability (Types I, II, III)	See 3.6.1	See 4.6.2 or ASTM D6182 1/	X	-
Blocking	3.6.1	ASTM D6116	X	-
Thickness	See 3.7	ASTM D1813	X	-
Staining (Types I, II, III)	Table I	ASTM D6012 2/	X	-
Colorfastness to crocking (Types I, II, III, V, VI, VII)	Table I	ASTM D5053 2/	X	-
Cracking, low temperature (Types I, II, III)	Table I	ASTM D6075, 3/ and 4.6.3	X	-
Shrinkage temperature	Table I	ASTM D6076	X	-
Hexane-soluble material	Table I	ASTM D3495	-	X
Total ash	Table I	ASTM D2617	-	X
pH	Table I	ASTM D2810	-	X
Chromic oxide	Table I	ASTM D2807	-	X
Elongation	Table II	ASTM D2211	X	-
Stitch tear strength	Table III	ASTM D4705	X	-
Stiffness (Types V, VI, VII, VIII)	Table IV	ASTM D2821 and 4.6.4	X	-
Fungicide (Class 1)	See 3.8	ISO 13365-1 4/	-	X
Toxicity	See 3.9	See 4.7	-	X

1/ Exception to ASTM D6182: the grain surface of the folded specimen shall be rubbed together under moderate pressure. The duration of the rubbing shall be 30 seconds.
2/ Evaluated using AATCC EP8.
3/ The diameter of the mandrels shall be 1/8 inch.
4/ When testing DIMPTS, use an HPLC analytical standard to measure the concentration of DIMPTS in accordance with ISO 13365-1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

4.6 Methods of testing and inspection.

4.6.1 Visual shade examination. The finished leather shall match the standard sample when viewed using the AATCC EP9, Evaluation Procedure for Visual Assessment of Color Difference of Textiles, Option C, with sources simulating artificial daylight D_{75} illuminant with a color temperature of 7500 (± 200) K illumination of 100 (± 20) foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2856 (± 200) K.

4.6.1.1 Dyeing. The leather shall be examined to verify the color is a good match to the shade standard prior to application of the finish. The sample shall be prepared by abrading the top finish off the leather sample using a rotary platform double head abrader as specified in ASTM D3884. The abrader shall be cycled until the leather under the finish is visible, approximately 500 cycles. The color under the finish shall be compared to the standard sample using the procedure for shade matching and shall be a good match. Five (5) samples shall be examined.

4.6.2 Finish Stability. One (1) 4 by 1-inches test specimen shall be used. The test specimen shall be placed in a circulating air oven set at 110ºF (± 5ºF) for a period of 24 hours. After 24 hours, remove the specimen from the oven and place in desiccator at room temperature containing calcium chloride for 2 hours. After removing from desiccator, fold the specimen sharply by hand at an 180º angle with the finish side on the inside of the bend, pressing tightly together with the fingers and rolling back and forth for three (3) complete cycles. The bend shall be visually examined and the presence of finish cracking, flaking and looseness or parting of finish from the leather shall be reported.

4.6.3 Cracking, low temperature (Types I, II and III). The leather shall be tested for cracking in accordance with ASTM D6075 except that the specimen size shall be 4 by 1-inches rectangle of leather. The specimen shall be folded twice upon itself by folding the specimen along the length dimension with the flesh side in and then folding again at right angles to the original fold. The specimen shall be observed with the naked eye and the presence of cracking or parting of the finish from the leather shall be reported.

4.6.4 Measurement of stiffness (before and after soaking).

4.6.4.1 Stiffness after soaking (Types V, VI, VII and VIII). Any individual specimen exceeding the maximum stiffness values specified before soaking shall not be tested for stiffness after soaking.

The specimens shall be immersed in 1000 milliliters of distilled water at 140º (± 5ºF) (60º ± 3º C) for 20 (± 2) hours. Complete immersion of the specimens shall be accomplished by placing a floating cover on the vessel used for immersion of the specimens. After the required immersion period, the specimens shall be removed from the water and reconditioned in accordance with standard atmospheric conditions as specified in the test method. The reconditioned specimens shall be placed flesh side down on a ruler graduated in decimal inches and the distance between the benchmarks shall be measured to the nearest 0.05 inch. If the distance is 3.4 to 3.6 inches, test the specimen in accordance with ASTM D2821. If the distance is 3.2 inches or less, the specimen shall be reported as a test failure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

If the distance between benchmarks is 3.25 to 3.35 inches, the specimen shall be stretched before testing. To stretch the specimen, place the specimen on the ruler and align line one of the benchmarks with a division line on the rule. Hold the specimen against the ruler by placing the fingertip of one hand on the aligned benchmark. With the thumb and index finger of the other hand, lightly grip the specimen near the aligned benchmark, then slide the finger and thumb along the specimen to the other benchmark while exerting pressure on the specimen that is sufficient to obtain the required distance between the benchmarks. If the required distance between the benchmarks has been obtained (3.4 to 3.6 inches), test the specimens in accordance with ASTM D2821. If the distance between the benchmarks is greater than 3.6 inches discard the specimen and test a new specimen selected from the same sample of leather from which the discarded specimen was obtained. The new specimen shall be tested for stiffness before and after soaking. The test results obtained when the discarded specimen was tested for stiffness before soaking shall not be reported.

4.7 Toxicity test. Unless otherwise specified (see 6.2), an acute dermal irritation study and a skin sensitization study shall be conducted. When the results of the studies indicate the end item is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure (see 2.3). If the toxicity requirement (see 3.9) can be demonstrated with historical use data, toxicity testing may not be required (see 6.2).

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Department or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The leather is intended for use in gloves, garments, mittens and equipage.

THIS SPACE IS INTENTIONALLY LEFT BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification
b. Type and class required (see 1.2)
c. The specific issue of individual documents referenced
d. When first article is required (see 3.1)
e. Color when other than natural color is required (see 3.5)
f. Thickness required (see Table I)
g. When toxicity is required (see 3.9)
h. Conformance inspection (see 4.3)
i. Inspection conditions (see 4.3.1)
j. Packaging (see 5.1)

6.3 Standard sample. For access to information such as standard shade samples contact the Defense Supply Center Philadelphia's website for their Specification/Pattern/Drawing Request form, at https://www.dla.mil/TroopSupport/ClothingandTextiles/SpecRequest.aspx. Complete the request form and then submit. Requests to use equivalent materials should be sent to the contracting officer for approval by the military services.

6.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

6.5 Subject term (key word) listing.

Flesh
Full grain
Fungicide
Mold resistant
Splits

6.6 Changes from previous issue. Marginal notations are not used on this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army - GL
Navy - AS

Preparing Activity:
DLA-CT

Review activities:
Army - MD
Navy - NU

(Project 8330-2021-002)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:40Z
Check the source to verify that this is the current version before use.