P-C-420a
December 1, 1965
SUPERSEDING
Int. Fed. Spec. P-C-00420 (Army-GL)
January 13, 1965

FEDERAL SPECIFICATION

CLEANING COMPOUND, AUTOMOBILE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 This specification covers one type and grade of liquid automobile cleaner (see 6.1).

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

Federal Specification:

PPP-C-96—Cans, Metal, 28 Gage and Lighter.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 141—Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Federal Hazardous Substances Labeling Act.

(Application for copies should be addressed to the U. S. Department of Health, Education, and Welfare, Food and Drug Administration, Washington, D. C., 20203.)

American Society for Testing and Materials (ASTM) Designation:

D1310-63—Method of Test for Flash Point of Volatile Flammable Materials by Tag Open-Cup Apparatus.

E70-52T—Method of Test for pH of

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

Aqueous Solutions with the Glass Electrode.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa., 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials. The materials used in the automobile cleaner shall include petroleum distillates, mild abrasives, an emulsifying agent and water in such proportions as to conform to the requirements of this specification.

3.2 Chemical and physical requirements. The cleaner shall conform to the requirements specified in table I when tested as specified in 4.3.2.

TABLE I. *Chemical and physical requirements*

Requirement	Minimum	Maximum
Nonvolatile matter, percent	15.0	40.0
Abrasive content (expressed as percent ash)	10.0	20.0
Steam distillates, percent ...	2.5	45.0
pH value	5.0	9.6
Flash point (Tag open cup)	140°F.	—

3.3 Stability. The cleaner shall show not more than 5 percent separation upon standing and shall not separate into more than two layers when tested as specified in 4.3.2. The cleaner shall be a uniform dispersion after moderate shaking.

3.4 Performance.

3.4.1 *Gloss increase.* The cleaner shall increase the gloss of prepared lacquered and enameled panels (low-gloss panels) by not less than 20 gloss units when tested as specified in 4.3.2.

3.4.2 *Abrasiveness.* The cleaner shall not cause a decrease in gloss in excess of 30 percent of that obtained by the use of the standard abrasive material when tested as specified in 4.3.2.

3.5 Labeling. The labeling shall comply with the provisions of the Federal Hazardous Substances Labeling Act. Each unit container shall be durably and legibly marked as follows:

"CLEANING COMPOUND,
AUTOMOBILE
(Stock Number)

DIRECTIONS FOR USE

1. If finish is gritty, wash car first.
2. Shake cleaner well before using.
3. Saturate with cleaner a soft clean dampened cloth folded into a pad and apply to a section at a time using a circular motion with enough pressure to loosen all dirt.
4. Let film of cleaner dry on car and wipe off dried cleaner with a soft, clean cloth.
5. Repeat application for badly oxidized finishes.

Do not use in sun or on hot surfaces.
Contract Number
(Unit Quantity)
Date Packed"

3.6 Workmanship. The cleaner shall be uniform in appearance and free from foreign matter.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:47Z
Check this source to verify that this is the current version before use.

4.2.1 *Component and material inspection.* In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.3 Inspection of the end item.

4.3.1 *Examination of the end item.* The end item shall be examined for the defects in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) set forth in 4.3.1.4. The lot size shall be expressed in unit containers of the specified capacity for the examinations in 4.3.1.1 and 4.3.1.2 and in units of shipping containers for the examinations in 4.3.1.3.

4.3.1.1 *Examination of the end item for visual defects.* The sample unit for this examination shall be one filled unit container.

Examine	Defect
ıtainer	Not in accordance with contract requirements. Not specified size, type, or class container. Inner seal and exterior coating not as required. Any evidence of seepage or leakage from any part of the container including closure and seams. Bulged or distorted container.
Labeling	Not as specified, missing, incomplete, illegible or smeared.
Appearance of cleaner	Not uniform in appearance. Presence of foreign matter.

4.3.1.2 *Examination of the end item for net contents.* The sample unit for this examination shall be one filled unit container. The lot shall be unacceptable if the average net content is less than the specified or indicated quantity.

4.3.1.3 *Examination of preparation for delivery.* An examination shall be made to determine that interior packaging, packing, and marking comply with the requirements of this specification. The sample unit for this examination shall be one shipping container, fully packed, selected just prior to the closing operation. Closed shipping containers, fully prepared for delivery shall be examined for closure defects.

Examine	Defect
Interior packaging	Unit package not packaged as specified. Components or materials not as specified. Closure of interior package not as specified.
Packing	Not in accordance with contract requirements. Number of interior packages per shipping container not as specified. Container not as specified, closures not accomplished by specified or required methods or materials. Inadequate application of components such as: incomplete closure of container flaps, loose or inadequate strapping or stapling.
Marking (exterior and interior)	Omitted, illegible, incorrect, incomplete, or not in accordance with contract requirements.

4.3.1.4 *Inspection levels and AQLs for examinations.* The inspection levels, for determining the sample size, and AQLs, expressed in defects per 100 units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	I	2.5
4.3.1.2	S-4	—
4.3.1.3	S-2	2.5

4.3.2 *Testing of the end item.* The methods of testing listed in table II shall be followed for each lot. The lot size shall be expressed in gallons of automobile cleaner. Each lot shall consist of units of product of a single composition manufactured under essentially the same conditions, and at essentially the same time. The sample unit for testing shall be a one quart composite obtained by thoroughly mixing equal portions from samples selected at random through-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

out the lot in the frequency indicated below. The composite shall be placed in a clean, dry, sealed quart container. Care shall be exercised to prevent contamination or alteration of the composite during the sampling, weighing, and storage. All test reports shall contain the individual values utilized in expressing the final results. The lot shall be unacceptable if the composite fails to meet any test requirement specified.

Lot size (gallons)	Sample frequency
800 or less	2
801 up to and including 22,000	3
22,001 or more	5

TABLE II. *Instructions for testing of end item*

Characteristic	Specification reference		Requirements applicable to composite sample	Number determinations	Results reported as
	Requirement	Test method			
Nonvolatile matter, percent	Table I	4.4.1	X	2	Average of 2 determinations, to nearest 0.1 percent.
Abrasive content (expressed as percent ash)	Table I	4.4.2	X	2	Average of 2 determinations, to nearest 0.1 percent.
Steam distillate, percent	Table I	4.4.3	X	2	Average of 2 determinations, to nearest 0.1 percent.
pH value	Table I	4.4.4	X	1	Nearest 0.1 pH unit.
Flash point (Tag open cup)	Table I	4.4.5	X	2	Average of 2 determinations, to nearest 1°F.
Stability	3.3	4.4.6	X	1	Pass or fail.
Gloss increase:					
Lacquered panels	3.4.1	4.4.7	X	4	Average of 4 determinations, to nearest gloss unit.
Enameled panels	3.4.1	4.4.7	X	4	Average of 4 determinations, to nearest gloss unit.
Abrasiveness:					
Lacquered panels	3.4.2	4.4.8	X	4	Average of 4 determinations, to nearest 1 percent.
Enameled panels	3.4.2	4.4.8	X	4	Average of 4 determinations, to nearest 1 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

4.4 Test procedure.

4.4.1 *Nonvolatile matter.* Weigh 10.00 ± 0.01 grams (g.) of cleaner into a tared flat-bottom dish approximately 8 cm. in diameter provided with a tightly fitted cover. Remove the cover and place sample over a steam bath, for a minimum of 2 hours, until the bulk of volatile matter has evaporated, and then place in a forced draft, vented oven maintained at 105° ± 2° C. for 4 hours. Cool in a desiccator, replace cover, and weigh residue. Calculate percent nonvolatile matter as follows:

$$\text{Percent of nonvolatile matter} = \frac{\text{weight of residue} \times 100}{\text{weight of sample}}$$

4.4.2 *Abrasive content.* The abrasive content shall be determined in accordance with method 5262 of Fed. Test Method Std. No. 141. The percent ash shall be taken as the abrasive content of the cleaner.

4.4.3 *Steam distillate content.* Determine the steam distillate content of a 100 g. sample of cleaner in accordance with the procedure in method 4352 of Fed Test Method Std. No. 141. Draw off the separated, clear distillate layer from the separatory funnel into a tared weighing bottle. Calculate percent distillate as follows:

$$\text{Percent steam distillate} = \frac{\text{weight of distillate} \times 100}{\text{weight of sample}}$$

4.4.4 *pH value.* Determine the pH of the undiluted cleaner at 25° ± 1° C. using a pH meter in accordance with ASTM E70-52T.

4.4.5 *Flash point.* The flash point (Tag open cup) shall be determined in accordance with ASTM D1310-63.

4.4.6 *Stability.* One hundred ml. of cleaner shall be placed in a 100-milliliter (ml.) ground glass-stoppered graduate. The graduate shall be stoppered and left undisturbed at a temperature of 68° to 80° F. for 24 hours. The emulsion shall not break into more than two layers. The upper layer separation shall not exceed a volume of 5 ml. The cleaner shall then be moderately shaken and allowed to stand for 10 minutes. At the end of this time, there shall be no visible separation. The sample of cleaner shall then be subjected to three successive cycles, each cycle consisting of 24 hours at 10° ± 1° F. followed by complete thawing at room temperature and thorough shaking. The cleaner shall then be allowed to stand for 1 hour, at the end of which time the upper layer separation shall not exceed 5 ml. and the cleaner shall not separate into more than two layers.

4.4.7 *Gloss increase.* Four low gloss lacquer test panels and four low gloss enamel test panels, prepared as specified in 4.5 shall be cleaned with the test cleaner as specified in 4.4.7.1 and the gloss of the cleaned test panels determined as specified in 4.4.7.2. The increase in gloss shall be the difference between the gloss of the low gloss test panel (4.5.3.5) and the gloss of this panel after cleaning.

4.4.7.1 *Procedure for cleaning panels.* Place a test panel in the cleaning and abrasion apparatus (4.5.2.1) in a position so that the length of the panel is parallel to the motion of the cleaning head which shall pass over the entire panel surface. Place metal or other suitable panels of equal thickness on both ends of the test panel to hold it in place and provide a level surface for the cleaning head to travel. Apply 5 ml. of cleaner to the wool cloth cleaning head and with finger distribute the cleaner evenly over the 3-1/2- by 2-inch area and clean panel for 50 oscillations (100 strokes). Apply 5 ml. more cleaner to the wool cloth as before and clean panel for an additional 50 oscillations (100 strokes). Carefully remove cleaner from test panel by washing in a warm detergent and water solution and rinse in distilled water. The panel shall then be dried in an oven.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

4.4.7.2 *Procedure for determining gloss.* The specular gloss shall be determined in accordance with method 6101 of Fed. Test Method Std. No. 141 using a Gardner 60° Glossmeter or equivalent. The 60° specular gloss readings shall be taken along the lengthwise axis of the panel. A minimum of three readings shall be taken on each panel to determine the average gloss value of the panel. All readings shall be within 2 gloss units of the average gloss for the panel.

4.4.8 *Abrasiveness.* Four high gloss lacquer test panels and four high gloss enamel test panels, prepared as specified in 4.5, shall be cleaned with the test cleaner as specified in 4.4.7.1, and the gloss of the cleaned test panels determined as specified in 4.4.7.2. The decrease in gloss shall be the difference between the gloss of the high gloss test panels (4.5.3.4) and the gloss of the high gloss test panels after cleaning. Four high gloss lacquer and four high gloss enamel test panels shall be cleaned (4.4.7.1) with a uniform mixture consisting of 4 g. of standard abrasive (4.5.1.6) and 50 g. of oil (4.5.1.7) and the gloss determined (4.4.7.2). The decrease in gloss due to the standard abrasive-oil mixture shall be determined as with the cleaner. Abrasiveness of the cleaner shall be calculated as follows:

$$\text{Percent decrease in gloss} = \frac{\text{Gloss decrease due to cleaner} \times 100}{\text{Gloss decrease due to standard abrasive-oil mixture}}$$

4.5 Preparation of standard test panels.

4.5.1 *Materials.*

4.5.1.1 *Steel panels.* The test panels (see 6.4.1) shall be rust-free cold rolled steel, measuring 0.032 by 3 by 6 inches, ground flat and even on one side and having received a phosphate coating in accordance with method 2011 of Fed. Test Method Std. No. 141 or equivalent.

4.5.1.2 *Lacquer and enamel primer.* The primer shall be an automotive-type primer suitable for use with either lacquer or enamel finishes.

4.5.1.3 *Lacquer.* An automotive typ black, acrylic lacquer such as DuPont No. 88-L Black Lucite Acrylic lacquer or equivalent.

4.5.1.4 *Enamel.* The automotive-type, black, fast drying enamel such as Ditzler Jet Black Enamel, DQE-9000 (Fast Drying) or equivalent (see 6.4.2).

4.5.1.5 *Iron oxide, red.* Jeweler's rouge, commercial grade.

4.5.1.6 *Standard abrasive.* The standard abrasive for test purposes shall consist of Cellite 110, or equal (see 6.4.3). The abrasive shall have the following properties:

Condition	uniform, fluffy powder
Composition	essentially SiO_2
Grit	none
Porosity	65 to 85 percent
Particle size (sedimentation method)	4 to 20 micron
Refractive index	1.45 to 1.4
Retained on a No. 325 screen	15 percent (maximum)

4.5.1.7 *Oil.* Light white mineral oil, light liquid paraffin, NF., viscosity 125/135, or equivalent.

4.5.1.8 *Wool cloth.* A 100 percent worsted wool flannel with approximately 48 ends, 44 picks per inch, 2/42 worsted 64/70s both warp and filling, weighing 5 to 6 ounces per square yard (see 6.4.4).

4.5.2 *Apparatus.*

4.5.2.1 *Cleaning and abrasion apparatus.* The cleaning and abrasion apparatus shall consist essentially of an electric motor mounted on a flat metal plate, and a mechanism through which the motor imparts a reciprocating motion to a wool cloth cleaning head lengthwise across a test panel positioned on a platform situated above th mechanism (see 6.4.5). The power is transmitted from the motor to a driving arm by means of a belt, pulley, and gear reduction box. A flexible wire, guided by a pulley

Source: https://assist.dla.mil - Downloaded: 2026-02-25T04:14:57
Check the source to verify that this is the current version before use.

at each end of the platform, runs from the head. Tension on the wire is just sufficient to take up any slack. The cleaning head with the wool cloth is reciprocated through a distance of 13 inches in a straight path over the length of the test panel at approximately 37 oscillations (74 strokes) per minute.

4.5.2.1.1 *Cleaning head.* The cleaning head shall consist of a metal block and a wool cloth. The metal block shall have a rectangular base approximately 3-1/2 inches long and 2 inches wide (see 6.4.5 abrasion boat). A double thickness of the wool cloth shall be secured to the base of the metal block by means of clamps (12- by 2-inch piece folded to measure 6- by 2-inch). (The total weight of the metal block and wool cloth shall be 1.00 ± 0.05 pound.)

4.5.2.2 *Glossmeter.* Gardner 60° glossmeter or equivalent with an accuracy of ± 2 gloss units (see 6.4.6).

4.5.3 *Procedure.*

4.5.3.1 *Surface preparation.* A minimum of 24 steel panels (4.5.1.1) shall be vapor degreased or solvent-cleaned to remove all oil, grease, and fingerprints.

4.5.3.2 *Application of lacquer.* The ground side of 12 steel panels (4.5.1.1) shall be spray coated with a primer (4.5.1.2) applying a minimum of two medium wet coats. Air dry the panels a minimum of 2 hours and lightly wet sand to smooth finish using 400 grit sand paper after each primer application. Then apply to each panel at least 3 medium wet coats of automotive-type black lacquer (4.5.1.3). Air dry the panels a minimum of 2 hours and lightly wet sand to smooth finish using 400 grit sand paper between coats of lacquer. Allow the finished panels to air dry for a minimum of 7 days, then bake in a forced-draft oven maintained at 250° ± 5° F. for 2 hours, prior to use.

4.5.3.3 *Application of enamel.* Twelve steel panels (4.5.1.1) shall be spray coated with a primer (4.5.1.2) and automotive-type black enamel (4.5.1.4) in the manner specified in 4.5.3.2. Age and bake the finished panels as specified in 4.5.3.2.

4.5.3.4 *Preparation of high gloss lacquered and enameled test panels.* Eight lacquered panels and eight enameled panels shall be uniformly rubbed with a fine abrasive such as red iron oxide powder to obtain panels with a gloss of 85-90 gloss units. The abrasive material shall be thoroughly removed by washing the panels with detergent and water and by rinsing in distilled water. The panels shall then be dried in an oven. Gloss determinations shall be accurately made and recorded as specified in 4.4.7.2.

4.5.3.5 *Preparation of low gloss lacquered and enameled test panels.* Four lacquered panels and four enameled panels shall be uniformly rubbed with a mixture consisting of 4 g. of standard abrasive (4.5.1.6) and 50 g. of mineral oil (4.5.1.7) to obtain a gloss of 40 to 50 gloss units. Wash panels to remove abrasive as specified in 4.5.3.4 and accurately determine and record gloss as specified in 4.4.7.2.

5. PREPARATION FOR DELIVERY

For civil agency procurement, the definitions and application of levels of packaging and packing shall be in accordance with Fed. Std. No. 102.

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2), (civil agencies, see 6.3).

5.1.1 *Level A.* The cleaning compound shall be furnished in 1-pint oblong cans conforming to type V, class 4, with inner seal and exterior coating plan B of PPP-C-96, except that 0.25-pound electrolytic tinplate, ternplate, or blackplate shall not be used. The pint cans of cleaning compound shall be packaged in accordance with the interior packaging requirements of the appendix of PPP-C-96.

5.1.2 *Level C.* The cleaning compound shall be packaged in accordance with industry's practice.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.* Cleaning compound, packaged as specified in 5.1, shall be packed in accordance with the overseas shipment requirements in the appendix of PPP-C-96.

5.2.2 *Level B.* Cleaning compound, packaged as specified in 5.1, shall be packed in accordance with the domestic shipment requirements in the appendix of PPP-C-96.

5.2.3 *Level C.* Cleaning compound, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The automobile cleaner covered by this specification is intended for the cleaning (removal of dull oxidized paint, tar, and road film deposits) of lacquer and enamel automobile finishes prior to the application of an automobile paste wax.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Level B packaging (civil agencies). When level B packaging is specified for civil agency procurement, the requirements in 5.1.1 shall apply.

6.4 Testing materials and equipment.

6.4.1 *Test panels.* Q-Panels, 3- by 6-inch standard steel test panels may be obtained from the Q-Panel Company, 15610 Industrial Parkway, Cleveland 35, Ohio.

6.4.2 *Enamel.* Automotive-type enamel may be obtained from the Pittsburgh Plate Glass Co., Ditzler Color Division, 8000 West Chicago Avenue, Detroit 4, Mich.

6.4.3 *Cellite* 110. Cellite 110 may be obtained from Johns-Manville Company, 22 East 40th Street, New York 16, N. Y.

6.4.4 *Wool cloth.* Wool cloth, designated Style 503A, 100 percent worsted flannel, may be obtained from Testfabrics Inc., 55 Vandom Street, New York, N. Y., 10013.

6.4.5 *Cleaning and abrasion apparatus.* Washability Machine w/abrasion boat, Gardner Laboratories, Inc., Bethesda 14, Md.

6.4.6 *Glossmeter.* Glossmeter, 60°, Portable, Gardner Laboratories, Inc., Bethesda, 14, Md.

6.5 Transportation description. Transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Cleaning compounds, not otherwise indexed by name, liquid.
Carload minimum weight 24,000 pounds, subject to Rule 34, Uniform Freight Classification.

Motor:

Cleaning compounds, not otherwise indexed, liquid.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

Truckload maximum weight 24,000 pounds, subject to Rule 115, National Motor Freight Classification.

MILITARY CUSTODIANS:

Army—GL
Navy—SA
Air Force—69

Review activities:

Army—GL, MD
Navy—SA, YD
Air Force—69

User activity:

Navy—MC

Preparing activity:

Army—GL

Review and User information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing Of DOD Standardization Documents.

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.