P-W-155a
AUGUST 11, 1960
SUPERSEDING
Fed. Spec. P-W-155
August 27, 1954

FEDERAL SPECIFICATION

WAX, FLOOR, WATER-EMULSION, SLIP-RESISTANT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—Slip-resistant water-emulsion floor wax covered by this specification is intended for use on asphalt tile, rubber tile and linoleum and other floor surfaces. It should not be used on wooden floors unless the floor is properly sealed. The product is used without dilution. This product exhibits the optimum balance of all desirable wax properties, including slip-resistance and durability. The quality level is essentially based upon and controlled by standard samples (see 6.3). Slip-resistance of this product has been determined to be acceptable. Complete satisfaction from the product will be obtained with a possible exception on ramps and similar abnormal locations where the requirement for gaining additional slip-resistance may necessitate some sacrifice in durability (see 6.1).

1.2 Classification.

1.2.1 *Grade and concentrations.*—Water-emulsion floor wax covered by this specification shall be one grade, and two concentrations:

(a) 12 percent (12.0 to 12.5 percent solids)
(b) 16 percent (16.0 to 16.5 percent solids)

Note.—(a) is generally used in office space and on corridors with normal to light traffic, (b) where there is heavy traffic. However, (b) will provide proportional additional wear under all traffic conditions.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification.

Federal Specifications:

PPP–C–96—Cans, Metal, 28 Gage and Lighter.
PPP–D–729—Drums; Metal, 55-Gallon (For Shipment of Non-Corrosive Material).
PPP–D–760—Drums and Pails, Metal (5 and 16.64 Gallon).

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).
Fed. Std. No. 595—Colors.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, At-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

lanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standard:

MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. — The following publications of the issues in effect on date of invitation for bids, unless otherwise specified, form a part of this specification:

Uniform Freight Classification Rules.

(Copies may be obtained from the Uniform Freight Classification Committee, 1 Park Avenue, New York 16, N. Y.)

American Society For Testing Materials—Standards—Part 4:

ASTM Designation: E 70–52T — Method for Determination of the pH of Aqueous Solutions with the Glass Electrode (Tentative).

(Copies may be obtained from the American Society for Testing Materials, 1916 Race Street, Philadelphia, Pennsylvania).

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also widely distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Qualification. — Slip-resistant water-emulsion floor wax furnished under this specification shall be a product which has been tested and has passed the qualification tests specified herein (see 6.2).

3.2 Slip-resistance and durability. — The product shall be equal to or better than the standard samples with respect to slip-resistance and durability when tested in accordance with 4.4 (see 3.12, 6.3, 6.4).

3.3 Nonvolatile matter (total solids). — The nonvolatile content for concentration (a) shall be not less than 12.0 percent nor more than 12.5 percent and for concentration (b) not less than 16.0 percent nor more than 16.5 percent when tested in accordance with 4.3.1.

3.4 pH.—The pH of the water-emulsion floor wax shall be not greater than 10.0 when tested in accordance with 4.3.2.

3.5 Film characteristics. — The film produced by the product shall show no pronounced whiteness, shall have a smooth finish, and shall be clear and free from particles when tested in accordance with 4.3.3.

3.6 Sediment. — The amount of sediment present in the water-emulsion floor wax shall be not more than 0.1 percent by volume and shall be soft and free from grit when tested in accordance with 4.3.4.

3.7 Stability.—The product shall remain in the same fluid state as made, and shall show no creaming, gelling or separation for a period of nine months when stored under normal conditions in original unopened containers. In addition the product shall meet the above stability requirement when tested in accordance with 4.3.5.

3.8 Removability.—The dried film on the test panel shall be completely removed after 75 oscillations when tested in accordance with 4.3.6.

3.9 Water spotting.—The dried film shall show no separation from the surface of the test panel and only slight whitening after buffing when tested in accordance with 4.3.7.

3.10 Odor.—The product shall have no offensive odor nor shall it develop an offensive odor upon storage in the original, unopened container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

3.11 Workmanship.—Products under this specification shall be produced by the application of skillful and modern techniques, utilizing the proper blending of high-grade materials with suitable and adequate manufacturing facilities to effectively control the optimum balance of all desirable wax properties, as defined herein.

3.12 Standard samples. — Standard samples represent the quality acceptable for Government use with respect particularly to slip resistance and durability, and will serve as the reference standards for qualification and the examination of deliveries (see 6.3).

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling procedures.

4.1.1 *For inspection lots.*—For purpose of sampling, a lot shall consist of all wax of the same concentration offered for delivery at one time. Samples shall be protected from any possibility of freezing. All the tests in 4.3 and 4.4 shall be run on the samples for acceptance. The sample shall consist of 10- 1-gallon subdivisions of wax taken in accordance with 4.1.2.

4.1.2 *Method of sampling.*

(a) From 1-gallon original containers. Select at random 10- 1-gallon containers. Retain all, if no code marks are present. If cans or containers are coded, or production identified, retain all of the same mark and attempt to fill back with containers from the same production so that the sample will consist of 10- 1-gallon cans of the same code or mark.

(b) From original unopened 5-gallon drums. Select at random two drums (same identifying code, if possible). Make 5- 1-gallon representative subdivisions from one drum and retain the other drum.

(c) From original unopened 55-gallon drums. Select a drum at random. Make 10, 1-gallon representative subdivisions from the same drum.

4.1.3 *Identification and disposition.* — All subdivisions of the sample taken in accordance with 4.1.2 shall be properly identified including any code or batch numbers and numbered 1 to 10 inclusive (not applicable to the reserve 5-gallon drum). Subdivisions 1 to 5 inclusive shall be distributed as directed by the procuring agency or authorized representative. The remaining subdivisions shall be set aside and retained at the site of sampling pending further instructions.

4.1.4 *For qualification.*—The samples offered for qualification by the manufacturer shall be from production batches of the same size used in producing wax in commercial quantities. Small pilot plant and experimental formulations will not be considered as complying. The inspector shall take sufficient one-gallon cans for qualification (see 3.1). Each can shall be labeled as follows:

PERCENTAGE OF SOLIDS
DATE OF MANUFACTURE
CODE NUMBER (TO BE ENTERED BY INSPECTOR)
"KEEP FROM FREEZING" (CAN AND CONTAINER)

All tests in 4.3 and 4.4 shall be run on samples for qualification.

4.2 Inspection of deliveries.—Inspection shall be made on predetermined cycles by the procuring agency or a duly authorized representative at the time and place designated by the procuring agency (see 6.4).

4.3 Laboratory tests.—The following tests shall be made on one 1-gallon sample selected as specified in 4.1.2.

4.3.1 *Nonvolatile matter (total solids).*— Weigh to the nearest milligram approximately two grams of the sample, in duplicate, by using a weighing burette into tared, dried, flat bottom dishes of approximately six centi-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

meters in diameter. Place in a forced draft drying oven and heat at 105°-110°C. for 16 hours. Cool, weigh, and calculate results. Duplicate samples shall check within 0.1 percent and the average shall be within the concentration specified.

4.3.2 *pH value.*—Determine the pH value of the wax by means of a meter utilizing a glass electrode. The apparatus and procedure used shall be in accordance with ASTM Designation: E 70–52T.

4.3.3 *Film characteristics.*—Take a clear piece of glass plate approximately 3 inches by 5 inches long of a thickness not more than ¼ inch. Pour 50 milliliters of the sample over the surface, which is supported at an angle of 45° to the horizontal. Allow the sample to drain and dry in a nearly vertical position at a temperature of 23° ± 1°C. and a relative humidity of 50 ± 4 percent. Observe the film for signs of whiteness and smoothness. Observe the film through the underside of the glass plate for clearness and particles.

4.3.4 *Sediment.*—Measure 100 ml. of the well-mixed water-emulsion wax into each of two graduated ASTM pear-shaped or cone-shaped centrifuge tubes and stopper the tubes. Balance the two tubes in their holders. Place the two tubes on opposite sides of the head of the centrifuge and whirl for ten minutes at a rate, calculated from the equation given in 4.3.4.1, sufficient to produce a relative centrifugal force (r.c.f.) of between 500 and 700 at the tips of the whirling tubes (see table I for the relationship between diameter of swing, r.c.f., and r.p.m.). Read the volume of sediment in each tube, estimating to the nearest 0.1 ml. if necessary. Record the average of the two readings as the percentage of sediment.

4.3.4.1 *Calculation.* — The speed of the rotating heads of the centrifuge is calculated as follows:

$$\text{r.p.m.} = 265 \sqrt{\frac{\text{r.c.f.}}{\text{d}}}$$

where r.c.f. = relative centrifugal force
d = diameter of swing, inches, measured between tips of opposite tubes when in rotating position.

Note.—This procedure is essentially the same as ASTM Designation: D 1290–53T.

TABLE I.—*Rotation speeds applicable for centrifuges of various diameter of swing*

Diameter of swing, inches[1]	R.p.m. at 500 r.c.f.	R.p.m. at 700 r.c.f.
12	1710	2030
13	1650	1950
14	1590	1880
15	1530	1810
16	1480	1760
17	1440	1700
18	1400	1660
19	1360	1610
20	1330	1570
21	1300	1530
22	1270	1500
23	1240	1460
24	1210	1430

4.3.5 *Stability (heat test).*—Pour 100 milliliters of sample into a 4-ounce clean, glass bottle (approximately 15 cm. high). Securely close the bottle and allow to stand undisturbed near the center of an oven maintained at 52°C. for 168 hours. Remove the sample, allow to cool to room temperature and test for compliance with 3.7.

4.3.6 *Removability.*

4.3.6.1 *Preparation of test panel.* — Prepare a new 6 x 6 inch OTL[1] linoleum panel, rigidly mounted, by buffing carefully with number 00 oil-free steel wool to bring the gloss between 5 and 10; if the gloss exceeds

[1] OTL linoleum panels can be obtained from the Chemical Specialties Manufacturers Association, 50 E. 41st St., New York, N. Y.

[2] A suitable instrument is the 60° Gloss Meter, Gardner Laboratory, or its equivalent.

[3] The brush and washability apparatus may be obtained from the Henry A. Gardner Laboratory, Inc., 4723 Elm Street, Bethesda, Maryland.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

10, discard the panel.[2] Using a Mohr pipette, drop 0.4 milliliter of the sample on the prepared linoleum panel which has been carefully leveled. Touch the center of the sharp edge of a 2-inch wide doctor blade applicator having .008 inch clearance to the emulsion. Move the applicator from side to side so that the emulsion covers the entire sharp edge. Spread the emulsion rapidly over a length of 4 inches by moving the applicator back and forth to produce a uniform coat 2 inches by 4 inches, removing the applicator at the center of a stroke. Allow the resultant film to dry 24 hours at 23° ± 1°C. and 50 ± 4 percent relative humidity in still air.

4.3.6.2 *Apparatus.*[3]

4.3.6.2.1 *Brush.*—The brush block shall be an aluminum block, 3½ inches by 1½ inches by ½ inch with 60 holes in the block, each ⅛ inch in diameter. The holes shall be solidly filled with stiff, black, butt-cut, Chinese-hog bristle. The bristles shall extend ¾ inch beyond the block and the abrading surface shall be as nearly plane as possible. Symmetrically placed weights shall be added to the brush-box assembly to bring the total weight to one pound.

4.3.6.2.2 *Washability apparatus.*—The apparatus shall consist essentially of an electric motor mounted on a flat metal plate and a mechanism through which the motor can impart a reciprocating motion to the brush-box assembly across the test panel clamped to the plate. The power shall be transmitted from the motor to a driving arm means of a belt, pulley, and gear-reduction box. A flexible wire shall be attached from the driving arm to each end of the brush-box assembly through adjustable springs and shall be guided by a pulley on each side of the plate. The tension on the wire shall be just sufficient to take up any slack. The path of travel of the brush shall be approximately 15 inches and the speed of the brush shall be approximately 37 oscillations per minute.

4.3.6.3 *Procedure.*—Place the OTL panel on the plate of the washability apparatus in such a manner that the brush will travel at right angles approximately through the center of the dried film on the panel. Place a clean panel on each side of the test panel to provide a surface on which the brush travels and to prevent the test panel from moving with the brush. Soak the brush in 2 percent (anhydrous soap content) aqueous solution of neutral potassium oleate soap to which 5 milliliters of 28 percent ammonium hydroxide is added per 1000 milliliters of soap solution. Stop the motor after 75 oscillations and remove the panel. Blot off the excess soap solutions by means of a clean, dry absorbent cloth and then examine for complete removal. Any evidence of the presence of wax film remaining, disregarding hair lines due to skipping of bristles, shall be considered as incomplete removal.

4.3.7 *Water spotting.* — Apply two thin-coats[4] of sample wax with a swab on a new OTL panel that has been rigidly mounted and buffed as specified in 4.3.6.1. Allow first coat to dry for 24 hours at 23° ± 1°C. and 50 ± 4 percent relative humidity. Carefully apply the second coat using as little pressure as possible, allow to dry two hours, buff well with lamb's wool, either manually or by machine, and continue drying for an additional 22 hours under the same conditions. Place 1 milliliter of distilled water on the panel and allow to stand undisturbed for 1 hour at the above standard conditions of temperature and humidity. Lightly wipe the water off with a soft, dry cloth. Buff as above and examine for compliance with 3.9.

[4] Thin coats resulting from spreading 1500 sq. ft. or more per gallon of wax can be obtained by modifying Method B of ASTM D 1436. Pipet 1 ml emulsion onto the center of the prepared OTL panel 6" x 6". Place cheesecloth strip, washed to remove sizing, 2" x 3", 4 ply, over the solution and allow it to absorb the emulsion. Distribute the emulsion evenly over the surface and draw cheesecloth downward once, in separate strokes, until the entire panel is crossed, with no more pressure than is exerted by the hand. Dry and apply second coat with new cheesecloth applicator and buff as indicated above. 0.45 ml over 36 sq. in. = 2,000 sq. ft./gal.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

4.4 Floor test procedure for slip-resistance and durability.

4.4.1 *Selection and preparation of test floor.*

4.4.1.1 Light colored such as (buff or light yellow), asphalt tile floor of like new quality should be selected. The floor should be free from abnormal bumps and irregularities. Floors surrounding the test panels should not be unreasonably dirty. The surrounding floors need not be cleaned or stripped at the same time as the test panels but they should be normal with respect to cleanliness.

4.4.1.2 Relatively heavy and as nearly equal as possible traffic conditions should prevail on all test panels. Test panels should not be selected in areas of abnormal traffic conditions such as in or adjacent to elevators, heavy traffic main doorway entrances, etc.

4.4.1.3 *Size of test panels.*—Each test panel should be not less than 12 feet in length along the normal line of traffic and should not be smaller than 60 square feet.

4.4.1.4 *Preparation of test floor.*—The test floor should be cleaned and thoroughly stripped of old wax by use of an effective wax remover (see 6.1 (a)). Before waxing, each test panel should be rinsed three times with clear water so as to remove all traces of cleaner or detergent. The effectiveness of good cleaning can be measured by gloss readings which should be not greater than 10 and many floors go as low as 4 or 5. More than one treatment may be necessary on floors which have a "built-up" wax film.

4.4.2 *Application of wax—important.*—Samples for qualification and standard samples in the correct concentration should be applied at the same time adjacent to each other if possible, but in no case more than one panel removed.

4.4.2.1 A clean pail and a 16- to 24-ounce mop, new, or like new, should be provided for each sample. The identification of the pail and mop with the respective code numbers of the samples will reduce the possibility of any mix-up or contamination. Mop should be very clean wrung almost dry of clear rinse water and dried before it is used to apply wax.

4.4.2.2 *Application.*—Apply the first thin coat of each sample of wax to the test panel which has previously been marked with its code number. Uniformity of application on all panels is essential. Allow sufficient time for apparent drying, then buff with a machine, using a clean, soft polishing brush.

4.4.2.3 Apply the second thin coat on top of the first as lightly as possible. After apparent drying, buff again with a soft polishing brush.

4.4.2.4 The test panels should be swept daily with a soft bristle brush and damp mopped weekly with new, or like new mops and clean, cold water, followed by buffing with a clean, soft, polishing brush. Mop should only be sufficiently damp for dirt pick-up and should not leave water on the floor.

4.4.3 *Evaluation of samples.*—The 12 percent solids products shall be evaluated against the 12 percent standard for 6 weeks and the 16 percent solids products against the 16 percent standard for 8 weeks. Evaluation shall be made immediately after application of the samples to the test floor and thereafter weekly after damp mopping and buffing but prior to traffic. Known variables from one test panel to another, such as traffic conditions or floor surfaces should be carefully translated to insure there is neither compromise in quality of samples, nor unfair elimination due to imposing extraordinary conditions. It is in order to retest on another panel against the standard for confirmation. At any time the sample under test is considered inferior to the standard, it shall be rejected. For acceptance, the samples shall be equal to or better than the standard at all times for every quality considered.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

4.4.3.1 *Slip-resistance.*—Determine the relative slip-resistance by comparison against the standard sample by exerting an angular foot pressure on the floor panel using clean, dry leather soles. Any wax accumulation on the sole should be removed. Small differences in slip-resistance are magnified by use of a clean, smooth sheet of paper under the foot.

Note.—The area of heaviest traffic should not be used for examination of slip-resistance.

4.4.3.2 *Durability.*—Durability is determined by observing dirt retention, general appearance, gloss, and buffability.

4.4.3.2.1 *Dirt retention.*—Determine the degree of dirt retention by comparison against the standard sample by visual examination, noting particularly discoloring traffic marks.

4.4.3.2.2 *General appearance, gloss, buffability.*—Determine the general appearance, including gloss and buffability, by comparison against the standard sample by visual examination, noting particularly nondiscoloring traffic scuff marks.

4.4.3.3 To assist in the evaluation of dirt retention and general appearance, a device has been developed and tested which limits the area of observation to a square of 36 inches (4 tiles). This method may be used at the option of the evaluation committee.

4.4.3.3.1 *Template.*—A window or template of 36 inches by 36 inches is cut from a square of oil cloth or other material, 48 inches by 48 inches, and each end attached to any suitable piece of wood.

4.4.3.3.2 *Position of template on floor.*—The template is placed in the same relative position on the test panel and on the standard panel. The area within the window is used exclusively for the evaluation of dirt retention and general appearance. Slip resistance is determined on any area outside the window within the limits of the test panel, and outside the area of heaviest traffic.

5. PREPARATION FOR DELIVERY

The levels of preservation, packaging and packing protection used are defined in Fed. Std. No. 102 (for civil agencies only).

5.1 Packaging.—Packaging shall be level A or C as specified (see 6.5).

5.1.1 *Level A.*—The floor wax shall be furnished in one-gallon, five-gallon or 55-gallon containers. The one-gallon container shall conform to type V, class 4, exterior coating plan B of Federal Specification PPP–C–96. The five-gallon container shall conform to type I of Federal Specification PPP–D–760, with exterior coating conforming to color No. 24087 of Federal Standard No. 595. The 55-gallon container shall conform to type I or II of Federal Specification PPP–D–729, except that the coating shall conform to color specified herein.

5.1.2 *Level C.*—The floor wax shall be packaged in accordance with the manufacturer's commercial practice.

5.2 Packing.—Packing shall be level A, B, or C as specified (see 6.5).

5.2.1 *Level A.*—The one-gallon containers shall be packed in accordance with the requirements of the appendix to Federal Specification PPP–C–96 for domestic shipment. The five-gallon and 55-gallon containers shall not require overpacking.

5.2.2 *Level B.*—The one-gallon containers shall be packed in accordance with the requirements of the appendix to Federal Specification PPP–C–96 for domestic shipment. The five-gallon and the 55-gallon containers shall not require overpacking.

5.2.3 *Level C.*—The floor wax, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Containers shall be in accordance with Uniform Freight Classification Rules or regulations of other carriers applicable to the mode of transportation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 *Freezing precaution.* — The label of the issue packages and shipping containers shall bear a plain and conspicuous legend:

KEEP FROM FREEZING

so as to insure the shipment and handling of the product in an unfrozen state.

5.3.2 *Civil agencies.*—In addition to the marking specified in 5.3.1 and any special marking required by the contract or order, marking shall be in accordance with Federal Standard No. 123.

5.3.3 *Military agencies.*—In addition to the marking specified in 5.3.1, and any special marking required by the contract or order, marking shall be in accordance with Military Standard MIL–STD–129. The marking shall include the date of manufacture and the lot, batch, or control number.

6. NOTES

6.1 To obtain the performance which this product can give, reasonable care should be exercised in its use:

(a) *Stripping.* — Old wax should be removed completely and the floors rinsed with clear water to remove all traces of detergent or cleaner. Likewise the factory finish on new floors should be completely removed. Gloss meter readings of no higher than 10 are an indication of fairly good cleaning. Suitable wax removers can be obtained under the following Stores Stock Catalog numbers:

FSC–6850–664–7052	1-gal. container
FSC–6850–664–7053	5-gal. container
FSC–6850–664–7054	55-gal. container
FSC–6850–664–7055	1-gal. container
FSC–6850–664–7050	5-gal. container
FSC–6850–664–7051	55-gal. container

The only difference in the above removers is concentration; the first three being diluted about 1 to 9 parts of water and the last three about 1 to 35 parts of water.

(b) *Application.* — At least two coats should be applied to new or old stripped floors, followed by buffing after thorough drying. The wax should be spread evenly and thinly at the rate of about 1500 square feet or more per gallon.

(c) *Maintenance.*—For effective performance of wax, floors should be dry brushed (or vacuumed) daily and damp mopped and buffed weekly or oftener under heavy traffic conditions.

6.2 The attention of suppliers and procuring activities is called to the requirements for qualification as provided in section 3 of this specification and GSA Reg. 1–II–201.03 which provides that solicitations for bids by advertising shall contain, in substance, the following statement:

> In the procurement of products requiring qualification, bids secured through formal advertising will be considered only for such products as have, prior to the bid opening date, been tested and approved for inclusion in the qualified products list whether or not such products have actually been so listed by that date. Manufacturers are urged to communicate with the Director, Quality Control Division, Federal Supply Service, General Services Administration, Washington 25, D.C., and arrange to have the product they propose to offer tested for qualification. (Time may not permit qualification for eligibility under this invitation, but products which qualify would be eligible under future invitations.)

6.3 The standard samples are available at cost in both concentrations, namely, 12 percent and 16 percent. Inquiry should be addressed to the Director, Quality Control Division, Federal Supply Service, General Services Administration, Washington 25, D. C.

6.4 Approved inspection activity. — The testing of deliveries of wax under this specification requires essentially the same experi-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

enced personnel as used in the qualification of samples. The procuring agency may arrange for such testing directly with the Director, Quality Control Division, Federal Supply Service, General Services Administration, Washington 25, D. C.

6.5 Ordering data. — Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Concentration of wax desired (see 1.2.1).

(*c*) Levels of packaging and packing required (see 5.1 and 5.2).

6.6 Transportation description.—Transportation description applicable to this item:

Polishing compounds, not otherwise indexed by name, including floor wax.

Carload minimum weight 36,000 pounds.

Truckload minimum weight 36,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M Q
Navy—Sh
Air Force.

Orders for this publication are to be placed with ı, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.