MILITARY SPECIFICATION

ENVELOPE, DRUG DISPENSING, 100s

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers an envelope suitable for dispensing drugs in pharmacies of military medical facilities.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposals, form a part of the specification to the extent specified herein

SPECIFICATIONS

FEDERAL

PPP-B-566	- Boxes, Folding Paperboard.
PPP-B-585	- Boxes, Wood, Wirebound.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Box, Setup.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to Hq, Defense Personnel Support Center, ATTN Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document, or by letter.

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards and drawing, required by suppliers in connection with specific procurement functions, should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY (TAPPI)

T 401 Fiber Analysis of Paper and Paperboard.
T 402 Conditioning Paper and Paperboard for Testing.
T 403 Bursting Strength of Paper.
T 410 Basis Weight of Paper and Paperboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 1 Dunwoody Park, Atlanta, GA 30341.)

3. REQUIREMENTS

3.1 Material Material for the envelopes shall be of the highest quality throughout, and suitable for the purpose intended

3 1.1 Paper. The paper shall be white woven, tub-sized, and of suitable composition so that lines ruled or characters written with ink shall be clear cut. After erasure of ruled lines and written or typed characters, the paper shall retain good writing and typing quality, and appearance of surface Paper shall consist of 100 percent chemical bleached wood pulp fibers, when tested in accordance with 4.4.2. The paper shall have a minimum bursting strength of 25 points as tested on a standard Mullen tester in accordance with 4.4.3 The paper shall have a basis weight of 90.2 grams ± 5% per square meter (24 pounds ± 5% for 500 sheets 17 by 22 inches) when tested in accordance with 4.4.4.

3 1.2 Gum The gum used as the sealing agent shall be of good quality, light in color, nontoxic and tasteless It shall not be obnoxious to the smell, and shall be of the best adhesive quality, capable of being quickly activated with water.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

3.2 Style and design. Drug dispensing envelopes shall be 2-1/2 (+ 1/8,-1/16) inches by 4-1/4 (+ 1/8 - 1/16) inches, full gum pay or coin envelopes. A flap shall be provided so that the envelope may be sealed. The inside edge of the flap shall be impregnated with a gum-sealing agent (see 3.1.2), along its entire inside length. Envelope design shall be in accordance with Figure 1.

3.3 Printing. The printing on the face of the envelope shall be in accordance with Figure 1. All printing, including borders, shall be a medium green color as demonstrated by the standard color sample which will be provided upon request by the procuring activity (see 6.2). The printing shall be sharp, clearly defined, and legible.

3.4 Adhesion with water. When tested as specified in 4.4.5, the gummed side of the flap shall adhere instantly to the envelope, and shall remain so firmly affixed after drying 2 hours, that it cannot be removed without pulling fibers from the paper.

3.5 Blocking (adhesion without water). When tested as specified in 4.4.6, the gummed flap shall not adhere to the envelope.

3.6 Workmanship. Envelopes shall be uniformly made, and be free from imperfections which detract from their appearance or may impair their serviceability. The gum shall be thoroughly dried before the envelopes are packed.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4 1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.




FIGURE 1. Envelope, Drug Dispensing

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the paper, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the item identification, the name of the material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be performed in accordance with MIL-STD-105 and Table I. The unit of product is one envelope.

TABLE I. FOR EXAMINATION.

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	S-3	2.5
Minor defects	S-3	4.0
For dimensional examination	S-2	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and Table II.

Table II. For tests.

Characteristic	Requirement	Test procedure	Inspection level	AQL
Paper	3.1.1	4.4.2	S-1	*
Bursting strength	3.1.1	4.4.3	S-1	*
Basis weight	3.1.1	4.4.4	S-1	*
Adhesion with water	3.4	4.4.5	S-2	*
Blocking	3.5	4.4.6	S-2	*

*Acceptance number shall be zero.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

4.3 Examination. The envelope shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the following table:

Table III. Classification of defects.

Categories	Defects
Major	
101	Envelope not free of tears splits, slits and holes.
102	Envelope not free of wrinkles, sharp creases, blisters and chafed spots.
103	Envelope not provided with rounded flap.
104	Other sides not folded and sealed.
Minor	
201	Envelope not creased at beginning of flap
202	Not free of dirt and foreign material.
203	Adhesive or gum on inside or outside of envelope except flap inside).
204	Flaps curl.
205	Color not medium green as specified.
206	Printing missing, incomplete, incorrect and illegible.
207	Adhesive not applied evenly and completely.

*Examination shall not be restricted to the classified defects listed above.

4.3.2 Dimensional examination. The envelope shall be examined for defects in dimensions. Any dimension not within the tolerance specified herein shall be classified as a defect.

4.3.3 Envelope count. The average count per package shall be not less than 100 envelopes. Inspection level shall be S-1

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements. The sample unit shall be three envelopes. Not more than one sample unit, randomly selected, shall be drawn from any exterior container. For testing purposes, the lot size shall be expressed in packages of 100 envelopes.

4.4.1 Paper conditioning. Prior to tests, paper shall be conditioned in accordance with TAPPI test method T 402.

4.4.2 Paper. Paper shall be tested for fiber analysis in accordance with TAPPI test method T 401.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

4.4.3 Bursting strength. Paper bursting strength shall be determined in accordance with TAPPI test method T 403.

4.4.4 Basis weight. Paper shall be tested for basis weight in accordance with TAPPI test method T 410.

4.4.5 Adhesion with water. The gummed side of the flap shall be moistened with water, pressed firmly against the envelope sealing surface, and examined for adequate sealing at the end of two hours.

4.4.6 Blocking. Condition an envelope at 73 degrees Fahrenheit (^{o}F.), $\pm$ 3°, and 80% percent relative humidity, $\pm$ 2 percent, for 24 hours. At the end of the conditioning period, place the gummed flap of the envelope against the envelope surface, place a weight, equivalent to 1 pound per square inch, on the flap and allow envelope to remain in the stated atmospheric condition for another 24 hours.

4.5 Packaging inspection. The inspection of the unit, intermediate package, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

5. PACKAGING

5.1 Packaging. Packaging shall be Level A or C, as specified (see 6.1).

5.1.1 Unit of issue. One package containing one hundred envelopes, as specified, constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Unit package. One hundred envelopes shall be clean, dry and secured with a paper band or shall be packaged in a box conforming to PPP-B-566 or PPP-B-676. Closure shall be as specified in the appendix of the applicable box specification.

5.1.2.2 Intermediate package. Twelve unit packages shall be packaged in a box conforming to PPP-B-566, PPP-B-636, class domestic or PPP-B-676. Closure shall be as specified in the appendix of the applicable box specification.

5.1.3 Level C. One hundred envelopes shall be clean, dry and packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing Packing shall be Level A, B or C, as specified (see 6.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

5.2.1 Level A. Twelve intermediate packages (144 unit packages) shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-636, class weather-resistant. Closure, strapping and waterproofing shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B. Twelve intermediate packages (144 unit packages) shall be packed in an exterior container degigned for a type 2 load and conforming to PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The packaged envelopes shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129 Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following

a. Title, number and date of specification.

b. National Stock Number (NSN).

c. Selection of applicable levels of packaging and packing (see 5.1 and 5.2)

6.2 The following medium green colors are considered to comply with the color requirement in 3.3. Superior Printing Ink Co.'s "Bond Silk Green Deep 1033 HB." S.H. and G.B. Siebold, Inc.'s "No. 376-98D," or Interchemical Corp , Printing Ink Division, IPI'S "Bond Silk Green 58P 10834."

6.3 This specification does not cover all types, classes, grades or sizes of the commodity indicated by the title of this specification, or those which are commercially available but is intended to cover the types normally procured to meet military requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

6.4 This specification covers the following item as listed in the Federal Supply Catalog:

National Stock No.	Item Identification
8105-00-559-3051	ENVELOPE, DRUG DISPENSING, 100s

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DSA-DM

Project No. 8105-0267

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government Fold on lines on reverse side, staple in corner, and send to preparing activity Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements Attach any pertinent data which may be of use in improving this document If there are additional papers, attach to form and place both in an envelope addressed to preparing activity

DOCUMENT IDENTIFIER AND TITLE

MIL-E-37579 ENVELOPE, DRUG DISPENSING, 100s

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1 HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A GIVE PARAGRAPH NUMBER AND WORDING

B RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3 IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4 REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, PA 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:02Z
Check the source to verify that this is the current version before use.