INCH-POUND

TT-C-490D
INTERIM AMENDMENT 1
September 14, 1994

FEDERAL SPECIFICATION

# CLEANING METHODS FOR FERROUS SURFACES AND PRETREATMENTS FOR ORGANIC COATINGS

This interim amendment is approved by the U.S. Army Research Laboratory/ Materials Directorate, with TT-C-490D, dated March 31, 1993.

PAGE 1

Add as new paragraph 1.2.2:

"1.2.2 Ozone depleting chemicals. The cleaning material shall not contain any chemical which is classified in the Clean Air Act Amendments of 1990 as a Class I or Class II ozone depleting substance."

PAGE 5

3.4.2.1: Delete and substitute:

"3.4.2.1 Stress relief. Parts cold worked after heat treatment and parts having a hardness of Rockwell C40 or greater shall be stress relieved prior to phosphating."

PAGE 16

Table III, Under Cleaning Method; Method II, Delete:

"MIL-D-26847 and MIL-T-81533"

Note: Ozone depleting solvents are no longer specified for degreasing or cleaning the surface of parts. Solvent selection is left to the discretion of the manufacturer.

Preparing activity:
Army - MR
Project MFFP-A551


DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:16Z
Check the source to verify that this is the current version before use.