TT-P-350b
May 15, 1967
SUPERSEDING
Fed. Spec. TT-P-350a
September 11, 1961

FEDERAL SPECIFICATION

PIGMENT, LAMPBLACK - DRY

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers lampblack pigment for use in protective coatings.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues, in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

Federal Specification:

TT-P-143 - Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing, and Marking of.

Federal Standard:

Fed. Test Method Std. No. 141 - Paint, Varnish, Lacquer, and Related Materials; methods of Inspection, Sampling, and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications and standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.)

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, and Auburn, Washington.)

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Lampblack pigment shall be the product made by burning oils or tars with or without out gas, in such a manner as to form a deposit of carbon or soot. It shall be a soft, dry powder, free from admixtures of any other substances, and shall conform to table I.

TABLE I. Requirements

	Minimum	Maximum
Coarse particles (residue retained on No. 325 sieve), (percent)		0.25
Ash (percent)		.5
Acetone extract (percent)		.5
Specific gravity	1.75	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:16Z
Check the source to verify that this is the current version before use.

3.2 The mass color and character of tint shall be the same as, and the tinting strengt not less than that of the standard (see 6.3.). The oil absorption when specified (see 6.2), shall be within plus or minus 10 percent of that of a sample mutually agreed upon by buyer and seller.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Lot. A lot shall consist of all material offered for delivery at one time, manufactured as one batch, or continuously manufactured from the same material within a specified time period.

4.3 Sampling and inspection.

4.3.1 Sampling and inspection shall be in accordance with methods 1011, 1021, or 1031 of Fed. Test Method Std. No. 141, as applicable.

4.4 Test procedures.

4.4.1 The following tests shall be conducted in accordance with the test methods specified in Fed. Test Method Std. No. 141.

Tests	Method
Coarse particles	4101
Ash	5261
Acetone extract 1/	5151
Oil absorption	4191
Mass color	4220
Tinting strength	4221
Specific gravity	4181

1/ If the acetone extract is colorless, it is safe to assume that the amount of extract will be within the limits of the specification, but if the extract is colored, the quantitative determination should be made. This is an arbitrary method and details should be strictly followed. It is practically impossible to remove all matter soluble in acetone from lampblack. See Goodwin and Park, Ind. Eng. Chem 20, 621 (June 1928).

4.4.2 Packaging, packing, and marking. The pigment shall be inspected for compliance with packaging, packing, and marking requirements of section 5.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing, and marking. The lampblack-dry shall be packaged, packed, and marked in accordance with TT-P-143. The levels of packaging and packing shall be A, B, o C, as specified (see 6.2). The pigment shall be furnished in 1-pound bags (see 6.2).

6. NOTES

6.1 Intended use. The pigment covered by this specification is intended for use in protective coatings. It may be used as either a solid color or for tinting.

6.2 Ordering data. Purchasers should select the preferred options permitted herein an include the following information in procurement documents:

(a) Title, number, and date of this specification.

(b) Whether the pigment shall conform to the oil absorption of the mutally agreed upon sample (see 3.2).

(c) Size container required (see 5.1).

(d) Applicable levels of packaging and packing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:16Z
Check the source to verify that this is the current version before use.

6.3 The most important properties of lampblack are its color, character of tint, and tinting strength. Unless otherwise specified, the National Bureau of Standards Sample No. 318 will be used. (Obtainable from National Bureau of Standards, Washington, D. C. 20402.)

6.4 The dry pigment should be purchased by net weight. Paste-in-oil is covered by TT-P-381.

6.5 The pigment covered by this specification has a specific gravity of about 1.78, and thus 1-pound bulks 0.06743 gallons.

CUSTODIANS:
Navy - AS
Army - MO
Air Force - WRAMA (85)

Preparing activity:
Navy - AS

Review activities:
Army - MR, MF
Navy - AS, OS, SH
Air Force - 85

User activity:
Army - ME

CIVIL AGENCIES INTEREST:

GSA - FSS
GPO - TTC

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 5 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:16Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:16Z
Check the source to verify that this is the current version before use.