INCH-POUND
MIL-C-11015/21G
25 October 2021
SUPERSEDING
MIL-C-11015/21F
14 May 2001


MILITARY SPECIFICATION SHEET

CAPACITOR, FIXED, CERAMIC DIELECTRIC (GENERAL PURPOSE), STYLES CK64, CK65, CK66, CK67, CK68, and CK69

INACTIVE FOR NEW DESIGN AFTER 31 MARCH 1999.
FOR REPLACEMENT PURPOSES ONLY.

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-C-11015.



Inches	mm
.001	0.03
.004	0.10
.032	0.81
.062	1.57
.375	9.53
1.250	31.75

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are in parentheses.
3. Metric equivalents are in millimeters and are given for general information only.
4. Insulating coating shall not extend more than .125 inch (3.18 mm) along lead wires measured from a tangent to the coating surface drawn perpendicular to the lead wires.

Dimensions		
Style	L ± .040 (1.02)	T ± .040 (1.02)
CK64	.730 (18.54)	.167 (4.24)
CK65	.790 (20.07)	.167 (4.24)
CK66	.890 (22.61)	.167 (4.24)
CK67	.950 (24.13)	.167 (4.24)
CK68	1.050 (26.67)	.330 (8.38)
CK69	1.110 (28.19)	.330 (8.38)

FIGURE 1. Dimensions and configuration.

AMSC N/A
FSC 5910

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:57Z
Check the source to verify that this is the current version before use.

TABLE I. Styles CK64, CK65, CK66, CK67, CK68, and CK69 characteristics.

Part or identifying number (PIN) 1/	Rated voltage (V_{dc})	Rated temperature and voltage-temperature limits	Capacitance (pF)	Capacitance tolerance
CK64AW511M-	1,600	AW	510	M
CK64AW681M-	1,600	AW	680	M
CK64AW821M-	1,600	AW	820	M
CK64AW102M-	1,600	AW	1,000	M
CK64AW152M-	1,600	AW	1,500	M
CK64AW222M-	1,600	AW	2,200	M
CK64AW332M-	1,600	AW	3,300	M
CK64AW392M-	1,600	AW	3,900	M
CK65AW472M-	1,600	AW	4,700	M
CK66AW562M-	1,600	AW	5,600	M
CK67AW682M-	1,600	AW	6,800	M
CK67AW752M-	1,600	AW	7,500	M
CK68AW103M-	1,600	AW	10,000	M
CK69AW153M-	1,600	AW	15,000	M

1/ The complete PIN will include the letter “E” to indicate an epoxy coated capacitor (when applicable) or “-“ will be deleted for wax impregnated case.

REQUIREMENTS

Dimensions and configuration: See figure 1.

Case type: Disk, wax impregnated or epoxy coated (E).

Capacitance value: See table I.

Capacitance tolerance: ± 20 percent (M).

Rated temperature: -55°C to +85°C.

Dielectric withstanding voltage(DWV): In accordance with MIL-C-11015.

Dielectric:

Test voltage: 250 percent of rated voltage.

Body insulation:

Test potential: 3000 volts dc.

Barometric pressure (reduced): In accordance with MIL-C-11015 and MIL-STD-202-105, condition B (50,000 ft).

Test potential: 2,000 volts dc.

Insulation resistance (IR): In accordance with MIL-C-11015 and MIL-STD-202-302, condition B. 200,000 megohms, minimum.

Dissipation factor (DF): 2.0 percent maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:57Z
Check the source to verify that this is the current version before use.

Vibration, high frequency: In accordance with MIL-C-11015 and MIL-STD-202-204, condition D (20 g's).

Thermal shock and immersion: In accordance with MIL-C-11015.

DWV: 250 percent of rated voltage.

IR: 150,000 megohms, minimum.

Salt atmosphere (corrosion): Not applicable.

Terminal strength: In accordance with MIL-C-11015.

Moisture resistance: In accordance with MIL-C-11015.

DWV: 250 percent of rated voltage.

IR: 150,000 megohms, minimum.

Cap.: Within tolerance of table I value.

Solderability: In accordance with MIL-C-11015. 2 terminals.

Resistance to soldering heat: In accordance with MIL-C-11015.

IR: 200,000 megohms, minimum.

ΔCap.: $\pm$ 5 percent of initial measurement.

ΔDF: 0.5 percent, maximum.

Voltage-temperature limits: In accordance with MIL-C-11015.

Life (at elevated ambient temperature): In accordance with MIL-C-11015.

Test potential: 200 percent of rated voltage.

DWV: 250 percent of rated voltage (at 25°C).

IR: 100,000 megohms, minimum (at 85°C and 25°C).

Cap.: Within tolerance of table I value (at 25°C).

DF: 2.0 percent, maximum (at 25°C).

Marking: In accordance with MIL-C-11015.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:57Z
Check the source to verify that this is the current version before use.

Referenced documents: In addition to MIL-C-11015, this document references the following:

MIL-STD-202-105
MIL-STD-202-204
MIL-STD-202-302

Changes from previous issue: The margins of this specification are marked with vertical lines to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 85
DLA - CC

Preparing activity:
DLA - CC

(Project 5910-2021-034)

Review activities:
Army - MI
Navy – AS, OS, SH
Air Force - 19

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:57Z
Check the source to verify that this is the current version before use.