MILITARY SPECIFICATION

* LEATHER, CALFSKIN AND KIP, AND LACING, HANDICRAFT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

* 1.1 Scope. This specification covers the requirements for full grain, vegetable tanned, calfskin or kip leather in the form of whole skins and cut lacing.

* 1.2 Classification. The leather and the lacing shall be furnished in the following types, classes and treatments as specified (see 6.2).

Type I	-	Whole calfskin or kip leather.
Type II	-	Cut calfskin or kip lacing.
Class 1	-	Smooth finished, full grain with natural tannage color on both sides and added finish on grain side.
Class 2	-	Smooth finished, full grain, natural tannage color on flesh side, with added dye and finish on grain side.
Class 3	-	Full grain with natural tannage color on both sides, no added finish.
Treatment A	-	Mildew resistant treated.
Treatment B	-	Not mildew resistant treated.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research and Development Command, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8330

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

UU-P-268 - Paper, Kraft, Wrapping.
PPP-B-636 - Boxes, Shipping, Fiberboard.

MILITARY

MIL-L-43432 - Leather, Packaging and Packing Of.

STANDARDS

FEDERAL

FED-STD-311 - Leather, Methods of Sampling and Testing.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions, should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, DC 20036.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Materials.

* 3.1.1 Type I. Type I leather shall be full grain calfskin in the form of whole skins, or full grain kip leather in the form of whole skins or sides.

3.1.2 Type II. The type II lacing shall be full grain calfskin or kip. The lacing shall be flat with beveled edges. The width of the lacing shall be 3/32 + 1/64, -0 inch (2.4 + 0.4, -0 mm). Unless otherwise specified (see 6.2), the lacing shall be furnished on spools in lengths of 100 + 10, -0 yards (91 + 9, -0 m).

3.2 Tannage. Only vegetable tanning materials shall be used in tanning the type I leather and the leather for type II lacing.

3.3 Physical requirements.

* 3.3.1 Trim (type I, form and area). Type I calf leather shall be furnished in the form of whole skins. The type I kip leather shall be furnished in the form of whole skins or sides. The leather shall be trimmed in accordance with standard commercial practice. The area expressed in terms of square feet (m^2) shall be legibly marked in the butt area on the flesh side. The area of the calfskin shall be not greater than 17-3/4 square feet (1.6 m^2). The area of the whole kipskin shall be not greater than 28 square feet (2.6 m^2). The area of the kip sides shall be not greater than 14 square feet (1.3 m^2).

3.3.2 Thickness. The thickness of the leather and the lacing shall be as specified (see 6.2). A tolerance of $\pm$ 1/2 ounce (0.2 mm) will be permitted. The flesh side may be skived, shaved, or buffed to obtain a uniform thickness. Note: 1 ounce = 1/64 inch (0.4 mm).

3.3.3 Color and finish.

3.3.3.1 Class 1. The color of the grain side and the flesh side shall be natural as produced by the tanning agents. The grain side shall have a light application of finish to assist in making the natural color uniform. The grain surface shall be smooth finished by glazing, rolling, or smooth plating. The flesh side shall be free of loose flesh and shall be buffed smooth.

Source: https://assist.dla.mil -- Downloaded: 20260-18T02:26Z
Check the source to verify that this is the current version before use.

3.3.3.2 Class 2. The color of the grain side shall be as specified (see 6.2). The color of the flesh side shall be natural as produced by the tanning agents. The grain side shall have a light application of finish and dye containing only sufficient pigment to provide uniformity of color (see 6.3). The grain surface shall be smooth finished by glazing, rolling, or smooth plating. The flesh side shall be free of loose flesh and shall be buffed smooth.

3.3.3.3 Class 3. The color of the grain side and the flesh side shall be natural as produced by the tanning agents. A finish shall not be applied to either the grain side or the flesh side. The flesh side shall be free of loose flesh and shall be buffed smooth.

3.3.4 Colorfastness (type I, classes 1 and 2). The leather shall be tested for resistance to dry and wet crocking in accordance with 4.3. Staining of the dry cloth shall be not lower numerically than Munsell value 9.0 and staining of the wet cloth shall be not lower numerically than Munsell value 8.5.

* 3.3.5 Breaking force (type II). At least 80 percent of the specimens tested shall meet the breaking force values shown in table I when tested as specified in 4.3.

TABLE I. Breaking force requirements (type II)

Thickness	Breaking force, minimum	
	Pounds	(N)
Up to 2-3/4 ounces (1.1 mm)	8.0	(36)
3 ounces (1.2 mm) and greater	11.0	(49)

* 3.3.6 Stitch tearing strength (type I). At least 80 percent of the specimens tested shall meet the stitch tearing strength values shown in table II when tested as specified in 4.3.

TABLE II. Stitch tear requirements (type I)

Thickness	Stitch tearing strength, minimum	
	Pounds	(N)
Up to 2-3/4 ounces (1.1 mm)	18.0	(80)
3 ounces (1.2 mm) and greater	22.0	(98)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

3.3.7 Elongation (type I). At least 80 percent of the specimens tested shall have elongation values no greater than 40 percent at the forces indicated in table III when tested as specified in 4.3.

TABLE III. Elongation force (type I)

Thickness	Force	
	Pounds	(N)
Up to 2-3/4 ounces (1.1 mm)	45.0	(200)
3 ounces (1.2 mm) and greater	60.0	(267)

3.3.8 Cracking. The leather shall not crack when tested as specified in 4.3.

3.4 Chemical requirements.

3.4.1 Type I and type II. The leather and lacing shall conform to the chemical requirements of table IV when tested as specified in 4.3.

TABLE IV. Chemical requirements

Characteristic	Minimum	Maximum
Chloroform-soluble material, percent 1/	4.0	12.0
Ash, percent 1/	-	3.0
Lead (qualitative)	2/	2/
pH value	3.3	5.0

1/ Moisture free basis.

2/ The presence of lead is prohibited (see 6.3).

3.4.2 Treatment A. When treatment A is specified, the leather shall contain not less than 0.18 and not more than 0.70 percent paranitrophenol fungicide when tested as specified in 4.3 (see 6.4).

3.5 Workmanship. The finished leather and lacing shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

* 4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with FED-STD-311 and MIL-STD-105 except where otherwise indicated hereinafter.

* 4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected in accordance with all the requirements of referenced specifications, drawings, and standards, unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.2.2 Examination of the end item. The end item shall be examined for visual and dimensional defects listed in 4.2.2.3 and 4.2.2.6.

* 4.2.2.1 Examination of type I (visual). The sampling procedure for visual examination of type I leather shall be in accordance with FED-STD-311. The sample unit shall be one calfskin, one kipskin or one kip side as applicable. The lot size shall be expressed in units of one skin or side.

4.2.2.2 Examination of type II (visual). The sampling procedure for visual examination of type II leather lacing shall be in accordance with MIL-STD-105. The sample unit shall be 10 linear yards (9 m). The lot size shall be expressed in units of one spool. The inspection level and acceptable quality level shall be in accordance with 4.2.2.7.

* 4.2.2.3 Examination for visual characteristics.

Examine	Defect
Material:	
Type I	Not full grain calf or kip.
Type II	Not full grain calfskin lacing or kip lacing.
	Not flat with beveled edges.
	Not furnished on spools.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

Examine	Defect
Trim and form:	
Type I	Not as specified.
Color:	
Classes 1 and 3	Not natural tannage color on both sides.
Class 2	Color of grain side not as specified. Not natural tannage color on flesh side.
Finish:	
Class 1	Grain side does not have light application of finish.
Class 2	Grain side does not have light application of finish and dye.
Classes 1 and 2	Grain side does not have smooth finish.
Class 3	Grain side has application of finish.
Classes 1, 2 and 3	Flesh side not buffed smooth. Flesh side not free of loose flesh.
Quality of leather:	
Type I	Discoloration, stain, cut, scratch, hole, brand, hip mark, rough shoulder, heavy vein, deep fat wrinkle, or other defects which individually or collectively impair the cutting value of more than 12 percent of the total area of the skin or side.
Type II	Any defect or combination of defects listed for type I.

NOTE: Light, well healed, scratches or grub holes; light fat wrinkles; or slight stains shall not be classified as defects.

* 4.2.2.4 Examination of type I (dimensional). The sampling procedure for dimensional examination of type I leather shall be in accordance with FED-STD-311, except that a sample size of 15 and a rejection number of 2 shall be applicable for thickness determinations on lots consisting of 51 or more units of product. The sample for the dimensional examination may be obtained from the sample used for the visual examination. The sample unit shall be one skin or side as applicable. The lot size shall be expressed in units of one skin or side as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

4.2.2.5 Examination of type II (dimensional). The sampling procedure for dimensional examination for type II leather lacing shall be in accordance with MIL-STD-105. The sample unit shall be one spool. The lot size shall be expressed in units of one spool. The inspection level and acceptable quality level shall be in accordance with 4.2.2.7.

* 4.2.2.6 Examination for dimensional characteristics.

Examine	Defect
Thickness 1/	Thickness not as specified.
Area expressed in terms of square feet (type I)	Not as marked on unit.
Calfskin	Area greater than 17-3/4 square feet (1.6 m^2)
Kip (whole skin)	Area greater than 28 square feet (2.6 m^2)
Kip (side)	Area greater than 14 square feet (1.3 m^2)
Marking (type I)	Omitted, illegible or not in area specified.
Length (type II)	Not spooled in length specified.
Width (type II) 1/	Not as specified.

1/ The thickness of type I leather shall be determined in accordance with Method 1011 of FED-STD-311. No individual thickness determination shall be less than the minimum or greater than the maximum specified. The spring type gage specified in Method 1011 of FED-STD-311 shall be used in determining the thickness of the type II leather lacing and a rule calibrated to 1/64 inch (0.4 mm) shall be used to determine the width. The thickness and the width of type II shall be determined at 10 yard (9 m) intervals. If the put up of the type II lacing will not permit determination to be made at 10 yard (9 m) intervals, the thickness and width determination shall be made at the midpoint of ten lengths randomly selected from the spool.

4.2.2.7 Inspection level and acceptable quality level (AQL). The inspection levels and AQLs expressed in defects per 100 units shall be as follows:

Examination	Inspection level	AQL
For defects applicable to 4.2.2.2 visual characteristics	II	4.0
For defects applicable to 4.2.2.5 dimensional characteristics	S-3	4.0

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:26Z
Check the source to verify that this is the currentversion before use.

* 4.2.3 Packaging inspection.

4.2.3.1 Type I. An examination shall be made to determine that packaging, packing and marking comply with the applicable requirements of MIL-L-43432.

* 4.2.3.2 Type II. An examination shall be made to determine that preservation-packaging, packing and marking comply with the section 5 requirements. The sampling procedure for this examination shall be in accordance with MIL-STD-105. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be closed. Examination for the closure defects listed below shall be made on shipping containers fully prepared for delivery. The lot size shall be the number of containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flap, improper taping, loose strapping, or inadequate stapling. Bulged or distorted container.
Weight	Net weight exceeds requirement.

4.3 End item testing. The methods of testing specified in FED-STD-311 wherever applicable and as listed in table V shall be followed. For type I leather, the sampling procedure and location from which the sample unit is to be obtained shall be in accordance with FED-STD-311. The sample required for testing type II leather shall be taken from fifteen spools selected at random from the lot. The sample size shall be fifteen 1 yard (0.9 m) pieces. One yard (0.9 m) shall be selected from each spool. All test reports shall contain the individual values utilized in expressing the final results. The lot shall be rejected if any of the following conditions exists.

a. More than three test failures occur for breaking force, stitch tearing strength, or elongation.

b. More than one test failure occurs for the remaining requirements applicable to the sample unit.

c. Any composite test result fails to meet the specified requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

TABLE V. Tests

Characteristic	Requirement paragraph	Test method	Requirement applicable to Sample unit	Composite
Material identification	3.1	1/	-	-
Tannage	3.2	1/	-	-
Colorfastness, type I, classes 1 and 2	3.3.4	3031	X	-
Breaking force, type II	3.3.5	2021 2/	X	-
Stitch tearing strength, type I	3.3.6	2151	X	-
Elongation, type I	3.3.7	2021	X	-
Cracking	3.3.8	4021 3/	X	-
Chloroform-soluble material	3.4.1	6341	-	X
Ash	3.4.1	6421	-	X
Lead (qualitative)	3.4.1	6551	-	X
pH value	3.4.1	6621	-	X
Paranitrophenol (treatment A)	3.4.2	6711	-	X

1/ A certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ The specimen for the type II lacing shall be 6 inches (152 mm) in length and 3/32 + 1/64, -0 inch (2.4 + 0.4, -0 mm) in width. To prevent the specimen from breaking at the jaws, drum-type grips with eccentric clamps may be used or the regular type jaws may be faced with heavy duck before inserting the specimen.

3/ The mandrel shall be 1/4 inch (6.4 mm) diameter. For type II laces, the specimen shall be a 6 inch (152 mm) length of the lace.

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level A or C (see 6.2).

5.1.1 Type I.

5.1.1.1 Level A (type I). Leather of like description only, shall be packaged in accordance with the applicable requirements of MIL-L-43432.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

* 5.1.1.2 Level C (type I). Leather shall be preserved-packaged to afford adequate protection against physical damage during shipment from the contractor to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the contractor for retail distribution.

5.1.2 Type II.

5.1.2.1 Level A (type II). Lacing of like description only, furnished in the length as specified in 3.1.2, shall be neatly wound on a chipboard spool consisting of a tube and mechanically attached circular ends. Each spool shall be wrapped with a band of transparent plastic film or with 30 pound minimum basis weight (49 g/m^2) kraft paper conforming to type I, grade B of UU-P-268. The wrap shall completely inclose the lacing on the spool and shall be secured with gummed paper or pressure-sensitive tape.

5.1.2.2 Level C (type II). Lacing shall be preserved-packaged to afford adequate protection against physical damage and deterioration during shipment from the contractor to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the contractor for retail distribution.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Type I packing.

5.2.1.1 Level A or B packing (type I). Leather of like description only, shall be packed in accordance with the applicable requirements of MIL-L-43432.

* 5.2.1.2 Level C packing (type I). Leather shall be preserved-packaged as specified in 5.1 and shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the Uniform Classification or National Motor Freight Classification, as applicable.

5.2.2 Type II packing.

* 5.2.2.1 Level A packing (type II). Lacing of like description only, preserved-packaged as specified in 5.1.2, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed, in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of the container specification except that the inspection shall be in accordance with 4.2.3.2. The weight of the contents of each shipping container shall not exceed 65 pounds (29.5 kg).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

5.2.2.2 Level B packing (type II). Lacing of like description only, preserved-packaged as specified in 5.1.2, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification except that the inspection shall be in accordance with 4.2.3.2. The weight of the contents of each shipping container shall not exceed 65 pounds (29.5 kg).

* 5.2.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification except that the inspection shall be in accordance with 4.2.3.2.

* 5.2.2.3 Level C packing (type II). Lacing, preserved-packaged as specified in 5.1.2, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Type I leather is primarily intended for use in making tooled leather items and hat bands. Type II leather lacing is primarily intended for use in leather-craft work in occupational therapy.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type, class, and treatment required (see 1.2 and 6.4).
(c) Length of lacing, when length is other than specified (see 3.1.2).
(d) Thickness required (see 3.3.2).
(e) Color required (see 3.3.3.2).
(f) Selection of applicable levels of preservation-packaging and packing (see 5.1 and 5.2).
(g) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.2.1).

6.3 Lead salts. Lead chromate, lead pigments, or other lead salts should not be used in the finish.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

6.4 Paranitrophenol. Paranitrophenal has a tendency to leach out of the leather when the leather becomes wet and will stain items which are in intimate contact with the treated leather. Consideration should be given to this factor when determining whether treatment A should be specified.

6.5 Changes from previous issues. The margins of this specification are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Air Force - 99
DLA - CT

Preparing activity:

Army - GL

Project No. 8330-0137

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-L-13816D Leather, Calfskin and Kip, And Lacing, Handicraft

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026l0-18T02:26Z
Check the source to verify that this is the currentversion before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK RESEARCH and DEVELOPMENT COMMAND
NATICK, MASSACHUSETTS 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
DRXNM-TDC

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD-314

U.S. MAIL

Commander
US Army Natick Research and Development Command
ATTN: DRXNM-TDC
Natick, MA 01760

NATICK OP 1 JUL 77
FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:26Z
Check the source to verify that this is the current version before use.