MILITARY SPECIFICATION

LITHIUM HEXAFLUOROARSENATE (FOR USE IN AMMUNITION)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one grade of Lithium Hexafluoroarsenate ($LiAsF_6$) for use in lithium reserve type batteries. (see 6.7).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification For

STANDARDS

MILITARY

MIL-STD-129 - Marking for Shipping and Storage

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement function should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

FSC: 6810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM-E11	- Wire-Cloth Sieves for Testing Purposes
ASTM-E70	- pH of Aqueous Solutions with the Glass Electrode
ASTM-E168	- Infrared Quantitative Analysis, Rec. Practices
ASTM-E203	- Water Using Karl Fischer Reagent
ASTM-E258	- Total Nitrogen in Organic Materials by Modified Kjeldahl Method
ASTM-E300	- Sampling Industrial Chemicals

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103).

3. REQUIREMENTS

3.1 Material. The material shall be lithium Hexafluoroarsenate ($LiAsF_6$) conforming to the following requirements: (6.7)

3.1.1 Form. The material shall be in the form of white crystalline powder at room temperature and shall be free of dirt, chips, grease and other foreign matter when examined as specified in 4.4.3.1 (see 6.3).

3.1.2 X-ray diffraction. The material shall have an x-ray diffraction pattern which conforms to Table I when tested as specified in 4.4.3.2.

Table I

Peak, d-value (decreasing order of intensity)
3.63
4.14
2.17
4.33
1.81

3.1.3 Infra-red spectroscopy. The material shall possess an infrared spectrum conforming to Table II given below and the infrared spectrum given in Figure 1 when tested as specified in 4.4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

Table II

Peak, Microns	Range
2.96	2.85-3.05
6.15 (this peak may appear as a doublet)	6.00-6.30
14.60	13.50-14.90
26.60	25.50-31.00

3.1.4 Impurities. The impurities present in the material shall not exceed the values given in Table III when tested in accordance with the applicable paragraph. In addition, the total of all impurities shall not exceed 2500 ppm.

Table III

Impurities	Maximum Allowable Concentration	Test Paragraph
Metallic Impurities		4.4.3.4
Copper	50	
Magnesium	50	
Sodium	300	
Silver	50	
Iron	200	
Aluminum	50	
Nickel	50	
Chromium	50	
Calcium	50	
Silicon	100	
Nitrogen	50	4.4.3.5
Halogens		4.4.3.6
Chlorine	50	
Bromine	50	
Iodine	50	
Sulfur	50	4.4.3.7
Carbon	300	4.4.3.8
Hydrogen	800	4.4.3.8
Oxygen Containing Compounds	None Detectable	4.4.3.9
Water	200	4.4.3.10

3.1.5 Properties. The material shall conform with the following properties when tested in accordance with the applicable test paragraph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

Property	Requirement	Test Paragraph
pH		4.4.3.11
in Water	4.0 to 7.0	
in Methyl Formate (MF)	3.8 to 7.5	
Solubility in MF, %	100	4.4.3.12
Hydrolysis/Dehydration		4.4.3.13
Methanol,% max @200 hrs	12	
Dimethylether, % max @200 hrs	0.1	
Particle Size		4.4.3.14
Thru a SS No. 25,% min	50	
Thru a SS No. 120,%min	25	
Potential	<450 mv	4.4.3.15

3.2 First article testing. This specification makes provisions for first article testing. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.. (see 6.1)

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection and Standard Quality Assurance Provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of Inspections. The inspection requirements specified herein are classified as follows:

a. First Article Inspection (see 4.3)
b. Quality Conformance Inspection (see 4.4)

4.3 First article inspection

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article shall consist of 2 pounds of $LiAsF_6$ obtained by sampling as described in 4.4.2.1. The sample shall be obtained from a production lot which has been produced by the contractor using the same production processes, procedures and equipment as will be used in fulfilling the contract. All materials, shall be obtained from the same sources of supply as will be used in regular production.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

4.3.2 Inspections to be performed. The sample will be subjected by the Government to any or all of the examinations or tests specified in 4.4.3 of this specification.

4.3.3 Rejection. See MIL-A-48078 (PA).

4.4 Quality Conformance Inspection

4.4.1 Lot formation. A lot shall consist of one or more batches of $LiAsF_6$ produced by one manufacturer, in accordance with the same specification, or same specification revision, under one continuous set of operating conditions. Each lot shall consist of that quantity of $LiAsF_6$ that has been subjected to the same unit chemical or physical mixing process intended to make the final product homogeneous. The product shall be submitted for inspection in accordance with MIL-STD-105.

4.4.2 Testing (see 6.3 and 6.6). Sampling and testing shall be performed in a dry atmosphere.

4.4.2.1 Sampling. Approximately 1 pound of $LiAsF_6$ shall be withdrawn from each batch to be sampled using ASTM Procedure E300-70 for solids. Samples shall be selected for inspection in accordance with MIL-STD-1235, CSP-1 Plan, Inspection Level II, AQL 6.5%. If any sample fails to meet any test requirement the batch represented by the sample shall be rejected. All batches produced between the time that the last batch was tested and accepted and the batch which failed should be tested in accordance with the applicable methods given in paragraph 4.4.3. If any of these batches fail to meet any of the test requirements, that batch shall also, be rejected. In addition, after any failure of a batch the contractor will return to 100% inspection until "i" successive batches are accepted as required by MIL-STD-1235. The samples shall be subjected to the tests listed below:

Inspection/Requirement	Defect Classification
Form & Color (see 3.1.1)	Major B
X-ray Diffraction (see 3.1.2)	Major B
Infra-red Spectroscopy (see 3.1.3)	Major B
Oxygen Containing Compounds (see 3.1.4)	Major B
Moisture (see 3.1.4)	Major B
pH (see 3.1.5)	Major B
Solubility (see 3.1.5)	Major B
Particle Size	Major B
Potentiometric Value	Major B

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

4.4.2.2 Inspection Equipment. The government reserves the right to inspect the contractor's equipment and determine that he has available and utilizes correctly, measuring and test equipment of the required accuracy and precision and that the instruments are of the proper type and range to make measurements of the required accuracy. Commercial inspection equipment, shall be employed where applicable for all tests and examinations specified in 4.4.3. The contractor is responsible for assuring proper calibration procedures are followed. Government approval of inspection equipment is required prior to its use for acceptance purpose.

4.4.3 Test methods and procedures. (see 6.2) The tests in 4.4.3.4 thru 4.4.3.14 shall be performed using prescribed analytical procedures for replicate determinations given in standard analytical textbooks (see 6.3).

4.4.3.1 Form. Spread approximately 1/2 pound of the sample on a flat surface and examine the material visually for the presence of contamination and form at a magnification of 25X. The sample shall be examined in a dry atmosphere area.

4.4.3.2 X-Ray Diffraction. An X-ray diffraction pattern of the material shall be obtained using a powder X-ray diffraction technique described in a standard or reference textbook on X-ray diffraction.

4.4.3.3 Infra-red Spectroscopy. Perform an infra-red spectrographic analysis of the material in accordance with method given in ASTM-E-168.

4.4.3.4 Metallic Impurities. Determine the metallic impurities using a Atomic Absorption method described in a standard or reference textbook.

4.4.3.5 Nitrogen. Determine the nitrogen content using a colorimetric method of analysis (suitable for materials containing only a few parts per million nitrogen) described in a standard or reference textbook (see 6.8).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

4.4.3.6 Halogens. Determine the halogens present in the compound using a spectrophotometric method described in the literature or reference textbook (see 6.4).

4.4.3.7 Sulfur. Determine the sulfur present in the compound using a method appearing in the literature or a reference textbook (see 6.5).

4.4.3.8 Carbon. Determine the carbon present in the compound using a direct combustion method appearing in a reference textbook. It is suggested that the direct combination method utilize purified nitrogen gas and a two-part combination tube; 500-700 mg of sample in the rear section and Copper Oxide (CuO) catalyst in the forward section and the following procedures be used:

a. Heat catalyst to 500°C
b. Heat samples to 180°C for 1/2 hour.
c. Absorb CO_2 in an Ascarite filled cartridge and absorb water in an Anhydrone filled cartridge.
d. Weigh cartridge
e. Calculate % carbon and % hydrogen according to the following equations:

$$\%C = \frac{(\text{Wt } CO_2)(12)}{(44)\ (\text{grams of sample})} \times 100$$

$$\%H = \frac{(\text{Wt } H_2O)\ (2)}{(18)\ (\text{grams of sample})} \times 100$$

4.4.3.9 Oxygen Containing compounds. Determine the presence of oxygen containing compounds present in the material by using a pyrolysis mass spectrographic method which appears in a standard or a reference textbook.

4.4.3.10 Water (see 6.3). Determine the moisture content of the material using the Karl Fischer method given in ASTM-E203.

4.4.3.11 pH. Prepare a 1 Molar solution in the $LiAsF_6$ by dissolving 195.86g of the sample into a liter of distilled water and determine the pH of the resultant solution in accordance with the method given in ASTM-E70.

In addition, prepare a 2 Molar solution of the $LiAsF_6$ by dissolving 391.72g of the sample into a liter of Methyl Formate. Quantitatively transfer 100 ml of this solution to a 1000 ml volumetric flask and dilute to the mark with distilled water. Determine the pH of this solution in accordance with the method given in ASTM-E70. The pH measurement is continued until a constant value is observed for at least a 10 minute period. Carbon dioxide should be excluded by an inert atmosphere.

In the above procedures smaller solutions can be prepared with respective corresponding weights of materials reduced accordingly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

4.4.3.12 Solubility in Methyl Formate. Transfer 9.79 grams of the sample to a 100 ml beaker and add 25 ml Methyl Formate. Add a magnetic stirring bar and allow to stir for 30 minutes at ambient on a magnetic stirrer. Remove stirring bar from beaker and allow beaker to stand for 3 minutes. During mixing the container must be sealed to prevent loss of methyl formate. Observe for any residual solute or turbidity.

4.4.3.13 Hydrolysis/Dehydration. Determine the hydrolysis/dehydration of the 2 molar solution prepared in 4.4.3.11 as follows:

4.4.3.13.1 Equipment
- a. Injection part packed with glass wool.
- b. Column - Chromosorb 101, 4' X 1/8" diameter
- c. Detector - Flame ionization
- d. Carrier Gas - Helium at 20 cc/min

4.4.3.13.2 Procedure: Add 10% distilled water to 4 ml of the MF solution. Store this solution at 57 $\pm$ 1°C for 200 hours in a suitable glass container (5cc vial) capable of being sealed air tight with stopper and withstanding 100 psi. Remove stoppered container and measure by standard gas chromatographic techniques:

Methanol - 200 hours
Dimethyl Ether - 200 hours

4.4.3.14 Particle Size. Superimpose the sieves of the meshes required in 3.1.5 as defined in ASTM E11 and attach the receiving pan to the bottom. Place 100 grams of the sample in the top sieve, mount the assembly on a shaker and operate the shaker for 5 minutes. At the end of 5 minutes weigh the granules retained in each sieve and in the pan and calculate the percentages of each.

4.4.3.15 Potentiometric Value. Check the potentiometric value (EMF) of a 2 Molar solution of the sample in methyl fomrate (see 4.4.3.11) in accordance with ASTM-E70 or equivalent except that meter shall be set to indicate millivolts and electrodes shall be: Saturated Calomel and Platinum.

5. PREPARATION FOR DELIVERY

5.1 Packing

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

5.1.1 Level A and Level C. Unless otherwise specified the $LiAsF_6$ shall be packed in accordance with manufacturer's commercial practice to assure acceptance by common carrier for safe delivery at first destination for immediate use.

5.2 Marking. Unless otherwise specified, the shipping containers shall be marked in accordance with MIL-STD-129, and shall include the lot number.

6. NOTES

6.1 Ordering data. See MIL-A-48078 (PA).

6.2 Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted thru the Contracting Office to: Commander, ATTN: SARPA-QA-A-P, Picatinny Arsenal, Dover, New Jersey 07801. This description should include but not be limited to the procedures used, the accuracy and precision of the method, test data to demonstrate the accuracy and precision and drawings of any special equipment required.

6.3 The material is extremely hygroscopic and the handling of the sample should be in a strictly anhydrous atmosphere or should be conducted with dry, closed samplers. All equipment needs to be dried in a vacuum oven at 50°C or higher.

6.4 Method described in F.W. Chapman Jr and R.M. Sherwood, Anal, Chem., 29 (2), 172 (1957) has been found applicable.

6.5 Methods described in J.S. Fritz, S.S. Yamamura, Anal. Chem., 29(1) 158 (1957) or Standard Methods of Chem. Analysis, IIB, 2483 have been found applicable.

6.6 Toxicity. Specific information regarding toxicological properties of lithium hexafluoroarsenate is not available. Normal precautionary procedures associated with the use of inorganic arsenate salts should be observed. In addition, since hydrofluoric acid is formed in acidic aqueous media, appropriate precautions for hydrofluoric acid should be taken.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

6.7 Material meeting the requirements of this specification was previously obtained from.

U.S. Steel Corporation
Agri. Chemicals Division
30 Pryor Street S. W.
P. O. Box 1685
Atlanta, Georgia 30301

6.8 A suitable colorimetric method for nitrogen is described in Methods for Chemical Analysis of Water and Wastes, p154, Environmental Protection Agency, 1971, Cincinnati, Ohio 45268.

Custodian:
Army-PA

Preparing Activity:
Army-PA

Project Number: 6810-AA65

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.




FIGURE 1 INFRARED SPECTRUM OF QUALIFIED SAMPLE OF $LiAsF_6$

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:39Z
Check the source to verify that this is the current version before use.