MIL-W-80105C
18 April 1985
SUPERSEDING
MIL-W-80105B
26 October 1979

MILITARY SPECIFICATION

WELDING TORCH SETS, ARC, GAS SHIELDED TUNGSTEN ELECTRODE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers welding torch sets which, when connected to a suitable power source, have the function of welding ferrous and non-ferrous metals by the gas tungsten-arc welding (GTAW) Method.

1.2 Classification. This specification covers welding torch sets of the following types and sizes, as specified (see 6.2.1).

Type I - Air Cooled
- Size 80 - 80 Amp
- Size 125 - 125 Amp
- Size 150 - 150 Amp
- Size 200 - 200 Amp

Type II - Liquid Cooled
- Size 225 - 225 Amp
- Size 300 - 300 Amp
- Size 500 - 500 Amp

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Industrial Plant Equipment Center, ATTN: DIPEC-SSM, Memphis, Tennessee 38114-5297, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 3431

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-W-45562 - Welding and Soldering Equipment, Supplies and Accessories, Packaging of.

STANDARDS

FEDERAL

FED-STD-H28 - Screw Thread Standards for Federal Services.

FED-STD-376 - Preferred Metric Units for General Use by the Federal Government.

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein.

U. S. DEPARTMENT OF LABOR

OSHA 2206 - General Industry, OSHA Safety and Health Standards (29 CFR 1910).

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington, DC 20402.)

(Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM-D-3951 - Commercial Packaging, Standard Practice for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 First Article. When specified (see 6.2.1), a sample shall be subjected to first article inspection (see 4.3 and 6.2).

3.2 Design. The welding torch set shall be new and one of the manufacturer's current models capable of welding ferrous and non-ferrous metals in accordance with the requirements herein. The welding set shall include all components, parts, and features necessary to meet the performance requirements specified herein. All parts subject to wear, breakage, or distortion shall be accessible for adjustment, replacement, and repair.

3.2.1 Measurement systems. Unless otherwise specified, either the U.S. Customary System of Units (US) or the International System of Units (SI) shall be used in the design and construction of the welding set. When only one system of measurements is acceptable, the particular system required shall be as specified (see 6.2.1). In this specification, all measurements, dimensions, sizes and capacities are given in US units. These measurements may be converted to SI units through the use of the conversion factors and methods specified in FED-STD-376.

3.2.1.1 Measuring and indicating device calibrations. Unless otherwise specified, either the U.S. Customary System of Units (US) or the International System of Units (SI) shall be used to graduate measuring and indicating devices such as scales, pressure gauges, and other similar devices. When only one system of graduation is acceptable, the particular graduation required shall be as specified (see 6.2.1). Regardless of the measurement system used, all measuring and indicating devices on the welding set shall be graduated in the same system.

3.2.2 Reclaimed materials. The welding set may contain reclaimed materials provided such materials will not jeopardize the welding set's intended use and performance. The reclaimed materials shall have been reprocessed, remanufactured or recycled in a manner which will restore them

Source: https://assist.dla.mil -- Downloaded: 202640-23T04:39Z
Check the source to verify that this is the current version before use.

to the same chemical composition and physical properties as the materials originally selected for use on the welding set.

3.2.3 Energy efficiency. The welding set and all its applicable components that directly consume energy in normal operation shall be designed and constructed for the highest degree of energy efficiency as governed by the latest developments available within the industry.

3.2.4 Safety and health requirements. Covers, guards, or other safety devices shall be provided for all parts of the welding set that present safety hazards. The safety devices shall not interfere with the operation of the welding set. The safety devices shall prevent unintentional contact with the guarded part, and shall be removable to facilitate inspection, maintenance and repair of the parts. All welding set parts, components, mechanisms, and assemblies furnished on the welding set, whether or not specifically required herein, shall comply with all of the requirements of OSHA 2206 that are applicable to the welding set itself. Additional safety and health requirements shall be as specified (see 6.2.1).

3.2.5 Mercury restriction. The welding set shall not contain mercury or mercury compounds nor be exposed to free mercury during manufacture.

3.2.6 Asbestos restriction. Asbestos and materials containing asbestos shall not be used on or in the welding set.

3.2.7 Environmental protection. The welding set shall be designed and constructed such that, under the operating, service, transportation and storage conditions described herein, the welding set shall not emit materials hazardous to the ecological system as prescribed by Federal, state or local statutes in effect at the point of the installation.

3.2.8 Interchangeability. To provide for replacement of worn or damaged parts, all parts shall be manufactured to definite dimensions and tolerances that will permit installation of replacement parts without modification to the part or the welding set.

3.3 Construction. The welding set shall be constructed of parts which are new, without defects and free of repairs. The structure shall be capable of withstanding all forces encountered during operation of the welding set to its maximum rating and capacity without permanent distortion.

3.3.1 Welding, brazing or soldering. Welding, brazing, or soldering shall be employed only where specified in the original design. None of these processes shall be employed as a repair measure for any defective part.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

3.3.2 Fastening devices. All screws, pins, bolts, and other fasteners shall be installed in a manner to prevent change of tightness. Fastening devices subject to removal or adjustment shall not be swaged, peened, staked, or otherwise permanently installed.

3.3.3 Surfaces. All surfaces shall be clean and free of sand, dirt, fins, sprues, flash, scale, flux, and other harmful or extraneous materials. All edges shall be either rounded or beveled unless sharpness is required to perform a necessary function. Except as otherwise specified herein, the condition and finish of all surfaces shall be in accordance with the manufacturer's commercial practice.

3.3.4 Painting. All surfaces requiring paint shall be cleaned of all foreign matter. Unless otherwise specified (see 6.2.1), the welding set shall be painted in accordance with manufacturer's standard commercial practice which shall be not less than one coat of primer and one coat of finish color or one coat of electrostatically applied epoxy powder paint.

3.3.5 Threads. All threaded parts used in the welding set and its related attachments and accessories shall conform to FED-STD-H28 and the applicable "Detailed Standard" section referenced therein.

3.3.6 Dials. Dial diameters shall be such that graduations may be easily read. Dials shall be permanently and legibly engraved or etched on a nonglare background.

3.4 Performance. When connected to the specified power source, shielding gas supply and 40° C or lower coolant supply (type II), the welding sets shall be capable of producing satisfactory welds in any position on ferrous and non-ferrous materials. The welding sets shall be capable of performing welding operations when using alternating current, stabilized high-frequency current super-imposed on either the alternating current, direct current straight polarity or direct current reverse polarity. Using super-imposed high-frequency alternating current, the welding sets shall be capable of performing quality welds on aluminum plate in accordance with the requirements of table I. The liquid coolant pressure range for the type II units shall be from 30 to 50 PSIG. Each welding set shall be capable of continuous operation using the size electrodes and argon gas flow range specified in table II.

3.5 Components. The welding set shall consist of, but not be limited to, the following basic components:

a. Torch, cable, and gas hose assembly.
b. Coolant hose assembly (type II).
c. Gas regulating equipment.

3.5.1 Torch, cable, and hose assembly. The torch shall be constructed of light-weight, high-impact resistance materials having high dielectric strength. The torch shall have a handle and a head with an electrode

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:39Z
Check the source to verify that this is the current version before use.

TABLE I - AC-TIG Welding performance.

Diameter of Tungsten Electrode (Inch)	Aluminum Thickness (Inch)	Filler Rod Diameter (Inch)	Alternating Current (Amperes)	Joint Type	Number of Passes	Gas Flow CF/HR
1/16	3/32	3/32	70-100	Square Butt	1	20
3/32	1/8	1/8	125-160	Square Butt	1	25
1/8	1/8	1/8	125-160	Square Butt	2	25
3/16	1/4	1/8	225-257	60° Single Bevel	2	25
3/16	1/4	3/16	250-320	60° Single Bevel	1	30
1/4	3/8	1/4	325-400	60° Single Bevel	2	35
1/4	1/2	1/4	375-450	60° Single Bevel	3	35
5/16-3/8	1	1/4-3/8	500-600	60° Single Bevel	--	35-45

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

TABLE II - Electrode diameters and gas flow requirements.

Type and Size	Electrode Capacity (Diameter-Inch) Chuck or Collet and Collet Body Required for Each	*Argon Gas Flow (CU-Ft/HR)
Type I, Size 80	0.020 0.040 1/16	5-25
Type I, Sizes 125 & 150	0.020 0.040 1/16 3/32	5-30
Type I, Size 200	0.020 0.040 1/16 3/32 1/8	5-35
Type II, Size 225	0.020 0.040 1/16 3/32 1/8	5-35
Type II, Size 300	0.020 0.040 1/16 3/32 1/8 5/32	5-40
Type II, Size 500	3/32 1/8 5/32 3/16	15-45

* Range in which satisfactory welds shall be obtainable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

holding device, electrode extension cap, and a gas nozzle. The cable and hoses shall terminate into the end of the handle. Unless otherwise specified, the head shall be positioned to the handle at an angle of 70 degrees. When required, angle of the head to the handle shall be either 90 degrees fixed, 90 degree flexible or straight flexible as specified (see 6.2.1). The head of the torch shall have gas passages to direct the flow of shielding gas to the weld zone area. In addition to the gas passages, the type II torch shall have leakproof liquid coolant passages that will direct the flow of coolant to and from the torch. The torch shall be furnished complete with an interchangeable electrode holding device (collet assembly), electrode extension cap, nozzle, all required seals, gas lens, hoses and welding cable, all assembled and ready for use when fitted with proper size electrode and connected to the required supply sources. The length of the electrode extension cap and the length of the nozzle on the gun shall be as specified (see 6.2.1). When specified (see 6.2.1), extra nozzles, extension caps, and collet assemblies shall be provided for each gun.

3.5.1.1 Electrode holding device. Each torch shall be furnished with the necessary chucks or collets, collet body and collet inserts required to use all size electrodes specified in table II for the size torch.

3.5.1.2 Electrode extension cap. The torch shall have provisions for using various lengths of tungsten electrodes.

3.5.1.3 Gas nozzles. The torch shall have a removable nozzle or cup to direct and form a pattern of shielding gas around the weld zone area and still provide adequate visibility of the arc. The nozzle shall be made of heat resistant metal, ceramic or glass material, and shall be easily replaceable without the use of tools.

3.5.1.4 Cable and hose assembly. The assembly shall consist of a shielding gas hose, liquid coolant hose (type II), hose connections, and a welding current cable. The assembly shall be attached to the torch and ready for use. The length of the assembly shall be not less than 12 feet, measured from the end of the handle to the hose connections and conductor terminals. When specified (see 6.2.1), the hose and cable assembly shall be 25 feet in length.

3.5.1.4.1 Shielding gas and coolant hose. The hose shall be made of heat resistant vinyl plastic, synthetic rubber, or plastic lined rubber material. The hose shall be compatible with the gases used in the gas tungsten-arc processes, and with anti-freeze solutions and anti-corrosion inhibitors used in the cooling system. The coolant hose for the type II sets shall comply with the pressure and temperature requirements in paragraph 3.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

3.5.1.4.2 Hose connections. The hose connections for the shielding gas and coolant hoses shall be compatible with the components of the set and accessories. The gas and coolant hoses shall have threaded connections on the input ends and the connection for the gas hose shall be for connecting to the regulator and flowmeter.

3.5.1.4.3 Welding current cable. The cable shall be extra fine stranded soft copper wire. The cable for the type II set shall be treated or coated to resist corrosion by the coolant. The cable shall have insulation of adequate dielectric strength to provide operator protection. The insulation shall fit loosely around the conductor and may also serve as a hose for the flow of shielding gas or coolant. The input current terminal and hose adaptor of the conductor shall have a hole not less than .500 inch in diameter for connection to the power supply.

3.5.1.4.4 Cable and hose protection. The cable and hose assembly for the type II welding set shall be wrapped or otherwise enclosed with a removable nonconductive, fireproof sheath which may be removed without disconnecting the torch hoses or cable. The sheath shall enclose the assembly from the end of the torch handle to within not less than three feet of the assembly.

3.5.2 Gas equipment. Each welding set shall be furnished with the following gas equipment:

a. One pressure regulator with input pressure gauge for use with both argon and helium.

b. One flowmeter with minimum included range of from 5 to 95 cubic feet per hour of helium.

c. One flowmeter with minimum included range of from 0 to 60 cubic feet per hour of argon.

3.5.2.1 Flowmeter. The flowmeter shall be of the floating-ball or floating-vane type. Single or dual flowmeters are acceptable. Single-type flowmeters shall have a separate scale for each gas, calibrated to the ranges mentioned above. The flowmeter and pressure regulator may be furnished as a single unit.

3.5.2.2 Pressure regulator. The pressure regulator shall have an input gauge calibrated in PSI for use with both argon and helium gas. When specified, the pressure regulator shall be of the two-stage regulating type.

3.6 Optional equipment.

3.6.1 Hoses. When specified (see 6.2.1), additional liquid coolant hose and gas hose shall be provided. Number to be provided and length of each hose shall be as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

3.6.2 Overheat protective device. When specified (see 6.2.1), the type II torch shall have a device to shut-off the welding current to protect the torch and current conductor from overheating in the event of restricted coolant flow of the gas and coolant pressure. The connections shall be compatible with the connection of the components of the welding set.

3.6.3 Liquid coolant pressure regulator. When specified (see 6.2.1), a liquid coolant pressure regulator shall be provided. The regulator shall be capable of reducing the high pressure of the coolant supply to a pressure within the operating range of the torch.

3.6.4 Self-contained liquid cooling system. When specified (see 6.2.1), the type II torch shall be provided with a portable, self-contained cooling system of the recirculating pump type. The system shall consist of a tank, electric motor-driven pump, pressure regulator, and a strainer or filter. The system shall be of adequate capacity to provide the proper cooling of the welding torch at all times. All materials shall be noncorroding and noncontaminating to the water system.

3.7 Marking of instruction plates, indicating plates and nameplates. All words on instruction and indicating plates shall be in the English language. Characters shall be engraved, etched, embossed, printed or stamped in boldface on a contrasting background.

3.7.1 Nameplate. Unless otherwise specified (see 6.2.1), a nameplate shall be placed in the package with each welding set. The nameplate shall contain the information listed below. If the welding set is a special model, the model designation shall include the model of the basic standard model and a suffix identified in the manufacturer's permanent records. The captions listed may be shortened or abbreviated, provided the entry for each caption is clear as to its identity.

Nomenclature
Manufacturer's name
Manufacturer's model designation
Manufacturer's serial number
Contract Number or Order Number
National Stock Number or Plant Equipment Code
Date of manufacture

3.8 Technical data. When technical data is required it shall be furnished in accordance with the requirements of the contract.

3.9 Workmanship. Workmanship of the welding set and accessories shall be of a quality equal to that of the manufacturer's commercial equipment of the type specified herein.

4. QUALITY ASSURANCE PROVISIONS

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).

b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article inspection is required, it shall be applied to the first article submitted in accordance with 3.1. Unless otherwise specified (see 6.2.1), first article inspection shall consist of the examination in 4.5 and all tests in 4.6. Failure of the item to pass the first article tests shall be cause for rejection.

4.4 Quality conformance inspection. Quality conformance inspection shall be applied to each item prior to being offered for acceptance under the contract. Unless otherwise specified (see 6.2.1) quality conformance inspection shall consist of at least the examination in 4.5 and the inspection in 4.7. Failure of the item to pass the examination or tests shall be cause for rejection.

4.5 Examination. The welding torch set and equipment shall be examined for design, construction, materials, components, electrical equipment, and workmanship to determine compliance with the requirements of this specification.

4.6 Tests.

4.6.1 Operational test. The welding torch set shall be connected to an alternating current power supply with super-imposed high frequency. The gas shall be turned on and adjusted to the proper flow, and an arc started. (No actual welding need be done.) There shall be no evidence of high frequency current or gas leakage at any part of the torch except at the outlet nozzle. The assembly shall be checked for gas leaks by turning off the electrical current and immersing the unit in water. A gas or water leak anywhere in the assembly shall be cause for rejection of the welding set. The gas flow through the hose and electrode holder, for the gas leak test, shall be at the highest rate specified in table II for the particular set

4.6.2 Performance test. Using alternating super-imposed high-frequency current, the welding set shall be tested in accordance with the requirements

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:39Z
Check the source to verify that this is the current version before use.

of table 1. A weld shall be made using the largest size tungsten electrode for each type and size of welding set furnished. The weld shall be made without stopping except for normal interruption of the arc. There shall be no evidence of damage to the torch by heat or of the softening or distortion of the parts. The weld zone shall be inspected for the proper shielding from the atmosphere. There shall be no evidence of oxidation, such as dull or dark areas.

4.7 Packaging inspection. Packaging shall be inspected to determine compliance with the requirements of section 5.

5. PACKAGING

5.1 Packaging, packing, and marking. Unless otherwise specified, packaging, packing, and marking shall be in accordance with ASTM-D-3951. When required, packaging, packing and special marking shall be accomplished in accordance with MIL-W-45562 as specified (see 6.2.1).

6. NOTES

6.1 Intended use. The welding sets covered by this specification are to be used for gas tungsten-arc welding of ferrous and non-ferrous metals in repair shops, manufacturing, field construction, and pipe fabrication.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Type and size required, etc. (see 1.2).

c. When first article is required for inspection and approval (see 3.1).

d. If welding set is required to be configured in a specific measurement system (US or SI), state required system (see 3.2.1).

e. If measuring and indicating devices are required to be graduated in a specific measurement system (US or SI), state required system (see 3.2.1.1).

f. Additional safety and health requirements, if required (see 3.2.4).

g. Painting, if different (see 3.3.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

h. Torch, angle of head, and fixed or flexible, specify (see 3.5.1).

i. Specify length of extension cap (short, medium or long) and length the nozzle shall be on the gun (see 3.5.1). (Standard nozzle lengths available, inches: 5/8, 1, 1-5/32, 1-5/16, 1-7/32, 1-11/16, 1-13/16, 1-7/8, 1-27/32, 1-31/32 and 3-7/32)

j. Specify size and quantity of extra collet assemblies required, specify length and quantity of extra electrode extension caps required and specify length and quantity of extra nozzles required in 3.5.1).

k. Specify 25-foot hose and cable assembly, if required (see 3.5.1.4).

l. Extra liquid and gas hose, if required, specify number required of each and length (see 3.6.1).

m. Overheat protective device (type II only), if required (see 3.6.2).

n. Liquid coolant pressure regulator, if required (see 3.6.3).

o. Self-contained liquid cooling system, if required (see 3.6.4).

p. Nameplate, if different (see 3.7.1).

q. First article inspection, if different (see 4.3).

r. Quality conformance inspection, if different (see 4.4).

s. Level of packaging, packing and marking, if different (see 5.1).

6.2.2 Contract data requirements. Required technical data such as operator's manuals, parts lists, wiring diagrams, foundation and anchor bolt plans and acceptance test reports should be specified on a DD Form 1423, Contract Data Requirements List, incorporated into the contract.

6.3 First article. When first article inspection is required, the item to be tested should be the first item offered for acceptance under the contract. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examination, test and approval of the first article.

6.4 Safety and health requirements. Paragraph 3.2.5 requires compliance only with those OSHA requirements that concern the welding set itself. It does not require compliance with those OHSA requirements that concern "the welding set in its operating environment" such as noxious vapors, air contaminants, and heat. Since OSHA limits the total hazard level of these

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:39Z
Check the source to verify that this is the current version before use.

hazards in the environment (and does not limit the hazard level of individual welding sets in the environment) the procuring activity is advised to analyze the existing hazard levels in the proposed operating environment, and specify additional requirements that will integrate the welding set into its future operating environment. The above, and any other additional safety and health requirements should be specified in detail under 6.2.1(g).

6.5 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:
Army - AL
Navy - SH
Air Force - 99

Review Activity:
Army -ME, CE
Navy - SH
Air Force - 84
DLA- GS

User Activities:
Navy - YD, MC, CE

Preparing Activity:
DLA-IP

Project Number:
3431-0161

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY
Headquarters
Defense Industrial Plant Equipment Center
Memphis, Tennessee 38114-5297

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Industrial Plant Equipment Center
ATTN: DIPEC-SSM
Memphis, Tennessee 38114-5297

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-W-80105C	Welding Torch Sets, Arc, Gas Shielded Tungsten Electrode

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:39Z
Check the source to verify that this is the current version before use.