
FED SUP CLASS 5307



UNDERSIZE AND OVERSIZE IDENTIFICATION			-.003 (-3)	STANDARD	+ 003 (3)	+ 006 (6)	+ 009 (9)	+.012 (12)
C			.495 -.500	.495 -.500	.495 -.500	.495 -.500	.504 -.509	.504 -.509
PD BEFORE PLATING			.4528- .4528	.4548-.4558	.4578-.4588	.4608-.4618	.4638-.4648	.4668-.4678
PD AFTER PLATING			.4523-.4538	.4553-.4568	.4583-.4598	.4613-.4628	.4643-.4658	.4673-.4688
PD LEAD THREAD			.4450-.4470	.4480- .4500	.4510-.4530	.4540-.4560	.4570-.4590	.4600-.4620
L	A	B	PART NUMBER	PART NUMBER	PART NUMBER	PART NUMBER	PART NUMBER	PART NUMBER
1.938	1.000	750	AN129137	AN129138	AN129139	AN129140	AN129141	AN129142
2.188	1.250	.750	AN129143	AN129144	AN129145	AN129146	AN129147	AN129148

INACTIVE FOR DESIGN AFTER 26 OCTOBER 1972 NO SUPERSEDING STANDARD

NOTE PITCH DIAMETERS OF BOTH THREADED ENDS SHALL BE CONCENTRIC WITHIN .006 FIR
(a) CROSS THREADING PERMISSABLE AT THREAD RUNOUTS ON SHORT STUDS
MATERIAL STEEL AMS 6322 (AMS 6320 MATERIAL MAY ALSO BE USED FOR THESE PARTS UNTIL 1 JAN 1960)
HARDNESS ROCKWELL C26-32
FINISH CADMIUM PLATE AMS 2400 DIMENSIONS ARE AFTER PLATING EXCEPT WHERE SHOWN
SURFACE ROUGHNESS AS291
MANUFACTURING SPECIFICATION AMS 7456
(3) INSPECTION ALL PARTS SHALL UNDERGO MAGNETIC INSPECTION IN ACCORDANCE WITH AMS2640
BREAK SHARP EDGES 003- 015 UNLESS OTHERWISE SPECIFIED
DIMENSIONS IN INCHES UNLESS OTHERWISE SPECIFIED TOLERANCES, LINEAR DIMENSIONS ± 010
DO NOT USE UNASSIGNED PART NUMBERS
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE ENGINE AND PROPELLER UTILITY PARTS COMMITTEE OF THE SAE

APPROVED 19 May 50 REVISED (1) 23 Jun 58 (2) 16 Oct 72 (3) 30 June 1986

DISTRIBUTION STATEMENT A Approved for public release, distribution is unlimited.

☆U S GOVERNMENT PRINTING OFFICE 1986 — 605 036/43906

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T14:27Z
Check the source to verify that this is the current version before use.