[METRIC]

A-A-1611A
April 4,1994
SUPERSEDING
A-A-1611
April 17, 1981

COMMERCIAL ITEM DESCRIPTION

CARD, INDEX

The General Services Administration has authorized the use of this commercial item description

SCOPE
This Commercial Item Description covers cotton or linen and chemical wood index cards, white and colored.

CLASSIFICATION

The index cards covered by this specification shall be in the following Grades.

Grade A - 100% cotton or linen fibers
Grade B - Not less than 25% cotton or linen fibers; the remainder shall be chemical wood pulp.
Grade C - Chemical wood pulp, white and colored.

1. **SALIENT CHARACTERISTICS**

A. Stock: Grade A stock shall conform to the requirements of JCP-K30, 100% Cream-White Index. Basis weight: 226 g/m^2 (125 pounds)$\pm$ 5%, when tested in accordance with TAPPI test method T410. Grain direction shall be parallel to the long dimension of the index card.

Grade B stock shall conform to the requirements of JCP-K20, 25% Index, White and Colored. Basis weight shall be as specified in the contract or ordering document, with a tolerance of $\pm$ 10%, when tested in accordance with TAPPI test method T410. Grain direction shall be parallel to the long dimension of the index card.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, N.Y. 10278.

DISTRIBUTION STATEMENT A:
Approved for public release; Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

Grade C stock shall conform to the requirements of JCP-K10, Index, White and Colored. Basis weight shall be as specified in the contract or order, with a tolerance of ± 10%, when tested in accordance with TAPPI test method T410. Grain direction shall be parallel to the long dimension of the index card.

B. Color: The color of the index card shall be white, blue, buff, green, pink, salmon, or yellow, as specified in the contract or ordering document and shall conform to the standard sample(s) as adopted by Joint Committee on Printing.

C. Dimensions: The card dimensions shall be 3 by 5, 4 by 6, or 5 by 8 inches (± 1/16 inch), as specified in the ordering document. NOTE: When the difference in length between the two diagonals does not exceed 1/32 inch, the card shall be considered square.

D. Rulings: Cards shall be unruled, or ruled on one side, as specified. Rulings shall be parallel to the long dimension of the cards and in accordance with standard commercial practice. Ruled lines shall be clear cut and continuous.

Workmanship: The index cards shall be clean and free from lint, fuzz, holes, nicks, dirt or loose particles and shall be uniform in color and formation. The cards shall be cleanly and uniformly cut with smooth edges.

2. REGULATORY REQUIREMENTS:

The contractor shall certify that the minimum content standard shall be 50% recovered materials, including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definitions of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(a) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

3. QUALITY ASSURANCE:

Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government.

The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms t the producer's own drawings, specifications, and quality assuranc practices. The government reserves the right to require proof of conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Each lot of Cards, Index shall be inspected for conformance to th requirements herein. Sampling for inspection shall be in accordance with MIL-STD-105 using the plans specified below.

1. Visual and dimensional characteristics - Inspection Level I with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one index card.

2. Tests - Sampling shall be in accordance with plan II of TAPPI T400, for the required tests.

4. PREPARATION FOR DELIVERY:

Packaging, packing and marking shall be as specified in the contract o purchase order.

5. REFERENCED DOCUMENTS:

The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, P.O. Box 105113
Atlanta, GA 30348
(404) 446-1400

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

MIL-STD-105 is available from:

STANDARDIZATION DOCUMENTS ORDER DESK
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Government Paper Standards, Joint Committee on Printing Publications (JCP) are available from:

The Superintendent of Documents
US Government Printing Office
Washington, DC 20402.

6. **NOTES:**

A. Ordering Data: Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Grade.
(2) Dimensions.
(3) Color.
(4) Basis weight.
(5) Punching (when applicable).
(6) Ruling (when applicable).
(7) Specific packaging, packing, palletization and, marking requirements.
(8) Whether chlorine or chlorine compound bleaching is acceptable.

B. **Item Identifiers/Reference Part Number System (For Cataloging Use Only)**

AA1611 - A: This example describes a 100% cotton or linen fiber index card.

GRADE A - 100% cotton or linen fibers.
B - Not less than 25% cotton or linen fibers; the remainder shall be bleached chemical wood pulp.
C - Chemical wood pulp, white and colored.

Preparing activity

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.