[METRIC]
A-A-2951
October 2, 1995

COMMERCIAL ITEM DESCRIPTION

PAPERBOARD, DRAWING

The General Services Administration has authorized the use of this commercial item description as a replacement for UU-P-663 which is cancelled.

1. SCOPE This description covers single and double faced paperboard for use in pencil, ink and water color drawings.

2. CLASSIFICATION The paperboard shall be of the following, as specified:

2.1 Type 1 - Single faced
2 - Double faced

2.1.1 Grade A - 100% cotton or linen
B - 50% cotton or linen

2.1.2 Class 1 - Rough finish
2 - Smooth finish

3. SALIENT CHARACTERISTICS.

3.1 Material.

3.1.1 Facing sheet. The facing sheet shall be white in color. The fiber furnish of the facing sheet for Grade A shall contain not less than 100 percent cotton or linen fiber. The facing sheet for Grade B shall contain not less than fifty percent cotton or linen fiber and shall be free from unbleached or groundwood pulp. The facing sheet basis weight for both grades shall be 120g/m^2 (32 pounds (17 x 22 - 500)) minimum.

3.1.2 Backing sheet. The backing sheet of Type 1 paperboard shall be any color except white to the facing sheet to establish the intended facing sheet. The backing sheet for Type 2 shall conform to 3.1.1.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

3.1.3 Paper Core. The paper core shall be made from cellulosic, fibrous material.

3.2 Construction. The drawing paperboard shall be produced by pasting the facing and the backing sheets to the paperboard core. The finished drawing paperboard shall be flat and have even working surfaces free from mechanical defects or separation of facing and backing sheets from the paperboard core.

3.3 Dimensions.

3.3.1 Size. Drawing paperboard shall be furnished in either sizes 55.88cm x 76.20cm or 76.20cm x 101.60cm (22"x30" or 30"x40"), as specified. A tolerance of +/- 3.175mm (1/8 inch) shall be allowed for each dimension. The sheets shall be trimmed square on four sides with smooth, clean-cut edges. The finished paperboard shall be considered square if the difference between the two diagonals does not exceed 3.175mm (1/8 inch).

3.3.2 Thickness. The thickness shall be as specified in the contract or order.

3.4 Identification and Marking. Type 1 paperboard shall be identified by the manufacturer's name or trade mark on the backing sheet. Manufacturer's name or trade mark appearing as a colorless impression in one corner of all sizes of single or double faced paperboard is optional.

3.5 Surface bonding. The drawing surface(s) of each type, grade and class of paperboard shall be free of lint, fuzz, or loose particles.

3.6 Workmanship. Drawing paperboard shall be flat and uniform in thickness throughout. Facing and backing sheets shall be free from hard spots, wrinkles, shall be securely bonded to the paperboard core or any other defects that may affect appearance or serviceability of the drawing paperboard.

3.7 Bleaching. To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4. REGULATORY REQUIREMENTS

4.1 The contractor shall certify that the facing and backing sheets shall be no less than 50% recovered materials including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993. As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

The paper core shall be no less than 100% postconsumer recovered materials in accordance with Title 40 CFR, Part 250. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.2 Recycled Content Labeling. The recycled content shall be marked on the product or unit pack.

5. QUALITY ASSURANCE PROVISIONS

5.1 Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5.2 Suppliers are encouraged to use quality control (QC) techniques that exhibit control over their processes (e.g. (Statistical Process Control) SPC techniques) as defined in American National Standards Institute (ANSI) Z1.1, Z1.2 and Z1.3/ American Society for Quality Control (ASQC) B.1, B.2 and B.3 that systematically reduce excess variations. Objective evidence shall be available that demonstrates overall measurement adequacy techniques and controls. These techniques shall ensure quality levels equal to, or greater than, those cited in applicable technical document or, herein.

5.2.1 End item inspection may be used by the offeror or the Government representative, as a means to determine the effectiveness of the in process quality controls. In process controls shall not be substituted for end item performance testing.

5.2.2 For those characteristics for which there are no such controls, or for end item performance test, lot by lot sampling for inspection/test shall be required. Sampling shall be in accordance with the American National Standards Institute (ANSI)/ American Society for Quality Control (ASQC) Z1.4, Sampling Procedures and Tables for Inspection by Attributes (Application for copies can be obtained from American Society for Quality Control, P.O. Box 3005, 611 E. Wisconsin Avenue, Milwaukee, WI 53201-4606.

5.2.3 An inspection lot shall consist of all like items submitted for inspection at one time. The inspection level shall be S-3 with an AQL of 3 % defective. The supplier must provide objective evidence (tests and inspection records) that the presented material meets the requirements of the sampling plan as indicated above.

6. PACKAGING, PACKING, AND MARKING Packaging, packing, and marking shall be as specified in the contract or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

7. NOTES.

7.1 Part Identification Number (PIN). The following part identification numbering procedure is for government purposes and does not constitute a requirement for the contractor.

A-A-2951 - 1A1 Example of reference part number for a single faced, 100% cotton or linen, rough finish drawing paperboard.

- 1 - Type 1 - Single faced
  - Type 2 - Double faced
- A - Grade A - 100% cotton or linen
  - Grade B - 50% cotton or linen
- 1 - Class 1 - Rough finish
  - Class 2 - Smooth finish

7.2. Applicable documents and documents sources. The following documents form a part of the Commercial Item Description to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply:

(1) ANSI\ASQC-Z1.4 is available from American National Standard Institute, 11 West 42 St., NY, NY 10036. (212) 642-4900
(2) Copies of Executive Order 12873, dated October 20, 1993 may be obtained from: The White House Publications Office, New Executive Office Building, White House, Att: Publications, Washington, DC. 20500 (202) 395-7332
(3) Copies of Title 40, Code of Federal Regulation, Protection of Environment, Part 250, Guideline for Federal Procurement of Paper and Paper Products containing Recovered Materials may be purchased through: Government Printing Office, Washington, D. C. Phone: (202) 512-1800

8. ORDERING DATA Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

A) Title, number and date of this specification
B) Type, Grade, Class, Thickness and Size required
C) Whether bleaching without use of chlorine, chlorine dioxide, or chlorine compound is required.
D) Packaging, packing, labeling and marking requirements

8.1 National Stock Numbers (NSNs). The following is a list of NSNs assigned which correspond to this CID. The list may not be indicative of all possible NSNs associated with the CID.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

NSN
7530-00-180-6306
7530-00-270-6684
7530-00-270-6686
7530-00-515-0478
7530-00-515-0812
7530-00-317-4219

MILITARY INTERESTS:

DOD has waived coordination of this document

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.