MIL-C-13739A (FA)
AMENDMENT 1
6 March 1974

MILITARY SPECIFICATION

COMPOSITION, DELAY

This Amendment forms a part of Specification MIL-C-13739A(PA), dated 15 November 1965 and is approved for use by all Departments and Agencies of the Department of Defense.

2. APPLICABLE DOCUMENTS

Drawing:

Add the following:

8822131 - Fuze, Grenade, Hand, M213 Assembly

Paragraph 3.1, Materials, Potassium Perchlorate MIL-P-217, Delete: "Granulation IV" and substitute "Grade A, Class 4, except that the grit requirement shall be none."

Add the following subparagraphs to paragraph 3.5

"3.5.1 Contamination Control. There shall be no contamination including lubricating oil, hydraulic fluids, etc., in the delay composition."

"3.5.2 Adherence of Delay Composition. No delay composition shall be allowed to adhere to the mixing equipment. The mixing equipment shall be disassembled and cleaned periodically to assure that delay composition is not allowed to build up on the equipment. The equipment shall be seamless and of such a design as to minimize adherence of delay composition."

Paragraph 4.1.2: Add subparagraph h as follows:

"h. A statement of findings for each lot of delay composition."

Add paragraph 4.1.3.3 as follows:

4.1.3.3 Inspection Equipment. The government reserves the right to inspect the contractor's equipment and determine

FSC: 1370

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:14Z
Check the source to verify that this is the current version before use.

that he has available and utilizes correctly, measuring and test equipment of the required accuracy and precision and that the instruments are of the proper type and range to make measurements of the required accuracy. Commercial inspection equipment, shall be employed where applicable for all tests and examinations specified in 4.3 thru 4.9. The contractor is responsible for assuring proper calibration procedures are followed. Government approval of all inspection equipment is required prior to its use for acceptance purpose.

Add to paragraph 4.6.1 Procedure.

Line 2 after "Dwg 7548570 add "or Dwg 8822131"

Line 4 after "M204A2 add "or M213"

Delete from paragraph 4.6.1 "(2) Average column height"

(4) Standard deviation

Delete "$\sigma = \frac{V-D}{n-1}$" and add

"$\sigma = \sqrt{\frac{V-D}{n-1}}$"

Add paragraph 4.8 as follows:

"4.8 Contamination

4.8.1 Control (see 3.5.1 Major Defect, Code No. 08001. The contractor shall provide adequate controls to prevent contaminants of any kind from getting into the delay composition. Machinery, environments and operations utlized to handle delay composition shall be visually inspected at least once every two hours of operation to determine that the delay composition does not contain or is not likely to contain lubricating oil, hydraulic oil or other contaminants.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:14Z
Check the source to verify that this is the current version before use.

4.8.2 Contamination Test. Spread approximately 25 grams of the composition on a sheet of flat glass plate. Shine an ultra violet source of light in a dark room on the material and examine.If fluorescence occurs, it is due to presence of organic contaminants. Any evidence of contamination which is found in the delay composition shall cause rejection of all production since the last previous inspection."

Add paragraph 4.9 as follows:

"4.9 Adherence of Delay Composition (see 3.5.2 Major Defect, Code No. 09001, The contractor shall provide adequate controls to prevent delay composition from ahering to the mixing equipment. Such equipment shall be cleaned at least once every four (4) hours of operation to prevent adherence of delay composition. Any evidence of delay composition adhering to the mixing equipment shall cause rejection of all production until the equipment is cleaned to the satisfaction of the Government."

Custodian:
Army-PA

Preparing Activity:
Army-PA

Project Number: 1370-A025

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:14Z
Check the source to verify that this is the current version before use.